

THE MANUAL OF
PRACTICAL POTTING



FRANKLIN INSTITUTE LIBRARY
PHILADELPHIA, PA.

THE MANUAL
OF
PRACTICAL POTTING

THE MANUAL
OF
PRACTICAL POTTING

*REVISED AND ENLARGED
FOURTH EDITION*

SPECIALLY COMPILED BY EXPERTS

AND EDITED BY

CHARLES F. BINNS

LONDON

SCOTT, GREENWOOD & SON

"THE POTTERY GAZETTE" OFFICES

8 BROADWAY, LUDGATE HILL, E.C.

CANADA: THE COPP CLARK CO. LTD., TORONTO
UNITED STATES: D. VAN NOSTRAND CO., NEW YORK

1907

[All rights remain with Scott, Greenwood & Son]

10
11
12
13
14
15
16

THE GETTY CENTER
LIBRARY

PREFACE TO THE FIRST EDITION

THE proprietors of the *Pottery Gazette*, in presenting the *Manual of Practical Potting* to the trade, desire to say that no pains have been spared to make the work of unique value to those engaged in the business, their sole aim being to render it so complete in every particular that it might become to be universally regarded as the chief text-book for reference wherever the manufacture of ceramics is followed.

The information contained in the manual cannot fail to be of interest to every manufacturer desirous of perfecting his productions to the highest excellence. The various formulæ now published for the first time are the outcome of years of study and repeated experiment on the part of several members of the trade, whose individual experience has been of an exceptionally practical nature. The classification of the information given into a chain of connection has rendered them easy of instant comprehension by the intelligent operator.

The progressive improvements in the manufacture of china and earthenware which have taken place during the last forty years have indisputably raised the art to a pitch of excellence unequalled in the whole of the world's history—a culmination of circumstances mainly attributable to untiring practical and scientific research and experiment.

PREFACE TO THE SECOND EDITION.

A SECOND edition of the *Manual of Practical Potting* being demanded, the compilers have revised the whole work with the view of bringing the information up to date.

A number of new recipes have been acquired, and are incorporated in the body of the work, while some obvious errors have been corrected.

In the recipes built up by the labours of the bygone masters of the potter's art there seems to the scientific mind much that is obsolete, but there is, at the same time, something to be learned from them. Old methods have been superseded, but the results attained long ago are still pre-eminent in some directions. It is well, therefore, not to cast aside the work of a former generation as unworthy of attention; perchance even the scientist can be taught, and the best man is always he who is willing to learn.

It must not, however, be supposed that any great number of the recipes here given are old; very many of them are in use at the present time in the best English manufactories, while some apply, as is neces-

sary for the completeness of the work, only to the cheaper grades of ware. The clever potter will use these mixtures as suggestions, and, taught by his superior skill, will modify them to suit his own purpose.

CONTENTS.

	PAGE
Introduction—The Rise and Progress of the Potter's Art	1

CHAPTER I.—BODIES.

China and Porcelain Bodies	7
Parian Bodies	15
Semi-Porcelain and Vitreous Bodies	18
Mortar Bodies	23
Earthenware, Granite, and C. C. Bodies	24
Miscellaneous Bodies	29
Sagger and Crucible Clays	30
Coloured Bodies	32
Jasper Bodies	36
Coloured Bodies for Mosaic Painting	44
Encaustic Tile Bodies	45
Body Stains	46
Coloured Dips	47

CHAPTER II.—GLAZES.

China Glazes	55
Ironstone Glazes	64
Earthenware Glazes	66
Glazes without Lead	83
Miscellaneous Glazes	84
Coloured Glazes	85
Majolica Colours	91

CHAPTER III.—GOLD AND GOLD COLOURS.

Gold	93
Purple of Cassius	97
Marone and Ruby	98
Enamel Colour Bases	99
Enamel Colour Fluxes	107
Enamel Colours	112
Mixed Enamel Colours	119
Antique and Vellum Enamel Colours	121
Under-Glaze Colours	125

	PAGE
Under-Glaze Colour Fluxes	125
Mixed Under-Glaze Colours	141
Flow Powders	144
Oils and Varnishes	145

CHAPTER IV.—MEANS AND METHODS.

Reclamation of Waste Gold	146
The Use of Cobalt	147
Notes on Enamel Colours	148
Liquid or Bright Gold	150

CHAPTER V.—CLASSIFICATION AND ANALYSIS.

Classification of Clay Ware	152
Lord Playfair's Analysis of Clays	153
The Markets of the World	154
Time and Scale of Firing	156
Standard Weights of Potters' Materials	157
Decorated Goods Count	158

CHAPTER VI.

Comparative loss of Weight of Clays	159
-----------------------------------------------	-----

CHAPTER VII.

Slop Ground Felspar Calculations	163
--------------------------------------------	-----

CHAPTER VIII.

The Conversion of Slop Body Recipes into Dry Weight	168
---------------------------------------------------------------	-----

CHAPTER IX.

The Cost of Prepared Earthenware Clay	174
-------------------------------------------------	-----

CHAPTER X.—FORMS AND TABLES.

Articles of Apprenticeship	186
Manufacturer's Guide to Stocktaking	188
Table of Relative Values of Potters' Materials	190
Hourly Wages Table	191
Workmen's Settling Table	192
Comparative Guide for Earthenware and China Manufacturers in the Use of Slop Flint and Slop Stone	193
Foreign Terms applied to Earthenware and China Goods	194
Table for the Conversion of Metrical Weights and Measures on the Continent and South America	195
INDEX	199



THE RISE AND PROGRESS OF THE POTTER'S ART IN ENGLAND.

THE art of husbandman ranks as the only competitor in antiquity with the potter's craft in the history of the world's industries, data unique and indubitable being abundantly manifest to prove the correctness of this assertion.

The earliest exponents of the potter's art have rendered most remarkable aid in elucidating abstruse theories concerning the literature and manners and customs of nations, the record of which would have been otherwise entirely lost. From this cause alone the practice of the potter's art excites a deep and peculiar interest, irrespective of any other consideration to which its operations may tend.

No branch of manufacture presents so intimate and ancient an alliance between art and utility as that of the potter, whose earliest productions take their rise from a date which in the Eastern Hemisphere is lost in the darkness of remote antiquity. The ceramic art, both in its theory and practice, unites a combination of qualities unknown in any other expression of human skill. No other industry presents so many divers considerations, all of them of the utmost interest, and each one rich in economic and scientific application.

Finding its materials at or near the surface of the earth, pottery displays manufactures the most simple and yet the most varied—the easiest to fabricate, and, though fragile, of

incomparable durability. The products of these substances are absolutely endless in their variety, while in their most successful exponents their beauty may be pronounced as matchless.

Every species of form, from the classical severity of the early Greek period to the florid luxuriance of the wares of Saxony, France, and, one may now fairly add, England, here finds a fitting and worthy medium.

A material which science teaches to present the most lustrous surface, which is solid, imperishable, and admirably qualified for the application of varied and brilliant colouring, offers such inducements to the painter that even the pencil of the glorious Raffaele himself was occasionally employed in its decoration.

Without doubt the potter's art had its rise in the land of Egypt, from whence it travelled to Greece; and to the refined taste of that country the ceramic industry is indebted for its most beautiful shapes. The Romans did much to diffuse the making of pottery in the countries conquered by them, in this country especially. Ever since the Roman invasion potteries have had an existence in different parts of England, particularly in Staffordshire, as is evidenced by the quantity of pottery fragments that have been upturned in the course of ages.

The term "pottery" is derived from the Latin *poterium*, the name given by the Romans to drinking vessels; but this does not convey any signification denoting either form or substance.

The word "ceramic," the generic title by which works in this department of art manufacture are now known, is derived from the Greek. It primarily signifies the "horn of an animal." It has obtained its generally recognised signification from the early use of horns for drinking purposes, which in their turn gave place to articles made from plastic materials.

For many years the manufacture of pottery was of the most primitive type; but it gradually came to be regarded as the vehicle for artistic taste, and, in the mediæval age, attracted the attention of famous artists on the Continent, as is evidenced by the lovely works, still extant, associated with the honoured names of Palissy and Luca della Robbia, which for all time will be regarded as masterpieces.

Although the potter's art flourished in China prior to the Christian era, in this country very little was known of it until the reign of Elizabeth, who endeavoured to found potteries, with but indifferent success; indeed, little of importance was accomplished until the close of the sixteenth century. The first articles of which we find mention made were butter-pots and "tygs," the latter a peculiar species of handled drinking vessel. Ornamental dishes appear to have been made at Burslem, "the mother of the potteries," as early as 1650, the glazing of which was effected by means of lead. Thirty years later the purest accident led to the substitution of salt for lead in this particular, the first use of which was made by a potter named Palmer. The ware when salt glazed was known as "cranch ware," and the manufacture proved a source of considerable employment.

The first attempts that were made to imitate the work of the Eastern potters was a decided failure; but in 1690 two brothers, named Elers, discovered a bed of fine compact clay at Bradwell Wood, near Burslem, which enabled them to produce with exact success a fictitious Japanese ware.

The use of calcined and ground flint as an ingredient of pottery is attributed to the younger Astbury in 1720, and led to great and highly important improvements in the wares in Staffordshire. The new material was used in combination with pipe-clay and sand, coloured with oxide of copper and manganese.

A year later another innovation was introduced by Ralph

Daniel, of Cobridge, from France, in the shape of moulds of plaster of Paris, which speedily became adopted by the English potters.

The forms and patterns of the wares produced at this period were generally obtained from the silver plate of the time; the colours of the bodies were known as drab or cream-coloured and white. Painted ware of a crude type also came into general use a few years later; but it was not until the middle of the century that printed ware was introduced.

Such was the condition of English pottery manufacture in the district specially identified with the art when another Pallissy arose in England in the person of the great Wedgwood, who was born in the year 1730. At an early age he worked as a thrower at the potter's wheel in his elder brother's manufactory; but the state of his health compelled him to relinquish this occupation, and he afterwards followed the natural inclination of a mind richly endowed both with ingenuity and enterprise. In the year 1759 he succeeded in making a rich cream-coloured ware, by which he quickly attained a high degree of celebrity, so much so that he at once became the royal potter. At the same time Wedgwood sold his ware at a price which brought it within the means of general consumption both at home and abroad. How Josiah Wedgwood enhanced the reputation of the Staffordshire Potteries is a matter of common knowledge. Suffice it to say, that since his day the art in the district has shown no retrograde movement; on the contrary, it has gone on increasing year by year in excellence, till at the present time it towers above any of its foreign competitors.

Contemporaneously with Wedgwood, the china works at Bow and Chelsea came into prominence, followed by those of Plymouth, Derby, and Bristol. It was at Plymouth that the first true porcelain of hard paste was made by the

learned Dr. Cookworthy, although it had previously been produced by Böttcher at Meissen in Saxony, whose success was so great that he induced the Elector of that country to establish a royal manufactory of porcelain near Dresden, which is in existence at the present day, as is also another manufactory first established through royal influence at Sèvres in France.

The Royal Porcelain Works at Worcester were established by Dr. Wall in 1751. Five years later the important process of transfer printing was discovered and adopted at Worcester, from which place it travelled to Coalport in Shropshire, and thence to the Potteries of Staffordshire.

Besides the names before mentioned as important factors in the dissemination of the ceramic art in this country, Messrs. Minton, Spode and Copeland, Ridgway, Davenport, and many others, have done yeoman service in furthering the industry, which has now grown to enormous proportions.

In the year 1700 the whole of the Pottery district only contained fifty ovens, the small holding capacity of which permitted only a very restricted output. Again, in the year of the Great Exhibition, 1851, which did so much to encourage the potter's art, the number of fictile establishments in Staffordshire only numbered one hundred and thirty-three; while at the present time this has increased to the phenomenal number of three hundred and forty in the Potteries alone, while there is a large number of pottery manufactories scattered over different parts of England, Scotland, and Wales. The sum total of the exports of china and earthenware from this country alone amounted to considerably over two millions in 1892, to say nothing of the enormous increase of home consumption. From this it will be apparent to what considerable proportions the industry has grown during the last forty years.

The introduction of mechanical aid in place of manual labour will, to a great extent account for the increment of production, together with more methodical means for effective manufacture necessitated by the enlarged demand.

The institution of Government Schools of Art throughout the country, and the holding of Exhibitions, have done much both to encourage the necessary artists and designers, and to bring the taste of the public up to the high standard it now occupies; and it is obvious that the ceramic art as it has itself progressed in excellence has had a benign influence not only on the English race, but all over the world.

The potter's art has still a great future before it, not only in producing things of increased beauty and utility, but in finding employment for the teeming masses of the population of the districts specially identified with its manufacture.





CHAPTER I.

BODIES.

CHINA AND PORCELAIN BODIES.

IN selecting a china body regard must be had both to the class of work intended to be produced and to the decree of fire available. Generally speaking, the more bone there is in a mixture the greater will be the heat necessary; but, on the other hand, a body that will stand a severe fire is of better appearance and finer quality than a less refractory one. Some of the following recipes are in use by leading manufacturers, and amongst them will be found bodies of almost every conceivable variety:—

I LONGPORT CHINA BODY.

225 lbs. Calcined Bone	.	.	.	} Glaze No. 1.
150 „ China Clay	.	.	.	
82 „ China Stone	.	.	.	
15 „ Flint	.	.	.	

472

2 ALCOCK'S CHINA BODY.

70 lbs. Calcined Bone	.	.	.	} Glaze No. 3.
50 „ China Stone	.	.	.	
40 „ China Clay	.	.	.	

160

3 **ALCOCK'S CHINA FIGURE BODY.**

86 lbs. Calcined Bone	.	.	.	} Glaze No. 3.
62 „ China Stone	.	.	.	
50 „ China Clay	.	.	.	

 198
4 **CHINA CASTING BODY.**

42 lbs. Calcined Bone	.	.	.	} Glaze No. 3.
24 „ China Stone	.	.	.	
18 „ China Clay	.	.	.	
6 „ Flint	.	.	.	

 90
5 **CHINA BODY.**

200 lbs. Ground Bone	.	.	.	} Glaze No. 4.
130 „ China Stone	.	.	.	
150 „ China Clay	.	.	.	
10 „ Flint	.	.	.	

 490
6 **CHINA BODY.**

440 lbs. Calcined Bone	.	.	.	} Glaze No. 4.
260 „ China Stone	.	.	.	
260 „ China Clay	.	.	.	
25 „ Flint	.	.	.	

 985
7 **CHINA BODY.**

350 lbs. Calcined Bone	.	.	.	} Glaze No. 5.
275 „ China Stone	.	.	.	
250 „ China Clay	.	.	.	

 875

8 DESSERT CHINA BODY.

140 lbs.	Calcined Bone	.	.	.	} Glaze No. 5.
100 "	China Clay	.	.	.	
80 "	Swedish Felspar	.	.	.	
10 "	Flint	.	.	.	

 330
9 DESSERT CHINA BODY.

140 lbs.	Calcined Bone	.	.	.	} Glaze No. 5.
90 "	China Stone	.	.	.	
80 "	China Clay	.	.	.	
7 "	Blue Clay, finely sifted	.	.	.	

 317
10 CHINA BODY (1810)

40 lbs.	Calcined Bone	.	.	.	} Glaze No. 6.
36 "	China Clay	.	.	.	
25 "	China Stone	.	.	.	
2 "	Flint	.	.	.	

 103
11 CHINA BODY.

400 lbs.	Calcined Bone	.	.	.	} Glaze No. 9.
200 "	China Stone	.	.	.	
300 "	China Clay	.	.	.	

 900
12 CHINA BODY.

300 lbs.	Calcined Bone	.	.	.	} Glaze No. 9.
150 "	China Clay	.	.	.	
90 "	China Stone	.	.	.	
20 "	Flint	.	.	.	

 560

13

CHINA BODY.

230 lbs.	Calcined Bone	.	.	.	} Glaze No. 10.
120	„ China Clay	.	.	.	
100	„ China Stone	.	.	.	

 450

14

CHINA BODY.

450 lbs.	Calcined Bone	.	.	.	} Glaze No. 13.
230	„ China Stone	.	.	.	
220	„ China Clay	.	.	.	
30	„ Flint	.	.	.	

 930

15

CHINA BODY.

370 lbs.	Calcined Bone	.	.	.	} Glaze No. 14.
250	„ China Clay	.	.	.	
130	„ China Stone	.	.	.	
35	„ Flint	.	.	.	

 785

16

SPODE'S BODY.

120 lbs.	Bone	} ground together.	.	} Glaze No. 15.
80	„ Flint		.	
Add				
80	„ China Stone	.	.	
40	„ China Clay	.	.	

 320

17

CHINA BODY.

856 lbs.	Bone	}
700	„ Stone	
360	„ China Clay	

 1916

18 FENTON CHINA BODY.

290 lbs. Bone	}
171 „ Stone	
150 „ China Clay	
20 „ Flint	

 631
19 CHINA BODY.

696 lbs. Bone	}
528 „ Stone	
396 „ China Clay	
60 „ Flint	

 1680
20 NANTGARW CHINA BODY (Soft Paste).

175 lbs. Lynn Sand	}	Fritted.
25 „ Pearl Ash		

325 lbs. Bone	}
200 „ Fritt	
100 „ China Clay	

 625
21 FRITT CHINA BODY.

25 lbs. Lynn Sand	}	Fritted.
2 „ Pearl Ash		

12½ lbs. Fritt	}
60 „ Bone	
50 „ Stone	
50 „ China Clay	
7½ „ Ball Clay	

 180

22

CHINA BODY.

50 lbs. Bone	}
40 „ Stone	}
24 „ China Clay	}

 114

23

CHINA BODY.

50 lbs. Bone	}
35 „ Stone	}
20 „ China Clay	}

 105

24

CHINA BODY.

34 lbs. Bone	}
36 „ Stone	}
32 „ China Clay	}

 102

25

CHINA BODY.

365 lbs. Bone	}
343 „ Stone	}
216 „ China Clay	}

 924

26

LAKIN'S CHINA BODY.

360 lbs. Bone	}
230 „ China Clay	}
50 „ China Stone	}
20 „ Flint	}
20 „ Blue Clay	}

 680

27

CHINA BODY.

80	lbs. Bone	} Glaze No. 8.
35	„ China Clay	
15	„ Blue Clay	
80	„ Stone	
15	„ Flint	

 225

28

CHINA BODY.

50	lbs. Bone	}
40	„ Stone	
34	„ China Clay	
2	„ Flint	

 126

29

CHINA BODY.

588	lbs. Bone	} Glaze No. 17.
354	„ Stone	
312	„ China Clay	

 1254

30

CHINA BODY.

856	lbs. Bone	}
254	„ Stone	
432	„ China Clay	
170	„ Blue Clay	

 1712

31

MASON'S CHINA BODY.

28	lbs. Bone	}
20	„ China Clay	
16	„ Stone	
3	„ Flint	

 67

32

CHINA BODY.

35	lbs.	Bone	.	.	.
17	„	China Clay	.	.	.
20	„	Stone	.	.	.
3	„	Blue Clay	.	.	.

75

33

PORCELAINE FRANÇAIS LIMOGES.

50	parts	China Clay	.	.	.
40	"	Felspar	.	.	.
10	"	Flint	.	.	.
6	"	Steatite	.	.	.

106

34

CHINA BODY.

50	lbs.	Bone
35	„	China Clay
8	„	Stone
3	„	Flint
4	„	Blue Clay

100

CHINA BODIES.

	35	36	37	38	39	40	41	42
Bone	200	144	24	80	40	240	640	50
Stone	180	60	16	80	33	260	426	30
China Clay	75	84	16	35	30	260	387	30
Blue Clay	80	...	8	15
Flint	30	24	...	15
	565	312	64	225	103	760	1453	110

[illegible]

PARIAN BODIES.

Parian is theoretically an imitation of marble, and is composed in the main of felspar and stone, to which are added other materials in order to simplify the manufacture and firing.

China Clay is used on account of its refractory nature, and a little flint is sometimes employed, though an excess of this will give an unpleasant heavy effect to the body. In the employment of glass care must be taken to secure uniformity of composition. English flint glass will be found to give the best results.

1 PARIAN FRITT.

80 lbs. Lynn Sand	.	.	.	} Caleine at Biscuit heat.
35 „ Felspar	.	.	.	
15 „ Stone	.	.	.	
12 „ Pearl Ash	.	.	.	
<hr/>				
142				

2 PARIAN BODY.

50 lbs. Fritt, No. 1	.	.	.	}
130 „ Felspar	.	.	.	
130 „ China Clay	.	.	.	
20 „ Flint Glass	.	.	.	
<hr/>				
330				

3 PARIAN BODY FOR STATUETTES.

50 lbs. Fritt, No. 1	.	.	.	}
85 „ Felspar	.	.	.	
75 „ China Clay	.	.	.	
<hr/>				
210				

4 PARIAN BODY FOR SMALL ARTICLES.

200	lbs. China Clay
350	„ Felspar
25	„ Flint
<hr/>					
575					

5 PARIAN BODY.

300	lbs. Felspar
180	„ China Clay
<hr/>					
480					

6 PARIAN BODY.

200	lbs. Felspar
100	„ China Stone
150	„ China Clay
<hr/>					
450					

7 PARIAN FOR LACES AND DRAPERY.

60	lbs. Felspar
40	„ China Stone
55	„ China Clay
<hr/>					
155					

8 PARIAN BODY.

8	lbs. China Clay
6	„ Stone
8	„ Felspar
3	„ Flint Glass
<hr/>					
25					

9 PARIAN BODY.

12 lbs. China Clay
5 „ Stone
6 „ Felspar
3 „ Flint Glass
<hr/>				
26				

10 PARIAN BODY.

30 lbs. China Clay
30 „ Stone
38 „ Felspar
<hr/>				
98				

11 PARIAN BODY.

40 lbs. China Clay
40 „ Stone
80 „ Felspar
<hr/>				
160				

12 PARIAN BODY.

24 lbs. Felspar
8 „ China Clay
<hr/>				
32				

PARIAN BODIES.

	13	14	15
China Clay	8	6	8
Stone	16	6	8
Felspar	4	8	2
Flint Glass	4	2	2
	32	22	20

SEMI-PORCELAIN AND VITREOUS BODIES.

Ironstone, stoneware and vitreous are interchangeable terms, and are applied to those bodies of which the fracture is presumed to be granular rather than chalky. Many of these are termed semi-porcelain because they are partially translucent when well fired, and in fact it is to the fire that they all owe their strength and quality. The large proportion of Cornish stone used gives to the ware its vitreous nature, while the flint prevents it becoming too flexible in the oven. These bodies are subject to loss from over-fire, which, owing to the large proportion of fluxing materials present, will cause blisters to rise on the surface.

1 LONGPORT SEMI-CHINA BODY.

Fritt	12 lbs. Flint	.	.	.	} Calcine in Biscuit Oven.
	2 „ Carbonate of Potash	.	.	.	
	12 „ Red Lead	.	.	.	
	1 lb. Cobalt Blue	.	.	.	
<hr/>					
	27				

Mixture	7 lbs. Fritt	.	.	.	} Glaze No. 2.
	100 „ Flint	.	.	.	
	500 „ China Clay	.	.	.	
	400 „ Stone	.	.	.	
<hr/>					
	1007				

2 LONGPORT IRONSTONE BODY.

11 ins. Ball Clay	} Glaze No. 1.
7½ „ China Clay	
7½ „ Stone	
1 in. Flint	

3

STONE BODY.

480 lbs. Stone	}
250 „ Blue Clay	
240 „ China Clay	
10 „ Glass	

 980

4

WHITE STONE BODY.

400 lbs. Stone	}
200 „ Flint	
200 „ China Clay	
16 pails Ball Clay, 24 ozs.	

Stain as required.

5

IRONSTONE BODY.

170 lbs. Blue Clay	}	Glaze No. 2.
230 „ China Clay		
300 „ China Stone		
90 „ Flint		

 790

6

IRONSTONE BODY.

7 $\frac{3}{4}$ ins. Ball Clay	}	Glaze No. 2.
3 $\frac{1}{4}$ „ Flint		
4 $\frac{1}{2}$ „ China Clay		
3 $\frac{1}{4}$ „ Stone		

 18 $\frac{3}{4}$

7

MORTAR BODY.

16 $\frac{1}{2}$ ins. Ball Clay	}
7 $\frac{3}{4}$ „ China Clay	
11 $\frac{3}{4}$ „ Stone	

 36

8

MORTAR BODY.

264 lbs.	China Stone	.	.	.	}
264 „	Blue Clay	.	.	.	}
40 „	China Clay	.	.	.	}
40 „	Flint	.	.	.	}

 608

9

LONGPORT MORTAR BODY.

120 lbs.	Ball Clay	.	.	.	}
120 „	China Clay	.	.	.	}
20 „	Flint	.	.	.	}
240 „	Stone	.	.	.	}
8 „	Flint Glass	.	.	.	}

 508

10

MORTAR BODY.

19 ins.	Ball Clay	.	.	.	}
11 „	China Clay	.	.	.	}
8½ „	Flint	.	.	.	}
9½ „	Stone	.	.	.	}

 48

11

STONE BODY.

15 lbs.	Ball Clay	.	.	.	}
16 „	China Clay	.	.	.	}
8 „	Flint	.	.	.	}
12 „	Stone	.	.	.	}

 51

12

STONE BODY.

14 lbs.	Ball Clay	.	.	.	}
10 „	China Clay	.	.	.	}
6 „	Flint	.	.	.	}
18 „	Stone	.	.	.	}

 48

13 VITREOUS BODY.

8 lbs.	Ball Clay
18 "	China Clay
9 "	Flint
18 "	Stone

 53
14 VITREOUS BODY.

14 lbs.	Ball Clay
6 "	China Clay
4 "	Flint
22 "	Stone

 46
15 STONE BODY.

21 lbs.	Ball Clay
14 "	China Clay
3 "	Flint
15 "	Stone

 53
16 INSULATOR BODY.

480 lbs.	Cornish Stone
250 "	Blue Ball Clay
240 "	China Clay, Common
10 "	Flint Glass

 Glaze No. 1.

 980
17 PEARL GRANITE BODY.

168 lbs.	Cornish Stone
223 "	Cornish Clay
300 "	Flint
100 "	Blue Clay

 Glaze No. 1.

 791

18

IRONSTONE BODY.

19 $\frac{3}{4}$ ins.	Ball Clay
11 $\frac{1}{4}$ „	China Clay
8 $\frac{1}{2}$ „	Flint
8 $\frac{1}{2}$ „	Stone

 Stain as required.

48

19

STONE AND MORTAR BODY.

16 ins.	Ball Clay
2 „	China Clay
14 „	Stone

 Stain as required.

32

20

MASON'S STONE BODY.

12 $\frac{1}{2}$ lbs.	China Clay
2 $\frac{1}{2}$ „	Blue Clay
12 $\frac{1}{2}$ „	Flint
10 „	Stone

 Stain as required.
37 $\frac{1}{2}$

21

IRONSTONE BODY.

80 lbs.	Ball Clay
70 „	China Clay
60 „	Flint
40 „	Stone

 250

22

IRONSTONE BODY.

2 $\frac{1}{2}$ lbs.	Ball Clay
12 $\frac{1}{2}$ „	China Clay
12 $\frac{1}{2}$ „	Flint
10 „	Stone

 Stain as required.
37 $\frac{1}{2}$

23

MORTAR BODY.

12 lbs. Ball Clay	
2 „ China Clay	
2 „ Flint	
6 „ Stone	

 22

24

IRONSTONE BODY.

16 lbs. Ball Clay	
30 „ China Clay	
6 „ Flint	
35 „ Stone	

 87

MORTAR BODIES.

Dry Weight.

	25	26	27	28	29
Blue Clay	60	24	60	30	25
China Clay	10	10	20	10	24
Stone	30	10	20	10	48
Flint	10	5	15
	110	49	115	50	97

EARTHENWARE, GRANITE, AND C. C. BODIES.

Under this heading are placed a variety of bodies of a less vitreous nature than the preceding. They are for the most part porous to some extent, and do not need so hard a fire as those of the ironstone class. Some are suitable for printing, while others are constructed mainly with a view to simplicity of working. In some cases the chief difference between granite and C. C. is that the former is stained, while the latter is not. The slips are, of course, all of the standard weight unless otherwise stated.

I BEST PRINTED BODY.

21 ins. Ball Clay	}
14 „ China Clay	
8 „ Flint	
5 „ Stone	
— Stain as required.	
48	

2 PRINTED BODY.

16 ins. Ball Clay	}
9 „ China Clay	
6½ „ Flint	
1½ „ Stone	
—	
33	

3 BEST BODY.

14 ins. Ball Clay	}	Glaze No. 4.
10½ „ China Clay		
8 „ Flint		
4½ „ Stone		
— Stain as required.		
37		

4 **WHITE GRANITE BODY.**

12 $\frac{1}{2}$	ins.	Ball Clay	.	.	.	} Glaze No. 4.
12 $\frac{1}{2}$	"	China Clay	.	.	.	
6 $\frac{3}{4}$	"	Flint	.	.	.	
4 $\frac{1}{4}$	"	Stone	.	.	.	

 36
5 **PALETTE BODY.**

14 $\frac{1}{2}$	ins.	Ball Clay	.	.	.	} Glaze No. 30.
11 $\frac{3}{4}$	"	China Clay	.	.	.	
8 $\frac{1}{2}$	"	Flint	.	.	.	
2 $\frac{1}{2}$	"	Stone	.	.	.	

 37 $\frac{1}{4}$
6 **BLUE PRINTED BODY.**

13 $\frac{1}{2}$	ins.	Ball Clay	.	.	.	} Glaze No. 4.
13 $\frac{1}{2}$	"	China Clay	.	.	.	
6	"	Flint	.	.	.	
3	"	Stone	.	.	.	

 36
7 **DOOR FURNITURE BODY.**

10	ins.	Ball Clay	.	.	.	} Glaze No. 27.
13	"	China Clay	.	.	.	
8 $\frac{1}{2}$	"	Flint	.	.	.	
4 $\frac{1}{2}$	"	Stone	.	.	.	

 36
8 **COMMON BODY.**

27	ins.	Ball Clay	.	.	.	} Glaze No. 30.
14	"	China Clay	.	.	.	
8 $\frac{1}{2}$	"	Flint	.	.	.	
4 $\frac{1}{2}$	"	Stone	.	.	.	

 54

9 COMMON PRINTED BODY.

14 ins. Ball Clay	} Glaze No. 30.
8½ „ China Clay	
6¼ „ Flint	
2 „ Stone	

 30¾

10 EARTHENWARE BODY.

12 ins. Ball Clay	}
6 „ China Clay	
5 „ Flint	
1½ „ Stone	

 24½

11 PEARL WHITE BODY.

10 ins. Ball Clay	}
5 „ China Clay	
5 „ Flint	
2½ „ Stone	

 22½

12 CHALK BODY.

60 lbs. Black Clay	} Glaze No. 29.
60 „ China Clay	
90 „ Flint	

 210

13 ALCOCK'S EARTHENWARE BODY.

18 ins. Ball Clay	}
11½ „ China Clay	
9 „ Flint	
3½ „ Stone	

 Stain as required.

42

14 PRINTED BODY.

22 $\frac{1}{2}$	ins. Ball Clay
5	„ China Clay
5	„ Flint
1	in. Stone

 33 $\frac{1}{2}$
15 BEST PRINTED BODY.

14 $\frac{1}{2}$	ins. Ball Clay
9	„ China Clay
7	„ Flint
2	„ Stone

 32 $\frac{1}{2}$
16 PRINTED BODY.

28	ins. Ball Clay
19	„ China Clay
10	„ Flint
6 $\frac{3}{4}$	„ Stone

 63 $\frac{3}{4}$
17 GRANITE BODY.

11 $\frac{1}{4}$	ins. Ball Clay
9	„ China Clay
7 $\frac{5}{8}$	„ Flint
2 $\frac{1}{4}$	„ Stone

 30 $\frac{1}{8}$
18 C. C. BODY.

24 $\frac{1}{2}$	ins. Ball Clay
13 $\frac{1}{2}$	„ China Clay
7	„ Flint
3	„ Stone

 48

19 IVORY BODY.

32 ins.	Ball Clay
20 „	China Clay
8 „	Flint
4 „	Stone

64

20 C. C. BODY.

28 ins.	Ball Clay
6 „	China Clay
6 „	Flint
1 $\frac{1}{4}$ „	Stone

41 $\frac{1}{4}$

21 LONGPORT C. C. BODY.

20 ins.	Ball Clay
7 „	China Clay
6 „	Flint
1 in.	Stone

34

22 COMMON PRINTED BODY.

14 ins.	Ball Clay
10 „	China Clay
6 „	Flint
3 „	Stone

Stain as required.

33

23 PRINTED BODY.

30 ins.	Ball Clay
25 „	China Clay
16 „	Flint
6 „	Stone

77

24 PIN BODY (GOOD).

20	lbs.	Blue Clay
10	„	Flint
60	„	Stone
20	„	Plaster

110

25 GRANITE BODY.

16	lbs.	Blue Clay
30	„	China Clay
35	„	China Stone
6	„	Flint

— Stain as required.

87

MISCELLANEOUS BODIES.

I POROUS CELL BODY.

20	lbs.	Ball Clay
14	„	Flint
20	„	China Clay

54

2 MOULD BODY.

12½	ins.	Flint
6¼	„	China Clay
3¾	„	Ball Clay

22½

3

SANITARY BODY.

23 $\frac{1}{4}$	ins. Ball Clay	}
3	„ Flint	
13	„ China Clay	
14 $\frac{1}{2}$	„ Stone	
<hr/>					
53 $\frac{3}{4}$					

4

WHITE TILE BODY.

14 $\frac{1}{2}$	ins. Ball Clay	.	.	.	}
8 $\frac{1}{2}$	„ Flint	.	.	.	
11 $\frac{3}{4}$	„ China Clay	.	.	.	
2 $\frac{1}{2}$	„ Stone	.	.	.	
<hr/>					
37 $\frac{1}{4}$					

SAGGER AND CRUCIBLE CLAYS.

I

SAGGER CLAY.

2	cwts. Weathered Grey Marl .	.	}
12	lbs. Cryolite .	.	

2

CRUCIBLE CLAY.

8 ins. Stourbridge Clay, 26 ozs.	.	.	}
5 „ Ball Clay, 24 ozs.	.	.	
1 in. Cryolite, 32 ozs.	.	.	
<hr/>			
14			

3 CRUCIBLE CLAY.

12 ins. Stourbridge Clay, 26 ozs.	.	.	.	}
8 „ Ball Clay	}
1 in. Flint	}
<hr/>				
21				

4 CRUCIBLE CLAY.

8 lbs. Ball Clay	}
5 „ Ground Coke	}
4 „ Graphite Ore	}
<hr/>				
17				

5 CRUCIBLE CLAY.

1 lb. Ball Clay	}
1 „ Graphite Ore	}
<hr/>				
2				

6 RING CLAY.

6 lbs. Ball Clay	}
4 „ Flint	}
<hr/>				
10				

COLOURED BODIES.

Recipes for coloured bodies are always more or less uncertain to follow on account of the great variations in the natural clays so often employed. It is in following such recipes as are here given that the art of the body-mixer is seen. He must thoroughly know his materials, and be prepared to deviate intelligently from the lines laid down.

1 CITRON BODY.

14 ins. Marl, 26 ozs.
7 „ Ball Clay
7½ „ China Clay
2½ „ Flint
1 in. Stone

— Add Body stain to the required tint.

32

2 LILAC PORCELAIN BODY.

200 lbs. Bone
25 „ Ball Clay
115 „ China Clay
20 „ Flint
10 „ Stone
15 „ Cawk Stone
1¼ „ Cobalt Blue

— 386¼

3 CANARY.

25 ins. Shelton Marl Slip, 24 ozs.
5¾ „ China Clay
1 in. Stone

— 31¾

4

YELLOW BODY.

4	lbs. Marl	}
2	„ China Clay	
1	lb. Flint	
1 $\frac{1}{4}$	lbs. Stone	
<hr/>						
8 $\frac{1}{4}$						

5

BROWN.

50	lbs. Red Clay	}
7 $\frac{1}{2}$	„ Common China Clay	
1	lb. Manganese	
1	„ Flint	
<hr/>						
59 $\frac{1}{2}$						

6

BROWN OR COTTAGE BODY.

20	lbs. Red Clay	}
8	„ China Clay	
4	„ Blue Clay	
2	„ Flint	
<hr/>						
34						

7

CANE BODY.

5	ins. Marl, 26 ozs.	.	.	.	}
2	„ Ball Clay	.	.	.	
1½	„ Flint	.	.	.	
<hr/>					
8½					

8

CANE BODY.

200	lbs. Best Marl	}
100	„ Cornish Stone	
<hr/>						
300						

9 DRAB BODY.

118 gallons C. C. Slip at 24 ozs. .	}
7 pints Nickel Oxide Slip, 24 ozs. .	
24 ozs. Cobalt Stain	

10 PERSIAN CHINA BODY.

72 quarts China Slip, 27 ozs. .	}
21 ozs. Nickel	

11 LIGHT DRAB BODY.

50 lbs. Dried Shavings	}
1 lb. Manganese	

 51
12 LIGHT DRAB BODY.

200 lbs. Black Marl	}
200 „ Blue Ball Clay	
200 „ China Clay	
50 „ Flint	

 650
13 DRAB BODY.

210 lbs. Blue Clay	}
80 „ Flint	
8 „ Oxide of Nickel	

 298
14 EGYPTIAN BLACK.

50 lbs. Blue Clay	}
40 „ Ochre	
20 „ Ironstone	
15 „ Manganese	

 125

15 EGYPTIAN BLACK.

240 lbs.	Blue Clay	}
120	„ Ochre	
42	„ Iron-scales	.	.	.	
45	„ Manganese	.	.	.	
<hr/>					
447					

16 DRY BLACK BODY.

120 lbs. Ochre	}
120 „ Blue Clay	
16 „ Manganese	
<hr/>					
256					

17 EGYPTIAN BLACK BODY.

65 lbs. Ball Clay	}
60 „ Ironstone	
10 „ Manganese	.	.	.	
<hr/>				
135				

18 EGYPTIAN BLACK.

235 lbs.	Blue Ball Clay	.	.	.	}
25	„ Calcined Nickel	.	.	.	
45	„ Manganese	.	.	.	
15	„ China Stone	.	.	.	
<hr/>					
320					

19 EGYPTIAN BLACK.

50 qts.	Ball Slip at 24 ozs. to pint .	}		
72 lbs.	Ironstone
22	„ Manganese	.	.	.

20

GREEN BODY.

64 qts. Ball Slip	}
1 lb. Verdigris	}

21

GREEN BODY.

60 lbs. Ball Clay	}
20 „ Stone	}
20 „ Flint	}
12 ozs. Calcined Copper	}

22

LIGHT GREEN BODY.

32 qts. Ball Slip	}
11 lbs. Cornish Stone	}
12 „ China Clay	}
9 „ Flint	}
8 „ Green Chrome	}

23

GREEN BODY.

40 qts. Ball Slip	}
1 $\frac{1}{4}$ lbs. Ground Blue Vitriol	}

JASPER BODIES.*Dry Weight.*

	24	25	26	27
Blue Clay	17	18	15	28
China Clay	17	14	20	16
Stone	33	20	20	34
Cauk Stone (Sulphate of Barytes)	27	28	36	20
Flint Glass	4	6	6	6
Blue Calx	2	6	3	3
	100	92	100	107

28 GREEN JASPER BODY.

29	lbs. Stone	}
29	„ China Clay	
29	„ Paris White	
16	„ Blue Clay	
$\frac{1}{4}$	lb. Oxide Chrome	}
$\frac{1}{2}$	„ „ Cobalt	

 103 $\frac{3}{4}$

29 WHITE JASPER FOR COLOURED DIPS.

25	lbs. Stone	}
25	„ Whiting	
25	„ China Clay	
25	„ Ball Clay	

 100

30 LILAC BODY (ALCOCK'S).

265	lbs. Blue Clay	}
340	„ China Clay	
265	„ Flint	
90	„ Stone	
5	„ Cobalt Blue	

 965

31 LILAC BODY.

1	gal. China Slip, 27 ozs.	}
1 $\frac{1}{2}$	ozs. Body Stain	

32 YELLOW STONE BODY.

170	lbs. Yellow Marl	}
80	„ Felspar	

 250

33 OLD MAJOLICA BODY.

20 ins.	Red Clay,	26	ozs.	to	pint	.	}
8	„	Blue Clay	}
4	„	China Clay	}
2	„	Flint	}

 34

34 OLD MAJOLICA BODY.

30 ins.	Red Clay,	26	ozs.	to	pint	.	}
4	„	China Clay	}
3	„	Flint	}

 37

35 OLD MAJOLICA BODY.

40 ins.	Red Clay,	26	ozs.	to	pint	.	}
10	„	Blue Clay	}
4	„	China Clay	}
2	„	Flint	}

 56

36 OLD MAJOLICA BODY.

50 ins.	Red Clay,	26	ozs.	to	pint	.	}
7½	„	Ball Clay	}
1 in.	Flint	}

 58½

37 OLD MAJOLICA BODY.

260 lbs.	Red Clay	}
72	„	Common Clay	.	.	.	}
10	„	Flint	.	.	.	}

 342

38

ORANGE.

4 lbs. Good Marl	.	.	.	}
2 „ China Clay	.	.	.	}
1 lb. Flint	.	.	.	}
1 „ China Stone	.	.	.	}

8

39

PALE DRAB BODY.

9½ ins. Ball Clay	.	.	.	}
16½ „ Marl, 26 ozs.	.	.	.	}
140 lbs. Felspar	.	.	.	}

40

DRAB BODY.

54 galls. C. C. Body Slip, 26 ozs.	.	.	.	}
3½ pts. Nickel, 27 ozs.	.	.	.	}
10 ozs. Blue Calx	.	.	.	}

41

TURQUOISE BODY.

40 galls. Ball Slip	.	.	.	}
3 lbs. Turquoise Stain, No. 42	.	.	.	}

42

TURQUOISE STAIN.

16 lbs. Barytes	.	.	.	}
20 „ Oxide Zinc	.	.	.	}
4 „ Ground Blue Calx	.	.	.	}

— Fritted at the top of Glost Oven.

40

43

TURQUOISE BODY.

50 galls. Ball Slip, 24 ozs.	.	.	.	}
3 lbs. Turquoise Stain, No. 42	.	.	.	}

44 **LIGHT TURQUOISE BODY.**

62 galls. Ball Slip, 24 ozs.	.	.	.	}
3 $\frac{1}{4}$ lbs. Turquoise Stain, No. 42	.	.	.	}

45 **TURQUOISE BODY.**

15 ins. Ball Clay	.	.	.	}
6 „ China Clay	.	.	.	}
5 $\frac{1}{2}$ „ Flint	.	.	.	}
5 $\frac{1}{2}$ „ Stone	.	.	.	}
15 pts. Body Stain, No. 4	.	.	.	}

46 **SAGE BODY.**

10 ins. Marl, 26 ozs.	.	.	.	}
15 „ Ball Clay	.	.	.	}
2 $\frac{1}{2}$ „ Flint	.	.	.	}
4 $\frac{1}{2}$ „ Stone	.	.	.	}
8 pts. Body Stain, No. 4	.	.	.	}

47 **SAGE BODY.**

90 qts. Ball Slip	.	.	.	}
64 pts. Sage Body, No. 46	.	.	.	}
8 „ Turquoise Stain, No. 42	.	.	.	}

48 **SALMON BODY.**

60 qts. Best Marl, 26 ozs. to a pint	.	.	.	}
12 „ Red Slip, 24 „ „	.	.	.	}
13 „ Flint, 32 „ „	.	.	.	}

 85
49 **TERRA COTTA (SOUTH KENSINGTON).**

50 lbs. Best Red Clay	.	.	.	}
1 lb. Flint	.	.	.	}

 51

50

RED BODY.

50 lbs. Red Clay	}
2 „ Stone	}

 52

51

RED BODY (POROUS).

40 lbs. Bradwell Clay	}
4 „ China Clay	}
1 lb. Flint	}

 45

52

GREEN DRAB BODY.

2 lbs. China Clay	}
2 „ Ball Clay	}
4 „ Stone	}
4 ozs. Oxide Nickel	}

 $8\frac{1}{4}$

53

DRY SMEARING BODY.

2 lbs. Ball Clay	}
3 „ Calcined Ochre	}
4 „ Oxide Manganese	}
1 lb. Chromate Iron	}

 10

54

SMEARING BODY.

15 lbs. Ball Clay	}
$1\frac{1}{2}$ „ Manganese	}
$4\frac{3}{4}$ „ Chromate Iron	}

 $21\frac{1}{4}$

55

SMEARING BODY.

16	lbs.	Ball Clay	.	.	.	}
1 $\frac{1}{2}$	„	Stone	.	.	.	
5	„	Oxide Manganese	.	.	.	

 22 $\frac{1}{2}$

56

SMEARING BODY.

8	lbs.	Ball Clay	.	.	.	}
6	„	Calcined Ochre	.	.	.	
1 $\frac{1}{4}$	„	Oxide Manganese	.	.	.	
1 $\frac{1}{2}$	„	Chromate Iron.	.	.	.	

 16 $\frac{3}{4}$

57

DRY SMEARING BLACK.

16	lbs.	Ball Clay	.	.	.	}
4	„	Manganese	.	.	.	
4	„	Ironstone	.	.	.	
8	„	Red Clay	.	.	.	

 32

58

EGYPTIAN BLACK.

21	lbs.	Ball Clay	.	.	.	}
3	„	Red Clay	.	.	.	
4	„	Manganese	.	.	.	
4	„	Ironstone	.	.	.	

 32

59

EGYPTIAN BLACK.

30	lbs.	Blue Clay	.	.	.	}
40	„	Ochre	.	.	.	
50	„	Manganese	.	.	.	
10	„	Iron Scales	.	.	.	

 130

60

FAWN POROUS BODY.

40 lbs. Bradwell Clay
4 „ Ball Clay
2 „ Flint

 46

61

ROCKINGHAM.

4 lbs. Red Clay
4 „ China Clay
1 lb. Flint

 9

62

PURPLE CHINA BODY.

3 lbs. Bone
2½ „ Ball Clay
2 „ Stone
1 lb. China Clay
½ oz. Oxide Cobalt

63

SLATE CHINA BODY.

1 qt. China Body Slip
¼ oz. Nickel
¼ „ Blue Calx

COLOURED BODIES FOR MOSAIC PAINTING.

I FAWN POROUS BODY FOR FOUNDATION.

40 lbs. Red Clay	} This body is intended for plateaux and
4 „ Blue Clay	
2 „ Flint	
<hr/>	
46	

wine coolers, to be ornamented with variously tinted Slips. The piece to be decorated must be kept in the green state; otherwise the Slips will not sufficiently adhere to the surface, but will chip and peel off when fired. The latter operation must only be at a moderate temperature, say in the easiest part of the Earthenware Biscuit Oven. The Slips must all be well ground.

2 WHITE SLIP.

4 lbs. Blue Clay	}
2 „ China Clay	.	.	.	
2 „ Flint	.	.	.	
1 lb. Stone	.	.	.	
<hr/>				
9				

3 BLUE SLIP.

20 parts White Slip, No. 2	.	.	.	}
1 part Blue Calx	.	.	.	
<hr/>				
21				

4

BLACK SLIP.

4 lbs. Egyptian Black Slip, No. 15 .	
1 lb. White Slip, No. 2 . . .	
1 „ Blue Slip, No. 3 . . .	

 6

5

ORANGE SLIP.

4 lbs. Yellow Marl	
2 „ China Clay	
1 lb. Flint	
$\frac{1}{4}$ „ Stone	

 $7\frac{1}{4}$

6

GREEN SLIP.

12 lbs. White Slip, No. 2	
1 lb. Oxide Nickel	
$\frac{1}{4}$ „ Blue Slip, No. 3	

 $13\frac{1}{4}$
ENCAUSTIC TILE COLOURS.

I

WHITE.

20 lbs. Ball Clay	
10 „ China Clay	
10 „ Flint	
5 „ Stone	

 45

2

BLUE.

25 lbs. White Clay, as above . . .	
$1\frac{1}{4}$ „ Blue Calx	

 $26\frac{1}{4}$

3

BLACK.

12 lbs.	Egyptian Black Body, No. 15			
3 „	White Clay, No. 1	.	.	
3 „	Blue Clay, No. 2	.	.	

 18

4

GREEN.

12 lbs.	White Clay, No. 1	.	.	
1 lb.	Blue Clay, No. 2	.	.	
1 „	Oxide Nickel	.	.	

 14

5

YELLOW.

10 lbs.	Ball Clay	.	.	.
5 „	China Clay	.	.	.
10 „	Flint	.	.	.
5 „	Stone	.	.	.
15 „	Best Marl, ground	.	.	.

 45
BODY STAINS.

The following recipes have been gathered from various sources, and are only applicable to the ordinary purpose of counteracting the yellow coloration of commercial clays. It will be considered by some that the use of glass is obsolete, and perhaps a better flux than any here given will be found in Cornish stone, used in the proportion of about five parts of stone to one of black oxide. The main consideration in the preparation of a stain is that it should be ground very well, and passed through as fine a lawn as can be procured.

I

3 lbs.	Black Oxide Cobalt	.	.	
5 „	Flint Glass	.	.	

2

12½ lbs. Black Oxide Cobalt . . .	}
20 „ Ground Pitchers . . .	}

3

3 lbs. Black Oxide Cobalt . . .	}
3 „ Ground Pitchers . . .	}

4

15 lbs. Black Oxide Cobalt . . .	}	Calcine in Glost Oven.
15 „ Flint . . .		
3¼ „ Red Lead . . .		

5

6½ lbs. Black Oxide Cobalt . . .	}	Calcine in Glost Oven.
5 „ Flint . . .		
5 „ Flint Glass . . .		

6

3 ozs. Black Oxide Cobalt . . .	}	Run down.
5 lbs. Flint Glass . . .		

COLOURED DIPS.

The success of a coloured dip is dependent entirely upon the shrinkage of the body to which it is applied. If a want of agreement is found to exist, a little flint or clay added to the dip will diminish or increase its contraction as may be required.

I**AZURE.**

12 qts. White Slip (unflinted). . .	}
4 ozs. Fluxed Blue . . .	}

2 BLACK.

36	galls.	Red Clay Slip	.	.	.	}
25	lbs.	Ironstone	.	.	.	
25	„	Ochre	.	.	.	
15	„	Manganese	.	.	.	

3 BLACK FOR LAYING IN.

36	galls.	Red Clay Slip	.	.	.	}
30	lbs.	Ironstone	.	.	.	
20	„	Ochre	.	.	.	
10	„	Manganese	.	.	.	

4 BLACK FOR BANDS.

20	qts.	White Body Slip, 26 ozs.	.	.	}
5	lbs.	Ground Iron Scales	.	.	

5 BLACK.

12	qts.	White Body Slip, 26 ozs.	.	.	}	
$\frac{1}{2}$	lb.	Manganese	.	.		.
$1\frac{1}{4}$	lbs.	Ochre	.	.		.

6 BLACK.

20	qts.	White Body Slip, 26 ozs.	.	.	}	
2	lbs.	Nickel	.	.		.
4	„	Manganese	.	.		.
3	„	Ochre	.	.		.

7 GREEN.

5	qts.	Cane Slip	.	.	.	}
5	ozs.	Blue Calx	.	.	.	
1	oz.	Oxide Copper	.	.	.	

8 BLUE DIP.

10 galls. White Slip (unflinted)	.	}
4 ozs. Cobalt	.	}

9 SKY BLUE DIP.

12 galls. White Body Slip, 26 ozs.	.	}
4 ozs. Cobalt	.	}

10 DRAB DIP.

12 qts. White Body Slip, 26 ozs.	.	}
3 ozs. Manganese	.	}
3 „ Blue Calx	.	}

11 DARK DRAB DIP

10 qts. White Body Slip, 26 ozs.	.	}
2½ ozs. Manganese	.	}
2½ „ Blue Calx	.	}

12 DOVE DIP.

12 qts. White Body Slip, 26 ozs.	.	}
1½ lbs. Oxide Manganese	.	}
½ lb. Ochre	.	}

13 FAWN DIP.

24 qts. White Body Slip, 26 ozs.	.	}
1 lb. Crocus Martis (finely ground)	.	}

14 FRENCH GREY DIP.

12 galls. White Body Slip, 26 ozs.	.	}
6 ozs. Blue Calx	.	}

15

FRENCH GREY DIP.

4 galls.	White Body Slip, 26 ozs.	.	.	}
1 gall.	Yellow Slip, 26 ozs.	.	.	}
4 ozs.	Blue Calx	.	.	}
4 „	Oxide Uranium	.	.	}
2 „	Manganese	.	.	}

16

BROWN DIP.

150 lbs.	Bradwell Clay	.	.	.	}
100 „	Bright Hanley Marl	.	.	.	}
50 „	Ochre	.	.	.	}

17

GREY DIP.

36 galls.	White Body Slip, 26 ozs.	.	.	}
$\frac{1}{2}$ lb.	Fluxed Blue	.	.	}
1 „	Manganese	.	.	}

18

GREEN DIP.

36 galls.	White Body Slip, 26 ozs.	.	.	}
48 ozs.	Oxide Chrome, ground and washed	.	.	}

19

GREEN DIP.

5 qts.	White Body Slip, 26 ozs.	.	.	}
4 ozs.	Oxide Copper	.	.	}
10 „	„ Nickel	.	.	}

20

GREEN DIP.

4 qts.	White Body Slip, 26 ozs.	.	.	}
4 ozs.	Oxide Nickel	.	.	}
1 oz.	Blue Calx	.	.	}

21 OLIVE GREEN DIP.

4 qts. White Body Slip, 26 ozs.	.	.	.	}
12 ozs. Oxide Nickel	.	.	.	
10 „ Fluxed Blue	.	.	.	
1 oz. Iron Scales	.	.	.	

22 FLESH-COLOURED DIP.

8 qts. White Body Slip, 26 ozs.	.	.	.	}
4 „ Red Clay, 26 ozs.	.	.	.	

23 ASH-COLOURED DIP.

6 lbs. C. C. Clay	}
2 ozs. Fluxed Blue	.	.	.	

24 MOCHA STAIN.

12 lbs. Calcined Nickel	}	To be well ground and mixed with body according to shade of colour desired.
6 „ Black Pitchers		
6 „ Iron Scales		
2 ozs. Flint Glass		
6 „ Blue Calx		

25 “BLACK JACK’S MOCO” STAIN.

6 lbs. Black Pitchers	}	To be well ground and mixed with body to required strength.
3 „ Ironstone		
3 „ Oxide Nickel		
3 „ Flint Glass		
1½ „ Fluxed Blue		

26 LILAC DIP.

24 qts. White Slip, 26 ozs.	.	.	.	}
1 lb. Crocus Martis (Red Oxide Iron)	.	.	.	
1 oz. Blue Calx	

27

MULBERRY DIP.

20 qts. Red Clay, 26 ozs.	.	.	}
1 pt. Nickel, 27 ozs.	.	.	}
2 ozs. Flint Glass	.	.	}

28

DARK MULBERRY DIP.

20 qts. Red Slip, 26 ozs.	.	.	}
1 qt. Nickel, 27 ozs.	.	.	}
2 ozs. Flint Glass	.	.	}

29

PINK DIP.

13 qts. Body Slip, 26 ozs.	.	.	}
3 „ Whiting, 26 ozs.	.	.	}
3 „ China Stone, 32 ozs.	.	.	}
3 „ U. G. Crimson, 32 ozs.	.	.	}
3 „ Common Glaze, 28 ozs.	.	.	}

30

DARK RED DIP.

3 qts. White Body Slip, 26 ozs.	.	.	}
2 „ Red Clay, 26 ozs.	.	.	}
4 ozs. Blue Calx .	.	.	}

31

RED DIP.

3 qts. Red Clay, 26 ozs.	.	.	}
$\frac{1}{4}$ oz. Copperas .	.	.	}

32

PINK DIP.

2 qts. Ball Clay, 24 ozs.	.	.	}
1 qt. U. G. Pink, 32 ozs.	.	.	}
1 „ Whiting, 28 ozs.	.	.	}

33

MAROON DIP.

7 lbs. Blue Clay	}
2 $\frac{1}{4}$ „ U. G. Pink	
6 ozs. Sal Ammoniac	

34

BLUSH DIP.

10 galls. White Slip(unflinted), 26 ozs.	}
10 ozs. Sal Ammoniac	
2 „ U. G. Crimson	

35

PURPLE DIP.

40 qts. Blue Clay	}
1 oz. Blue Calx	
2 ozs. Manganese	

36

TURQUOISE DIP.

5 lbs. Ball Clay	}	Calcine in Glost Oven and grind.
5 „ Oxide Zinc		
3 „ Blue Calx		

40 pts. Body Slip	}
1 pt. Stain, as above, 32 ozs.	

37

BLUE DIP.

4 lbs. China Stone	}
1 lb. China Clay	
3 pts. Bone Slip	
3 „ Ball Slip	
10 ozs. Cobalt Blue	

38

GREEN DIP.

5 qts. Cane Slip	
5 ozs. Ground Zaffre	
1 oz. Copper Scales	

39

OLIVE DIP.

12 qts. Cane Slip	
$\frac{1}{2}$ oz. Zaffre	
2 ozs. Copper Scales	

40

GREEN DIP.

1 qt. Blue, No. 37	
$1\frac{1}{2}$ ozs. Ground Nickel	





CHAPTER II.

GLAZES.

IN the preparation of a glaze much depends upon the proper fritting of the soluble materials. Some few fritts contain lead or flint glass, and these should not be melted in the fritt kiln, but should be put in well-flinted saggars in the Glost Oven. Care should also be taken to ascertain, by a series of trials, the proper temperature at which a glaze should be fired; a very common error is to over-fire the glaze in attempting to secure brilliancy. The result is the exact opposite: the glaze is impoverished, its finer constituents are volatilised, and a harsh granular surface is left. At the proper fire a glaze should remain on all the higher projections of the ware, and should appear rich and mellow to the eye and touch.

CHINA GLAZES.

I LONGPORT CHINA GLAZE.

<i>Fritt</i> —150 lbs.	Borax	.	.	.
90	„ Stone	.	.	.
115	„ Flint	.	.	.
48	„ Whiting	.	.	.
19	„ China Clay	.	.	.
<i>Glaze</i> —314	„ Fritt	.	.	.
157	„ Stone	.	.	.
118	„ White Lead	.	.	.
34	„ Flint	.	.	.

2 LONGPORT SEMI-CHINA GLAZE.

<i>Fritt</i> —140 lbs.	Borax	.	.	.	}
80 „	Stone	.	.	.	
115 „	Flint	.	.	.	
70 „	Whiting	.	.	.	
25 „	China Clay	.	.	.	
<i>Glaze</i> —350 „	Fritt	.	.	.	}
210 „	China Stone	.	.	.	
135 „	White Lead	.	.	.	
45 „	Flint	.	.	.	
9½ ozs.	Stain	.	.	.	

3 ALCOCK'S CHINA GLAZE.

<i>Fritt</i> —68 lbs.	Borax	.	.	.	}	Body Nos. 2, 3, 4.
56 „	China Stone	.	.	.		
45 „	Flint	.	.	.		
45 „	Whiting	.	.	.		
34 „	China Clay	.	.	.		
<i>Glaze</i> —265 „	Fritt	.	.	.	}	
52 „	Flint	.	.	.		
53 „	Stone	.	.	.		
79 „	Lead	.	.	.		

4 CHINA GLAZE.

<i>Fritt</i> —120 lbs.	Borax	.	.	.	}	Body Nos. 5 and 6.
51 „	Flint	.	.	.		
51 „	Stone	.	.	.		
21 „	Whiting	.	.	.		
<i>Glaze</i> —130 „	Fritt	.	.	.	}	
51 „	Stone	.	.	.		
48 „	Lead	.	.	.		

5 CHINA GLAZE.

<i>Fritt</i> —121	lbs.	Borax	.	.	.	}	Body Nos. 7, 8, 9.
66	„	Whiting	.	.	.		
66	„	Flint	.	.	.		
81	„	Stone	.	.	.		
51	„	China Clay	.	.	.		
<i>Glaze</i> —270	„	Fritt	.	.	.	}	
50	„	White Lead	.	.	.		
50	„	Flint	.	.	.		
50	„	Stone	.	.	.		

6 CHINA GLAZE.

<i>Fritt</i> —138	lbs.	Borax	.	.	.	}	Body No. 10.
140	„	Stone	.	.	.		
130	„	Flint Glass	.	.	.		
122	„	Flint	.	.	.		
<i>Glaze</i> —520	„	Fritt	.	.	.	}	
120	„	White Lead	.	.	.		

7 CHINA GLAZE.

<i>Fritt</i> —35	lbs.	Borax	.	.	.	}	
20	„	Spar	.	.	.		
20	„	Stone	.	.	.		
10	„	China Clay	.	.	.		
<i>Glaze</i> —80	„	Fritt	.	.	.	}	
30	„	White Lead	.	.	.		

8 CHINA GLAZE.

<i>Fritt</i> —50	lbs.	Borax	.	.	.	}	Body No. 27.
80	„	Stone	.	.	.		
33	„	Whiting	.	.	.		
39	„	Flint	.	.	.		
<i>Glaze</i> —520	„	Fritt	.	.	.	}	
100	„	White Lead	.	.	.		

9

CHINA GLAZE.

<i>Fritt</i> —70	lbs.	Borax	.	.	.	} Body Nos. 11 and 12.
60	„	Stone	.	.	.	
20	„	Whiting	.	.	.	
20	„	Flint	.	.	.	
<i>Glaze</i> —165	„	Fritt	.	.	.	
90	„	White Lead	.	.	.	

10

CHINA GLAZE.

<i>Fritt</i> —140	lbs.	Borax	.	.	.	} Body No. 13.
160	„	Stone	.	.	.	
100	„	Flint	.	.	.	
<i>Glaze</i> —352	„	Fritt	.	.	.	
70	„	White Lead	.	.	.	

11

CHINA GLAZE.

<i>Fritt</i> —45	lbs.	Borax	.	.	.	}
60	„	Stone	.	.	.	
10	„	Flint	.	.	.	
<i>Glaze</i> —112	„	Fritt	.	.	.	
40	„	White Lead	.	.	.	

12

CHINA GLAZE.

<i>Fritt</i> —95	lbs.	Borax	.	.	.	}
125	„	Stone	.	.	.	
35	„	Flint	.	.	.	
<i>Glaze</i> —250	„	Fritt	.	.	.	
72	„	White Lead	.	.	.	

13

CHINA GLAZE.

<i>Fritt</i> —53	lbs.	Borax	.	.	.	} Body No. 14.
24	„	Stone	.	.	.	
30	„	Felspar	.	.	.	
20	„	Flint	.	.	.	
10	„	Whiting	.	.	.	
<i>Glaze</i> —90	„	Fritt	.	.	.	
30	„	Stone	.	.	.	
30	„	White Lead	.	.	.	

14

CHINA GLAZE.

<i>Fritt</i> —40	lbs.	Borax	.	.	.	} Body No. 15.
50	„	Stone	.	.	.	
30	„	Flint	.	.	.	
30	„	Flint Glass	.	.	.	
<i>Glaze</i> —147	„	Fritt	.	.	.	
30	„	White Lead	.	.	.	

15

SPODE'S GLAZE.

<i>Fritt</i> —40	lbs.	Borax	.	.	.	} Body No. 16.
170	„	Stone	.	.	.	
100	„	Flint	.	.	.	
20	„	Flint Glass	.	.	.	
<i>Glaze</i> —325	„	Fritt	.	.	.	
40	„	White Lead	.	.	.	

16

CHINA GLAZE.

<i>Fritt</i> —30	lbs.	Stone	.	.	.	} Run down in flinted saggars at bottom of Glost Oven.
15	„	Flint	.	.	.	
77½	„	Red Lead	.	.	.	
6	„	Carbonate Soda	.	.	.	
<i>Glaze</i> —15	„	Fritt	.	.	.	
12	„	Flint Glass	.	.	.	
10	„	White Lead	.	.	.	

17 CHINA GLAZE.

<i>Fritt</i> —128	lbs.	Borax	.	.	.	} Body No. 29.
158	„	Stone	.	.	.	
94	„	China Clay	.	.	.	
125	„	Flint	.	.	.	
62	„	Whiting	.	.	.	
1½	„	Pearl Ash	.	.	.	
3	„	Nitrate Potash	.	.	.	
20	„	Carbonate Soda	.	.	.	
<i>Glaze</i> —443	„	Fritt	.	.	.	
10	„	Flint	.	.	.	
50	„	Whiting	.	.	.	
10	„	China Clay	.	.	.	
17	„	Stone	.	.	.	
141	„	White Lead	.	.	.	

18 SPECIAL CHINA GLAZE.

<i>Fritt</i> —110	lbs.	Borax	.	.	.	} Body No. 37.
66	„	Stone	.	.	.	
50	„	Flint	.	.	.	
33	„	Whiting	.	.	.	
30	„	China Clay	.	.	.	
<i>Glaze</i> —230	„	Fritt	.	.	.	
34	„	Stone	.	.	.	
28	„	Flint	.	.	.	
28	„	White Lead	.	.	.	

19 FELSPAR CHINA GLAZE.

<i>Fritt</i> —20	lbs.	Sand	.	.	.	} Body Nos. 17, 30.
20	„	Borax	.	.	.	
12	„	Stone	.	.	.	
20	„	Felspar	.	.	.	
10	„	Whiting	.	.	.	
3	„	Arsenic	.	.	.	
<i>Glaze</i> —83	„	Fritt	.	.	.	
12	„	Stone	.	.	.	
32	„	White Lead	.	.	.	

20

CHINA GLAZE.

<i>Fritt</i> —100	lbs.	Stone	.	.	.	} Body Nos. 17, 30.
90	„	Flint	.	.	.	
100	„	Whiting	.	.	.	
150	„	Borax	.	.	.	
28	„	China Clay	.	.	.	
24	„	Carbonate Soda	.	.	.	
<i>Glaze</i> —360	„	Fritt	.	.	.	
200	„	Stone	.	.	.	
60	„	Flint	.	.	.	
100	„	White Lead	.	.	.	
30	„	Felspar	.	.	.	

21

CHINA GLAZE.

<i>Fritt</i> —207	lbs.	Borax	.	.	.	} Body No. 29.
60	„	China Clay	.	.	.	
100	„	Stone	.	.	.	
80	„	Flint	.	.	.	
80	„	Whiting	.	.	.	
<i>Glaze</i> —520	„	Fritt	.	.	.	
59	„	White Lead	.	.	.	
59	„	Stone	.	.	.	
59	„	Flint	.	.	.	
			.	.	.	

22

CHINA GLAZE.

<i>Fritt</i> —200	lbs.	Stone	.	.	.	}
100	„	Flint	.	.	.	
48	„	Whiting	.	.	.	
28	„	China Clay	.	.	.	
135	„	Borax	.	.	.	
<i>Glaze</i> —500	„	Fritt	.	.	.	
25	„	Whiting	.	.	.	
42	„	White Lead	.	.	.	
			.	.	.	
			.	.	.	

23

CHINA GLAZE.

<i>Fritt</i> —180	lbs.	Borax	.	.	.	}
160	„	Stone	.	.	.	
80	„	Flint	.	.	.	
80	„	Whiting	.	.	.	
30	„	China Clay	.	.	.	
24	„	Carbonate Soda	.	.	.	
<i>Glaze</i> —540	„	Fritt	.	.	.	}
80	„	Flint	.	.	.	
80	„	White Lead	.	.	.	

24

CHINA GLAZE.

<i>Fritt</i> —80	lbs.	Stone	.	.	.	}
90	„	White Lead	.	.	.	
76	„	Borax	.	.	.	
65	„	Flint	.	.	.	
44	„	Carbonate Soda	.	.	.	
10	„	Oxide Tin	.	.	.	
2	„	Enamel Blue	.	.	.	}
<i>Glaze</i> —320	„	Fritt	.	.	.	
100	„	White Lead	.	.	.	
100	„	Stone	.	.	.	}

25

MASON'S CHINA GLAZE.

<i>Fritt</i> —35	lbs.	Borax	.	.	.	}
58	„	Stone	.	.	.	
22	„	Flint	.	.	.	
22	„	Flint Glass	.	.	.	
<i>Glaze</i> —125	„	Fritt	.	.	.	}
75	„	White Lead	.	.	.	

26

CHINA GLAZE.

<i>Fritt</i> —60 lbs.	Borax	.	.	.
80	„ Stone	.	.	.
50	„ Whiting	.	.	.
40	„ Felspar	.	.	.
10	„ Nitre	.	.	.
10	„ Flint	.	.	.
<i>Glaze</i> —100	„ Fritt	.	.	.
45	„ Stone	.	.	.
32	„ White Lead	.	.	.

27

FRENCH GLAZE.

<i>Fritt</i> —120 parts	Felspar	.	.	.
200	„ Borax	.	.	.
150	„ Flint	.	.	.
40	„ China Clay	.	.	.
80	„ Whiting	.	.	.
<i>Glaze</i> —250	„ Fritt	.	.	.
65	„ White Lead	.	.	.
65	„ Felspar	.	.	.

28

CHINA GLAZE.

<i>Fritt</i> —135 lbs.	Felspar	.	.	.
75	„ Borax	.	.	.
37½	„ Paris White	.	.	.
30	„ Flint	.	.	.
<i>Glaze</i> —540	„ Fritt	.	.	.
108	„ China Clay	.	.	.

29

PRINTED GLAZE FOR CHINA.

<i>Fritt</i> —225 lbs.	Felspar	.	.	.
90	„ Borax	.	.	.
45	„ Paris White	.	.	.
45	„ Flint	.	.	.
<i>Glaze</i> —337	„ Fritt	.	.	.
67	„ China Clay	.	.	.

30

WHITE GLAZE.

<i>Fritt</i> —202 lbs.	Felspar	.	.	.	}
112 „	Borax	.	.	.	
56 „	Paris White	.	.	.	
45 „	Flint	.	.	.	
<i>Glaze</i> —367 „	Fritt	.	.	.	}
30 „	China Clay	.	.	.	
12 „	White Lead	.	.	.	

IRONSTONE GLAZES.

1

LONGPORT OLD STONE GLAZE.

100 lbs.	Lead	.	.	.	}	
45 „	Stone	.	.	.		Body
25 „	Flint	.	.	.		Nos. 2, 3, 11, 16,
15 „	China Clay	.	.	.		17.
5 „	Flint Glass	.	.	.		

This is one of the oldest and most successful unfritted glazes known in the Potteries.

2

IRONSTONE GLAZE.

<i>Fritt</i> —38 lbs.	Tinical	.	.	.	}	
25 „	Stone	.	.	.		
20 „	Flint	.	.	.		
18 „	Whiting	.	.	.		
15 „	China Clay	.	.	.		Body
<i>Glaze</i> —160 „	Fritt	.	.	.	}	Nos. 5, 6, 12.
32 „	Stone	.	.	.		
32 „	Flint	.	.	.		
57 „	White Lead	.	.	.		

3 IRONSTONE GLAZE.

<i>Fritt</i> —18 lbs. Borax	.	.	.	} Body Nos. 7, 13.
40 „ Stone	.	.	.	
20 „ Flint	.	.	.	
20 „ Glass	.	.	.	
<i>Glaze</i> —To each 140 lbs. Fritt add,				
75 lbs. White Lead	.	.	.	

4 IRONSTONE GLAZE.

<i>Fritt</i> —30 lbs. Borax	.	.	.	} Body No. 8.
70 „ Stone	.	.	.	
<i>Glaze</i> —To above add,				
90 lbs. Stone	.	.	.	
50 „ Flint	.	.	.	
40 „ Whiting	.	.	.	
150 „ White Lead	.	.	.	

5 SEMI-PORCELAIN GLAZE.

<i>Fritt</i> —100 lbs. Borax	.	.	.	}
65 „ Stone	.	.	.	
55 „ Whiting	.	.	.	
60 „ Flint	.	.	.	
20 „ China Clay	.	.	.	
<i>Glaze</i> —200 „ Fritt	.	.	.	
120 „ Stone	.	.	.	
60 „ White Lead	.	.	.	

6 STONE GLAZE.

<i>Fritt</i> —135 lbs. Borax	.	.	.	}
112 „ Stone	.	.	.	
90 „ Flint	.	.	.	
90 „ Whiting	.	.	.	
68 „ China Clay	.	.	.	
<i>Glaze</i> —530 „ Fritt	.	.	.	
106 „ Stone	.	.	.	
158 „ White Lead	.	.	.	
104 „ Flint	.	.	.	

7

IRONSTONE GLAZE.

<i>Fritt</i> —90 lbs.	Stone	.	.	.	}
20 „	Salts of Soda	.	.	.	
<i>Glaze</i> —33 „	Fritt	.	.	.	
33 „	Stone	.	.	.	
85 „	Whiting	.	.	.	
80 „	White Lead	.	.	.	

EARTHENWARE GLAZES.

I

BEST WHITE GLAZE.

<i>Fritt</i> —140 lbs.	Borax	.	.	.	}	Body No. 1.
80 „	Stone	.	.	.		
115 „	Flint	.	.	.		
70 „	Whiting	.	.	.		
25 „	China Clay	.	.	.		
<i>Glaze</i> —350 „	Fritt	.	.	.		
210 „	Stone	.	.	.		
135 „	White Lead	.	.	.		
45 „	Flint	.	.	.		
9½ ozs.	Stain	.	.	.		

2

No. 8 GLAZE.

<i>Fritt</i> —100 lbs.	Borax	.	.	.	}	Body No. 2.	
50 „	Stone	.	.	.			
40 „	Flint	.	.	.			
40 „	Whiting	.	.	.			
30 „	China Clay	.	.	.			
<i>Glaze</i> —180 „	Fritt	.	.	.	}		
36 „	Stone	.	.	.			
36 „	Flint	.	.	.			
50 „	White Lead	.	.	.			
9 ozs	Stain	.	.	.			

3 MATT BLUE GLAZE.

<i>Fritt</i> —50 lbs.	Tinical
105	„ Stone
55	„ Flint
20	„ Oxide Tin
12	„ White Lead

Glaze—To above charge of Fritt add
10 lbs. White Lead, and “dip thin.”

4 COMMON PERSIAN GLAZE.

<i>Fritt</i> —80 lbs.	Tinical
90	„ Stone
60	„ Flint
40	„ Whiting
16	„ China Clay

<i>Glaze</i> —250	„ Fritt
95	„ Stone
25	„ Whiting
140	„ White Lead

Body
Nos. 3, 4, 6, 15,
17.

5 PRINTED GLAZE.

<i>Fritt</i> —60 lbs.	Tinical
38	„ Flint
28	„ Whiting
12	„ China Clay

<i>Glaze</i> —170	„ Fritt
40	„ Stone
56	„ White Lead

Body No. 6.

6

GLAZE FOR PINK.

<i>Fritt</i> —158	lbs.	Borax	.	.	.	}
70	„	Stone	.	.	.	
75	„	Flint	.	.	.	
70	„	Whiting	.	.	.	
55	„	China Clay	.	.	.	
12	„	Soda	.	.	.	}
<i>Glaze</i> —100	„	Fritt	.	.	.	
20	„	Stone	.	.	.	
20	„	Flint	.	.	.	
80	„	White Lead	.	.	.	

7

EARTHENWARE GLAZE.

<i>Fritt</i> —70	lbs.	Tinical	.	.	.	}
100	„	Stone	.	.	.	
50	„	Flint	.	.	.	
20	„	Whiting	.	.	.	
<i>Glaze</i> —100	„	Fritt	.	.	.	}
25	„	White Lead	.	.	.	

8

EARTHENWARE GLAZE.

<i>Fritt</i> —60	lbs.	Borax	.	.	.	}
100	„	Stone	.	.	.	
20	„	Flint	.	.	.	
30	„	Whiting	.	.	.	
10	„	China Clay	.	.	.	
<i>Glaze</i> —300	„	Fritt	.	.	.	}
180	„	Stone	.	.	.	
120	„	White Lead	.	.	.	
70	„	Flint	.	.	.	

9 EARTHENWARE GLAZE.

<i>Fritt</i> —120	lbs.	Tinical	.	.	.	}
180	„	Stone	.	.	.	
100	„	Flint	.	.	.	
60	„	Whiting	.	.	.	
10	„	China Clay	.	.	.	
<i>Glaze</i> —300	„	Fritt	.	.	.	}
100	„	White Lead	.	.	.	

10 EARTHENWARE GLAZE.

<i>Fritt</i> —60	lbs.	Borax	.	.	.	}
80	„	Stone	.	.	.	
20	„	Flint	.	.	.	
5	„	Whiting	.	.	.	
5	„	China Clay	.	.	.	
<i>Glaze</i> —300	„	Fritt	.	.	.	}
160	„	Stone	.	.	.	
30	„	Flint	.	.	.	
160	„	White Lead	.	.	.	

11 DAISY GLAZE.

<i>Fritt</i> —90	lbs.	Borax	.	.	.	}
50	„	Stone	.	.	.	
50	„	Flint	.	.	.	
20	„	Whiting	.	.	.	
<i>Glaze</i> —To above add,						}
70	lbs.	Stone	.	.	.	
70	„	White Lead	.	.	.	

12 FRENCH WHITE GLAZE.

<i>Fritt</i> —70 lbs.	Tineal	.	.	.	}
70 „	Stone	.	.	.	
70 „	Flint	.	.	.	
40 „	Whiting	.	.	.	
30 „	China Clay	.	.	.	
<i>Glaze</i> —To above add,					}
60 lbs.	Stone	.	.	.	
100 „	White Lead	.	.	.	

13 PERSIAN GLAZE.

<i>Fritt</i> —84 lbs.	Tineal	.	.	.	}
96 „	Stone	.	.	.	
64 „	Flint	.	.	.	
40 „	Whiting	.	.	.	
16 „	China Clay	.	.	.	
<i>Glaze</i> —240 „	Fritt	.	.	.	}
96 „	Stone	.	.	.	
140 „	White Lead	.	.	.	

14 FLOW GLAZE.

<i>Fritt</i> —40 lbs.	Tineal	.	.	.	}
50 „	Stone	.	.	.	
10 „	Felspar	.	.	.	
<i>Glaze</i> —85 „	Fritt	.	.	.	}
40 „	Flint	.	.	.	
40 „	Stone	.	.	.	
10 „	China Clay	.	.	.	
90 „	White Lead	.	.	.	

15 EARTHENWARE GLAZE.

<i>Fritt</i> —76	lbs.	Borax	.	.	.	}
71	„	Tinical	.	.	.	
81	„	Flint	.	.	.	
94	„	Stone	.	.	.	
81	„	Whiting	.	.	.	
33	„	China Clay	.	.	.	
<i>Glaze</i> —336	„	Fritt	.	.	.	}
200	„	Stone	.	.	.	
26	„	Flint	.	.	.	
78	„	White Lead	.	.	.	

16 BEST C. C. GLAZE.

<i>Fritt</i> —85	lbs.	Borax	.	.	.	}
50	„	Flint	.	.	.	
50	„	Stone	.	.	.	
20	„	Whiting	.	.	.	
<i>Glaze</i> —280	„	Fritt	.	.	.	}
91	„	Stone	.	.	.	
15	„	Flint	.	.	.	
190	„	White Lead	.	.	.	

17 MAYER'S GLAZE.

<i>Fritt</i> —70	lbs.	Tinical	.	.	.	}
50	„	Stone	.	.	.	
40	„	Whiting	.	.	.	
32	„	China Clay	.	.	.	
25	„	Flint Glass	.	.	.	
10	„	White Lead	.	.	.	
<i>Glaze</i> —90	„	Fritt	.	.	.	}
18	„	Stone	.	.	.	
18	„	Flint	.	.	.	
25	„	White Lead	.	.	.	

18 ALCOCK'S GLAZE.

<i>Fritt</i> —120	lbs.	Borax	.	.	.	}
65	„	Stone	.	.	.	
45	„	Whiting	.	.	.	
50	„	Flint	.	.	.	
25	„	China Clay	.	.	.	
<i>Glaze</i> —160	„	Fritt	.	.	.	}
40	„	Stone	.	.	.	
30	„	Flint	.	.	.	
60	„	White Lead	.	.	.	

19 HANLEY GLAZE.

<i>Fritt</i> —105	lbs.	Borax	.	.	.	}
100	„	Stone	.	.	.	
35	„	White Lead	.	.	.	
40	„	Flint	.	.	.	
18	„	Whiting	.	.	.	
<i>Glaze</i> —160	„	Fritt	.	.	.	}
24	„	Flint	.	.	.	
30	„	Stone	.	.	.	
80	„	White Lead	.	.	.	

20 FLOW GLAZE.

<i>Fritt</i> —50	lbs.	Stone	.	.	.	}
60	„	Carbonate Soda	.	.	.	
10	„	Fluor-spar	.	.	.	
<i>Glaze</i> —85	„	Fritt	.	.	.	}
40	„	Stone	.	.	.	
40	„	Flint	.	.	.	
10	„	China Clay	.	.	.	
90	„	White Lead	.	.	.	

21 EARTHENWARE GLAZE.

<i>Fritt</i> —105 lbs.	Tinical	.	.	.	}
100	„ Stone	.	.	.	
50	„ Flint	.	.	.	
20	„ Whiting	.	.	.	
<i>Glaze</i> —100	„ Fritt	.	.	.	}
25	„ White Lead	.	.	.	

22 EARTHENWARE GLAZE.

<i>Fritt</i> —60 lbs.	Tinical	.	.	.	}
100	„ Stone	.	.	.	
50	„ Flint	.	.	.	
20	„ Whiting	.	.	.	
<i>Glaze</i> —100	„ Fritt	.	.	.	}
250	„ White Lead	.	.	.	

23 EARTHENWARE GLAZE.

<i>Fritt</i> —67 lbs.	Tinical	.	.	.	}
50	„ Flint	.	.	.	
100	„ Stone	.	.	.	
20	„ Whiting	.	.	.	
<i>Glaze</i> —180	„ Fritt	.	.	.	}
40	„ White Lead	.	.	.	

24 EARTHENWARE GLAZE.

<i>Fritt</i> —120 lbs.	Tinical	.	.	.	}
102	„ Flint	.	.	.	
54	„ Whiting	.	.	.	
36	„ China Clay	.	.	.	
<i>Glaze</i> —200	„ Fritt	.	.	.	}
100	„ Stone	.	.	.	
10	„ Felspar	.	.	.	
65	„ White Lead	.	.	.	

25 FELSPATHIC GLAZE.

<i>Fritt</i> —100	lbs.	Felspar	.	.	.	}
46	„	Bicarbonate Soda	.	.	.	
10	„	White Lead	.	.	.	
10	„	French Chalk	.	.	.	
3	„	China Clay	.	.	.	
<i>Glaze</i> —150	„	Fritt	.	.	.	}
80	„	Felspar	.	.	.	
46	„	White Lead	.	.	.	

26 RAW GLAZE.

100	lbs.	Felspar	.	.	.	}	Ground for use.
110	„	White Lead	.	.	.		
10	„	Whiting	.	.	.		

27 EARTHENWARE GLAZE.

<i>Fritt</i> —160	lbs.	Borax	.	.	.	}	Body Nos. 11 and 17.
80	„	Flint	.	.	.		
80	„	Stone	.	.	.		
20	„	China Clay	.	.	.		
60	„	Whiting	.	.	.		
<i>Glaze</i> —200	„	Fritt	.	.	.	}	
200	„	Stone	.	.	.		
120	„	White Lead	.	.	.		

28 EARTHENWARE GLAZE.

<i>Fritt</i> —40	lbs.	Borax	.	.	.	}
25	„	Stone	.	.	.	
20	„	Flint	.	.	.	
18	„	Whiting	.	.	.	
15	„	China Clay	.	.	.	
<i>Glaze</i> —160	„	Fritt	.	.	.	}
32	„	Stone	.	.	.	
32	„	Flint	.	.	.	
75	„	White Lead	.	.	.	

29

C. C. GLAZE.

<i>Fritt</i> —100	lbs.	Borax	.	.	.	}
100	„	Stone	.	.	.	
50	„	Flint	.	.	.	
<i>Glaze</i> —100	„	Fritt	.	.	.	
100	„	White Lead	.	.	.	}

30

COMMON GLAZE.

<i>Fritt</i> —120	lbs.	Tineal	.	.	.	}	Body Nos. 22 and 23.
55	„	Flint	.	.	.		
70	„	Stone	.	.	.		
40	„	Whiting	.	.	.		
20	„	China Clay	.	.	.		
<i>Glaze</i> —180	„	Fritt	.	.	.	}	
50	„	Stone	.	.	.		
70	„	White Lead	.	.	.		

31

RAW WHITE GLAZE.

100	lbs.	White Lead	.	.	.	}	Grind for use.
50	„	Stone	.	.	.		
25	„	Flint	.	.	.		
10	„	Whiting	.	.	.		
10	„	China Clay	.	.	.		

32

PRINTED GLAZE.

<i>Fritt</i> —240	lbs.	Stone	.	.	.	}	Body No. 12.
90	„	Boracic Acid	.	.	.		
35	„	Carbonate Soda	.	.	.		
60	„	Whiting	.	.	.		
<i>Glaze</i> —720	„	Fritt	.	.	.	}	
314	„	Stone	.	.	.		
165	„	White Lead	.	.	.		

33 GRANITE GLAZE.

<i>Fritt</i> —135 lbs.	Borax	.	.	.	}	Body No. 18.
112	„ Stone	.	.	.		
90	„ Flint	.	.	.		
90	„ Whiting	.	.	.		
68	„ China Clay	.	.	.		
<i>Glaze</i> —530	„ Fritt	.	.	.	}	
104	„ Flint	.	.	.		
106	„ Stone	.	.	.		
158	„ Lead	.	.	.		

34 PRINTED GLAZE.

<i>Fritt</i> —90 lbs.	Boracic Acid	.	.	}
63	„ China Clay	.	.	
90	„ Whiting	.	.	
53	„ Carbonate Soda	.	.	
159	„ Flint	.	.	
<i>Glaze</i> —500	„ Fritt	.	.	}
174	„ Stone	.	.	
200	„ White Lead	.	.	

35 PRINTED GLAZE.

<i>Fritt</i> —240	lbs.	Stone	.	.	.	}
35	„	Carbonate Soda	.	.	.	
60	„	Whiting	.	.	.	
90	„	Boracic Acid	.	.	.	
<i>Glaze</i> —720	„	Fritt	.	.	.	}
314	„	Stone	.	.	.	
165	„	White Lead	.	.	.	

36 PRINTED GLAZE.

<i>Fritt</i> —65 lbs.	Tinical	.	.	.
85 „	Stone	.	.	.
45 „	Flint	.	.	.
25 „	Whiting	.	.	.
<i>Glaze</i> —170 „	Fritt	.	.	.
20 „	Stone	.	.	.
45 „	White Lead	.	.	.
5 „	Flint	.	.	.

37 PRINTED GLAZE.

<i>Fritt</i> —100 lbs.	Borax	.	.	.
50 „	Stone	.	.	.
40 „	Flint	.	.	.
40 „	Whiting	.	.	.
30 „	China Clay	.	.	.
<i>Glaze</i> —180 „	Fritt	.	.	.
36 „	Stone	.	.	.
50 „	White Lead	.	.	.
36 „	Flint	.	.	.

38 PRINTED GLAZE.

<i>Fritt</i> —100 lbs.	Borax	.	.	.
75 „	Stone	.	.	.
60 „	Flint	.	.	.
60 „	Whiting	.	.	.
45 „	China Clay	.	.	.
<i>Glaze</i> —200 „	Fritt	.	.	.
50 „	Stone	.	.	.
60 „	White Lead	.	.	.
40 „	Flint	.	.	.

39

BEST WHITE GLAZE.

<i>Fritt</i> —80	lbs.	Borax	.	.	.	}
104	„	Stone	.	.	.	
62	„	Flint	.	.	.	
36	„	Carbonate Soda	.	.	.	
104	„	Whiting	.	.	.	
134	„	Boracic Acid	.	.	.	
40	„	China Clay	.	.	.	
<i>Glaze</i> —270	„	Fritt	.	.	.	
150	„	Stone	.	.	.	
98	„	White Lead	.	.	.	
70	„	Flint	.	.	.	

40

MATT BLUE GLAZE.

<i>Fritt</i> —155	lbs.	Stone	.	.	.	}
97	„	Boracic Acid	.	.	.	
95	„	Carbonate Soda	.	.	.	
52	„	China Clay	.	.	.	
<i>Glaze</i> —370	„	Fritt	.	.	.	
94	„	Stone	.	.	.	
104	„	Flint	.	.	.	
62	„	Whiting	.	.	.	
180	„	White Lead	.	.	.	
			.	.	.	

41

EARTHENWARE PRINTED GLAZE.

<i>Fritt</i> —120	lbs.	Borax	.	.	.	}
56	„	Stone	.	.	.	
55	„	Whiting	.	.	.	
60	„	Flint	.	.	.	
19	„	China Clay	.	.	.	
15	„	Carbonate Soda	.	.	.	
<i>Glaze</i> —300	„	Fritt	.	.	.	
60	„	Flint	.	.	.	
135	„	Stone	.	.	.	
115	„	White Lead	.	.	.	

42

BORAX GLAZE FOR PINK.

<i>Fritt</i> —65 lbs. Borax	.	.	.	}
40 „ Flint	.	.	.	
25 „ China Clay	.	.	.	
25 „ Whiting	.	.	.	
15 „ Stone	.	.	.	
12 „ Carbonate Soda.	.	.	.	}
<i>Glaze</i> —60 „ Fritt	.	.	.	
12 „ Stone	.	.	.	
12 „ Flint	.	.	.	
24 „ White Lead	.	.	.	

43

TINCAL GLAZE.

<i>Fritt</i> —70 lbs. Tincal	.	.	.	}
50 „ Flint	.	.	.	
100 „ Stone	.	.	.	
20 „ Whiting	.	.	.	
<i>Glaze</i> —80 „ Fritt	.	.	.	}
20 „ White Lead	.	.	.	

44

TINCAL GLAZE.

<i>Fritt</i> —70 lbs. Tincal	.	.	.	}
80 „ Stone	.	.	.	
60 „ Flint	.	.	.	
20 „ Whiting	.	.	.	
10 „ Carbonate Soda.	.	.	.	
<i>Glaze</i> —To the above add,				}
60 lbs. Stone	.	.	.	
60 „ White Lead	.	.	.	
4 „ Borax	.	.	.	

45

BORAX GLAZE.

<i>Fritt</i> —62 lbs.	Borax	.	.	.	}
40	„ Flint	.	.	.	
25	„ China Clay	.	.	.	
25	„ Whiting	.	.	.	
15	„ Stone	.	.	.	
12	„ Carbonate Soda	.	.	.	
<i>Glaze</i> —150	„ Fritt	.	.	.	
30	„ Flint	.	.	.	
30	„ Stone	.	.	.	
60	„ White Lead	.	.	.	

46

BORACIC ACID GLAZE.

<i>Fritt</i> —40 lbs.	Boracic Acid	.	.	.	}
40	„ Whiting	.	.	.	
50	„ Stone	.	.	.	
30	„ Flint	.	.	.	
10	„ China Clay	.	.	.	
<i>Glaze</i> —200	„ Fritt	.	.	.	
50	„ Stone	.	.	.	
40	„ White Lead	.	.	.	
2	„ Borax	.	.	.	

47

BORACIC ACID GLAZE.

<i>Fritt</i> —20 lbs.	Boracic Acid	.	.	.	}
40	„ Carbonate Soda	.	.	.	
15	„ Whiting	.	.	.	
4	„ Nitre	.	.	.	
30	„ Flint	.	.	.	
20	„ Stone	.	.	.	
5	„ China Clay	.	.	.	
<i>Glaze</i> —80	„ Fritt	.	.	.	
50	„ Stone	.	.	.	
30	„ White Lead	.	.	.	

48

BORAX GLAZE.

<i>Fritt</i> —66 lbs.	Borax	.	.	.	}
30	„ Flint	.	.	.	
20	„ China Clay	.	.	.	
37	„ Stone	.	.	.	
30	„ Whiting	.	.	.	
<i>Glaze</i> —60	„ Fritt	.	.	.	}
15	„ Flint	.	.	.	
15	„ Stone	.	.	.	
25	„ White Lead	.	.	.	

49

WHITE GLAZE.

<i>Fritt</i> —100 lbs.	Stone	.	.	.	}
20	„ Flint Glass	.	.	.	
10	„ Flint	.	.	.	
10	„ Borax	.	.	.	
<i>Glaze</i> —100	„ Fritt	.	.	.	}
50	„ White Lead	.	.	.	

50

FRITT.

20 lbs.	Borax	.	.	.	}	Run down in saggers.
200	„ Stone	.	.	.		
50	„ Flint	.	.	.		
50	„ Whiting	.	.	.		
20	„ White Lead	.	.	.		
80	„ Soda	.	.	.		

51

WHITE GLAZE.

24 lbs.	Fritt, No. 50	.	.	.	}
60	„ Stone	.	.	.	
55	„ Flint	.	.	.	
70	„ White Lead	.	.	.	

52

C. C. GLAZE.

80 lbs.	Fritt, No. 50	.	.	.
120	„ Stone	.	.	.
30	„ Flint	.	.	.
15	„ Whiting	.	.	.
145	„ White Lead	.	.	.

53

PRINTED GLAZE.

160 lbs.	Fritt, No. 50	.	.	.
80	„ Stone	.	.	.
50	„ Flint	.	.	.
15	„ Whiting	.	.	.
100	„ White Lead	.	.	.

54

PRINTED GLAZE.

<i>Fritt</i> —108 lbs.	Borax	.	.	.
90	„ Stone	.	.	.
50	„ China Clay	.	.	.
12	„ Flint	.	.	.
12	„ Whiting	.	.	.
<i>Glaze</i> —80	„ Fritt	.	.	.
120	„ Stone	.	.	.
30	„ Flint	.	.	.
16	„ Whiting	.	.	.
140	„ White Lead	.	.	.

55

PRINTED GLAZE.

<i>Fritt</i> —200 lbs.	Stone	.	.	.
50	„ Flint	.	.	.
50	„ Whiting	.	.	.
20	„ Borax	.	.	.
20	„ White Lead	.	.	.
80	„ Carbonate Soda	.	.	.
<i>Glaze</i> —24	„ Fritt	.	.	.
40	„ Stone	.	.	.
25	„ Flint	.	.	.
5	„ Borax	.	.	.
140	„ White Lead	.	.	.

Run down in
saggers.

56

COMMON GLAZE.

<i>Fritt</i> —94	lbs.	Stone	.	.	.	}
25	„	Boracic Acid	.	.	.	
35	„	Carbonate Soda	.	.	.	
10	„	Whiting	.	.	.	
8	„	China Clay	.	.	.	
30	„	Flint	.	.	.	
6	„	Red Lead	.	.	.	}
<i>Glaze</i> —190	„	Fritt	.	.	.	
20	„	Stone	.	.	.	
10	„	White Lead	.	.	.	

GLAZES WITHOUT LEAD.

A good leadless glaze has long been sought after by potters, but it cannot be said that the right combination has yet been found. At a very hard fire a felspar glaze approaching the continental hard paste may be used, but this entirely deprives English earthenware of its simplicity and cheapness. Leadless glazes are notorious for bad working properties and for other faults. The following recipes are in use, but it is not claimed that they are perfect :—

I

COCKSON'S GLAZE.

90	lbs.	Borax	} To be well fritted, and then ground for use.
40	„	Felspar	
38	„	Flint	
36	„	Flint Glass	

2

LAKIN'S GLAZE.

60	lbs.	Borax	} To be fritted and ground, and to be dipped very thin.
60	„	Flint	
36	„	Stone	
4	„	Oxide Tin	

3 ROSE'S GOLD MEDAL LEADLESS GLAZE.

27 lbs. Felspar	} This mixture to be fritted, and then add three times the weight of fritt of Cal- cined Borax.
18 „ Borax	
4 „ Lynn Sand	
3 „ China Clay	
3 „ Nitre	
3 „ Carbonate Soda	

4 CHINA GLAZE WITHOUT LEAD.

<i>Fritt</i> —405 lbs. Felspar	}
225 „ Borax	
112 „ Whiting	
90 „ Flint	
<i>Glaze</i> —675 „ Fritt	}
135 „ China Clay	

MISCELLANEOUS GLAZES.

1 SAGGER WASH.

210 lbs. White Lead	}
120 „ Stone	
60 „ Flint	

2 SAGGER WASH.

150 lbs. White Lead	}
110 „ Stone	
90 „ Flint	

3 WASH FOR EARTHENWARE SAGGERS.

200 lbs. White Lead	}
100 „ Stone	
50 „ Flint	

COLOURED GLAZES.

There is probably not the demand now for coloured glazes that there once was, but the following recipes, culled mainly from the books of those who have passed away, may prove suggestive to the more scientific mind of the modern potter. These colours evidently constitute the palette of a kind of glaze kiln majolica.

1 AMBER GLAZE FOR BRISTOL STONEWARE.

110 lbs.	White Lead	.	.	.	}
15 "	Flint	.	.	.	
7½ "	Crocus Martis	.	.	.	

2 AMBER GLAZE.

110 lbs.	White Lead	.	.	.	}
15 "	Flint	.	.	.	
5 "	Crocus Martis	.	.	.	

3 DARK GREEN MAJOLICA.

18 lbs.	Red Lead	.	.	.	}
10 "	Flint	.	.	.	
5 "	Borate Lime	.	.	.	
5 "	Felspar	.	.	.	
2¾ "	Oxide Copper	.	.	.	

4 MAZARINE GLAZE FOR TILES.

8 lbs.	White Lead	.	.	.	}
1 lb.	Flint	.	.	.	
½ "	Oxide Cobalt	.	.	.	

5

MULBERRY GLAZE.

8 lbs. White Lead	.	.	.	}
1 lb. Flint	.	.	.	
$\frac{1}{2}$ „ Oxide Manganese	.	.	.	

6

GLAZE FOR COLOURING.

<i>Fritt</i> —24 lbs. Stone	.	.	.	}
9 „ Boracic Acid	.	.	.	
$3\frac{1}{2}$ „ Carbonate Soda	.	.	.	
6 „ Whiting	.	.	.	
<i>Glaze</i> —72 „ Fritt	.	.	.	}
31 „ Stone	.	.	.	
$16\frac{1}{2}$ „ White Lead	.	.	.	

7

PEA GREEN.

9 lbs. Glaze, No 6	.	.	.	}	Grind for use.
1 lb. White Lead	.	.	.		
$\frac{1}{2}$ „ Carbonate Copper	.	.	.		

8

PALE BRONZE.

9 lbs. Glaze, No. 6	.	.	.	}	Grind for use.
1 lb. White Lead	.	.	.		
$\frac{1}{2}$ „ Crocus Martis	.	.	.		
$\frac{1}{4}$ „ Carbonate Copper	.	.	.		

9

STRONG BRONZE.

9 lbs. Glaze, No. 6	.	.	.	}	Grind for use.
2 „ White Lead	.	.	.		
$\frac{1}{2}$ lb. Crocus Martis	.	.	.		
1 „ Carbonate Copper	.	.	.		

10

ORANGE.

11 lbs. White Lead	}	Grind for use.
$\frac{1}{2}$ lb. Flint		
$\frac{1}{2}$ „ Crocus Martis		

11

MAZARINE.

8 lbs. Glaze, No. 6	}	Grind for use.
1 lb. White Lead		
$\frac{1}{2}$ „ Prepared Oxide Cobalt		

12

GOLDEN BUFF.

9 lbs. Glaze, No. 6	}	Grind for use.
1 lb. White Lead		
1 „ Buff Base		

Buff Base—

3 lbs. Oxide Tin	}	Spread on plates and calcine easy in Glost Oven. Wash well.
6 „ Crude Antimony		
9 „ Red Lead		
$2\frac{1}{2}$ „ Sulphate Iron		

13

CHESTNUT BROWN.

9 lbs. Glaze, No. 6	}	
1 lb. White Lead		
1 „ Base		

Base—

$4\frac{1}{2}$ lbs. Oxide Zinc	}	Calcine at Biscuit heat, and wash well.
2 „ Bichromate Potash		
1 lb. Crocus Martis		

14

DARK GREEN.

9 lbs. Glaze, No. 6	}	
1 lb. White Lead		
1 „ Carbonate Copper		

15 STRONG FAWN GLAZE.

9 lbs. Glaze, No. 6	.	.	.	}
1 lb. White Lead	.	.	.	
$\frac{1}{4}$ „ Base	.	.	.	

Base—

4 lbs. Oxide Zinc	.	.	.	}	Calcine in Biscuit Oven.
2 „ Bichromate Potash	.	.	.		
1 lb. Crocus Martis	.	.	.		
2 lbs. Alumina	.	.	.		
$\frac{1}{2}$ lb. Flint	.	.	.		

16 RED BROWN.

9 lbs. Glaze, No. 6	.	.	.	}
$1\frac{1}{2}$ „ White Lead	.	.	.	
1 lb. Base, No. 15	.	.	.	

17 CHOCOLATE BROWN.

5 lbs. Glaze, No. 6	.	.	.	}
5 „ White Lead	.	.	.	
1 lb. Black Oxide Manganese	.	.	.	

18 BLUE GREEN.

9 lbs. Glaze, No. 6	.	.	.	}	Grind for use.
2 „ White Lead	.	.	.		
$\frac{1}{4}$ lb. Prepared Oxide Cobalt	.	.	.		
1 „ Carbonate Copper	.	.	.		

19 SEPIA BROWN.

3 lbs. Glaze, No. 6	.	.	.	}	Grind for use.
$2\frac{1}{2}$ „ White Lead	.	.	.		
$\frac{1}{2}$ lb. Black Oxide Manganese	.	.	.		

20

GOLDEN YELLOW.

5 lbs. Glaze, No. 6	.	.	.	} Grind for use.
5 „ White Lead	.	.	.	
2 „ Base below	.	.	.	

Base—

3 lbs. Oxide Tin	.	.	.	} Spread on Heeler Saggers, and fire in Biscuit Oven with plenty of air.
6 „ Crude Antimony	.	.	.	
9 „ Red Lead	.	.	.	
14 „ Common Alum.	.	.	.	

21

CRIMSON.

9 lbs. Glaze No. 6	.	.	.	} Grind for use.
1 lb. White Lead	.	.	.	
1 „ Base below	.	.	.	

Base—

19 lbs. Flint	.	.	.	} Mix well, and cal- cine in covered pots upon hardest part of Granite or China Biscuit.
21 „ Whiting	.	.	.	
6 „ Plaster Paris	.	.	.	
4 „ Fluor-Spar	.	.	.	
40 „ Oxide Tin	.	.	.	
1 lb. Bichromate Potash	.	.	.	

22

ROYAL BLUE.

60 lbs. White Lead	.	.	.	} Grind for use; if this is too strong, add a little No. 1 Glaze.
30 „ Stone	.	.	.	
10 „ Flint	.	.	.	
6 „ Prepared Oxide Cobalt	.	.	.	

23

CHOCOLATE.

40 lbs. Flint Glass	.	.	.	} Calcine in Glost Oven.
4½ „ Black Oxide Manganese	.	.	.	
15 „ of this Base	.	.	.	} Grind for use. Fire the Tiles
3 „ Glaze, No. 6	.	.	.	

dipped in this Glaze in easiest part of Glost Oven, or the tint will not be so rich.

24

IVORY ON WHITE.

9 lbs. Glaze, No. 6	.	.	.	} Grind for use.
1 lb. White Lead	.	.	.	
1 oz. Fawn Base, No. 15	.	.	.	

25

ORANGE GLAZE.

33 lbs. White Lead	.	.	.	}
4½ „ Flint	.	.	.	
1½ „ Crocus Martis	.	.	.	

26

PEA GREEN GLAZE.

8 lbs. White Lead	.	.	.	}
1 lb. Flint	.	.	.	
½ „ Black Oxide Copper	.	.	.	

27

MAZARINE GLAZE (LAKIN'S).

50 lbs. Flint	.	.	.	} Fritt and grind.
30 „ Borax	.	.	.	
22 „ White Lead	.	.	.	
10 „ Stone	.	.	.	
6 „ Carbonate Soda	.	.	.	
6 „ Oxide Tin	.	.	.	
3 „ Blue Calx	.	.	.	

28

RAW BLACK GLAZE.

100 lbs. White Lead	.	.	.	} Grind for use.
18 „ Flint	.	.	.	
40 „ Manganese	.	.	.	

29

SLATE GLAZE.

2 lbs. White Glaze	.	.	.	} Grind for use.
2 ozs. Oxide Nickel	.	.	.	

30

DRAB GLAZE.

60 lbs. Red Lead	.	.	.	} Grind for use.
10 „ Raddle	.	.	.	
2½ „ Flint	.	.	.	
5 ozs. Blue Calx	.	.	.	

MAJOLICA COLOURS.

For the sake of cheapness and simplicity these colours are frequently used in the raw state, but it is far better if they can be first fritted. Not only is the tint of colour arrived at with more certainty, but the effect upon the health of the workers is less prejudicial.

1

MAJOLICA SOFT GLAZE.

140 lbs. Red Lead	.	.	.	} Fritt in Glost Oven.
65 „ Lynn Sand	.	.	.	
50 „ Stone	.	.	.	
25 „ Borax	.	.	.	
10 „ Whiting	.	.	.	
5 „ Nitre	.	.	.	

2

BROWN.

33 lbs. White Lead	.	.	.	}
4½ „ Flint	.	.	.	
5 „ Crocus Martis	.	.	.	

3

WHITE.

16 lbs. Oxide Tin	.	.	.	} Calcine in Glost Oven.
12 „ Common Glaze	.	.	.	
8 „ Stone	.	.	.	
8 „ Borax	.	.	.	
4 „ White Lead	.	.	.	
1 lb. Carbonate Soda	.	.	.	

4

TURQUOISE.

Fritt, No. 1—

50 lbs.	Lynn Sand	.	.	.	} Calcine in Glost Oven.
6 "	Carbonate Soda	.	.	.	
4 "	Oxide Copper	.	.	.	
2½ "	Nitre	.	.	.	
2½ "	Bay Salt	.	.	.	

Fritt, No. 2—

50 lbs.	Fritt, No. 1	.	.	.	} Calcine in Glost Oven.
30 "	Oxide Tin	.	.	.	
20 "	Red Lead	.	.	.	
15 "	Enamel Flux, No 4	.	.	.	
15 "	Ground Glass	.	.	.	

Mixture—

18 lbs.	Fritt, No. 2	.	.	.	} Grind for use.
8 "	Enamel Flux, No. 4	.	.	.	

5

DARK GREEN.

18 lbs.	Red Lead	.	.	.	}
10 "	Flint	.	.	.	
5 "	Borate Lime	.	.	.	
5 "	Felspar	.	.	.	
2¾ "	Oxide Copper	.	.	.	





CHAPTER III.

GOLD.

IN the preparation and use of gold, success almost entirely hinges upon details of manipulation. The proportion of mercury used to alloy the gold of course influences the thickness of the gilding after firing; but the proper grinding of the alloyed metals, upon which ease and economy in working depend, is only to be attained by allowing the mixture to become old. Brown gold should first be crushed to a fine powder in a mortar, and after adding the mercury the two should be laid by for at least a week, receiving a thorough rubbing every day. By this means the alloy will become perfectly black before being sent to the mill, the grinding will be greatly accelerated, and flaking in the pan will be almost entirely prevented.

GOLD.

I LONGPORT BEST GOLD.

10 ozs. Brown Gold
7 „ Mercury
2 dwts. 12 grs. Bismuth
10 „ Flux, No. 8

2 LONGPORT CHASING GOLD.

18 dwts.	Brown Gold	.	.	.	}
15	„ Mercury	.	.	.	
1½	„ Silver	.	.	.	
½ dwt.	Prepared Bismuth	.	.	.	
1	„ Flux, No. 8	.	.	.	

3 LONGPORT COMMON GOLD.

16 dwts.	Brown Gold	.	.	.	}
12	„ Mercury	.	.	.	
4	„ Silver	.	.	.	
½ dwt.	Bismuth	.	.	.	
1	„ Flux, No. 8	.	.	.	

4 LAKIN'S GOLD.

12 dwts.	Green Gold	.	.	.	}
7½	„ Quicksilver	.	.	.	
1½	„ Oxide Silver	.	.	.	
1½	„ Gold Flux	.	.	.	

5 LAKIN'S BRONZE GOLD.

2½ dwts.	Ordinary Prepared Gold	.	.	.	}
2	„ Oxide of Copper	.	.	.	
1 dwt.	Mercury	.	.	.	
¼	„ Gold Flux	.	.	.	

6 HULME'S GOLD.

12 dwts.	Brown Gold	.	.	.	}
8	„ Quicksilver	.	.	.	
2	„ Oxide Silver	.	.	.	
1 dwt.	White Lead	.	.	.	

7 HULME'S BRONZE GOLD.

2½ dwts.	Burnish Gold . . .	}
3 „	Oxide Copper . . .	
1¼ „	Mercury . . .	
¼ dwt.	Flux, No. 8 . . .	

8 LIQUID GOLD FLUX.

4 ozs.	Canada Balsam . . .	}
2 „	Merbane Oil . . .	
40 drops	Oil of Lavender . . .	

9 MEDIUM GOLD.

10 dwts.	Brown Gold . . .	}
10 „	Mercury . . .	
5 „	Alloy . . .	
45 grs.	Oxide Bismuth . . .	
40 „	Prepared Silver . . .	

10 REGULAR GOLD.

10 dwts.	Brown Gold . . .	}
10 „	Mercury . . .	
3 „	Silver . . .	
5 „	Alloy . . .	
28 grs.	Oxide Bismuth . . .	

11 CHEAP GOLD.

10 dwts.	Brown Gold . . .	}
10 „	Mercury . . .	
8 „	Alloy . . .	
8 grs.	Silver . . .	
34 „	Flux, No. 8 . . .	

12

CHEAP GOLD.

10 dwts.	Brown Gold	.	.	.
10	„	Mercury	.	.
1 dwt.	12 grs.	Silver	.	.
3 dwts.	Alloy	.	.	.
12 grs.	Oxide Bismuth	.	.	.
17	„	Flux, No. 8	.	.

13

REGULAR GOLD.

10 dwts.	Brown Gold	.	.	.
10	„	Mercury	.	.
1 dwt.	Alloy	.	.	.
10 grs.	Silver	.	.	.
12	„	Oxide Bismuth	.	.
17	„	Flux, No. 8	.	.

14

HARD GOLD.

10 dwts.	Brown Gold	.	.	.
10	„	Mercury	.	.
11 grs.	Flux, No. 8	.	.	.
6	„	Silver	.	.
6	„	Alloy	.	.

15

REGULAR GOLD.

10 dwts.	Brown Gold	.	.	.
10	„	Mercury	.	.
10 grs.	Prepared Silver	.	.	.
10	„	Flux, No. 8	.	.

16

RICH GOLD.

1 oz.	Brown Gold	.	.	.
7½ dwts.	Mercury	.	.	.
30 grs.	Flux, No. 8	.	.	.

GOLD OR NOBLE COLOURS.**TO PREPARE "PURPLE OF CASSIUS."***Acid Solution, No. 1—*

3 parts Muriatic Acid (pure)	.	}
1 part Nitric Acid	.	}

Tin Solution, No. 2—

20 dwts. Muriatic Acid (pure)	.	}
10 „ Nitric Acid	.	}
20 „ Distilled Water	.	}

In 10 dwts. of acid solution, No. 1, contained in a glass or porcelain vessel, dissolve 1 dwts. brown gold.

In 50 dwts. of solution, No. 2, contained in a glass vessel, dissolve 10 dwts. well-granulated tin, which must be added by small pieces, each being allowed to dissolve before the addition of more. When the solution is complete it will assume the clear bright colour of brandy. The utmost care must be taken in this process. In a glass or porcelain vessel of sufficient size pour two quarts of pure distilled water, into which empty the gold solution, when it will become a pale straw colour, then add the tin solution very carefully. Stir continuously with a glass rod until the base is well formed, and this will be of a brilliant crimson tint. Time must be allowed for subsidence. The water should be removed gradually with a syphon and filtered, and the washing effected by constant changes of distilled water until the base is entirely freed from acid. The base is then collected on filter paper and dried, and is ready to be fluxed.

ROSE COLOUR.

Add to the above base,

1 dwts. Chloride of Silver	.	.	}
4 lbs. Rose Flux	.	.	}
1 lb. Flux, No. 8	.	.	}

and grind with care.

ROSE FLUX.

4 lbs. Cornish Stone	} Calcine in Glost Oven in an easy place.
8 „ Flint	
8 „ Red Lead	
12 „ Borax	
12 „ Flint Glass	
4 ozs. Nitre	

MARONE.

In preparing the base for marone, 10 dwts. of gold solution, No. 1, must be added to 20 dwts. of tin solution, No. 2. After precipitation add,

16 grs. Chloride of Silver	.	.	.	}
16 ozs. Marone Flux	.	.	.	}

and grind with care.

RUBY.

The base is the same as that for marone, but the mixture is—

6 grs. Chloride of Silver	.	.	.	}
4 ozs. Ruby Flux	.	.	.	}

MARONE FLUX.

36 ozs. Red Lead	} Calcine easy in Glost Oven.
14 „ Flint Glass	
50 „ Boracic Acid	

RUBY FLUX.

12 ozs. Red Lead	} Calcine easy in Glost Oven.
33 „ Flint Glass	
55 „ Borax	

ENAMEL COLOURS.— BASES.

1 RED.

Calcine sulphate of iron on heelers in hardening-on kiln, and wash thoroughly in hot water, afterwards drying for use. The tint of this colour entirely depends upon the heat at which it is calcined.

2 GREEN.

11 lbs. Alum	} Calcine in Biscuit Oven.
35 „ Oxide Chrome	
10 „ Oxide Zinc	

3 BLACK.

1 lb. Oxide Copper	} Calcine and grind well.
1 „ Oxide Cobalt	
1 „ Calcined Umber	

4 BUFF.

4 lbs. Tin Ash	}
1 lb. Crude Antimony	
1 „ Red Lead	
1 „ Red Oxide Iron	

5 GREEN.

8 lbs. Calcined Alum	} Calcine twice in Biscuit Oven.
1 lb. Oxide Chrome	
2 lbs. Black Oxide Cobalt	

6 BLUE.

9 lbs. Flint	} Calcine in Biscuit Oven.
13 „ Oxide Zinc	
3 „ Oxide Cobalt	
1 lb. Phosphate Soda	

7

BLUE.

40 lbs. Prepared Alum . . .	}	Calcine
3 „ Oxide Cobalt . . .		in Biscuit
$\frac{1}{2}$ lb. Oxide Zinc . . .		Oven.

8

BLUE GREEN.

2 lbs. Oxide Chrome . . .	}	Calcine in hard
1 lb. Zinc . . .		place of Biscuit
1 „ Carb. Cobalt . . .		Oven.

9

DEEP GREEN.

3 lbs. Oxide Chrome . . .	}	Grind in water,
1 lb. Carb. Cobalt . . .		and calcine in
		Biscuit Oven.

10

TURQUOISE.

Dissolve three parts prepared oxide of cobalt and one part oxide of zinc in sulphuric acid, then mix the solution with forty parts of alum dissolved in water. Evaporate to dryness, pound and calcine in crucibles at a red heat. If the turquoise is required to be green in tint, add to the alum solution about a sixteenth part of moist chromate of mercury.

11

SÈVRES TURQUOISE.

Dissolve two parts carbonate zinc and six parts carbonate cobalt in hydrochloric acid. Mix this with ninety-two parts of ammonia alum dissolved in water, after which add carbonate of soda until neutralised. Wash thoroughly and dry. Pass through a 30s. sieve, and calcine at a cherry-red heat until the *blue* shade is developed. Care must be taken not to have the heat too high, or it will become violet.

12

KING'S BLUE.

29 lbs. Carbonate Cobalt	.	.	.	} Calcine in Glost Oven.
29 „ Lynn Sand	.	.	.	
42 „ Carb. Potash	.	.	.	

13

YELLOW GREEN.

25 lbs. Flint	.	.	.	} Calcine at Biscuit heat, and pass through 60s. sieve. Wash thoroughly.
17½ „ Paris White	.	.	.	
17 „ Bichromate Potash	.	.	.	
5½ „ Plaster	.	.	.	
8 „ Felspar	.	.	.	
7½ „ Red Lead	.	.	.	

14

BLUE GREEN.

12 lbs. Prepared Alum	.	.	.	} Calcine in hardest place in Biscuit Oven.
3 „ Oxide Chrome	.	.	.	
3 „ Oxide Cobalt	.	.	.	

15

BLUE.

48 lbs. Prepared Alum	.	.	.	} Calcine in hard place in Biscuit Oven.
12 „ Oxide Zinc	.	.	.	
8 „ Oxide Cobalt	.	.	.	

16

DARK BLUE.

48 lbs. Oxide Zinc	.	.	.	} Calcine in hard place in Biscuit Oven.
24 „ Prepared Alum	.	.	.	
24 „ Flint	.	.	.	
9½ „ Oxide Cobalt	.	.	.	

17

BLUE.

24 lbs. Prepared Alum	.	.	.	} Calcine hard in Biscuit Oven.
24 „ Oxide Zinc	.	.	.	
4½ „ Oxide Cobalt	.	.	.	

18

TURQUOISE.

1 lb. Calcined Sulphate Copper . . .	} Calcine in Glost Oven.
2 lbs. Slaked Lime . . .	
2 „ Lynn Sand . . .	
$\frac{1}{2}$ lb. Common Salt . . .	

19

GREEN.

10 lbs. Bichromate Potash . . .	} Calcine in Biscuit Oven, and wash well.
5 „ Carbonate Cobalt . . .	
25 „ Prepared Alum . . .	

20

VICTORIA BLUE.

32 lbs. Oxide Zinc . . .	} Calcine in Biscuit Oven.
16 „ Flint . . .	
8 „ Boracic Acid . . .	
8 „ Oxide Cobalt . . .	
2 ozs. Nitrate of Potash . . .	

21

YELLOW BASE.

2 lbs. Crude Antimony . . .	} Calcine on dishes in easiest place of Glost Oven.
$4\frac{1}{2}$ „ Red Lead . . .	
$1\frac{1}{2}$ „ Oxide Tin . . .	

22

VICTORIA BLUE.

8 lbs. Flint . . .	} Calcine in Biscuit Oven.
4 „ Calcined Borax . . .	
6 „ Black Oxide Cobalt . . .	
16 „ Oxide Zinc . . .	

23

COMMON DARK GREEN.

$1\frac{1}{2}$ lbs. Oxide Chrome . . .	} Calcine in hardest part of Biscuit Oven, pound fine, and again calcine.
1 lb. Oxide Zinc . . .	
$2\frac{1}{2}$ lbs. Flint . . .	
$1\frac{1}{4}$ „ Borax . . .	
$7\frac{1}{2}$ „ Oxide Cobalt . . .	

24

MATT BLUE.

32 lbs.	Oxide Zinc	.	.	.	} Calcine in hardest part of Glost Oven.
16 "	Flint	.	.	.	
8 "	Borax	.	.	.	
6 "	Cobalt	.	.	.	

25

CORAL.

Dissolve $2\frac{1}{2}$ lbs. sugar of lead and 1 lb. bichromate potash separately in boiling water. Mix together, and allow to stand until a deposit is thrown down. The water must then be drained off, and the orange sediment put into plaster moulds to gradually dry.

26

MATT BLUE.

3 lbs.	Oxide Zinc	.	.	.	} Calcine in Glost Oven.
1 lb.	Oxide Cobalt	.	.	.	

27

PEACOCK BLUE.

16 lbs.	Prepared Alum	.	.	.	} Calcine in Biscuit Oven.
4 "	Oxide Cobalt	.	.	.	
2 "	Oxide Chrome	.	.	.	

28

PEACOCK BLUE.

19 lbs.	Base, No. 27	.	.	.	} Calcine in Biscuit Oven.
2 "	Oxide Cobalt	.	.	.	

29

BROWN.

40 lbs.	Oxide Zinc	.	.	.	} Calcine in Biscuit Oven.
6 "	Red Oxide Iron	.	.	.	
6 "	Oxide Chrome	.	.	.	
5 "	Litharge	.	.	.	
5 "	Boracic Acid	.	.	.	

30

FRENCH BROWN.

1 lb. Chromate Iron . . .	} Calcine on shallow saggers at top of Glost Oven.
1 $\frac{1}{4}$ lbs. Oxide Zinc . . .	
$\frac{1}{2}$ lb. Red Lead . . .	

31

BLUE.

40 lbs. Prepared Alum . . .	} Calcine twice in Biscuit Oven, and wash well.
3 „ Oxide Cobalt . . .	
1 $\frac{1}{2}$ „ Oxide Zinc . . .	

32

BLUE.

3 lbs. Oxide Cobalt . . .	} Calcine in Biscuit Oven.
6 „ Oxide Zinc . . .	
14 „ Red Lead . . .	
8 „ Flint . . .	

33

NAPOLEON GREEN.

10 lbs. Prepared Alum . . .	} Calcine in hard part of Biscuit Oven.
35 „ Oxide Chrome . . .	
10 „ Oxide Zinc . . .	
20 „ Cobalt . . .	

34

NAPOLEON GREEN.

40 lbs. Calcined Alum . . .	} Calcine in Biscuit Oven.
40 „ Cobalt . . .	
20 „ Oxide Chrome . . .	

35

TURQUOISE.

6 lbs. Oxide Zinc . . .	} Calcine at top of Glost Oven.
2 „ Oxide Copper . . .	
6 „ Red Lead . . .	
12 „ Felspar . . .	
2 „ Carbonate Soda . . .	
4 „ Flint . . .	
3 „ Paris White . . .	
3 „ Oxide Tin . . .	

36

BLUE.

40 lbs. Alum	.	.	.	} Calcine in Biscuit Oven.
3 „ Oxide Cobalt	.	.	.	
$\frac{1}{2}$ lb. Oxide Zinc	.	.	.	

37

BLUE.

32 lbs. Oxide Zinc	.	.	.	} Calcine in Glost Oven.
6 „ Oxide Cobalt	.	.	.	
16 „ Boracic Acid	.	.	.	

38

BLACK.

2 lbs. Oxide Cobalt	.	.	.	} Calcine at easy heat.
2 „ Oxide Manganese	.	.	.	
5 „ Nitrate Potash	.	.	.	

39

GREEN.

12 lbs. Calcined Alum	.	.	.	} Calcine in Biscuit Oven.
12 „ Chromate Mercury	.	.	.	
10 „ Oxide Cobalt	.	.	.	
3 „ Whiting	.	.	.	

40

BROWN.

6 lbs. Copperas	.	.	.	} Calcine in cru- cible until ebul- lition has ceased.
4 „ Sulphate Zinc	.	.	.	
13 „ Nitre	.	.	.	
				Wash well.

41

BROWN.

4 lbs. Copperas	.	.	.	} Treat as 40.
4 „ Sulphate Zinc	.	.	.	
10 „ Nitre	.	.	.	

42

BROWN.

2 lbs. Copperas	.	.	.	} Treat as 40.
2 „ Sulphate Magnesia	.	.	.	
6 „ Sulphate Zinc	.	.	.	
10 „ Nitre	.	.	.	

43

RED BROWN.

7 lbs. Oxide Zinc	.	.	.	} Calcine in Biscuit Oven.
1 $\frac{1}{4}$ „ Litharge	.	.	.	
1 $\frac{1}{4}$ „ Boracic Acid	.	.	.	
1 $\frac{1}{2}$ „ Oxide Chrome	.	.	.	
1 $\frac{1}{2}$ „ Red Oxide Iron	.	.	.	

44

TURQUOISE.

20 lbs. Flint	.	.	.	} Calcine in Glost Oven.
15 „ Calcined Soda	.	.	.	
3 „ Black Oxide Copper	.	.	.	

45

TURQUOISE.

25 lbs. Flint	.	.	.	} Calcine in Glost Oven.
19 „ Carbonate Soda	.	.	.	
3 „ Nitrate Potash	.	.	.	
3 „ Common Salt	.	.	.	
4 „ Oxide Copper	.	.	.	

46

TURQUOISE.

50 lbs. Flint	.	.	.	} Calcine in Glost Oven.
50 „ Carbonate Soda	.	.	.	
4 „ Oxide Copper	.	.	.	
3 „ Pearl Ash	.	.	.	
3 „ Common Salt	.	.	.	

47

BLACK.

1 oz. Calcined Copper	.	.	.	}
2 ozs. Calcined Umber	.	.	.	
2 $\frac{1}{2}$ „ Blue Calx	.	.	.	
4 „ Green Base, No. 14	.	.	.	

48

BLACK.

3 ozs. Oxide Manganese	.	.	.	}
1 oz. Iron Scales	.	.	.	
$\frac{1}{4}$ „ Calcined Copper	.	.	.	
4 ozs. Blue Calx	.	.	.	

49

ORANGE.

1 lb. Crude Antimony	.	.	.	}	Calcine in Glost Oven.
1 „ White Lead	.	.	.		
1 „ Red Oxide Iron	.	.	.		

50

ORANGE.

13 lbs. White Lead	.	.	.	}	Calcine in Glost Oven.
13 „ Antimony	.	.	.		
3 „ Burnt Sienna	.	.	.		
5 „ Red Oxide Iron	.	.	.		

ENAMEL FLUXES.

In a great number of fluxes in use a large proportion of glass is employed, due, doubtless, to the fact that the original compounders of these mixtures believed that glass was the most perfect combination of fusible materials. The great drawback to the use of glass is that its actual composition is not known to the potter. If glass be considered indispensable, it is most important that it should be procured of standard quality, and always from the same glass manufacturer. The cullet found in the possession of marine store dealers and other collectors is most unreliable, and usually consists of a large proportion of foreign glass which greatly differs from that employed in the original recipes. Most of these fluxes are described as being run down in Glost Oven; but it is better to subject them to a fire of shorter duration in a special kiln, as the long fire is apt to impair the finer qualities of the flux.

I

8 ozs. Flint Glass	} Run down in Glost Oven.
2 „ Red Lead	
2 „ Borax	

2

2 ozs. Flint Glass	} Run down in Glost Oven.
2 „ Flint	
6 drs. Borax	

3

4 ozs. Red Lead	} Run down in Glost Oven.
3½ „ Flint Glass	
2½ „ Borax	

4

5 ozs. Red Lead	} Run down in Glost Oven.
12 „ Flint Glass	
1 oz. Nitrate Potash	

5

1 oz. Nitre	} Run down in Glost Oven.
2 ozs. Flint Glass	
2 „ Red Lead	
1 oz. Flint	

6

3 ozs. Lead	} Run down in Glost Oven.
1 oz. Flint	

7

3 ozs. Flint Glass	} Run down in Glost Oven.
1 oz. Borax	
4 ozs. Flint	

8

6 lbs. Red Lead	}	Run down in easy part of Glost Oven.
4 „ Borax		
2 „ Flint		

9

6 ozs. Red Lead	}	Run down in easy part of Glost Oven.
6 „ Flint Glass		
1 oz. Borax		
1 „ Flint		

10

1 oz. Red Lead	}	Run down in Glost Oven.
1 „ Borax		
1 „ Litharge		
1 „ Flint Glass		

11

2 lbs. Borax	}	Run down in Glost Oven.
1 lb. Flint Glass		

12

4 lbs. Flint Glass	}	Run down in Glost Oven.
1½ „ Nitre		
1 lb. Borax		

13

2 lbs. Flint	}	Run down in Glost Oven.
3 „ Red Lead		
4 „ Borax		

14

4 lbs. Red Lead	}	Run down in Glost Oven.
3 „ Flint Glass		
2 „ Flint		
1½ „ Borax		

15

4 lbs. Borax	}	Run down in Glost Oven.
2 „ Flint		

16

2 lbs. Flint	}	Run down in Glost Oven.
1 lb. Borax		

17

12 lbs. Red Lead	}	Run down in Glost Oven.
5 „ Borax		
4 „ Flint Glass		

18

3½ lbs. Flint	}	Run down in easy place Glost Oven.
2 „ Lead		
3¼ „ Nitre		
6 „ Borax		

19

5 lbs. Borax	}	Run down in Glost Oven.
7 „ Flint Glass		
8 „ Red Lead		

20

8 lbs. Flint Glass	}	Run down in Glost Oven.
3 „ Red Lead		
3 „ Flint		
7½ „ Borax		

21

3 lbs. Red Lead	}	Run down in Glost Oven.
3 „ Borax		
2 „ Flint		

22

4 lbs. Borax	} Run down in Glost Oven.
3 „ Red Lead	
1½ „ Flint	

23

8 lbs. Red Lead	} Run down in Glost Oven.
3 „ Flint	
2 „ Flint Glass	
1 lb. Borax	

24

6 lbs. Red Lead	} Run down in Glost Oven.
2 „ Flint	
1½ „ Borax	

25

10 lbs. Flint Glass	} Run down in Glost Oven.
20 „ Red Lead	
5 „ Flint	
5 „ Borax	

26

10½ lbs. Flint Glass	} Run down in Glost Oven.
8 „ Borax	
6 „ Flint	
16 „ Red Lead	

27

3 lbs. Borax	} Run down in Glost Oven.
4 „ Red Lead	
2 „ Flint	

28

4 lbs. Borax	} Run down in hard place Glost Oven.
2 „ Flint Glass	
1 lb. China Stone	

29

13 lbs.	Red Lead	.	.	.	} Run down in Glost Oven.
2 $\frac{1}{4}$ „	Flint Glass	.	.	.	
4 $\frac{1}{2}$ „	Boracic Acid	.	.	.	

30

16 $\frac{1}{2}$ lbs.	Red Lead	.	.	.	} Run down in Glost Oven.
3 $\frac{3}{4}$ „	Flint Glass	.	.	.	
3 „	Borax	.	.	.	

ENAMEL COLOURS.

1

COPPER BLACK.

1 lb.	Caléined Copper	.	.	.	}
2 $\frac{1}{2}$ lbs.	Flux, No. 8	.	.	.	

2

COPPER BLACK.

1 lb.	Calcined Copper	.	.	.	}
1 oz.	„ Copperas	.	.	.	
1 lb.	Flux, No. 8	.	.	.	
2 ozs.	Flux, No. 3	.	.	.	

3

BLUE BLACK.

1 lb.	Blue Calx	.	.	.	}
1 „	Calcined Umber.	.	.	.	
6 lbs.	Flux, No. 8	.	.	.	
2 „	Green Base, No. 14	.	.	.	

4

SHINING BLACK.

1 oz.	Blue Calx	.	.	.	}
3 ozs.	Calcined Umber	.	.	.	
1 oz.	Flux, No. 8	.	.	.	

5

BLACK.

1 oz.	Blue Calx
1 „	Calcined Umber	.	.	.
3 ozs.	Green Base, No. 14	.	.	.
6 „	Flux, No. 22	.	.	.

6 **“WORCESTER” BLUE.**

16 ozs.	Flint Glass	.	.	.
1½ „	Blue Calx	.	.	.
1 oz.	Potash	.	.	.
1 „	White Enamel	.	.	.
3 ozs.	Red Lead	.	.	.

7 **“WORCESTER” BLUE.**

16 ozs.	Flint Glass	.	.	.
1½ „	Blue Calx	.	.	.
1 oz.	Borax	.	.	.
1 „	White Enamel	.	.	.
5 ozs.	Red Lead	.	.	.

8 **RHEAD AND GOODFELLOW'S BLUE.**

7½ lbs.	Flint Glass	.	.	.
½ lb.	Potash	.	.	.
1½ lbs.	Red Lead	.	.	.
½ lb.	Blue Calx	.	.	.
½ „	Saltpetre	.	.	.
½ „	White Enamel	.	.	.

9 **RHEAD AND GOODFELLOW'S DARK BLUE.**

8 lbs.	Flint Glass	.	.	.
1¾ „	Red Lead	.	.	.
¾ lb.	Blue Calx	.	.	.
¾ „	White Enamel	.	.	.
½ „	Pearl Ash	.	.	.

10 M. LEE'S ENAMEL BLUE.

16	ozs.	Flint Glass	.	.	.	}
$\frac{1}{2}$	oz.	China Stone	.	.	.	
5	ozs.	Red Lead	.	.	.	
$1\frac{1}{2}$	„	Blue Calx	.	.	.	
1	oz.	Nitre	.	.	.	
1	„	Potash	.	.	.	}

11 DARK BROWN.

1	lb.	Dark Copperas	.	.	.	}
5	lbs.	Flux, No. 8.	.	.	.	

12 DARK BROWN.

1	lb.	Calcined Umber	.	.	.	}
$\frac{1}{2}$	„	Burnt Sienna	.	.	.	
$3\frac{1}{2}$	lbs.	Flux, No. 7	.	.	.	

13 LIGHT BROWN.

1	lb.	Calcined Copper	.	.	.	}
6	lbs.	Flux, No. 10	.	.	.	
2	„	Copperas	.	.	.	
$\frac{1}{2}$	lb.	Ironstone	.	.	.	

14 DARK BROWN.

1	lb.	Copperas	.	.	.	}
2	lbs.	Flux, No. 8	.	.	.	
$\frac{3}{4}$	lb.	Flux, No. 7	.	.	.	

15 LIGHT BROWN.

1	lb.	Easy Calcined Umber	.	.	.	}
$3\frac{1}{2}$	lbs.	Flux, No. 1	.	.	.	

16 DEVONSHIRE BROWN.

1	lb.	Calcined Copperas	.	.	.	}
2	lbs.	Flux, No. 14	.	.	.	
$\frac{1}{2}$	lb.	Flux, No. 8	.	.	.	

17 **DEVONSHIRE BROWN.**

$\frac{1}{2}$ lb.	Crocus Martis	.	.	.	}
1	„ Manganese	.	.	.	
$\frac{1}{4}$	„ Calcined Copper	.	.	.	
3 lbs.	Antimony	.	.	.	
6	„ Flux, No. 7	.	.	.	

18 **HAIR BROWN.**

1 lb.	Oxide Manganese	.	.	.	}
3 lbs.	Flux, No. 8	.	.	.	

19 **HAIR BROWN.**

4 ozs.	Oxide Manganese	.	.	.	}
$\frac{1}{2}$ oz.	Blue Calx	.	.	.	
6 ozs.	Flux, No. 8	.	.	.	
$1\frac{1}{2}$ „	Flux, No. 2	.	.	.	

20 **CHOCOLATE BROWN.**

1 lb.	Chromate Iron	.	.	.	}
$\frac{3}{4}$ „	Chromate Lead	.	.	.	
2 lbs.	Burnt Sienna	.	.	.	
3 „	Oxide Zinc	.	.	.	
8 „	Flux, No. 7	.	.	.	

21 **CHOCOLATE BROWN.**

4 lbs.	Crocus Martis	.	.	.	}
12 „	Flux, No. 8	.	.	.	

22 **WHITE ENANEL.**

10 lbs.	Arsenic	.	.	.	}
$13\frac{1}{2}$ „	Red Lead	.	.	.	
18 „	Flint Glass	.	.	.	
6 „	Borax	.	.	.	
6 „	Nitre	.	.	.	

23 WHITE ENAMEL FOR JET.

17	lbs.	Arsenic
20	„	Red Lead
16	„	Flint Glass
7½	„	Borax
6¾	„	Nitre

24 ETCHING COLOUR FOR JET.

1¼	lbs.	Borax
1	lb.	Flint Glass
1¼	lbs.	Flint
3	„	Litharge

25 ETCHING COLOUR FOR JET.

3	lbs.	Borax
2¼	„	Flint
3	„	Flint Glass
3¼	„	Lead

Run down in
Enamel Kiln

26 FAWN FOR H. K.

4	lbs.	U. G. Devonshire Brown,
		No. 16
10	„	Flux, No. 8

Grind for use.

27 FAWN FOR REGULAR KILN.

6	lbs.	U. G. Devonshire Brown,
		No. 16
12	„	Flux, No. 8

Grind for use.

28 YELLOW GREEN.

2	lbs.	Green Base, No. 2
½	lb.	Yellow Base, No. 21
3	lbs.	Flux, No. 1

29 **YELLOW GREEN.**

2 lbs. Green Base, No. 2	.	.	.	}
$\frac{1}{2}$ lb. Yellow Base, No. 21	.	.	.	}
2 lbs. Flux, No. 9	.	.	.	}

30 **POMONA GREEN.**

1 lb. Oxide Green Chrome	.	.	.	}
$2\frac{1}{2}$ lbs. Flux, No. 6	.	.	.	}
1 „ Flux, No. 3	.	.	.	}

31 **POMONA GREEN.**

2 lbs. Oxide Green Chrome	.	.	.	}
3 „ Flux, No. 6	.	.	.	}
2 „ Flux, No. 1	.	.	.	}

32 **PEA GREEN.**

2 lbs. Green Base, No. 2	.	.	.	}
$\frac{1}{2}$ lb. Yellow Base, No. 21	.	.	.	}
3 lbs. Flux, No. 1	.	.	.	}

33 **BLUE GREEN.**

5 lbs. Oxide Chrome	.	.	.	} Run down.
5 „ Oxide Cobalt	.	.	.	
12 „ Alum	.	.	.	
36 „ Flux, No. 29	.	.	.	

34 **ORANGE RED.**

1 oz. Colcothar	.	.	.	}
3 ozs. Flux, No. 8	.	.	.	}

35 **ORANGE RED.**

$4\frac{1}{2}$ lbs. Colcothar	.	.	.	}
3 „ Flux, No. 7	.	.	.	}
1 lb. Flux, No. 8	.	.	.	}

36 **ORANGE RED.**

1 lb. Burnt Sienna	.	.	.	}
$2\frac{1}{2}$ lbs. Flux, No. 8	.	.	.	}

37 NASTURTIUM RED FOR GILDING ON.

2 lbs.	Bichromate Potash	} Run down.
30	„ Red Lead	
10	„ Nitrate Lead	
5	„ Calcined Borax	
5	„ Flint	

38 RAISED COMPOSITION.

30 ozs.	Yellow Base, No. 21	}
8	„ Flux, No. 8	
6	„ Tin Ash	
20	„ Orange, No. 36	

39 VELLUM FOR MENUS.

21 ozs.	Red Lead	} Calcine in Glost Oven.
4	„ Tin Ash	
6	„ Borax	
20	„ Flint	

40 TURQUOISE.

2 lbs.	Turquoise Base, No. 18	} Calcine in Glost Oven.
1½	„ Borax	
¾ lb.	Oxide Zinc	
½	„ Common Salt	

41 HARD KILN TURQUOISE.

2 ozs.	Borax	} Well crushed and mixed.
2	„ China Stone	
1 oz.	Flint	

Then add—

¼ oz.	Carbonate Zinc	}
½	„ Nitrate Copper	
2 dwts.	Common Salt	

Calcine the whole low down in Glost Oven, ventilating the saggars.

42 **HARD KILN WHITE ENAMEL.**

2	ozs.	Borax	} Calcine in Glost Oven.
2	"	China Stone	
1	oz.	Flint	
$\frac{1}{2}$	"	Oxide Tin	

MIXED ENAMEL COLOURS.

In every manufactory there are in use a number of colours which are produced by the simple method of mixing together the products of different colour makers. Without a knowledge of the actual colours in use it is manifestly impossible to say how they may be combined, but it is hoped that the following mixtures may at least prove suggestive :—

1 DRAB.

2 $\frac{1}{2}$	lbs.	Enamel Blue	}
1 $\frac{1}{2}$	"	Chrome Green	
3 $\frac{3}{4}$	"	Fawn	

2 DISTANCE.

3	lbs.	Shining Black	}
1 $\frac{1}{2}$	"	Purple	
1	lb.	Orange	

3 DISTANCE.

4	lbs.	Shining Black	}
1	lb.	Orange	
1	"	Rose Colour	
1	"	Purple	

4 BUFF FOR EARTHENWARE GROUNDS.

1	lb.	U.G. Orange	}
2	lbs.	Enamel Yellow	
6	"	Enamel Orange	

5 LIGHT BUFF FOR EARTHENWARE.

2 lbs. Enamel Orange	}
1 lb. Rose Colour	}

6 SPRIG BROWN.

2 lbs. Dark Brown	}
1 lb. Purple	}

7 CELADON.

4 lbs. Enamel Blue	}
3 „ Chrome Green	}
12 „ Flux, No. 8	}

8 FAWN.

3 lbs. U. G. Orange	}
2 „ Enamel Red	}
4 „ Flux, No. 8	}

9 LILAC.

5½ lbs. Enamel Blue	}
½ lb. Rose Colour	}
½ „ Purple	}

10 LILAC.

7 lbs. Enamel Blue	}
3¼ „ Purple	}
2 „ Rose Colour	}

11 OLIVE.

2 lbs. Shining Black	}
1 lb. Enamel Yellow	}
½ „ Enamel Blue	}

12 STONE COLOUR.

12 lbs.	Enamel Blue	.	.	.	}
4 $\frac{1}{4}$ „	Rose Colour	.	.	.	
4 „	Dark Chrome Green	.	.	.	
2 „	U. G. Pink	.	.	.	

13 SALMON.

2 lbs.	U. G. Orange	.	.	.	}
5 $\frac{1}{2}$ „	Flux No. 8	.	.	.	

ANTIQUE AND VELLUM ENAMEL COLOURS.

1 BROWN BRONZE.

4 ozs.	Oxide Manganese	.	.	.	}
12 „	Flux, No. 8	.	.	.	
1 oz.	Tin Ash	.	.	.	

2 NAVY BLUE.

16	ozs.	Flint	}
8	„	Carbonate Potash	
12	„	Red Lead	
12	„	Flint Glass	
6	„	Oxide Cobalt	
2	„	Common Salt	
4	„	Tin Ash	

3 WINDSOR RED.

5 lbs.	Bichromate Potash	.	.	.	}
2 $\frac{1}{2}$ „	Nitrate Lead	.	.	.	
7 $\frac{1}{2}$ „	Red Lead	.	.	.	
1 $\frac{1}{4}$ „	Calcined Borax	.	.	.	
2 „	Tin Ash	.	.	.	
1 lb.	Flint Glass	.	.	.	

4 BRONZE GREEN.

3 lbs.	Calcined Nickel
1 lb.	Iron Scale
2 lbs.	Blue Calx
3	„ Borax
2	„ Flint
1 lb.	Red Lead
1	„ Tin Ash

5 EMERALD GREEN.

10 ozs.	Flint Glass
6½	„ Borax
6	„ Flint
18	„ Red Lead
6½	„ Unfluxed Yellow
6½	„ Calcined Copper
2½	„ Tin Ash

6 MOSS GREEN.

10 ozs.	Flint Glass
20	„ Red Lead
5	„ Borax
5	„ Flint
2	„ Calcined Copper
1 oz.	Tin Ash

7 STRAW.

18 ozs.	Red Lead
16	„ Flint
6	„ Borax
3	„ Tin Ash
2½	„ Enamel Yellow

8

STONE COLOUR.

3 lbs.	Enamel Blue	.	.	.
3	„ Landscape Brown	.	.	.
1 $\frac{1}{4}$	„ U. G. Orange	.	.	.
2	„ Best Rose Colour	.	.	.
2	„ Best Chrome Green	.	.	.
2	„ U. G. Pink	.	.	.

9

OATMEAL.

30 ozs.	Red Lead	.	.	.
24	„ Flint	.	.	.
16	„ Borax	.	.	.
7	„ Tin Ash	.	.	.
3	„ Stone Colour, No. 8	.	.	.

10

POMPADOUR.

10 ozs.	Red Lead	.	.	.
9	„ Flint	.	.	.
6	„ Borax	.	.	.
2	„ Tin Ash	.	.	.
$\frac{1}{2}$ oz.	Rose Colour	.	.	.

11

CRUSHED STRAWBERRY.

9 ozs.	Red Lead	.	.	.
10	„ Flint	.	.	.
5	„ Borax	.	.	.
2 $\frac{1}{2}$	„ Tin Ash	.	.	.
3	„ Orange, No. 34	.	.	.
$\frac{1}{4}$ oz.	Ruby	.	.	.

12 MULBERRY VELLUM.

18	ozs.	Red Lead
16	„	Flint
6	„	Borax
5	„	Tin Ash
3	„	Devonshire Brown, No. 17

13 CRIMSON VELLUM.

10	ozs.	Red Lead
8	„	Flint
6	„	Borax
3	„	Tin Ash
2	„	Best Ruby

14 OLD GOLD VELLUM.

18	ozs.	Red Lead
18	„	Flint
7	„	Borax
3 $\frac{1}{2}$	„	Tin Ash
4	„	Enamel Orange

15 TERRA COTTA.

6	ozs.	Prepared Copperas
6	„	Borax
2	„	Red Lead
1	oz.	Flint
2	ozs.	Tin Ash

16 MYRTLE GREEN.

3	lbs.	Red Lead
2	„	Flint
$\frac{3}{4}$	lb.	Borax
$\frac{1}{2}$	„	Tin Ash
8	ozs.	Calcined Copper

UNDER-GLAZE COLOURS.

The majority of under-glaze colours are dependent upon the glaze itself for fluxing power, but in some cases it is desirable to soften the colour to some degree. Many so-called under-glaze fluxes are merely dilutents, no softer than the colour, but necessary in order to modify its strength.

FLUXES FOR UNDER-GLAZE COLOURS.**1 SOFT DRESDEN FLUX.**

10 lbs.	Borax	} Calcine in Biscuit Oven.
10 "	Flint	

2 FLUX.

37½ lbs.	Red Lead	} Run down in Glost Oven.
15 "	Flint	
4½ "	Borax	

3 FLUX.

9 lbs.	Flint	} Calcine in Biscuit Oven.
9 "	Stone	
4 "	Whiting	
3½ "	Borax	

4 FLOWING FLUX.

20 lbs.	Flint	} Calcine in Glost Oven.
6 "	Stone	
9 "	Borax	
4 "	Whiting	

5 DOVE FLUX.

10 lbs.	Tin Ash	} Calcine in Biscuit Oven.
40 "	Whiting	
20 "	Flint	

6

AMOY FLUX.

8 lbs.	China Clay	.	.	.	} Calcine in Biscuit Oven.
6 „	Ball Clay	.	.	.	
5 „	Whiting	.	.	.	
4 „	Tin Oxide	.	.	.	

7

BROSELEY FLUX.

4 lbs.	Stone	.	.	.	} Calcine in Biscuit Oven.
3 „	Flint	.	.	.	
4 „	Whiting	.	.	.	
3 „	Borax	.	.	.	
2 „	Nitre	.	.	.	

8

RATHBONE'S MATT BLUE FLUX.

13½ lbs.	Borax	.	.	.	} Run down in Glost Oven.
12 „	Red Lead	.	.	.	
11 „	Flint Glass	.	.	.	

9

RAW FLUX FOR BLUE.

6 lbs.	Flint	.	.	.	}
6 „	Whiting	.	.	.	
1 lb.	White Lead	.	.	.	

UNDER-GLAZE COLOURS.

I

BLUE FOR CHINA.

5 lbs.	Prepared Oxide Cobalt	.	.	.	}
10 „	Flux, No. 2	.	.	.	

2

EARTHENWARE COBALT.

12 lbs.	China Cobalt, No. 1	.	.	.	}
5 „	Flux, No. 1	.	.	.	

3 DRESDEN BLUE.

2 $\frac{3}{4}$ lbs.	Bamboo Blue
1 lb.	Black
1 „	Neutral, No. 5

4 BAMBOO BLUE.

4 lbs.	Black Oxide Cobalt
2 $\frac{1}{2}$ „	Ground Pitchers

5 NEUTRAL.

5 lbs.	Bamboo Blue, No. 4
3 „	Black
1 $\frac{1}{2}$ „	Flint

6 PEACOCK BLUE.

3 lbs.	Prepared Oxide Cobalt
$\frac{3}{4}$ lb.	Black
7 lbs.	Flux, No. 9.

7 STRONG WILLOW BLUE.

11 lbs.	Black Oxide Cobalt
2 „	Flint
2 „	Flint Glass

8 TEA WARE BLUE.

8 lbs.	Black Oxide Cobalt
4 $\frac{1}{2}$ „	Flint
2 $\frac{1}{2}$ „	Flint Glass

9 BROSELEY BLUE.

5 lbs.	Black Oxide Cobalt
9 „	Flint
5 „	Flint Glass

10 PALE BROSELEY BLUE.

4	lbs.	Black Oxide Cobalt	.	.	}
10	„	Flint	.	.	.
5	„	Flint Glass	.	.	.

11 FLOWING BLUE.

6½	lbs.	Black Oxide Cobalt	.	.	}
3¾	„	Flux, No. 6	.	.	.

12 FLOWING BLUE.

8	lbs.	Black Oxide Cobalt	.	.	}
5	„	Flux, No. 6	.	.	.

13 DARK BROSELEY BLUE.

6½	lbs.	Black Oxide Cobalt	.	.	}
6	„	Flux, No. 7.	.	.	.

14 PHEASANT BLUE.

½	lb.	Black Oxide Cobalt	.	.	}
9	lbs.	Flux, No. 6	.	.	.

15 DARK BANDING BLUE.

2	lbs.	Prepared Oxide Cobalt	.	.	}
10	„	Flux, No. 6	.	.	.

16 CROSS BLUE.

3	lbs.	Bamboo Blue, No. 17	.	.	}
3	„	Amoy Blue, No. 18	.	.	.

17 BAMBOO BLUE.

4	lbs.	Black Oxide Cobalt	.	.	}
2¼	„	Ground Pitchers	.	.	.

18 AMOY BLUE.

3 $\frac{3}{4}$ lbs.	Black Oxide Cobalt	.	.	.	}
6	„ Ground Pitchers	.	.	.	}

19 DARK IRONSTONE BLUE.

2 $\frac{3}{4}$ lbs.	Strong Cobalt	.	.	.	}
1 lb.	Black	.	.	.	}
1	„ Neutral	.	.	.	}
1	„ Flux, No. 6	.	.	.	}

20 COMMON PRINTING BLUE.

7 lbs.	Zaffre Blue	.	.	.	}
5	„ Flint	.	.	.	}
3	„ Flint Glass	.	.	.	}

21 GADROON BLUE.

2 $\frac{1}{2}$ lbs.	Oxide Cobalt	.	.	.	}
4	„ Flint	.	.	.	}
2	„ Flint Glass	.	.	.	}
1 lb.	China Clay	.	.	.	}

22 RATHBONE'S MATT BLUE.

1 lb. Black Oxide Cobalt	.	.	.	} Calcine in Biscuit Oven.
3 lbs. Oxide Zine	.	.	.	
Take of above base, 4 lbs.	.	.	.	} Calcine in Glost Oven.
Flux, No. 8, 5½ lbs.	.	.	.	

23 MATT BLUE.

$\frac{1}{2}$ lb.	Blue Calx	.	.	.	}	Calcine in hard Glost Oven, and wash well.
8 lbs.	Prepared Alum	.	.	.	}	
1 $\frac{1}{2}$ lbs.	Oxide Zine	.	.	.	}	
$\frac{3}{4}$ lb.	Flint Glass	.	.	.	}	

24 MATT BLUE (PALE).

$\frac{1}{4}$ lb.	Tea Ware Blue No. 8	.	.	.	} Calcine in Biscuit Oven.
8 lbs.	Prepared Alum	.	.	.	
$1\frac{1}{4}$ lbs.	Oxide Zinc	.	.	.	
$\frac{3}{4}$ lb.	Flint	.	.	.	

25 MATT BLUE.

$1\frac{1}{2}$ lbs.	Fine Blue Calx	.	.	.	} Calcine in Glost Oven.
3	„ Oxide Zinc	.	.	.	
1 lb.	Prepared Alum	.	.	.	
$5\frac{1}{2}$ lbs.	Flux, No. 8	.	.	.	

26 BROWN.

$5\frac{3}{4}$ lbs.	Chromate Iron	.	.	.	} Calcine in Biscuit Oven.
2	„ Manganese	.	.	.	
1 lb.	Black Antimony	.	.	.	
1	„ Crocus Martis	.	.	.	
$\frac{1}{4}$	„ Red Lead	.	.	.	

27 BROWN.

1 lb.	Calcined Umber	.	.	.	} Calcine in Biscuit Oven.
4 lbs.	Chromate Iron	.	.	.	
1 lb.	Manganese	.	.	.	
1	„ Crude Antimony	.	.	.	
$\frac{1}{4}$	„ Red Lead	.	.	.	

28 BROWN.

6 lbs.	Chromate Iron	.	.	.	} Calcine in Biscuit Oven.
1 lb.	Calcined Umber	.	.	.	
2 lbs.	Manganese	.	.	.	
$\frac{1}{4}$ lb.	Red Lead	.	.	.	

29 LESSORE'S BROWN.

For painting on Glaze to be fired in Glost Oven.

3 lbs.	Prepared Manganese	.	.	.	} Grind for use.
$\frac{1}{2}$ lb.	Enamel Flux, No. 8	.	.	.	

30 BROWN.

6 $\frac{1}{4}$ lbs.	Chromate Iron	.	.	.	} Calcine in Biscuit Oven.
$\frac{1}{2}$ lb.	Crude Antimony	.	.	.	
1 "	Manganese	.	.	.	
$\frac{1}{2}$ "	Red Lead	.	.	.	

31 BROWN.

5 lbs.	Crude Antimony	.	.	.	} Calcine in Biscuit Oven.
5 "	Red Lead	.	.	.	
2 $\frac{1}{4}$ "	Manganese	.	.	.	
1 $\frac{1}{4}$ "	Blue Calx	.	.	.	

32 PIEDMONT BLUE.

6 ozs.	Blue Calx	.	.	.	} Calcine in Glost Oven.
8 lbs.	Prepared Alum	.	.	.	
1 $\frac{1}{4}$ ozs.	Oxide Zinc	.	.	.	
$\frac{3}{4}$ oz.	Flint Glass	.	.	.	

33 PIEDMONT BLUE.

7 ozs.	Blue Calx	.	.	.	} Calcine in Glost Oven.
8 lbs.	Prepared Alum	.	.	.	
1 $\frac{1}{4}$ "	Oxide Zinc	.	.	.	
1 lb.	Flint Glass	.	.	.	

34 BROWN.

1 $\frac{1}{2}$ lbs.	Calcined Nickel	.	.	.	} Calcine in Biscuit Oven.
6 "	Crude Antimony	.	.	.	
3 $\frac{1}{2}$ "	Manganese	.	.	.	
1 $\frac{1}{2}$ "	Blue Calx.	.	.	.	

35 BROWN.

8 lbs.	Crude Antimony	.	.	.	} Calcine in Biscuit Oven.
8 "	Lead	.	.	.	
8 "	Manganese	.	.	.	
1 lb.	Blue Calx	.	.	.	

36

DARK BROWN.

6 lbs. Chromate Iron	} Calcine in Biscuit
1 lb. Manganese	
	Oven.

37

RED BROWN.

31 lbs. Manganese	} Calcine in Glost
6 „ Red Lead	
3½ „ Ground Glass	
6 „ Flint	
3½ „ Borax	
	Oven.

38

DARK BROWN.

4 lbs. Oxide Manganese	} Calcine in Glost
1¼ „ Green Oxide Chrome	
4 „ Stone	
1 lb. Enamel Flux, No. 8	
	Oven.

39

CHOCOLATE BROWN.

1 lb. Chromate Iron	} Calcine in Glost
3 lbs. Oxide Zinc	
¼ lb. Lead	
2 lbs. Tierra di Sienna	
	Oven.

40

BLACK.

3 lbs. Chromate Iron	} Calcine in Biscuit
1 lb. Iron Scales	
1 „ Oxide Nickel	
1 „ „ Manganese	
1½ lbs. Blue Calx	
	Oven.

41

BLACK.

12 lbs. Calcined Chromate Iron	} Calcine in Biscuit
1 lb. Cobalt Blue	
3 lbs. Flint Glass	
4 „ Flint	
	Oven.

42 **BLACK.**

2 lbs. Nickel	} Calcine in Biscuit Oven, and then wash well.
2 „ Blue Calx	
4 „ Ironstone	
1 $\frac{1}{4}$ „ Chromate Potash	
2 „ Manganese	

43 **BLACK.**

2 lbs. Chromate Iron	} Calcine in Biscuit Oven.
1 lb. Nickel	
1 „ Manganese	
$\frac{1}{4}$ „ Blue Calx	

44 **BLACK.**

$\frac{3}{4}$ lb. Manganese	} Calcine in Biscuit Oven.
1 $\frac{1}{4}$ lbs. Crude Antimony	
3 „ Red Lead	
3 „ Blue Calx	
$\frac{1}{4}$ „ Oxide Tin	

45 **LONGPORT BLUE GREEN.**

12 lbs. French Chrome	}
32 „ Oxide Zinc	
8 „ Prepared Oxide Cobalt	
5 „ Carbonate Potash	
5 „ Flint	
38 „ Flux, No. 1	}

46 **OLIVE GREEN.**

3 lbs. Calcined Nickel	}
1 lb. Iron Scales	
2 lbs. Best Cobalt Blue	
10 „ Flux, No. 1	

47 **OLIVE GREEN.**

2 lbs. Blue Calx	} Calcine in Glost Oven.
1½ „ Oxide Nickel	
1 lb. White Lead	

48 **GORDON GREEN.**

4 lbs. Oxide Chrome	} Calcine in Glost Oven.
3½ „ Oxide Zinc	
6 „ Flint	
1 lb. Flux, No. 1	

49 **VICTORIA GREEN.**

2 lbs. Chromate Lead	} Calcine in Biscuit Oven, and wash well.
3½ „ Flint	
3½ „ Whiting	
3 „ Bichromate Potash	

50 **VICTORIA GREEN.**

10 lbs. Chromate Lead	} Calcine in Biscuit Oven, and wash well.
30 „ Flint	
30 „ Whiting	
5 „ Sugar of Lead	

51 **LILAC.**

3½ lbs. Oxide Zinc	} Calcine in Biscuit Oven, and wash well.
3 „ Oxide Tin	
2 „ Chromate Lead	
1¼ „ Alum	
¾ lb. Black Oxide Cobalt	

52 **MULBERRY.**

54 lbs. Oxide Manganese	} Calcine in Glost Oven.
14 „ Nitre	
6 „ Borax	
6 „ Flint	
6 „ Flint Glass	

53

MULBERRY.

4 lbs. Blue Calx	}	Calcine in Glost Oven.
8 „ Oxide Manganese		
2 „ Nitre		
2 „ Borax		

54

MULBERRY.

1 lb. Black Oxide Cobalt	}	Calcine twice in Biscuit Oven.
4 lbs. Oxide Manganese		
1 lb. Ground Pitchers		

55

MULBERRY.

8 lbs. Oxide Manganese	}	Calcine in Biscuit Oven.
8 „ Oxide Tin		
2 „ Oxide Cobalt		
2½ „ Flint		
2 „ Chromate Iron		

56

ORANGE.

6 lbs. White Lead	}	Calcine in Biscuit Oven.
12 „ Glass of Antimony		
12 „ Crocus Martis		
36 „ Crude Antimony		

57

COMMON ORANGE.

6 lbs. Red Lead	}	Calcine in Biscuit Oven.
2½ „ Crocus Martis		
8½ „ Antimony		
1 lb. Oxide Tin		
3 lbs. Alum		

58

YELLOW.

4 lbs. Lead and Tin Ash	}	Calcine in Biscuit Oven.
1 lb. Crude Antimony		
2¼ lbs. White Lead		
1 lb. Flint		

59

YELLOW.

4 lbs. Lead and Tin Ash	.	.	.	} Calcine in Biscuit Oven.
1 lb. Litharge	.	.	.	
1 „ Crude Antimony	.	.	.	
1 „ Flint	.	.	.	
1 „ Flint Glass	.	.	.	

60

YELLOW.

4 lbs. Tin Ash	.	.	.	} Calcine in Biscuit Oven.
2 „ Crude Antimony	.	.	.	
2 „ Red Lead	.	.	.	

61

PINK.

20 lbs. Chromate Lead	.	.	.	} Calcine in Biscuit Oven, and wash repeatedly.
40 „ Tin Ash	.	.	.	
20 „ Whiting	.	.	.	
10 „ Lynn Sand	.	.	.	
20 „ Borax	.	.	.	

62

PINK.

18 lbs. Oxide Tin	.	.	.	} Calcine in Biscuit Oven, and wash well.
9 „ Whiting	.	.	.	
1 lb. Yellow Chrome	.	.	.	

63

PINK.

10 lbs. Chromate Lead	.	.	.	} Calcine in Biscuit Oven, and wash well.
160 „ Tin Ash	.	.	.	
80 „ Whiting	.	.	.	

64

PINK.

24 lbs. Tin Ash	.	.	.	} Calcine in hard place of Biscuit Oven, and wash well.
4 „ Ground Bone	.	.	.	
1½ „ Yellow Chrome	.	.	.	
8 „ Whiting	.	.	.	

65 **BEST PERSIAN PINK.**

2 $\frac{1}{4}$ lbs.	Oxide Tin	.	.	.	Calcine in Biscuit Oven, and wash well.
1 lb.	Whiting	.	.	.	
$\frac{1}{2}$ oz.	Green Oxide Chrome	.	.	.	
6 lbs.	China Stone	.	.	.	

66 **MARINE GREEN.**

1 $\frac{1}{4}$ lbs.	Oxide Chrome	.	.	.	Calcine in Biscuit Oven.
5 $\frac{1}{2}$ ozs.	Oxide Cobalt	.	.	.	
6	„ Oxide Zinc	.	.	.	
9	„ Whiting	.	.	.	

67 **BRONZE GREEN.**

1 lb.	Oxide Chrome	.	.	.	Calcine in Biscuit Oven.
2 $\frac{1}{4}$ lbs.	Flint	.	.	.	
1 $\frac{1}{4}$ „	Soda Crystals	.	.	.	

68 **VIOLET.**

50 ozs.	Pink, No. 61	.	.	.	Calcine in Biscuit Oven.
2	„ Flint	.	.	.	
4 $\frac{3}{4}$ „	Oxide Cobalt	.	.	.	
3	„ Carbonate Barytes	.	.	.	
$\frac{1}{4}$ oz.	Oxide Zinc	.	.	.	

69 **RUSSET BROWN.**

28 lbs.	Chromate Iron	.	.	.	Calcine in Biscuit Oven.
12	„ Oxide Manganese	.	.	.	
12	„ Iron Scales	.	.	.	
25	„ Oxide Zinc	.	.	.	
6	„ Litharge	.	.	.	

70 **VIOLET BROWN.**

$\frac{1}{2}$ lb.	Oxide Manganese	.	.	.	Calcine in Glost Oven.
4 lbs.	Carbonate Potash	.	.	.	
2	„ Red Lead	.	.	.	
5	„ Flint	.	.	.	

71

BLACK.

1 lb.	Bichromate Lead	.	.	.	} Spread on plates, and calcine in Glost Oven.
1	„ Oxide Manganese	.	.	.	
1	„ Blue Calx	

72

EDGING BLUE.

1 lb.	Black Oxide Cobalt	.	.	.	} Calcine in Biscuit Oven.
1	„ Whiting	.	.	.	
1	„ White Lead	.	.	.	
1	„ Flint	.	.	.	

73

LIGHT BROWN.

2 lbs.	White Lead	.	.	.	} Calcine in Glost Oven.
1 lb.	Antimony	
1	„ Oxide Manganese	.	.	.	

74

DARK BROWN.

3 lbs.	White Lead	.	.	.	} Calcine in Glost Oven.
6	„ Antimony	
1 lb.	Oxide Manganese	.	.	.	
1	„ Zaffre	.	.	.	

75

DARK BROWN.

3 lbs.	White Lead	.	.	.	} Calcine in Glost Oven.
2	„ Oxide Manganese	.	.	.	
1 lb.	Nitre	.	.	.	
1	„ Blue Calx	.	.	.	

76

BROWN.

3 lbs.	Glass Antimony	.	.	.	} Calcine in Biscuit Oven.
5	„ White Lead	.	.	.	
2	„ Oxide Manganese	.	.	.	
2	„ Blue Calx	

77

VICTORIA GREEN.

3 lbs. Whiting	}	Calcine in Glost Oven.
4½ „ Flint		
5 „ Chloride Lime		
6 „ Bichromate Potash		

78

YELLOW.

4 lbs. Tin Ashes	}	Calcine on Biscuit dishes at bottom Glost Oven.
1 lb. Red Lead		
1 „ Antimony		

79

YELLOW.

2 lbs. Litharge	}	Treat as 78.
2 „ Antimony		
1 lb. Tin Ash		

80

PINK.

40 lbs. Oxide Tin	}	Calcine in Biscuit Oven, and wash well.
20 „ Whiting		
3 „ Flint Glass		
1 lb. Oxide Chrome		

81

BROWN.

37 lbs. Red Lead	}	Calcine in Glost Oven.
37 „ Crude Antimony		
18 „ Oxide Manganese		
8 „ Blue Calx		

82

BLACK.

20 lbs. Red Lead	}	Calcine in Biscuit Oven.
25 „ Antimony		
15 „ Oxide Manganese		
40 „ Blue Calx		
5 „ Oxide Tin		

83

MULBERRY.

54 lbs.	Manganese	.	.	.	} Calcine in Glost Oven.
26 "	Blue Calx	.	.	.	
14 "	Nitre	.	.	.	
18 "	Flint Glass	.	.	.	
10 "	Flint	.	.	.	
6 "	Borax	.	.	.	

84

ORANGE.

3 lbs.	Litharge	.	.	.	} Spread on flinted dishes at top of Biscuit Oven.
2 "	Crude Antimony	.	.	.	
1 "	Crocus Martis	.	.	.	

85

UNIQUE.

43½ lbs.	Oxide Tin	.	.	.	} Calcine in hardest part of Biscuit Oven, and wash well.
9 "	Boracic Acid	.	.	.	
6 ozs.	Bichromate Potash	.	.	.	
22 "	Black Oxide Cobalt	.	.	.	

86

FLOWING BLUE.

5 lbs.	Black Oxide Cobalt	.	.	.	}
5 "	Flux, No. 4	.	.	.	

87

CHINA OVEN BLUE.

6 lbs.	Blue Cobalt	.	.	.	} Calcine in Glost Oven.
4 "	China Pitchers	.	.	.	
10 ozs.	Red Lead	.	.	.	

88

PRINTING BROWN.

12 lbs.	Chromate Iron	.	.	.	}
6 "	Oxide Manganese	.	.	.	

89

NAPIER BLUE.

2 lbs.	Blue Cobalt	.	.	.	}
5 "	Flint	.	.	.	
5 "	Whiting	.	.	.	

90

VICTORIA GREEN.

4 lbs. Bichromate Potash	} Calcine twice in earthenware biscuit, ventilating the saggers. Wash well.
4 „ Whiting	
4 „ Flint	
2 „ Fluato of Lime	

MIXED UNDER-GLAZE COLOURS.

These colours may, for the most part, be simply ground and then used. Where calcination is needed instructions are so given.

1

STAMPING BLACK.

5 lbs. Black	}
$\frac{1}{2}$ lb. Bamboo Blue	

2

BUFF.

4 lbs. Orange	}
$4\frac{1}{2}$ „ Yellow	

3

DOVE.

3 lbs. Blue	}
2 „ Pink	
1 lb. Brown	
8 lbs. China Stone	

4

FAWN.

$1\frac{1}{4}$ lbs. Pink	}
$\frac{1}{2}$ lb. Orange	

5

FAWN.

6 lbs. Pink	}
$2\frac{1}{2}$ „ Orange	
$\frac{1}{2}$ lb. Yellow	

6 CROSS GREEN.

3 lbs. Blue Green	}
1 lb. Sage Green	
$\frac{1}{2}$ „ Teaware Blue	

7 BAMBOO GREEN.

$2\frac{3}{4}$ lbs. Flowing Green	}
$\frac{1}{2}$ lb. Black	
$\frac{1}{2}$ „ Amoy Blue	

8 CROSSLET GREEN

4 lbs. Blue Green, No. 45	}
1 lb. Ground Pitchers	

9 GREEN.

$1\frac{1}{2}$ lbs. Victoria Green, No. 50	}	Caleine in Glost Oven.
$1\frac{3}{4}$ „ Oxide Chrome		

10 MARONE.

8 lbs. Pink	}
1 lb. Broseley Blue	
1 „ Amethyst	

11 MARONE.

18 lbs. Pink	}
1 lb. Blue	

12 NEUTRAL.

5 lbs. Amoy Blue	}
3 „ Black	
$1\frac{1}{2}$ „ Flint	

13 NEUTRAL.

6 lbs. Neutral, No. 12	}
$\frac{1}{2}$ lb. Amoy Blue	
2 lbs. Flint	

14 SLATE.

10 lbs. Black Oxide Cobalt	} Calcine in Biscuit Oven.
10 „ Pink	
5 „ Brown	
40 „ China Stone	

15 PURPLE BROWN.

30 lbs. Pink	}
1 lb. Black	

16 DOVER GREEN.

8 lbs. Green, No. 66	}
1½ „ Black	
5 „ Pitchers	

17 DOVE.

2 lbs. Black Oxide Cobalt	}
2 „ Pink	
1 lb. Brown	
8 lbs. China Stone	

18 UNIQUE.

10 lbs. Pink	} Calcine in Glost Oven.
1 lb. Oxide Cobalt	

19 AMETHYST.

5 lbs. U. G. Purple	}
¼ lb. Prepared Oxide Cobalt	

20 PURPLE.

8 lbs. Pink	}
1½ „ Napier Blue, No. 89	
½ lb. Oxide Cobalt	

21

LAVENDER.

6 lbs. Black	}
4 „ Willow Blue	
2 „ Pink	

22

CANTON.

10 lbs. U. G. Black	}
4 „ Prepared Oxide Cobalt	

FLOW POWDERS.

1

5 ozs. Red Lead	}
2 „ Common Salt	
2 „ Lime	

2

3 lbs. Paris White	}
3 „ Common Salt	
2 „ Borax	

A flow powder gives the best result when it is used at the top of the sagger. To effect this, sufficient powder is placed in a biscuit tea-cup, which is supported on a prop, so that the top of the cup nearly reaches to the level of the rim of the sagger.

OILS AND VARNISHES.**BALSAM OF SULPHUR.**

4 qts. Linseed Oil	.	.	} Mix the Resin and Oil on a slow fire. When the Resin is melted,
4 ozs. Black Resin	.	.	
1 lb. Sulphur	.	.	

and before the Oil boils, add the Sulphur. Boil the mixture very slowly until it "ropes" like Printer's Oil. If it will draw up two or three fine lines with the finger it is sufficient.

GROUNDING OIL.

4 qts. Linseed Oil	.	.	} Boil for two hours.
3 ozs. Red Lead	.	.	
2 „ Gum Mastic	.	.	
1 qt. Turpentine	.	.	

HARD GROUNDING OIL.

1 qt. Turpentine	.	.	} Grind the Turpentine and Gum until fine, add the Oil and Resin, and boil for two hours.
4 ozs. Gum Mastic	.	.	
$\frac{1}{4}$ pt. Linseed Oil	.	.	
$\frac{1}{2}$ oz. Resin	.	.	

PRINTER'S OIL.

4 qts. Linseed Oil	.	.	} Boil the first three together thoroughly, adding the Sulphur and Tar while the mixture is cooling.
1 qt. Rape Oil	.	.	
2 ozs. Red Lead	.	.	
3 „ Sulphur	.	.	
$\frac{1}{2}$ pt. Common Tar	.	.	



CHAPTER IV.

MEANS AND METHODS.

RECLAMATION OF WASTE GOLD.

It will always pay a potter to recover the gold from waste himself, rather than to sell it in its crude condition. The small ingots of gold that run to the bottom of the crucible are readily marketable, and the firing costs only a trifle.

All rags, waste, old pencils, and residue must be carefully collected, and the gilders' cups completely emptied. The mass of waste should then be put into glazed saggars, and set fire to in the open air. When burned to an ash the whole must be carefully collected, and, if necessary, pulverised. Any flux containing an abundance of oxidising substances will answer. If borax be used it should be roasted beforehand, or the great expansion may cause overflowing and loss of gold. Borax and nitre make a good flux, and there should be no stint of quantity. For melting purposes a crucible is better than a sagger, because the tapering form of the bottom gathers the gold into a single lump. The crucible should not be completely filled with flux, and it is a good plan to mix the waste powder with a small quantity of flux, and then to make a small pit in the centre of the flux in the crucible, and to fill up this pit with the gold. By this means the precious metal is kept from contact with the walls of the crucible, and is encouraged to fall direct to the bottom.

As to heat, the top of china glost is sufficient, but there is some risk in placing a crucible full of soft flux at the top of a bung, so that it is better to use the bottom of a Biscuit Oven, placing the crucible in a sagger half full of flint, in case of a breakage. If these operations be carefully performed, a small button of fine gold will be found at the bottom of each crucible.

THE USE OF COBALT.

An infallible method of detecting impure oxide. Dissolve either black oxide or prepared oxide, as the case may be, in pure muriatic acid diluted with distilled water, which very readily becomes saturated with cobalt, the solution yielding crystals of a red colour inclining to blue. On the other hand, if the solution becomes green in colour, it is owing to the presence of nickel or arsenic, either of which is inimical to the brilliancy of colour; and oxide so impure must be used with extreme caution.

Cobalt fluxes must be well mixed, the different ingredients very finely ground and perfectly dried, and they should be fired in the "forebung" of the Glost Oven in strong chambers. After being chipped they will require to be ground and well dried before being mixed with the cobalt oxides. In mixing the oxides with the fluxes it is a good plan to pass the mass through a sieve, so as to ensure that the particulars may more easily concrete when in a state of fusion. The mixture will require to be calcined in the Glost Oven, on no account above the "bag," in well-flinted earthenware crucibles or very strong chambers. After firing, the colour must be chipped free from all flint and pieces of pitcher. It is needful that the colours should be well washed twice, first with hot and then with cold filtered water after grinding at the mill, and lastly, well dried.

For painting on the glaze the colour should be used pre-

cisely as is the case with enamel colours, a thin coat to be applied in the first instance, and in the second a much thicker one. It is a safer plan to dry the pieces when decorated in either an enamel or hardening-on kiln. This is to a great extent a preventive of the colours running.

Matt blue is always a difficult colour to deal with. It is almost impossible to use it except in printing, and even then constant losses arise from the breaking up of the colour. This fault may be to a great extent obviated by hardening the colour, while unglazed, through the glaze kiln itself instead of through the hardening-on kiln. By this means the colour becomes firmly fixed to the ware, which afterwards only requires to be dipped in the usual way.

ENAMEL COLOURS.

In the making of enamel colours too much stress cannot possibly be laid on cleanliness and care. It is well to pass colour mixtures through a 30s. sieve after being well incorporated. Care must be taken that sieves and other utensils used in the mixing are, in all cases, most thoroughly cleansed.

The ingredients must be ground remarkably fine, and then so perfectly dried as to leave not the least humidity. This is particularly enjoined in the case of flint.

In the grinding of enamel colours at the mill the pans cannot be kept too clean, and should be well washed and brushed after each grinding, particularly about the spindle boxes of the mullers.

In the fritting of enamel colours in the Glost Oven, except when otherwise directed, it is not expedient to place them above the "bag." Nothing spoils the tint of colours more than their being scorched.

The different materials composing the fluxes should be finely ground or sieved, and most thoroughly incorporated before being fritted. After being passed through the fire

great care must be taken that none of the sagger or crucible adheres to the colour, otherwise mishap might ensue.

Attention must always be paid to the grinding and drying of fluxes. It is an essential feature that, before being mixed with the bases of colours, they should be perfectly dry.

CHROME RED.

Dichromate of lead, as it is called chemically, may be obtained by boiling oxide or carbonate of lead with an aqueous solution of monochromate of potassium, or by digesting the neutral chromate of lead in a dilute solution of caustic potash. The residuum should be well washed with distilled water. It is an insoluble scarlet-coloured powder.

CHROME YELLOW.

The simple chromate of lead is obtained in the following manner:—To a solution of a soluble salt of lead the addition is made of an equal part of chromate of potassium in solution, both being at boiling point. If the solutions are mixed in a cool state the precipitate will be pale yellow.

CHROMATE OF BARYTES

is prepared by dropping a solution of chromate of potassium into a solution of chloride of barium. The yellow precipitate must be well washed, and is as insoluble in water as the sulphate of barytes. Care should be exercised in touching these substances and solutions on account of their poisonous character.

DIOXIDE OF MANGANESE,

when found in its natural state, takes the name of pyrolusite. It is in this form that it becomes useful to the manufacturers of pottery. The chemical bye-product, precipitated black oxide of manganese, is also largely used.

SESQUIOXIDE OF MANGANESE

may be obtained by heating pure dioxide in a crucible to redness until the evolution of oxygen has ceased, or by exposing protonitrate of manganese to a red heat, the sesquioxide in either case remaining in the shape of a black powder.

THE PREPARATION OF LIQUID OR FRENCH BRIGHT GOLD.

Note.—The preparation of liquid gold requires the greatest possible care, not only on account of its valuable nature, but also, where caution is not exercised, the brightness of the metal may be seriously affected.

The acids, as well as the balsam and essential oils, require to be of the greatest possible purity, and the utensils should be Bohemian glass or hard porcelain.

The gold to be used must be roasted fine yellow gold.

GOLD SOLUTION.

The first operation is to prepare a strong solution, which may be done by dissolving two ounces of yellow gold in six ounces of muriatic acid and two ounces of nitric acid. The solution must be effected in a large testing glass of extra thickness. The gold requires to be added to the acids in small quantities at a time, otherwise excessive ebullition might take place. The solution may be noticed by the continual effervescence. When this ceases it may be taken for granted that the whole of the gold is dissolved. To ensure, however, that this is perfectly accomplished, it will be as well to let the test glass be in proximity to a very moderate heat. To the gold solution now add two dwts. of best granulated tin procurable. The latter will have the effect of again causing effervescence. When this ceases the mixture is accomplished.

THE MENSTRUUM.

The menstruum for liquid gold is composed of two parts of gurgun balsam and one part of oil of amber. These constituents must be incorporated with great nicety over a slow fire, and it is highly essential that this also should be done carefully.

LIQUID GOLD FOR USE.

When the menstruum is well mixed, the gold solution is then gradually added to the menstruum in small quantities at a time, being well stirred continually with a glass rod until the whole is thoroughly blended, which will probably take half an hour. The mixture may then be found too thick for use, and in this case the following flux may be added to the mass until a proper consistency is assumed, which can only be ascertained by close observation and experiment:—

LIQUID GOLD FLUX.

14 ozs. Gurgun Balsam.

8 „ Oil of Amber.

$\frac{1}{3}$ „ Essential Oil of Rosemary.

It may be observed that the longer liquid gold is allowed to stand after preparation the better it is, as its appearance is heightened by age.





CHAPTER V.

CLASSIFICATION AND ANALYSIS.

CLASSIFICATION OF CLAY WARE.

CLASS I.—Body uniformly fluxed, dense, cannot be scratched with the knife, fairly granular, translucent, very sonorous, white and uniform.

PORCELAIN.

Tender Porcelain.—Body easily fusible.

English.—Body consists of bone ash, china clay, and stone with felspar. Glaze contains borax and lead.

French.—The body consists of a vitreous mass with clay. The glaze is a leaden one of hard consistency.

Real Porcelain.—Body and glaze difficult of fusion.

CLASS II.—Body dense, cannot be scratched with the knife, sonorous, finely granular, not translucent.

STONEWARE.

Salt-glazed Stoneware.—Body of a reddish grey or bluish fracture. Generally glazed with a salt glaze.

Bristol Stoneware.—Light drab body, vitreous. Glazed with a stone and calcium glaze.

Ironstone Ware.—Body usually white and semi-vitrified. Artificially coloured, and has a composite glaze containing silica, calcium, borax, lead and alum.

CLASS III.—Body earthy, porous, pretty hard, opaque, texture open, little sonorous.

EARTHENWARE.

Fine Earthenware.—Body hard, white and sonorous. Glaze: a soft white one, containing both borax and lead.

Delft or Common Earthenware.—Body finely granular, more or less of a yellow tint, with a soft transparent glaze.

CLASS IV.—Body earthy, very porous, opaque, soft. Homogeneous texture, always coloured.

Commonest Pottery.—Usually seen partly glazed and partly unglazed. The glaze, consisting of salt and litharge, always easy of fusion and transparent.

Lustre Ware.—Body earthy, porous, opaque, and very soft. Texture not entirely uniform; with a metallic glaze, having no transparency.

CLASS V.—Body more or less not uniform, always coloured, very soft, porous and open, not sonorous and opaque.

Bricks, Tiles and Ornaments.—Sometimes glazed body, infusible except at a very high temperature.

Fire-proof Crucibles.—Body difficult of fusion. Not glazed.

LORD PLAYFAIR'S ANALYSIS OF PURE CLAYS.

CHINA CLAY.

Silica	45·56
Alumina with trace of Oxide of Iron	40·76
Lime	2·17
Potassa with trace of Soda	1·90
Magnesia	traces
Phosphoric Acid	traces
Sulphuric Acid	faint traces
Water	9·61
	<hr/>
	100·00

BLUE CLAY.

Silica	46·38
Alumina	38·04
Protoxide of Iron	1·64
Lime	1·20
Magnesia	traces
Water	13·44
	<hr/>
	100·00

RED CLAY.

Silica	49·44
Alumina	34·26
Protoxide of Iron	7·74
Lime	1·48
Magnesia	5·14
Water	1·94
	<hr/>
	100·00

**THE MARKETS OF THE WORLD AND THE
TRADE QUALITY OF THE IMPORTS OF
ENGLISH CHINA AND EARTHENWARE.**

CLASSIFICATION.

CLASS I. represents the countries which take the finest china and the best kind of earthenware.

CLASS II. represents those countries which take medium china and earthenware, both common printed and painted.

CLASS III. represents those countries only taking the commonest china and earthenware.

CLASS I.

<i>British Possessions.</i>	<i>Foreign Possessions.</i>
Canada (with the exception of the upper half of the North-Western Provinces).	Austria.
Indian Empire (Bengal).	Denmark.
„ (Madras).	France.
Victoria.	Germany.
Southern Australia.	Hungary.
Western Australia.	Italy.
New South Wales.	Russia.
Queensland.	U.S. America.

CLASS II.

<i>British Possessions.</i>	<i>Foreign Possessions.</i>
Australia, Southern.	U.S. America.
„ Western.	The Brazils.
Bermudas.	Belgium.
Cape Colony.	Bulgaria.
Cyprus.	Denmark.
Hong-Kong.	Holland.
Indian Empire (Punjab)	Japan.
„ (Madras).	Portugal.
Natal.	Montenegro.
New South Wales.	Norway.
New Zealand.	Roumania.
Tasmania.	Servia.
Queensland.	Spain.
	Sweden.
	Switzerland.
	Turkey.

CLASS III.

British Possessions.

Bermudas.
 Borneo.
 Burnah.
 Ceylon.
 Guiana.
 Honduras.
 Jamaica.
 Labuan.
 Mauritius.
 Newfoundland.
 Straits Settlements.
 Tasmania.

Foreign Possessions.

Argentina.
 Bolivia.
 Cambodia.
 Chili.
 Cochin China.
 Colombia.
 Congo States.
 Costa Rica.
 Cuba.
 Ecuador.
 Guatemala.
 Hayti.
 Persia.
 Peru.
 Mexico.
 San Salvador.
 Uruguay.
 Venezuela.

Cases may be known of all three classes of ceramic being sent to a country. It is, however, an unusual procedure.

APPROXIMATE TIME AND FUEL SCALE FOR OVEN FIRING.

	Number of Hours Fired.	Approximate Amount of Coal Consumed.
China Biscuit Oven	35 to 45	10 tons.
Earthenware Biscuit Oven	30 „ 40	8 „
China Glost Oven	10 „ 14	5 „
Earthenware Glost Oven	9 „ 12	4 „
Regular Enamel Kilns	5 „ 6	23 cwt.
Hard Kilns	6 „ 7	27 „

ENAMEL KILN FIRING.

PYROMETRICAL TEST ON CHINA SLATES WITH THUMB TRIALS
IN MAROON.

Estimated No. of Degrees Centigrade.	Estimated No. of Degrees Fahrenheit.	Gradation of Change of Tint.	Kiln Heat.
610	1130	Dirty Brown Tint	Regular Kiln.
650	1202	Brick Red	" "
690	1274	Brick Red passes to Rose, but Red retained on edges and thinner parts	" "
730	1346	Rose Colour passes to Purple	Hard Kiln.
770	1418	Rose Colour passes to Violet	" "
810	1490	Rose Colour passes to deep Violet	" "
850	1562	Violet becomes lighter	" "
890	1634	Rose Colour entirely disappears. Violet becomes pale	" "

STANDARD WEIGHTS OF POTTERS'
MATERIALS.

China Clay Slip should weigh 26 ounces to a pint.

Ball Clay	"	"	"	24	"	"
Whiting	"	"	"	26	"	"
Flint	"	"	"	32	"	"
Stone	"	"	"	32	"	"
Bone	"	"	"	30	"	"
Spar	"	"	"	32	"	"

DECORATED GOODS COUNT.

Article.						Numbers and Denominations.
Dinner Ware—						Count as 12 to dozen.
Plates,	10 inches	15
"	8	"	.	.	.	18
"	7	"	.	.	.	18
"	6	"	.	.	.	24
"	5	"	.	.	.	12
Dishes,	9	"	.	.	.	12
"	10	"	.	.	.	1 $\frac{1}{2}$ pieces.
"	12	"	.	.	.	2
"	14	"	.	.	.	2
"	16	"	.	.	.	2 $\frac{1}{2}$
"	18	"	.	.	.	2 $\frac{1}{2}$
Gravies,	16	"	.	.	.	3
"	18	"	.	.	.	3 $\frac{1}{2}$
"	20	"	.	.	.	2
Soup Tureen	Middles	2
"	Covers	2
"	Stands	1
Sauce Tureen	Middles	1
"	Covers	1
"	Stands	2 $\frac{1}{2}$ to dozen.
Vegetable Dishes,	8 inches	3
"	9	"	.	.	.	3
"	10	"	.	.	.	1 $\frac{1}{2}$
Sauce Boats	1 piece.
Sauce Boat Stands	3 pieces.
Salads	24
Fruit and Ice Saucers	24
Individual Pickles	36
"	Butters	1 piece.
Dessert Plates	1 $\frac{1}{2}$ pieces.
Low Comports	3
Tall	
Articles of Toilet Ware—						1 piece.
Ewer	1
Basin	1
Chamber	1
Soap	1
Upright Tray	1
Slop Jar	5 pieces.
Chamber Cover	1 or $\frac{3}{4}$ piece.
Brush Trays,	7 inches	1 $\frac{1}{2}$ pieces.
"	8	"	.	.	.	1 $\frac{3}{4}$
Teas	1 Tea.
Breakfasts	1 $\frac{1}{4}$ Teas.
Muffins,	6 inches	1 $\frac{1}{2}$
"	7	"	.	.	.	1 $\frac{1}{2}$
B. and B.'s	2
Slops	2
Sugars	1 $\frac{1}{2}$
Milks	2
Creams	2
Egg Cups	3 count as 2



CHAPTER VI.

COMPARATIVE LOSS OF WEIGHT OF CLAYS AND POTTERS' MATERIALS DURING DRYING AND FIRING.

OF each clay and material below named, 25 drams were taken in the commercial or damp state in which they were received, weighed with great care, and placed out on separate marked cards to air-dry by simple exposure on the top of the office desk for 20 hours, then finishing the drying by placing in front of the office fire for a short time, then weighing them again carefully, noting the weights, and subsequently firing each separately in marked cups in the Biscuit Oven. The above method is not by any means an exact one from a research point of view; but, as great care was bestowed on the experiments at each operation, the results are approximately correct and practically useful for several investigations a pottery manager may be called upon to make in connection with the trade at almost any time.

Dried Ground Flint (i.e. Calcined Selected Flints, Water Ground and Dried).—First sample, 25 drams taken, after drying weighed $24\frac{1}{4}$ drams, that is a loss of $\frac{3}{4}$ drams on 25, namely, 3 per cent. After firing this still weighed $24\frac{1}{4}$ drams.

Second sample, 25 drams taken, after drying weighed $24\frac{1}{2}$ drams, equals a loss of $3\frac{1}{2}$ per cent. This sample after firing only weighed 24 drams, giving a loss during firing of $\frac{1}{10}\frac{0}{10}$ per cent., and a total of 4 per cent. loss in both drying and firing.

Dried Ground Stone (i.e. Cornish China stone, Water Ground and Kiln Dried).—First sample, 25 drams taken, dried, then weighed $23\frac{1}{2}$ drams, loss by drying 6 per cent. After firing this sample weighed 23 drams, therefore the loss by firing was $2\frac{6}{17}$ per cent., which, with the 6 per cent., makes a total loss of 8 per cent. on the 25.

Second sample, 25 drams taken, after drying weighed $24\frac{7}{16}$ drams, showing a loss by drying of $2\frac{1}{4}$ per cent. After firing in the oven this weighed 24 drams, i.e. a loss of $1\frac{3}{5}\frac{4}{1}$ per cent. during firing alone, and a total loss on the 25 drams of 4 per cent.

China Clay, or Potters' China Clay.—First sample, 25 drams taken, after drying weighed $22\frac{5}{16}$, showing a loss of $10\frac{3}{4}$ per cent. This sample when fired weighed $19\frac{1}{2}$ drams, showing a loss in firing alone of $12\frac{3}{5}\frac{6}{57}$ per cent., the total on the 25 drams being 22 per cent.

Second sample, 25 drams taken, when dried weighed 22 drams, loss by drying 12 per cent.; when fired weighed $19\frac{1}{16}$ drams, loss in firing $\frac{1}{3}\frac{2}{5}\frac{1}{2}$ per cent., total loss $23\frac{3}{4}$ per cent.

Ball Clay, or blue clay, such as is usually employed for white earthenware manufacture in Staffordshire.—First sample, 25 drams taken, when dried weighed $19\frac{5}{8}$ drams, the percentage loss by drying being thus $21\frac{1}{2}$. After firing this sample weighed $17\frac{5}{16}$ drams, therefore percentage loss by firing was $11\frac{3}{4}\frac{4}{16}$, making a total loss of $30\frac{3}{4}$ per cent. for both drying and firing.

Second sample, 35 drams taken, after drying weighed $19\frac{1}{8}$ drams, giving a loss of $23\frac{1}{2}$ per cent. This sample when fired weighed 17 drams, which equals a percentage of $11\frac{1}{5}\frac{7}{8}$ loss in firing, which gives a total of 32 per cent. loss.

Earthenware Body Clay when ready for use by the pressers.—One sample only tested; 25 drams taken, after drying as described; this weighed $19\frac{1}{8}$ drams, indicating a

percentage loss on drying of $23\frac{1}{2}$ per cent. When fired, the weight registered was $18\frac{1}{4}$ drams, showing a loss during firing alone of $4\frac{8}{15}\frac{8}{3}$ per cent., and making a total loss of 27 per cent.

Tabulating the percentage results, we then have the following interesting comparison:—

Material.		Per Cent. Loss by Drying.	Per Cent. Loss by Firing.	Total Per Cent. Loss.
Flint	1st sample	3	0	3
"	2nd "	$3\frac{1}{2}$	$10\frac{0}{15}\frac{3}{3}$	4
Stone	1st "	6	$2\frac{0}{15}\frac{7}{3}$	8
"	2nd "	$2\frac{1}{4}$	$13\frac{4}{15}\frac{1}{1}$	4
China Clay	1st "	$10\frac{3}{4}$	$12\frac{3}{15}\frac{4}{3}$	22
"	2nd "	12	$13\frac{1}{15}\frac{4}{2}$	$23\frac{3}{4}$
Ball Clay	1st "	$21\frac{1}{2}$	$11\frac{5}{15}\frac{4}{3}$	$30\frac{1}{4}$
"	2nd "	$23\frac{1}{2}$	$11\frac{5}{15}\frac{5}{3}$	32
Body Clay	"	$23\frac{1}{2}$	$4\frac{8}{15}\frac{8}{3}$	27

The serviceable application of such results, when extended and confirmed, will be evident to practical potters. For instance, suppose it is required to calculate the quantity of body clay consumed in the manufacture of 100 dozens of any article of pottery, counting twelve to the dozen: take a few pieces in their dry biscuit state, freshly drawn from the oven, and weigh them: ascertain the average weight of one piece, multiply this weight by 1200, and then, presuming the 27 per cent., as per table, has been confirmed for the particular body of which the articles have been made, work out the sum by simple equations, thus—

$$\text{Product in lbs.} = x - \frac{27}{100}x.$$

x will then be the required weight of clay consumed in lbs.

Again, the results of such experiments may be useful in giving some indication of the degree of shrinkage to be expected in differently compounded bodies; and by thus

forecasting the shrinkage, an approximate allowance for or anticipation of this may be made, and the moulds corrected.

Further, these results show us better how to value the real costs of the several materials or clays of which a body is composed; for it is evident that if 100 lbs. of flint in a body clay means 97 lbs. in the biscuit warehouse, whereas 100 lbs. of ball clay means only about 59 or 60 lbs. of ware in the biscuit warehouse, the relative value of these two materials, as compared with their market price in a commercial condition, is very greatly modified.

For instance, 100 cwts. of dried ground flint in usual state costs, say, 2s. per cwt. = £10; it yields in biscuit ware 97 cwts.; therefore the cost per cwt. in the biscuit ware will be $200 \div 97 = 2.062s.$

100 cwts. of ball clay in commercial state costs, say, 1s. 4d. per cwt. = £6, 13s. 4d.; it yields in biscuit ware, say, 60 cwts.; therefore the cost per cwt. in the biscuit ware will be $133\frac{1}{3} \div 60 = 2.222s.$

Then, presuming our premises and inferences are quite correct, this shows that ball clay is actually 0.16s. per cwt. (say 2d. per cwt.) more expensive than flint in the biscuit warehouse. Other applications of these results will probably suggest themselves to practical potters as occasions arise.





CHAPTER VII.

SLOP GROUND FELSPAR CALCULATIONS AND EXPLANATORY PROOFS.

For the purposes of the Staffordshire earthenware trade, calcined flint or Cornish or Jersey stone, when finely ground in water, and in the condition technically known as Slop Flint or Slop Stone respectively (the finely ground particles being in suspension in water in a creamy consistency), is bought and sold by a certain definite standard; the customary standard of sale and purchase is that a peck of such slip flint or stone shall weigh 32 lbs., and in practice all pecks varying from this standard are reduced in account to an equivalent number of 32 lb. pecks. Taking this as a standard for slop ground felspar also, let us ask the question, What number of pecks of slop felspar of 32 lbs. weight each are equivalent in value to the number of pecks indicated by the under-mentioned weights on the weighbridge and by pint?—

- (I.) $9\frac{1}{4}$ cwts. at $34\frac{1}{4}$ ozs. to pint.
 (II.) 12 „ $34\frac{3}{4}$ „ „
 (III.) 13 „ $35\frac{3}{4}$ „ „

To find the number of pecks by actual measure we reduce the number of cwts. to lbs., and then divide by the pint weight in ozs., because whatever the pint weight is in ozs. so is the peck in lbs. Thus—

$$\left. \begin{array}{l} \text{(I.) } (9\frac{1}{4} \times 112) \div 34\frac{1}{4} = 30\cdot2481 \\ \text{(II.) } (12 \times 112) \div 34\frac{3}{4} = 38\cdot6762 \\ \text{(III.) } (13 \times 112) \div 35\frac{3}{4} = 40\cdot727 \end{array} \right\} \text{ pecks by measure.}$$

Now the relative value of these pecks by measure is determined by the number the figures of the pint weigh in ozs. in excess of 20, for the reason that every increase of 1 oz. of pint weight over 20 ozs. is dependent upon a displacement of water by the material; and as this takes place in perfectly regular succession, integral and fractional, if the pint weight is 32 ozs., namely, 12 ozs. over the 20, the displacement has been just twelve times greater than if the pint weight were 21 ozs. So if the pint weighs 34, the displacement has been fourteen times greater, and so on; consequently we proceed to reckon the equivalent number of 32 lb. pecks thus—

$$(I.) \quad 12 : 14\frac{1}{4} :: 30.2481 : 35.916 :$$

for each of the ascertained numbers of pecks by measure is $34\frac{1}{4}$ lbs., and therefore of relatively greater value than the standard by $2\frac{1}{4}$ in 12. So with the others—

$$(II.) \quad 12 : 14\frac{3}{4} :: 38.6762 : 47.539.$$

$$(III.) \quad 12 : 15\frac{3}{4} :: 40.727 : 53.454.$$

The answer in each instance is the number of 32 lb. pecks to which the actual number of slop pecks of the given weight are in value equal to.

In this manner, whether the pint weights are over or under the standard, the value may be found.

And in practice the rule may be made shorter by cancelling. Thus—

$$\begin{aligned} (I.) \quad & \frac{9\frac{1}{4} \times 112 \times 14\frac{1}{4}}{34\frac{1}{4} \times 12} = \frac{9\frac{1}{4} \times 9\frac{1}{3} \times 14\frac{1}{4}}{34\frac{1}{4}} \\ (II.) \quad & \frac{12 \times 112 \times 14\frac{3}{4}}{34\frac{3}{4} \times 12} = \frac{12 \times 9\frac{1}{3} \times 14\frac{3}{4}}{34\frac{3}{4}} \\ (III.) \quad & \frac{13 \times 112 \times 15\frac{3}{4}}{35\frac{3}{4} \times 12} = \frac{13 \times 9\frac{1}{3} \times 15\frac{3}{4}}{35\frac{3}{4}} \end{aligned}$$

For those who are willing to follow this inquiry very closely step by step, the more detailed explanatory proofs following may be helpful:—

(a) The mean or average specific gravity of felspar may be taken as 2.6216, because orthoclase = 2.4 to 2.6, oligoclase 2.6 to 2.7, labradorite 2.67 to 2.76 : total, 15.73, which divided by 6 = 2.6216, the mean specific gravity.

(b) If from a pint of water a bulk of water weighing precisely 1 oz. is extracted, and this bulk exactly replaced by an equal bulk of felspar of the above-named specific gravity, the weight of the pint will have increased 1.6216 oz. But a bulk of felspar equal to 1 oz. of water weighs 2.6216 ozs., presuming our average specific gravity is correct: therefore, to increase the pint weight 1.6216 oz., 2.6216 ozs. of felspar are required: and by consequence, to increase the pint weight 1 oz., 1.6166748 oz. is required; for $1.6216 : 1 :: 2.6216 : 1.6166748$.

(c) At 32 ozs. to pint the increase of weight per pint has been 12 ozs.: and as 1.6166748 oz. of felspar is required to increase the pint weight 1 oz., twelve times that weight is required to make the pint 32 ozs.: therefore a 32 oz. pint of slop felspar contains 12×1.6166748 oz. = 19.4009 ozs. of dry felspar; and so 1 peck of 32 lbs. contains 19.4009 lbs. dry weight of felspar.

(d) When the pint weight is 32 ozs. there are $3\frac{1}{2}$ pecks by measure in each cwt. of slop ($112 \div 32 = 3\frac{1}{2}$): and as each of these pecks contains 19.4009 lbs. dry felspar (see c), we infer that 1 cwt. of slop felspar will contain $3\frac{1}{2}$ times 19.4009 lbs. dry, namely, 67.9 lbs.

(e) At $34\frac{1}{4}$ ozs. to pint the increased weight in the pint is $14\frac{1}{4}$ ozs.; therefore the pint at $34\frac{1}{4}$ ozs. will contain $14\frac{1}{4} \times 1.6166748 = 23.0376$ ozs., and the peck of $34\frac{1}{4}$ lbs. slop will contain 20.0376 lbs. dry.

(f) When the peck is $34\frac{1}{4}$ lbs. there are $112 \div 34\frac{1}{4} = 3\frac{3}{5}$

pecks by measure in each cwt. of slop; therefore 1 cwt. of slop felspar at $34\frac{1}{4}$ ozs. to pint, and of the supposed specific gravity, contains $3\frac{3}{4} \times 23.0376$ lbs. dry, namely, 75.33469 lbs. dry.

(g) Then, because $3\frac{1}{2}$ pecks at 32 ozs. to pint contain 67.9 lbs. dry weight, the 75.33469 lbs. found by *f* are equivalent to $3\frac{1}{2} \times 75.3346 \div 67.9 = 3.88323$ pecks of 32 lbs. slop; therefore we calculate that $9\frac{1}{4}$ cwt. of slop felspar, at $34\frac{1}{4}$ ozs. to pint, are equivalent to 35.91987 pecks of slop felspar at 32 ozs. to pint.

Referring now to the earlier portion of this chapter, we see that by our simple rule we found the number to be 35.916, which, for all practical purposes, will be sufficiently near the absolutely correct.

(h) At $34\frac{3}{4}$ ozs. to pint the increase is $14\frac{3}{4}$; therefore, for the reasons already expressed, the dry contents equal $14\frac{3}{4} \times 1.6166748 = 23.84595$ ozs., and consequently the peck contains 23.84595 lbs. dry contents.

Again, at $34\frac{3}{4}$ lbs. to the slop peck there are $112 \div 34\frac{3}{4} = 3\frac{1}{3}\frac{1}{5}$ pecks by measure in each cwt.: therefore 1 cwt. of slop felspar, at $34\frac{3}{4}$ ozs. to pint, we infer contains $3\frac{1}{3}\frac{1}{5} \times 23.84595$ lbs., namely, 76.856 lbs. dry felspar.

But it has been shown that 67.9 lbs. dry weight equal $3\frac{1}{2}$ pecks, at 32 ozs. to pint, *i.e.* $3\frac{1}{2}$ 32 lb. slop pecks; therefore 76.856 lbs. dry = 3.9614 32 lb. pecks.

So, because 1 cwt. of slop felspar at $34\frac{3}{4}$ ozs. to the pint equals 3.9614 pecks at 32 lbs., consequently 12 cwt. slop at $64\frac{3}{4}$ ozs. to pint = 47.5368 32 lb. slop pecks.

Referring again to the result by the simpler rule, we find it was 47.539, and this is almost identical with the result now obtained.

(i) At $35\frac{3}{4}$ ozs. to pint the increase over 20 is $15\frac{3}{4}$ ozs.: therefore dry contents = $15\frac{3}{4} \times 1.6166748$, namely, 25.46262; therefore 1 peck contains 25.46262 lbs. dry.

When the slop peck weighs $35\frac{3}{4}$ lbs. there are $112 \div 35\frac{3}{4} = 3.132867$ pecks by measure in 1 cwt. of slop; so we calculate each cwt. of slop felspar at $35\frac{3}{4}$ ozs. to pint contains $(3.132867 \times 25.46232) = 79.77$ lbs. dry.

But it has been shown that, with felspar of the given specific gravity aforementioned, 67.9 lbs. dry are equivalent to $3\frac{1}{2}$ pecks of 32 lbs. each in the slop state. Therefore 79.77 lbs. dry = 4.1117 pecks of 32 lbs. each.

Therefore 1 cwt. of slop felspar at $35\frac{3}{4}$ ozs. to pint, although by measure it only contains 3.132867 pecks, still the equivalent in 32 lb. pecks of slop is 4.117 pecks, and for that reason 13 cwt. will be just 13 times 4.1117 , namely, 53.4521 pecks of 32 lbs.

In conclusion, we give examples of the application of the rule in its most condensed form for the most rapid calculations:—

- (I.) $(9\frac{1}{4} \times 9\frac{1}{3} \times 14\frac{1}{4}) \div 34\frac{1}{4} = 35.199.$
 (II.) $(12 \times 9\frac{1}{3} \times 14\frac{3}{4}) \div 34\frac{3}{4} = 47.539.$
 (III.) $(13 \times 9\frac{1}{3} \times 15\frac{3}{4}) \div 35\frac{3}{4} = 53.455.$





CHAPTER VIII.

THE CONVERSION OF SLOP BODY RECIPES OR FORMULÆ INTO DRY WEIGHT PRO- PORTIONS, AND *VICE VERSA*.

OCCASIONS arise in the course of long experience in manufacturing when changes of works or structural or mechanical alterations render it necessary, temporarily or permanently, to revert from a slop-weighing to a dry-weighing method. Circumstances may also cause interruption in the supplies of slop materials or variations in prices of the same that make the change desirable. From whatever cause this occurs, most manufacturers would like some assistance in checking their own calculations, lest by any means errors should creep in and lead to unfortunate losses, such as have at times occurred in this manner. From the fact that the specific gravities of the clays—flint, stone—are not very different from each other, and that it is usual to specify the pint weights respectively, as ball clay slip to be 24 ozs. to pint, china clay slip 26 ozs., slop flint 32 ozs., and slop stone 32 ozs., it becomes a comparatively simple reckoning. For at 24 ozs. to pint a pint of ball clay slip yields practically one-third of the dry weight of clay, as a pint of flint or stone at 32 ozs. to pint yields of dry material respectively; and china clay slip weighing 26 ozs. yields, as nearly as practicable, half the weight of dry material as slop flint or stone does at 32 ozs. to pint. Hence, if we wish to convert such a formula as the following to dry weight proportions:—

15 inches ball clay slip at 24 ozs. to pint.

9 „ china clay slip „ 26 „ „

6 „ slop flint „ 32 „ „

4 „ slop stone „ 32 „ „

we may do so accurately in a simple manner. Thus—

For the ball clay divide the 15 by 3, making 5; for the china clay divide the 9 by 2, making $4\frac{1}{2}$; and allow the figures for the flint and stone to remain unaltered. This gives us the proportions of positively dry materials.

5 parts by weight of dry ball clay.

$4\frac{1}{2}$ „ „ „ china clay.

6 „ „ „ flint.

4 „ „ „ stone.

Then ascertain the percentage of moisture in the clays and materials: presuming it to be—

18 per cent. in the ball clay,

$12\frac{1}{2}$ „ „ china clay,

3 „ „ flint,

4 „ „ stone,

we find the commercial weights by simple equations. Thus—

$$\text{Ball clay, } 5 = x - \frac{18}{100}x. \quad \therefore 5 = \frac{82}{100}x. \quad \therefore 500 = 82x.$$

$$\therefore x = \frac{500}{82} = 6\frac{1}{10}.$$

$$\text{China clay, } 4\frac{1}{2} = x - \frac{12\frac{1}{2}}{100}x. \quad \therefore 4\frac{1}{2} = \frac{87\frac{1}{2}}{100}x. \quad \therefore 450 = 87\frac{1}{2}x.$$

$$\therefore x = \frac{450}{87\frac{1}{2}} = 5\frac{1}{7}.$$

$$\text{Flint, } 6 = x - \frac{3}{100}x. \quad \therefore 6 = \frac{97}{100}x. \quad \therefore 600 = 97x$$

$$\therefore x = \frac{600}{97} = 6\frac{3}{16}.$$

$$\text{Stone, } 4 = x - \frac{4}{100}x. \quad \therefore 4 = \frac{96}{100}x. \quad \therefore 400 = 96x$$

$$\therefore x = \frac{400}{96} = 4\frac{1}{6}.$$

The equivalent proportions then will be—

$6\frac{1}{6}$ parts by weight of ball clay containing 18 p. c. moisture.

$5\frac{1}{2}$ „ „ china clay „ $12\frac{1}{2}$ „ „

$6\frac{3}{16}$ „ „ ground flint „ 3 „ „

$4\frac{1}{6}$ „ „ ground stone „ 4 „ „

For cases in which the pint weights of the formula to be converted are not in the usual order of 24 ozs., 26 ozs., 32 ozs., 32 ozs., our simple rule cannot immediately be applied. For instance, suppose it was required to convert the following slop formula to equivalent proportions in dry weights:—

15 inches ball clay slip at 24 ozs. to pint.

9 „ china clay slip „ 26 „ „

6 „ slop flint „ 31 „ „

4 „ slop stone „ $30\frac{1}{2}$ „ „

we must first ascertain the equivalent measures of flint and stone at 32 ozs. To do so multiply the inches given by the specified pint weight in ounces less 20 (that is, $31 - 20 = 11$) and divide by 12; thus $(6 \times 11) \div 12 = 66 \div 12 = 5\frac{1}{2}$.

Then for the stone $(4 \times 10\frac{1}{2}) \div 12 = 3\frac{1}{2}$. So we get the following:—

15 inches ball clay slip at 24 ozs. to pint.

9 „ china clay slip „ 26 „ „

$5\frac{1}{2}$ „ slop flint „ 32 „ „

$3\frac{1}{2}$ „ slop stone „ 32 „ „

Now we can apply the simple rule aforementioned, and so arrive at—

5	parts by weight of dry ball clay.
$4\frac{1}{2}$	„ „ china clay.
$5\frac{1}{2}$	„ „ flint.
$3\frac{1}{2}$	„ „ stone.

Then by making the calculations for moisture percentage in the clays and materials in the manner previously explained, *i.e.*, by means of simple equations, we find the commercial weight to be—

$6\frac{1}{10}$ parts by weight of ball clay containing 18 p. c. moisture.

$5\frac{1}{7}$	„	„	china clay	„	$12\frac{1}{2}$	„	„
$5\frac{2}{3}$	„	„	flint	„	3	„	„
$3\frac{2}{3}$	„	„	stone	„	4	„	„

Again, suppose the formula to be converted was as under:—

15	inches ball clay	slip at $23\frac{1}{2}$ ozs. to pint.
9	„ china clay	slip „ 25 „ „
6	„ slop flint	„ 33 „ „
4	„ slop stone	„ 31 „ „

Then to reduce the formula to standard pint weights the sums may be expressed thus—

Ball clay	$[(15 \times 3\frac{1}{2}) \div 4] \div 3 = 4\frac{9}{16}$ dry.
China clay	$[(9 \times 5) \div 6] \div 2 = 3\frac{3}{4}$ „
Flint	$[(6 \times 13) \div 12] \div 1 = 6\frac{1}{2}$ „
Stone	$[(4 \times 11) \div 12] \div 1 = 3\frac{2}{3}$ „

Then by means of simple equations, as indicated in previous instances, ascertain the equivalent weights of clays and materials in their usual commercial condition. Thus—

Ball clay	$4\frac{9}{16} = x - \frac{18}{100}x.$
China clay	$3\frac{3}{4} = \frac{100}{100}x - x.$
Flint	$6\frac{1}{2} = x - \frac{3}{100}x.$
Stone	$3\frac{2}{3} = x - \frac{4}{100}x.$

To convert recipes of dry weight proportions into recipes of slop measures of the customary weights to pint.

Suppose the formula to be—

200 lbs.	ball clay	in commercial state.
200	„ china clay	„ „
200	„ dry flint	„ „
150	„ dry stone	„ „

First of all, estimate the percentage of moisture in each clay and material, and deduct its per cent. Thus, say ball clay has been found to contain an average of 18 per cent. moisture, china clay $12\frac{1}{2}$ per cent., flint 3 per cent., and stone 4 per cent., then—

Ball clay	$= (200 - 36) = 164$	dry.
China clay	$= (200 - 25) = 175$	„
Flint	$= (200 - 6) = 194$	„
Stone	$= (150 - 6) = 144$	„

Then we can proceed in either of two ways; thus, by applying our simple rule in the reverse manner, so—

$164 \times 3 = 492 = 49\cdot2 = 16\frac{1}{3}$	inches slop	24	ozs.
$175 \times 2 = 350 = 35\cdot0 = 11\frac{2}{3}$	„	26	„
$194 \times 1 = 194 = 19\cdot4 = 6\frac{1}{2}$	„	32	„
$144 \times 1 = 144 = 14\cdot4 = 5$	„	32	„

Or, taking ascertained average dry weights of contents of 1 peck of the various slips, we divide the dry proportions thereby, thus—

$164 \div 6\frac{5}{6} = 24\frac{1}{2} = 16\frac{1}{3}$	inches slop.
$174 \div 9\frac{9}{16} = 18\frac{1}{3} = 12\frac{1}{3}$	„
$194 \div 19\frac{1}{6} = 9\frac{3}{4} = 6\frac{1}{2}$	„
$144 \div 19\frac{1}{4} = 7\frac{1}{2} = 5$	„

The two methods are thus shown to have only a trivial difference in results when compared as above.

Having thus obtained the slop formula, should the pint weights of the clay slips or slop materials, at any time obtainable, vary from the standards of 24, 26, 32, 32, respectively, mixing may still be proceeded with by the use of the "Special Ready Reckoner," or tables of equivalent measures of clay slips at different pint weights, compiled and published by Mr. W. J. Furnival.

In cases where it is intended to measure some of the clays or materials in a slop state, and to weigh the others in their commercially dry condition, whereas the body has hitherto been all measured slop :—

Ascertain the area of blending ark, then multiply by the depths of each material, and so obtain the pecks of each by measure. Then supposing the ball clay and china clay are to be weighed dry, and the flint and stone measured slop, as before, at 32 ozs. to pint, reduce the pecks to their dry contents by multiplying the number of pecks of ball clay slip by $6\frac{7}{8}$, and those of china clay slip by $9\frac{9}{16}$, then add the natural moisture percentage, and this gives the desired figures in lbs.

When it is required to find the dry recipe corresponding to a wet recipe, not only in relative proportions, but also in actually equivalent quantities or volume :—

Multiply the area measurements in inches of the blending ark by the several specified depths in inches of each slip, then divide the several numbers so obtained by 554.55, to find the respective number of pecks by measure. Then presuming the pint weights by the recipe are 24, 26, 32, 32, multiply the number of pecks of ball clay by $6\frac{7}{8}$ lbs., those of china clay by $9\frac{9}{16}$ lbs., those of flint by $19\frac{3}{4}$ lbs., and of stone by $19\frac{1}{4}$ lbs. Then, by simple equations, find the numbers equivalent in clays, etc., containing the usual percentage of moisture, and these will be the required weights.



CHAPTER IX.

A CALCULATION OF THE COSTS OF PREPARED WHITE EARTHENWARE GRANITE BODY CLAY, AND OF A GLAZE FOR THIS BODY.

FIRST of all, with regard to the body. Many circumstances conspire to render the cost of a prepared body clay more or less at one pottery than at another, such as the formula, the quality and value of the clays used, the costs of carriage thereon, the prices at which the flint and stone are purchased, the proportion of blue stain, the number of different bodies made, the economy in labour, wear and tear, waste, continuity or otherwise of working, the quantity of scraps remade, scarcely any two works being similar in all respects.

Consequently the resultant figures of these calculations will be of the character of examples, based mainly upon current methods and costs ruling in the Staffordshire potteries. By correcting the several items herein named to the actual costs at his own works, a manufacturer may arrive at a fairly correct estimate. The formula chosen is representative of a white earthenware body requiring a hard biscuit firing, such as is usually employed by manufacturers of what is technically known as granite ware, say to the point at which an average sample of Swedish felspar begins to melt.

The proportion of blue stain is rather less than for granite wear.

FORMULA OF BODY.

13	inches depth of ball clay slip at 24 ozs. to pint.		
12	„ „ china clay slip „ 26 „ „		
7	„ „ slop flint „ 32 „ „		
5	„ „ slop stone „ 32 „ „		

We will suppose the mixing or blending ark or tank to measure ten feet by five feet, and to have a depth of a few inches more than the total depth of the above-named blending, and say we use $3\frac{1}{3}$ pints of slop blue stain at 25 ozs. to pint: the stain being made of oxide of cobalt fluxed with half its own weight of china clay, calcined, and then ground in water and finely lawned. The costs of this will then work out thus: 2 lbs. of oxide of cobalt at 5s. 3d. per lb., 10s. 6d.; 1 lb. china clay, say 1d.; calcining and grinding, say 1s. 6d.: this gives a figure of about 4s. per lb. of dry stain. Now a pint of 25 ozs. to pint of such a stain is supposed to contain about $7\frac{1}{2}$ ozs. dry stain; $3\frac{1}{3}$ pints will then be $3\frac{1}{3} \times 7\frac{1}{2}$ ozs. = 23 ozs., say $1\frac{1}{2}$ lbs., at 4s. per lb.

It is taken for granted that the manufacturer has no clay mines or flint mills of his own, or, in the event of his having such, that they are worked independently: consequently, we estimate our costs at as nearly as possible average market prices now current in North Staffordshire.

The blending being done in a slip state, and the clays having been all previously intimately incorporated with water, so as to form semi-fluids or slips of the consistency of cream, it is necessary, for the purposes of the calculation, to discover what weight of dry clay or material is contained in a pint of the clay slip at the specified pint weight.

It must be observed, too, that there is a considerable difference in the pint weights of each of the four components,

one slip being 24 ozs. to pint, another 26 ozs., and the others 32 ozs. each; and this creates a great difference in the relative dry material contained in a pint of one slip as compared with another. Consequently, the actual proportion of material used in the body is not by any means apparent from a casual inspection of the simple depth in inches of each ingredient. The uninitiated may then ask what reason can be assigned for such a peculiar recipe. It is simply this: clays being in a state of minute subdivision, and also having an affinity for water, become thickened to a desirable degree with a less quantity of dry contents in the case of ball clay than in the case of china clay, and each of them much more so than in the case of flint and stone.

Lengthened experience has pointed out what weight to a pint each of the slips attains when in the most desirable or advantageous consistency for blending together with sufficient freedom, while at the same time not being thin enough to allow of a too ready subsiding or separation for the convenience of the operations of clay preparations.

There are two ways of ascertaining the dry contents of these several pints of slips: firstly, actual experiment; secondly, a calculation from the specific gravities of the materials.

Actual experiments were made thus: a pint of ball clay slip sieved through what are known as 14s. and 18s. mesh silk lawns, weighing $23\frac{2}{3}$ ozs. slop, yielded $5\frac{1}{4}$ ozs. of dry ball clay; this put again into a pint measure and filled up with water gave a slop pint weighing $23\frac{3}{16}$ ozs.

Another similar pint of ball slip clay weighing $23\frac{1}{8}$ ozs. slop yielded dry contents weighing $4\frac{3}{4}$ ozs.; this put into a pint measure and filled up with water gave a slop pint of $22\frac{7}{8}$ ozs. A pint of another sort of ball clay slip, sieved as above, weighing $23\frac{1}{16}$ ozs., yielded $4\frac{9}{16}$ ozs. dry clay, which when put into a pint measure and filled up with water gave

a slop pint of $22\frac{3}{4}$ ozs. Another pint of this ball clay slip, weighing 23 ozs., yielded $4\frac{1}{2}$ ozs., which, when put in a pint measure and filled up with water, weighed $22\frac{3}{4}$ ozs.

Another pint $21\frac{1}{2}$ ozs. slop gave $2\frac{5}{16}$ ozs. dry clay; this, when put into a pint measure and filled up with water, weighed $21\frac{7}{8}$ ozs. slop.

From the foregoing it is inferred that a 24 oz. pint contains $6\frac{7}{8}$ ozs. of dry ball clay.

Then as to china clay:—

A pint of china clay slip, sieved through 14s. and 18s. silk lawns, weighing 26 ozs. slop, was carefully dried, and yielded $9\frac{9}{16}$ ozs. dry china clay; this was put into a pint measure and filled up with water and weighed $25\frac{1}{16}$ ozs. Another pint of the same clay slip, weighing 23 ozs. slop, yielded $4\frac{3}{8}$ ozs. dry, which, when put into a pint measure and filled up with water, weighed $22\frac{9}{16}$ ozs. A pint of another sort of china clay slip similarly lawned, weighing 26 ozs., yielded $9\frac{1}{2}$ ozs. dry contents, and when put into a pint measure and filled up with water, weighed $25\frac{3}{8}$ ozs. Another pint of the same clay slip, weighing $24\frac{1}{8}$ ozs. slop, yielded $6\frac{1}{2}$ ozs. dry, which, when put into a pint measure and filled up with water, gave a slop pint weighing $23\frac{9}{16}$ ozs.

It seems reasonable, therefore, to infer that the average dry clay in a 26 oz. pint of china clay slip is, as nearly as practicable, $9\frac{9}{16}$ ozs.

To calculate dry contents from the specific gravity: Suppose the specific gravity to be 2.5, that is to say, we are supposing the clay or material when perfectly pure and dry to be bulk for bulk two and a half times heavier than water. Now, imagine a pint of water, namely, 20 ozs., having 1 oz. of water taken out, and a precisely similar bulk of the clay or material put in, the measure will still be exactly full, but will have increased in weight $1\frac{1}{2}$ ozs., and will now weigh $21\frac{1}{2}$ ozs. So we see that to increase the pint weight

$1\frac{1}{2}$ ozs. with the clay we have, we must add $2\frac{1}{2}$ ozs. of the dry clay.

Then to find dry contents of a 24 oz. slop pint of the known specific gravity 2.5, we use the proportional sum thus—

$$1\frac{1}{2} : 2\frac{1}{2} :: 4 : 6\frac{1}{3}.$$

In like manner, with a pint or slip weighing 26 ozs., and having a known specific gravity of 2.5—

$$1\frac{1}{2} : 2\frac{1}{2} :: 6 : 10,$$

and so on, according to specific gravity.

Proceeding with the calculation, by the formula we take of ball clay slip a depth of 13 inches with an area of mixing ark of 10 feet by 5 feet, *i.e.* 50 superficial feet, or 7200 square inches; then $7200 \times 13 = 93,600$ cubic inches of ball clay slip at 24 ozs. to a pint.

Reduced to pecks (*i.e.* $93,600 \div 554.55$), this is nearly 169 pecks. Now if we assume from foregoing experiments and theory that a 24 oz. pint of ball clay slip contains $6\frac{7}{16}$ ozs. dry clay, which is equal to $6\frac{7}{16}$ lbs. to the peck, we find that the 169 pecks of ball clay slip contain ($169 \times 6\frac{7}{16}$) 1087 lbs. dry.

Of china clay slip we take a depth of 12 inches, with the specified area of 10 feet by 5 feet, that is, 7200 square inches $\times 12 = 86,400$ cubic inches: then, $86,400 \div 554.55 = 156$ pecks, $156 \text{ pecks} \times 9\frac{9}{16} = 1490$ lbs. dry china clay.

Of slop flint we have 7 inches deep; therefore $7'' \times 10' \times 5' = 7 \times 7200 = 50,400$ cubic inches, and this gives $50,400 \div 554.55 = 91$ pecks; and as one peck of 32 lbs. of slop flint is estimated to contain $19\frac{3}{8}$ lbs. dry flint, the 91 pecks slop will be equal to about 1803 lbs. of dry flint.

Of slop stone we have 5 inches deep; that will be $5'' \times 10' \times 5' = 5 \times 7200 = 36,000$ cubic inches $= 36,000 \div 554.55$ pecks = say 65 pecks.

Calculating the 32 lbs. slop peck of stone at $19\frac{1}{4}$ lbs. dry contents, this gives us $65 \times 19\frac{1}{4} = 1251$ lbs.

In this manner we arrive at the following results as the positively dry proportions of the formula :—

1087	lbs.	dry	ball	clay.
1490	„	„	china	clay.
1803	„	„	flint.	
1251	„	„	stone.	
$1\frac{1}{2}$	„	„	blue	stain.

But ball clay and china are not commercially purchasable in a perfectly dry state, so we must further estimate what proportion of clay, etc., in the usual commercial state, is equivalent to the above figures.

Nothing short of actual experiment will aid us in these instances, and our experiments must be fairly averaged and considered to attain moderate accuracy, because so many little causes of variation exist in practice.

A wet lump of china clay was taken, which had been exposed to rain until quite damp, but not doughy or soft at all: this weighed 3 ozs. 10 drs. After drying slowly in an evaporating dish over a sand-bath heated by a Bunsen burner, the dry clay then weighed 43 drs., showing a loss of weight of 15 drs., which is equivalent to ($58 : 15 :: 100 : 25\cdot8$), a sensible moisture of say $25\frac{3}{4}$ per cent.

Another small lump of china clay, which, having been protected by the superincumbent clay, was only normally dry, about as clay usually is; this weighed 1 oz. 4 drs., and after drying in the manner aforementioned, weighed, when powder dry, 18 drs., showing a loss of 2 drs. in 20, which is equivalent to 10 per cent. of sensible moisture. It seems reasonable, therefore, to reckon average china clay in its commercial state as containing $12\frac{1}{2}$ per cent. hygroscopic moisture.

With ball clay the following experiments were made:—A wet lump that had been exposed to the rain until quite damp, but not sodden, weighing 3 ozs. 8 drs., was dried over an evaporating basin on a sand-bath, powdered and dried again (perhaps a little too much, as it began to blacken at the bottom): when dried this weighed 44 drs., *i.e.* a loss of 12 drs. in 56 drs., or say $21\frac{1}{2}$ per cent. of moisture had been removed.

Another lump rather more than commercially dry was taken, weighing 26 drs. dried in evaporating basin over a bath, slowly and carefully. When dried this yielded $21\frac{1}{2}$ drs., giving a loss of $4\frac{1}{2}$ drs. in 26, or $17\frac{1}{3}$ per cent.

Therefore it seems fair to assume an average percentage of moisture in commercial ball clay of 18 or 19 per cent.; more or less also at different seasons, because it is customary to expose these clays to the weather. To say 18 per cent. will, at anyrate, be within the mark.

In calculating our ball clay costs, it will then be necessary to reckon such a weight as that when 18 per cent. is deducted the weight of 1087 lbs. will remain as the positively dry contents. This necessitates the employment of elementary algebra. Thus—

$$1087 = x - \frac{18}{100}x \therefore 1087 = \frac{82}{100}x \therefore 82x = 108,700 \\ \therefore x = 1325\cdot6,$$

say 1326 lbs.

And the china clay in the same way will have to be calculated to such a figure as when $12\frac{1}{2}$ per cent. shall be deducted from it there will remain our dry weight of 1490 lbs. Therefore the sum may be expressed as follows:—

$$1490 = x - \frac{12\frac{1}{2}}{100}x$$

$$1490 = \frac{87\frac{1}{2}}{100}x$$

$$87\frac{1}{2}x = 149,000$$

$$\therefore x = 1702\cdot8,$$

say 1703 lbs. of commercial china clay.

There is, however, one other consideration that we must take account of, namely, the proportion of siftings or knockings. Now, if we allow, say 2 per cent. for the ball clay, and $\frac{1}{2}$ per cent. for the china clay, under this head, we shall probably be nearly correct. Say then—

Ball clay, commercial state . . . 1353 lbs.

China clay, commercial state . . . 1712 lbs.

For the formula and capacity of ark supposed, we then estimate to require for one blending—

1353 lbs. ball clay (in ordinary commercial condition).

1712 lbs. china clay (in ordinary commercial condition).

91 pecks slop flint at 32 ozs to pint.

65 pecks slop stone at 32 ozs. to pint.

As to quality and price of clays for such a body as the one indicated, the ball clay should largely consist of the best selected white ball clay, specially adapted for semi-porcelain, or some other very superior and white Devonshire ball clay. This necessarily adds a few shillings a ton to the first cost, but is compensated by the excellence of whiteness attained, with a minimum expenditure in blue stain. The cost of this white ball clay delivered in Staffordshire is about 30s. 6d. per ton net.

If two-thirds of such ball clay are used, together with one-third of the ordinary blue clays at about 5s. per ton

lower cost, this gives us, say, 29s. per ton as the cost price of our ball clay. Similar conditions apply to the china clay, for if superior results are to be attained, superior materials must be employed, say, for china clay, such qualities as I R and S, A1, J M, C D B, and similar kinds, associated perhaps with E D, V O B, and the like. If we fix the net cost price at an average of 34s. at the works, we shall, at anyrate, not be far above the actual cost of Staffordshire.

Then as to slop flint and stone. Assuming that these are bought as required, we shall escape a long series of calculations as to cost of breakdowns, lost time, boiler repairs, etc., and simply have to reckon the net price per slop peck of 32 lbs. Taking this at, say, 4d. for slop flint and 5d. for stone, less 10 per cent. discount, will be quite as low as we can fairly consider in our costs.

Summarising then, we have—

12 cwts. 0 qrs. 9 lbs. ball clay at 29s. per ton	£0	17	6
15 cwts. 1 qr. 4 lbs. china clay at 34s. per ton	1	6	0
91 pecks slop flint at 4d. (less 10 per cent.)	1	7	4
65 pecks slop stone at 5d. (less 10 per cent.)	1	4	5
1½ lbs. blue stain at 4s. per lb.	0	6	0
	<hr/>		
Total for materials	£5	1	3
	<hr/>		

The absolutely dry weights estimated to be required were 5632 lbs. Now if we consider pugged body clay when ready for use contains 23 per cent. of moisture, the yield will be theoretically 7314¼ lbs. Suppose we say 7250 lbs., or 64¼ cwts. This, at a cost of £5 1s. 3d., is equivalent to about 1s. 6¾d. per cwt., or £1 11s. 3d. per ton of pugged clay for clays, flint, stone, and stain.

The other items may be entered as follows:—

Labour : Clay-wheeling, slip-making, lawning, magnetizing, pumping, pressing, pugging, and tenting of engine and boiler	2s. 8d. per ton.
Estimated "up-keep," costs of press cloths and lawns	10d. „
Repairs to clay-making machinery, pumps, taps, and presses	1s. „
Oils, indiarubber, sundries	2d. „
Fuel and boiler repairs	8d. „
Gas, water rates, taxes, and insurance	6d. „
Rent, depreciation, and building repairs	1s. 6d. „
Management expenses	3d. „
Loss and scraps	3d. „
	<hr/>
	7s. 10d. per ton.
	<hr/>

Add to this the 31s. 3d. per ton, and we have 39s. 1d. per ton as the cost of the pugged body clay by the formula we have supposed as used.

THE GLAZE.

For our recipe we will take the proportions as under :—

<i>Fritt</i> .—168 lbs. English refined borax.
84 „ ground Cornish stone.
96 „ ground calcined flints.
84 „ whiting (calcium carbonate).
35 „ best china clay.

The above fritted together in the customary manner in a fritt kiln, run off, cooled, and weighed into stock.

GLAZE FOR THE MILL.

250 lbs. fritt as above.

160 „ ground Cornish stone.

70 „ ground calcined flint.

130 „ dry white lead.

Ground together intimately with water in a potter's glaze pan to a degree of fineness such as to be almost impalpable, then lawned and aged for say fourteen days or more.

SUMMARY OF COSTS OF FRITT.

1½ cwt. borax at 22s. 6d. per cwt.	.	£1	13	9
$\frac{3}{4}$ cwt. stone at 2s. 6d.	„	.	0	1 11
$\frac{7}{8}$ „ flint at 2s.	„	.	0	1 9
$\frac{3}{4}$ „ whiting at 1s. 9d.	„	.	0	1 3
35 lbs. china clay at 2s.	„	.	0	0 8
<hr/>				
		£1	19	4

Preparing the materials, weighing and

fritting 0 3 0

Fuel, interest, repairs 0 2 6

 £2 4 10

As to the yield, we estimate the 168 lbs. borax to give 90 lbs., the stone 80 lbs., flint 93 lbs., whiting 42 lbs., china clay 28 lbs., when fritted, or a total yield of fritt of say 333 lbs.; but there is a slight unavoidable loss, and the practical yield would probably be about 320 lbs. of clean fritt when perfectly dry. Then 45s. for 320 lbs. is as nearly as possible 15s. 9d. per cwt. for the dry fritt.

COSTS OF GLAZE.

250 lbs. fritt at 15s. 9d. per cwt.	. £1 15 6
160 „ stone at 2s. 6d. „	. 0 3 9
70 „ flint at 2s. „	. 0 1 3
130 „ lead at 16s. „	. 0 19 11
<hr/>	
610 lbs.	£3 0 5

GRINDING.

12½ se. fritt at 8d. per score	. 0 8 4
18 „ mixture at 4d. per score	. 0 6 0
<hr/>	
	£3 14 9
<hr/>	

Allowing a loss of say 10 lbs. weight in process, we have 600 lbs. clean glaze for £3, 14s. 9d., which is equivalent to say 14s. per cwt.

The conclusion we arrive at is then that, for such formulae as we have supposed, the cost in the Staffordshire potteries are pretty nearly as under:—

Body clay, ready for use . . .	39s. 1d. per ton.
Glaze	14s. per cwt.





CHAPTER X.

FORMS AND TABLES.

ARTICLES OF APPRENTICESHIP

made and entered into this day of 19
Between
of in the County of of the
first part, of of
in the County of of the second part, and
 of aforesaid, an
infant under the age of twenty-one years, of the third part,
as follows:—

The said doth hereby,
freely and voluntarily, and with the consent and approbation
of the said (testified by h
execution hereof), place and bind self apprentice to
the said his successors and
assigns, and them to serve and by them to be instructed in
that branch of the China and Earthenware Trade called
 for the term of years. And the said
 do hereby, for self, h
heirs, executors and administrators, covenant with the said
 h executors and assigns,
that the said shall honestly,
faithfully and diligently serve the said
 his executors and assigns, from the date
hereof, for and during the said term of years, as an

apprentice, and will not waste, damage or destroy any of the property or effects of the said

his (or their) executors and assigns, and will regularly attend at the place or places of business at or near

aforesaid during such hours as may be appointed
by the said executors or

assigns. And will not on any occasion, or under any pretence
whatever, absent self without permission.

And further, that the said

his heirs, executors or administrators, will at all times during the said apprenticeship provide the said

with sufficient clothing, board, lodging and washing.

And, lastly, that the said

heirs, executors or administrators, will indemnify the said heirs, executors or

assigns, against all losses, damages or expenses occasioned to them by reason of the disobedience or wilful default or neglect of the said

during his said apprenticeship.

And the said _____ in
consideration of the premises, do hereby accept the said _____
as an apprentice for the

term of _____ years, to be computed from the date hereof,
and do hereby, for _____ self, h _____ executors and assigns,
covenant with the said _____

his executors, administrators and assigns, that he will pay or cause to be paid to the said

during his apprenticeship, whether employed at

or at any other work on the manufactory, the following wages, namely:—

and after the same rate in each year for less than a week's work, which shall be deducted according to the days or parts of days on which the said
shall be absent or unable to perform the duties of his apprenticeship and service.

And, lastly, for the true performance of all and every the covenants and conditions hereinbefore contained, each of the said parties hereto (so far as he lawfully can or may) hereby binds himself and themselves unto the other.

In witness whereof the said
and _____ have hereunto set their
hands and seals the day and year first before written.
Signed, sealed and delivered by the

before-named

and

in the presence of

MANUFACTURER'S GUIDE TO STOCK- TAKING.

The basis upon which a full and fair trade or commercial value can be put in estimating the stock on a manufactory is a matter of grave interest to the manufacturer. The method advised in this work, although a revolution on accustomed ideas, is nevertheless a most feasible one, and is calculated to show the true standing of a business in every particular, especially in the case of moulds and engravings, the value of which, in these days of rapid change of fashion, has been considerably lowered.

MATERIALS.

The full value of materials delivered on the works may be given, less the customary discounts allowed by the supplier.

In cases where an admixture has taken place, this cost should be added. In the case of a large stock of Ball Clays and Sagger Marl, the increased value of its being aged should be taken into account.

UTENSILS.

Engines, Mill Power and Machinery should be estimated at their actual cost, with a depreciatory allowance of 5 per cent. for each year's working, and wear and tear caused by production. Ordinary trade working utensils, in fair condition, may be taken at actual cost, less a deduction for wear and tear.

Blocks, Moulds and Cases.—The sum total expended on modelling expenses, mould makers' wages, cost of plaster, proportion of rent during the three previous years, the exact value of the blocks and cases in use prior to the time given, can only be appreciated by the orders their shapes command. There is, at the same time, always a certain value placed on a shape which has had a phenomenal run.

Copper Plate Engravings and Etchings.—A computation should be made of the cost of designs, purchases of engraved and etched plates, engravers' and etchers' wages, and cost of planishing during the three previous years, added to which the value of the copper plates in stock accurately scaled at $7\frac{1}{2}$ d. per lb. This will give a fair net value.

MANUFACTURED STOCK.

Green Ware.—This should be taken at current trade prices, with a reduction of 60 per cent.

Biscuit Ware may also be taken at current trade prices. In this case, however, the discount should be 50 per cent.

Enamelled, Printed, White and Common Ware to be taken at their usual scales, less the customary discounts:

and off the whole of the manufactured stock, it is desirable to deduct 25 per cent. discount to cover establishment and selling expenses and bad debts, etc.

TABLE

Of Relative Values of Potters' Materials, Calculated in Grade from One Ton to one Pound.

Per ton of 2240 lbs.	Per cwt. of 112 lbs.	Per $\frac{1}{2}$ cwt. of 56 lbs.	Per $\frac{1}{4}$ cwt. of 28 lbs.	Per $\frac{1}{8}$ cwt. of 14 lbs.	Per lb. of 16 ozs.
£ s. d.	£ s. d.	£ s. d.	£ s. d.	£ s. d.	£ s. d.
28 0 0	1 8 0	0 14 0	0 7 0	0 3 6	0 0 3
30 6 8	1 10 4	0 15 2	0 7 7	0 3 $9\frac{1}{2}$	0 0 $3\frac{1}{4}$
32 13 4	1 12 8	0 16 4	0 8 2	0 4 2	0 0 $3\frac{1}{2}$
35 0 0	1 15 0	0 17 6	0 8 9	0 4 $4\frac{1}{2}$	0 0 $3\frac{3}{4}$
37 6 8	1 17 4	0 18 8	0 9 4	0 4 $8\frac{1}{2}$	0 0 4
39 13 4	1 19 8	0 19 10	0 9 11	0 4 $11\frac{1}{2}$	0 0 $4\frac{1}{4}$
42 0 0	2 0 10	1 0 5	0 10 $2\frac{1}{2}$	0 5 1	0 0 $4\frac{1}{2}$
44 6 8	2 4 4	1 2 2	0 11 1	0 5 $6\frac{1}{2}$	0 0 $4\frac{3}{4}$
46 13 4	2 6 8	1 3 4	0 11 8	0 5 10	0 0 5
49 0 0	2 9 0	1 4 6	0 12 3	0 6 $1\frac{1}{2}$	0 0 $5\frac{1}{4}$
51 6 8	2 11 4	1 5 8	0 12 10	0 6 5	0 0 $5\frac{1}{2}$
53 13 4	2 13 8	1 6 10	0 13 5	0 7 $7\frac{1}{2}$	0 0 $5\frac{3}{4}$
56 0 0	2 16 0	1 8 0	0 14 0	0 7 0	0 0 6
58 6 8	2 18 4	1 9 2	0 14 7	0 7 $3\frac{1}{2}$	0 0 $6\frac{1}{4}$
60 13 4	3 0 8	1 10 4	0 15 2	0 7 7	0 0 $6\frac{1}{2}$
63 0 0	3 3 0	1 11 6	0 15 9	0 7 $10\frac{1}{2}$	0 0 $6\frac{3}{4}$
65 6 8	3 5 4	1 12 8	0 16 4	0 8 2	0 0 7
67 13 4	3 7 8	1 13 10	0 16 11	0 8 $5\frac{1}{2}$	0 0 $7\frac{1}{4}$
70 0 0	3 10 0	1 15 0	0 17 6	0 8 9	0 0 $7\frac{1}{2}$
72 6 8	3 12 4	1 16 2	0 18 1	0 9 $0\frac{1}{2}$	0 0 $7\frac{3}{4}$
74 13 4	3 14 8	1 17 4	0 18 8	0 9 10	0 0 8
77 0 0	3 17 0	1 18 6	0 19 3	0 9 $7\frac{1}{2}$	0 0 $8\frac{1}{4}$
79 6 8	3 19 4	1 19 8	0 19 10	0 9 11	0 0 $8\frac{1}{2}$
81 13 4	4 1 8	2 0 10	1 0 5	0 10 $2\frac{1}{2}$	0 0 $8\frac{3}{4}$
84 0 0	4 4 0	2 2 0	1 1 0	0 10 6	0 0 9
86 6 8	4 6 4	2 3 2	1 1 7	0 10 $9\frac{1}{2}$	0 0 $9\frac{1}{4}$
88 13 2	4 8 8	2 4 4	1 2 2	0 11 1	0 0 $9\frac{1}{2}$
91 0 0	4 11 0	2 5 6	1 2 9	0 11 $4\frac{1}{2}$	0 0 $9\frac{3}{4}$
93 6 8	4 13 4	2 6 8	1 3 4	0 11 8	0 0 10
95 13 4	4 15 8	2 7 10	1 3 11	0 11 $11\frac{1}{2}$	0 0 $10\frac{1}{4}$
98 0 0	4 18 0	2 9 0	1 4 6	0 12 3	0 0 $10\frac{1}{2}$
100 6 8	5 0 4	2 10 2	1 5 1	0 12 $6\frac{1}{2}$	0 0 $10\frac{3}{4}$
102 13 4	5 2 8	2 11 4	1 5 8	0 12 10	0 0 11
105 0 0	5 5 0	2 12 6	1 6 3	0 13 $1\frac{1}{2}$	0 0 $11\frac{1}{4}$
107 6 8	5 7 4	2 13 8	1 6 10	0 13 5	0 0 $11\frac{1}{2}$
109 13 4	5 9 8	2 14 10	1 7 5	0 13 $8\frac{1}{2}$	0 0 $11\frac{3}{4}$
112 0 0	5 12 0	2 16 0	1 8 0	0 14 0	0 1 0

HOURLY WAGES TABLE.

No. of Hours	1d.	2d.	3d.	4d.	5d.	6d.	7d.	8d.	9d.	10d.	11d.	1s.
	s. d. s. d.	s. d. s. d.	s. d. s. d.	s. d. s. d.	s. d. s. d.	s. d. s. d.	s. d. s. d.	s. d. s. d.	s. d. s. d.	s. d. s. d.	s. d. s. d.	s. d. s. d.
1	0 1	0 2	0 3	0 4	0 5	0 6	0 7	0 8	0 9	0 10	0 11	0 12
2	0 2	0 4	0 6	0 8	0 10	1 0	1 2	1 4	1 6	1 8	1 10	2 0
3	0 3	0 6	0 9	1 0	1 3	1 6	1 9	2 0	2 3	2 6	2 9	3 0
4	0 4	0 8	1 0	1 4	1 8	2 0	2 4	2 8	3 0	3 4	3 8	4 0
5	0 5	0 10	1 3	1 8	2 1	2 6	2 11	3 4	3 9	4 2	4 7	5 0
6	0 6	1 0	1 6	2 0	2 6	3 0	3 6	4 0	4 6	5 0	5 6	6 0
7	0 7	1 2	1 9	2 4	2 11	3 6	4 1	4 8	5 3	5 10	6 5	7 0
8	0 8	1 4	2 0	2 8	3 4	4 0	4 8	5 4	6 0	6 8	7 4	8 0
9	0 9	1 6	2 3	3 0	3 9	4 6	5 3	6 0	6 9	7 6	8 3	9 0
10	0 10	1 8	2 6	3 4	4 2	5 0	5 10	6 8	7 6	8 4	9 2	10 0
11	0 11	1 10	2 9	3 8	4 7	5 6	6 5	7 4	8 3	9 2	10 1	11 0
12	1 0	2 0	3 0	4 0	5 0	6 0	7 0	8 0	9 0	10 0	11 0	12 0
13	1 1	2 2	3 3	4 4	5 5	6 6	7 7	8 8	9 9	10 10	11 11	12 12
14	1 2	2 4	3 6	4 8	5 10	7 0	8 2	9 4	10 6	11 8	12 10	14 0
15	1 3	2 6	3 9	5 0	6 3	7 6	8 9	10 0	11 3	12 6	13 9	15 0
16	1 4	2 8	4 0	5 4	6 8	8 0	9 4	10 8	12 0	13 4	14 8	16 0
17	1 5	2 10	4 3	5 8	7 1	8 6	9 11	11 4	12 9	14 2	15 7	17 0
18	1 6	3 0	4 6	6 0	7 7	9 0	10 6	12 0	13 6	15 0	16 6	18 0
19	1 7	3 2	4 9	6 4	7 11	9 6	11 1	12 8	14 3	15 10	17 5	19 0
20	1 8	3 4	5 0	6 8	8 4	10 0	11 8	13 4	15 0	16 8	18 4	20 0
21	1 9	3 6	5 3	7 0	8 9	10 6	12 3	14 0	15 9	17 6	19 3	21 0
22	1 10	3 8	5 6	7 4	9 2	11 0	12 10	14 8	16 6	18 4	20 2	22 0
23	1 11	3 10	5 9	7 8	9 7	11 6	13 5	15 4	17 3	19 2	21 1	23 0
24	2 0	4 0	6 0	8 0	10 0	12 0	14 0	16 0	18 0	20 0	22 0	24 0
25	2 1	4 2	6 3	8 4	10 5	12 6	14 7	16 8	18 9	20 10	22 11	25 0
26	2 2	4 4	6 6	8 8	10 10	13 0	15 2	17 4	19 6	21 8	23 10	26 0
27	2 3	4 6	6 9	9 0	11 3	13 6	15 9	18 0	20 3	22 6	24 9	27 0
28	2 4	4 8	7 0	9 4	11 8	14 0	16 4	18 8	21 0	23 4	25 8	28 0
29	2 5	4 10	7 3	9 8	12 1	14 6	16 11	19 4	21 9	24 2	26 7	29 0
30	2 6	5 0	7 6	10 0	12 6	15 0	17 6	20 0	22 6	25 0	27 6	30 0
31	2 7	5 2	7 9	10 4	12 11	15 6	18 1	20 8	23 3	25 10	28 5	31 0
32	2 8	5 4	8 0	10 8	13 4	16 0	18 8	21 4	24 0	26 8	29 4	32 0
33	2 9	5 6	8 3	11 0	13 9	16 6	19 3	22 0	24 9	27 6	30 3	33 0
34	2 10	5 8	8 6	11 4	14 2	17 0	19 10	22 8	25 6	28 4	31 2	34 0
35	2 11	5 10	8 9	11 8	14 7	17 6	20 5	23 4	26 3	29 2	32 1	35 0
36	3 0	6 0	9 0	12 0	15 0	18 0	21 0	24 0	27 0	30 0	33 0	36 0
37	3 1	6 2	9 3	12 4	15 5	18 6	21 7	24 8	27 9	30 10	33 11	37 0
38	3 2	6 4	9 6	12 8	15 10	19 0	22 2	25 4	28 6	31 8	34 10	38 0
39	3 3	6 6	9 9	13 0	16 3	19 6	22 9	26 0	29 3	32 6	35 9	39 0
40	3 4	6 8	10 0	13 4	16 8	20 0	23 4	26 8	30 0	33 4	36 8	40 0
41	3 5	6 10	10 3	13 8	17 1	20 6	23 11	27 4	30 9	34 2	37 7	41 0
42	3 6	7 0	10 6	14 0	17 6	21 0	24 6	28 0	31 6	35 0	38 6	42 0
43	3 7	7 2	10 9	14 4	17 11	21 6	25 1	28 8	32 3	35 10	39 5	43 0
44	3 8	7 4	11 0	14 8	18 4	22 0	25 8	29 4	33 0	36 8	40 4	44 0
45	3 9	7 6	11 3	15 0	18 9	22 6	26 3	30 0	33 9	37 6	41 3	45 0
46	3 10	7 8	11 6	15 4	19 2	23 0	26 10	30 8	34 6	38 4	42 2	46 0
47	3 11	7 10	11 9	15 8	19 7	23 6	27 5	31 1	35 3	39 2	43 1	47 0
48	4 0	8 0	12 0	16 0	20 0	24 0	28 0	32 0	36 0	40 0	44 0	48 0
49	4 1	8 2	12 3	16 4	20 5	24 6	28 7	32 8	36 9	40 10	44 11	49 0
50	4 2	8 4	12 6	16 8	20 10	25 0	29 2	33 4	37 6	41 8	45 10	50 0
51	4 3	8 6	12 9	17 0	21 3	25 6	29 9	34 0	38 3	42 6	46 9	51 0
52	4 4	8 8	13 0	17 4	21 8	26 0	30 4	34 8	39 0	43 4	47 8	52 0
53	4 5	8 10	13 3	17 8	22 1	26 6	30 11	35 1	39 9	44 2	48 7	53 0
54	4 6	9 0	13 6	18 0	22 6	27 0	31 6	36 0	40 6	45 0	49 6	54 0
55	4 7	9 2	13 9	18 4	22 11	27 6	32 1	36 8	41 3	45 10	50 5	55 0
56	4 8	9 4	14 0	18 8	23 4	28 0	32 8	37 4	42 0	46 8	51 4	56 0

WORKMEN'S SETTLING TABLE, CALCULATED FROM ONE TO TEN DOZENS
AT PER SCORE.

20 doz. pieces at	1s.	1s. 3d.	1s. 6d.	1s. 9d.	2s.	2s. 3d.	2s. 6d.	2s. 9d.	3s.	3s. 3d.	3s. 6d.	3s. 9d.	4s.	4s. 6d.	4s. 9d.	5s.
10 dozen	s. d.	s. d.	s. d.	s. d.	s. d.	s. d.	s. d.	s. d.	s. d.	s. d.	s. d.	s. d.	s. d.	s. d.	s. d.	s. d.
9 ..	0 6	0 7½	0 9	0 10½	1 0	1 1½	1 3	1 4½	1 6	1 7½	1 9	1 10½	2 0	2 3	2 4½	2 6
8 ..	0 5½	0 6½	0 8	0 9	0 11	1 0	1 1½	1 2½	1 4	1 5½	1 7	1 7½	1 10	2 0	2 0¾	2 3
7 ..	0 4¾	0 6	0 7	0 8	0 9½	0 10½	1 0	1 1	1 2	1 3½	1 4¾	1 4¾	1 7	1 9	1 10	2 0
6 ..	0 4	0 5	0 6	0 7	0 8	0 9	0 10½	0 11	1 0	1 1	1 2	1 2	1 4	1 6	1 7	1 9
5 ..	0 3½	0 4	0 5	0 6	0 7	0 8	0 9	0 9	0 10	0 11	1 0	1 0	1 2	1 4	1 4½	1 6
4 ..	0 3	0 3½	0 4½	0 5	0 6	0 6½	0 7½	0 8¾	0 9	0 9½	0 10½	0 11½	1 0	1 1½	1 2½	1 3
3 ..	0 2½	0 3	0 3½	0 4	0 4½	0 5	0 6	0 6½	0 7	0 7½	0 8¼	0 8¼	0 9	0 10	0 11	1 0
2 ..	0 1¾	0 2	0 2½	0 3	0 3½	0 4	0 4½	0 4½	0 5	0 5½	0 6	0 6	0 7	0 8	0 8½	0 9
1 ..	0 1	0 1½	0 1¾	0 2	0 2½	0 3	0 3	0 3½	0 3½	0 4	0 4	0 4	0 5	0 5	0 5½	0 6
0 ..	0 0½	0 0¾	0 1	0 1	0 1	0 1	0 1½	0 1½	0 1¾	0 2	0 2	0 2	0 2	0 2	0 2¾	0 3

COMPARATIVE GUIDE FOR EARTHENWARE AND CHINA MANUFACTURERS IN THE USE OF
SLOP FLINT AND SLOP STONE.

Machine Weight.		Pint of 28 ounces.	Pint of 29 ounces.	Pint of 29½ ounces.	Pint of 30 ounces.	Pint of 30½ ounces.	Pint of 31 ounces.	Pint of 31½ ounces.	Pint of 32 ounces.	Pint of 32½ ounces.	Pint of 33 ounces.	Pint of 33½ ounces.	Pint of 34 ounces.
Hundredweight of 112 lbs.													
Cwts.	Qrs.	Lbs.	Pecks.	Pecks.	Pecks.	Pecks.	Pecks.	Pecks.	Pecks.	Pecks.	Pecks.	Pecks.	Pecks.
16	0	0	35½	43½	44½	46	54	53	56½	58½	61½	64½	66
16	2	0	36½	44½	46½	48½	55½	55	57½	60	63½	66½	68
17	0	0	38½	45½	47½	50	55	57	60	61½	65½	68½	70
17	2	0	40½	46½	48½	51½	56½	58½	61½	64½	67½	70	72
18	0	0	42½	47½	50	53	58	60½	63	66½	69	71½	74
18	2	0	44½	48½	51½	54½	59½	62	64½	68	71½	73½	76
19	0	0	45½	49½	52½	55½	61	63½	66½	70	73½	75½	78
19	2	0	46½	50½	53½	56½	62½	65½	68½	71½	75½	77½	80
20	0	0	48	51½	54½	58½	64½	67½	70	73½	77½	79½	82
20	2	0	49	52½	55½	59½	66	68½	71½	75½	79½	81½	84
21	0	0	50	53½	56½	60½	67½	70½	73½	77½	81½	83½	86
21	2	0	51	54½	57½	61½	69	72½	75½	79	83	85½	88½
22	0	0	52	55	58	62½	71	74	77	81	85	87½	90
22	2	0	53	56	59½	63½	72½	75½	78½	82½	87	89	92½
23	0	0	54½	57½	60½	64½	73½	77	80½	84½	89	91½	94½
23	2	0	55½	58½	61½	65½	75½	78½	82½	86½	90½	93½	96½
24	0	0	57	60	63	66½	77	80½	84	88½	92½	95½	98½
24	2	0	58½	61½	64½	67½	78½	82	85½	90	94½	97½	100½
25	0	0	59½	62½	65½	69½	80	83½	87½	92	96½	99½	102½
25	2	0	60½	63½	67	70½	81½	85½	89½	93½	98½	101½	104½
26	0	0	62	65½	69½	72½	83	87	91	95½	100½	103½	107

Note.—16 pints of slop flint or stone weighing 32 lbs. are 1 peck; 40 pecks of slop flint or stone weighing 11 cwt. 1 qr. 20 lbs. are 1 tub.

FOREIGN TERMS APPLIED TO EARTHENWARE AND CHINA GOODS.

English.	German.	French.	Spanish.	Portuguese.
Dinner Plates.	Speiseteller.	Plât du diner.	Platos paros comida.	Lamina.
Soup "	Suppenteller.	Plât du bouillon.	Platos idem paros sopa.	Lamina sôpa.
Dessert "	Dessert-teller.	Plât du dessert.	Platos paros dulces.	Plata para dulca.
Comportiers.	Compoischusseln.	Comportiers.	Platos paros frutas.	Plata para fruta.
Ordinary Dishes.	Gewöhnliche Schüsseln.	Assiette.	Plato.	Plata.
Soup Tureens.	Suppenterrinen.	Soupère.	Sopera.	Sâpero.
Sauce "	Saucenterrinen.	Saucière.	Sauera.	Sauceró.
Baking Dishes.	Packschüsseln.	Toutière.	Tartera.	Tarteró.
Cover Dishes.	Deckschüsseln.	Cloche du plât.	Platos paros papas.	Plata para papa.
Ewer.	Eimer.	Pot à l'eau.	Aiquieros.	Nunio jarros.
Basin.	Waschbecken.	Bol.	Báson.	Bacia para lavén.
Chamber.	Nachtgeschirr.	Pot de chambre.	Orinal.	Ourinol.
Soap Tray.	Seifennapf.	Savonette.	Jabon.	Sabàs.
Tea Cup.	Theetassen.	Tasse à thé.	Tasa ó té.	Tassa on té.
Coffee Cup.	Kaffeetassen.	Tasse à café.	Tasa ó café.	Tass on café.

Note.—The measurement of size is always given according to the metrical standard. A standard of comparison appears on page 195 of the Manual.

TABLE FOR THE CONVERSION OF METRICAL WEIGHTS AND MEASURES USED ON THE CONTINENT AND SOUTH AMERICA.

Remarks.—The metrical or French system is based upon the (assumed) length of the fourth part of the terrestrial meridian. The ten millionth part of this was chosen as the unit of length, and called a *mètre*. The cube of the tenth part of the *mètre* was adopted as the unit of capacity, and denominated a *litre*. The weight of a litre of distilled water at its greatest density was called a *kilogramme*, of which the thousandth part, or *gramme*, was adopted as the unit of weight. The multiples of these, proceeding in decimal progression, are distinguished by the employment of the prefixes *deca*, *hecto*, *kilo*, and *myria* from the Greek, and the subdivisions by *deci*, *centi*, and *milli* from the Latin. A *décimètre* is equivalent as a measure of length to 3·93708 inches of the English system, as is also 1 litre or cubic *décimètre* equivalent to 1·760 of an English pint measure.

Metres into English Yards of 36 Inches.		Litres into English Quarts and Gallons.		Kilogrammes into English.			
	Yards.		Galls.	Quarts.	1 kilogramme equivalent to		
1 metre equivalent to	1·094	1 litre equivalent to	0	0·880	Cwts.	Qrs.	Lbs.
2 "	2·187	2 "	0	1·761	0	0	2
3 "	3·281	3 "	0	2·641	0	0	4
4 "	4·374	4 "	0	3·521	0	0	6
5 "	5·468	5 "	1	0·402	0	0	8
6 "	6·562	6 "	1	1·282	0	0	11
7 "	7·655	7 "	1	2·163	0	0	13
8 "	8·749	8 "	1	3·043	0	0	15
9 "	9·843	9 "	1	3·923	0	0	17
10 "	10·936	10 "	2	0·801	0	0	19
20 "	21·873	20 "	4	1·608	0	0	22
30 "	32·809	30 "	6	2·412	0	1	16
40 "	43·745	40 "	8	3·215	0	2	10
50 "	54·682	50 "	11	0·019	0	3	4
60 "	65·618	60 "	13	0·823	0	3	26
70 "	76·554	70 "	15	1·627	1	0	20
80 "	87·491	80 "	17	2·421	1	1	14
90 "	98·427	90 "	19	3·225	1	2	8
100 "	109·363	100 "	22	0·039	1	3	2
					1	3	21
					1	3	7

INDEX

INDEX.

ALCOCK'S China Body, 7.
 " " Glaze, 56.
 " " Glaze 72.
 Amber Glaze, 85.
 Analysis of Clays, 153.
 Antique Enamel Colours, 121.
 Apprentices' Legal Indenture Form, 186.
 Ash Colour Dip, 51.
 Azure Dip, 47.
 BALSAM of Sulphur, 145.
 Barytes, Chromate of, 149.
 Bases, Enamel Colours, 99.
 Best White Glaze, 78.
 Black, Blue, Enamel, 112.
 " Body Dips, 48.
 " Egyptian Body, 34, 35.
 " Enamel Base, 99.
 " " Colour, 112.
 " For laying in, 48.
 " Glaze, 90.
 " Shining, 112.
 " Under-Glaze, Ordinary, 132, 133.
 " Under-Glaze, Stamping, 141.
 Blue Printed Body, 25.
 " Antique Navy, 121.
 " Broseley, 128.
 " Dips, 53.
 " Enamel Base, 99, 100.
 " " Dark, 113.
 " " Lee's, 114.
 " " Rhead's, 113.
 " Glaze, 85, 87, 90.
 " Green Enamel Base, 100.
 " " " Colour, 117.
 " " Glaze, 88.
 " Peacock Enamel Base, 103.
 " Royal Glaze, 89.
 " Under-Glaze Amoy, 129.

Blue Under-Glaze Bamboo, 127.
 " " Banding, 128.
 " " Broseley, 128.
 " " Cobalt, 126.
 " " Common, 129.
 " " Cross, 128.
 " " Gadroon, 129.
 " " Ironstone, 129.
 " " Pheasant, 128.
 " " Piedmont, 131.
 " " Printing, 129.
 Bodies, Brown, 33.
 " C. C., 24.
 " China and Porcelain, 7.
 " Coloured, 32.
 " Crucible, 30.
 " Earthenware, 24.
 " Granite, 24.
 " Ironstone, 18.
 " Jasper, 36.
 " Majolica, 38.
 " Miscellaneous, 29.
 " Mortar, 23.
 " Parian, 15.
 " Porous, 29.
 " Rockingham, 43.
 " Sagger, 30.
 " Terra Cotta, 10.
 " Vitreous, 18.
 Body Stains, 46.
 Boracic Acid Glaze, 80.
 Borax Glaze, 80.
 " " for Pink, 79.
 Brown Cottage Body, 33.
 " Dips, 50.
 " Enamel Base, 103.
 " " Chocolate, 115.
 " " Dark, 114.
 " " Devonshire, 115.
 " " Hair, 115.
 " " Light, 114.
 " " Sprig, 120.

- Brown Glaze, Majolica, Chestnut, 87.
 " " " Chocolate, 89.
 " " " Red, 88.
 " " " Sepia, 88.
 " Lessore's, 130.
 " Under-Glaze, Chocolate, 132.
 " " Dark, 132, 138.
 " " Light, 138.
 " " Purple, 143.
 " " Violet, 137.
 " " Russet, 137.
 Buff, Enamel Grounding, 119.
 " Under-Glaze, 141.
- CANARY Body, 32.
 Cane Bodies, 33.
 Cassius, Purple of, 97.
 C. C. Bodies, 27, 28.
 C. C. Glaze, 71, 75, 82.
 Celadon Enamel Colour, 120.
 Chalk Body, 26.
 China Bodies, Alcock's, 7.
 " " Alcock's Figure, 8.
 " " Casting, 8.
 " " Dessert, 9.
 " " Fenton, 11.
 " " French, 14.
 " " Fritts, 11.
 " " Lakin's, 12.
 " " Lilac, 32.
 " " Limoges, 14.
 " " Longport, 10.
 " " Longport, Semi-China, 18.
 " " Mason's, 13.
 " " Nantgarw, 11.
 " " Persian, 34.
 " " Purple, 43.
 " " Slate, 43.
 " " Spode's, 10.
 " Glazes, Alcock's, 56.
 " " Felspar, 60.
 " " French, 63.
 " " Longport, 55.
 " " Longport, Semi-China, 56.
 " " Mason's, 62.
 " " Ordinary, 56-63.
 " " Printed, 63.
 " " Special, 60.
 " " Spode's, 59.
 Chocolate, Majolica Glaze, 88.
 Chromate of Barytes, 149.
- Chromes, Preparation of Oxide, 149.
 Citron Body, 32.
 Clay, Cost of Prepared, 174.
 " Ware, Classification of, 152.
 Clays, Analysis by Lord Playfair, 153.
 " Comparative Loss of Weight in Drying and Firing, 159.
 " Crucible, 30.
 " Standard Weights of Various, 157.
 " Ware, Classification of, 152.
 Cobalt, Blue Ordinary, 126.
 " Notes on the Use of, 147.
 Cockson's Leadless Glaze, 83.
 Coloured Bodies, 32.
 " " for Mosaic Painting, 44.
 " Dips, 47.
 " Glazes, 85.
 Colours, Antique, 121.
 " Enamel, 112.
 " " Bases, 99.
 " " Mixed, 119.
 " " Notes on, 148.
 " Gold or Noble, 97.
 " Majolica, 91.
 " Under-Glaze, 126.
 " " " Mixed, 141.
 Common Body, 25.
 " Printed Body, 26.
 " Glaze, 75, 83.
 Conversion of Slop to Dry Weight, 168.
 Coral Enamel Base, 103.
 Cost of Prepared Clay, 174.
 Count, Decorated Goods, 158.
 Crimson, Majolica Glaze, 89.
- DAISY Glaze, 69.
 Decorated Goods Count, 158.
 Dessert China Body, 9.
 Dioxide of Manganese, 149.
 Dips, Coloured, 47.
 Distance, Enamel Colour, 119.
 Door Furniture Body, 25.
 Dove, Body Dip, 49.
 " Under-Glaze Colour, 141.
 " Flux, 125.
 Drab, Bodies, Green, 41.
 " " Light, 34.
 " " Ordinary, 34, 39.
 " Dips, 49.
 " Enamel Colour, 119.

Drab, Glaze, 91.
 Drapery, Parian for, 16.
 Dry Weight, Conversion of, 168.

EARTHENWARE Bodies, Alcock's, 26.
 " " Best, 24.
 " " Best Printed, 24, 27.
 " " " Granite, 27, 29.
 " " Chalk, 26.
 " " Common Printed, 28.
 " " Door Furniture, 25.
 " " Ivory, 28.
 " " Longport, 28.
 " " Pearl White, 26.
 " " and Glazes, Calculation of Net Cost, 174.
 " Glazes, Alcock's, 72.
 " " Best White, 66.
 " " Common Cream Colour, 75.
 " " Fancy Colour, 85.
 " " French White, 70.
 " " Granite, 76.
 " " Hanley, 72.
 " " Matt Blue, 62.
 " " Mayer's, 71.
 " " " Number 8," 66.
 " " Ordinary, 68, 69.
 " " Printed, 76, 77.
 " " Raw White, 74.

Egypt, 2.

Egyptian Black Bodies, 34, 35.

Enamel Colour Bases, 99.

" " Fluxes, 107.

" Colours, 112.

" " Mixed, 119.

" " Notes on, 148.

" Kiln Firing, 156.

Encaustic Tile Colours, 45.

Etching Colour for Jet Ware, 116.

FANCY Coloured Glazes, 85.

Fawn Dips, 49.

" Enamel Colour, Regular, 116, 120.

" Glaze, 88.

" Hard Kiln, 116.

" Porous Body, 43.

Felspar, Slop Calculations of, 163.

Felspathic Glaze, 60, 74.

Fenton China Body, 11.

Firing, Enamel Kiln, 157.

" Time of, 156.

Flint, Comparative Guide for Slop, 193.

" Standard Weight of Slop, 157.
 Flow Glaze, 72.

" Powders, 144.

Flux for Liquid Gold, 151.

Fluxes, Enamel, 107.

" Under-Glaze, 125.

Foreign Terms applied to Ceramic Ware, 194.

French China Body, 14.

" Grey Dip, 49.

Fritt China Body, 11.

Fuel Scale for Oven and Kiln Firing, 156.

GLAZE, Alcock's, 72.

" Best White, 66, 78.

" Boracic Acid, 80.

" Borax, 80, 81.

" " for Pink, 66.

" C. C., 71, 75, 82.

" China and Porcelain, 55.

" " without Lead, 84.

" Cockson's, 83.

" Coloured, 85.

" Common, 75, 83.

" Cost of Prepared, 173.

" Daisy, 69.

" Earthenware, 66.

" Felspar, 74.

" Flow, 70.

" French, 63.

" " White, 70.

" Granite, 76.

" Green, 85, 87.

" Hanley, 72.

" Ironstone, 64.

" Lakin's, 83.

" Leadless, 83.

" Majolica, 91.

" Mason's, 62.

" Matt Blue, 67, 78.

" Mayer's, 71.

" Miscellaneous, 84.

" No. 8, 66.

" Persian, 67, 70.

" Printed, 67, 75, 76, 77, 78, 82.

" Raw, 74.

" Rose's Gold Medal, 84.

" Stone, 64.

" Tincal, 79.

" Vitreous, 64.

Gold and Gold Colours, 92.

- Gold, Cheap, 95, 96.
 " Colours, 97.
 " Hard, 96.
 " Longport Best, 92.
 " Preparation of Best, 92.
 " " Bronze, 94.
 " " Chasing, 94.
 " " Common, 94.
 " " Hulme's, 94.
 " " Lakin's, 94.
 " " Liquid, 150.
 " " Liquid Gold
 Flux, 95.
 " Regular, 95, 96.
 " Rich, 96.
 " Solution of, 150.
 " Waste, Reclamation of, 146.
 Goods, Decorated, Count, 158.
 Granite Bodies, 25, 27, 29.
 Green, Antique Emerald, 122.
 " " Moss, 122.
 " " Myrtle, 124.
 " Bodies, Dark, 36.
 " " Light, 36.
 " Dips, 48, 50.
 " " Olive, 51.
 " Enamel Bases, 99.
 " " Blue, 117.
 " " Bronze, 122.
 " " Gold Edge, 97.
 " " Pea, 117.
 " " Pomona, 117.
 " Jasper Body, 37.
 " Under-Glaze Bamboo, 142.
 " " " Blue, 117.
 " " " Bronze, 137.
 " " " Cross, 142.
 " " " Crosslet, 142.
 " " " Gordon, 134.
 " " " Marine, 137.
 " " " Olive, 133.
 " " " Victoria, 134.
 141.
 HANLEY Glaze, 72.
 Hard Gold, 96.
 Hulme's Bronze Gold, 96.
 Gold, 94.
 IMPORTS, Trade Quality of English
 Ceramic, 154.
 Insulator, Body, 21.
 Ironstone Bodies, Longport, 18.
 " " Mason's, 22.
 Ironstone Bodies, Ordinary, 18.
 " Glazes, Longport, 64.
 " " Mason's, 65.
 " " Ordinary, 64.
 JASPER Bodies, Green, 37.
 " " Ordinary, 36.
 LACE, Parian for, 16.
 Lakin's Bronze Gold, 94.
 " China Body, 12.
 " Gold, 94.
 " Leadless Glaze, 83.
 Leadless Glazes, Cockson's, 83.
 " " Lakin's, 83.
 " " Rose's Gold Medal,
 84.
 Lilac Body (Alcock's),
 " Dip, 51.
 " Earthenware Body, 37.
 " Enamel Colour, 120.
 " Porcelain Body, 32.
 " Under-Glaze Printing, 134.
 Limoges China Body, 14.
 Liquid Gold, 150.
 " Flux, 151.
 Longport, Best Gold, 93.
 " Chasing Gold, 94.
 " China Body, 7.
 " Common Gold, 94.
 " Glaze, 55.
 " Ironstone Body, 18.
 " Old Stone Glaze, 64.
 " Semi-China Glaze, 56.
 " " Body, 18.
 Loss of Weight of Clays, 159.
 MAJOLICA Bodies, Ordinary, 38.
 " " Old, 38.
 " Colours, Various, 91.
 " Glaze, Soft, 91.
 Manganese, Preparation of Oxide,
 149.
 Markets of the World, 154.
 Marone Body Dip, 53.
 " Enamel Base, 98.
 " " Colour, 98.
 " " Flux, 98.
 " Under-Glaze Printing, 142.
 Mason's China Body, 13.
 Materials, Grade Calculation of
 Relative Values of, 190.
 " Standard Weights of,
 157.

- Matt Blue, Rathbone's Under-Glaze Colour, 129.
 Mayer's Glaze, 71.
 Metrical Weights and Measures, Table for Conversion of, 195.
 Mocha Dip, 51.
 "Moco, Black Jack's," Dip, 51.
 Mortar Bodies, 19, 20, 23.
 Mosaic, Painting Slips, 44.
 Mould Body, 29.
 Mulberry Body Dip, 52.
 " Glaze, 86.
 " Under-Glaze Printing, 134, 135.

 NANTGARW China Body, 11.
 Neutral, Under-Glaze Printing, 142.

 OIL, Grounding, 145.
 " Printer's, 145.
 Old Majolica Body, 38.
 " Stone Glaze, Longport, 64.
 Olive, Enamel Colour, 120.
 Orange, Body, 39.
 " Enamel Red, 117.
 " Glaze, Transparent, 87.
 " Under-Glaze Printing, 135.
 Oven Firing, Time of, 156.

 PALETTE Body, 25.
 Parian Body for Laces and Drapery, 16.
 " " Ordinary, 15.
 " " Small Articles, 16.
 " " Statuettes, 15.
 " Fritt, 15.
 Pea Green Glaze, 86.
 Pearl Granite Body, 21, 26.
 Persian China Body, 34.
 " Glaze, 67, 70.
 " Pink Under-Glaze, 137.
 Pink, Borax Glaze for, 79.
 " Enamel Base, 97.
 " " Colour, 97.
 " Glaze for, 68.
 " Under-Glaze Printing, 136.
 Playfair, Lord, Analysis of Clays, 153.
 Porcelain Bodies, 7.
 Porous Cells Bodies, 29.
 Potter's Art, Rise and Progress of, in England, 1.
 Powders, Flow, 144.
 Prepared Clay, Cost of, 174.
 Prepared Glaze, Cost of, 174.
 Printed Bodies, 24, 27, 28.
 " Glaze, 67, 75, 76, 77, 78, 82.
 Purple China Body, 43.
 " of Cassius, 97.
 " Under-Glaze Printing, 143.
 Pyrometrical Test for Enamel Kiln Firing, 157.

 RAISED Gold Composition, 118.
 Raw White Glaze, 75.
 Reclamation of Waste Gold, 146.
 Red Bodies, Ordinary, 41.
 " " Porous, 41.
 " Chrome, 149.
 " Dips, 52.
 " Enamel Base, 99.
 " Nasturtium, 118.
 " Windsor, 121.
 Rise and Progress of the Potter's Art, 1.
 Rockingham Body, 43.
 Rose Colour Enamel, 97.
 " Flux, 98.
 Rose's Gold Medal Leadless Glaze, 84.
 Roughing Preparation for Slates, 118.
 Ruby Base, 98.
 " Flux, 98.

 SAGE Bodies, 40.
 Sagger Bodies, 30.
 " Washes, 84.
 Salmon Body, 40.
 " Enamel Grounding, 121.
 Sanitary Body, 30.
 Scale of Fuel and Firing, 156.
 Semi-Porcelain Bodies, 18.
 " Glaze, 65.
 Semi-China Glaze, Longport, 56.
 Sesquioxide of Manganese, 150.
 Slate China Body, 43.
 " Glaze, 90.
 " Under-Glaze Printing, 143.
 Slop Flint and Stone Guide, 193.
 Slop Felspar Calculations, 163.
 Smearing Bodies, 41, 42.
 Spode's China Body, 10.
 Stains, Body, 46.
 Statuettes, Parian for, 15.
 Stocktaking Guide, 188.
 Stone Bodies, Longport, Old, 18.
 " " Mason's, 22.
 " " Ordinary, 18.

- Stone Bodies, White, 19.
 „ Colour for Hard Kiln, 121.
 „ Glazes, Longport, Old, 64.
 „ „ Ordinary, 65, 66.
 „ Slop Stone Calculations, 193.
 „ Standard Weight of, 157.
 Sulphur, Preparation of Balsam, 145.
- TERRA COTTA, Antique Enamel, 124.
 „ „ Bodies, 40.
 Tincal, Glaze, 79.
 Tile, Body White, 30.
 „ Colours, Encaustic, 45.
 Time, Approximate, of Firing, 156.
 Turquoise, Body, 39.
 „ Dip, 53.
 „ Enamel Base, 100, 102,
 104, 106.
 „ „ Colour, 118.
 „ Sèvres, 100.
 „ Stain, 39.
- UNDER-GLAZE Colours, 126.
 „ „ Mixed Colours, 141.
 „ „ Printing Fluxes, 125.
 Unique, Under-Glaze, 140.
 Use of Cobalt, 147.
- VALUATION, for Stocktaking, 188.
 Varnishes, Oils and, 145.
 Vellum Colours, 121.
 Violet, Under-Glaze Printing, 137.
 Vitreous Bodies, 18.
 „ Longport, 18.
 „ Pearl Granite, 21.
 „ Mason's, 22.
- WAGES, Hourly Table, 191.
 Wash for Sagger, 84.
 Waste Gold, Reclamation of, 146.
 Weights of Materials, Standard, 157.
 White Enamel, Regular Kiln, 115.
 „ „ for Jet, 116.
 „ Glaze, 81.
 „ Granite Body, 25.
 „ Tile Body, 30.
 Workmen's Settling Table, 192.
 World, Markets of the, 154.
- YELLOW Bodies, 33.
 „ Chrome, 149.
 „ Enamel Base, 79.
 „ „ Colour, 97.
 „ Golden Glaze, 89.
 „ Under-Glaze Printing 136.

Catalogue OF Special Technical Books

FOR
MANUFACTURERS, TECHNICAL STUDENTS AND
WORKERS, SCHOOLS, COLLEGES, ETC.
BY EXPERT WRITERS

INDEX TO SUBJECTS.

PAGE	PAGE	PAGE
Agricultural Chemistry ... 10	Enamels ... 18	Petroleum ... 6
Air, Industrial Use of ... 12	Engraving ... 31	Pigments, Chemistry of ... 2
Alum and its Sulphates ... 9	Essential Oils ... 7	Plumbers' Work ... 27
Ammonia ... 9	Evaporating Apparatus ... 26	Porcelain Painting ... 17
Aniline Colours ... 3	External Plumbing ... 27	Pottery Clays ... 16
Animal Fats ... 6	Fats ... 5, 6	Pottery Decorating ... 15
Anti-corrosive Paints ... 4	Faults in Woollen Goods ... 21	Pottery Manufacture ... 14
Architecture, Terms in ... 30	Fruit Preserving ... 30	Pottery Recipes ... 14
Architectural Pottery ... 15	Gas Firing ... 26	Power-loom Weaving ... 19
Artificial Perfumes ... 7	Glass-making Recipes ... 16	Preserved Foods ... 30
Balsams ... 10	Glass Painting ... 17	Printers' Ready Reckoner ... 31
Bibliography ... 32	Glue Making and Testing ... 8	Printing Inks ... 3
Bleaching ... 23	Greases ... 5	Recipes for Oilmen, etc. ... 3
Bone Products ... 8	Hat Manufacturing ... 20	Resins ... 10
Bookbinding ... 32	History of Staffs Potteries ... 16	Risks of Occupations ... 11
Brick-making ... 15, 16	Hops ... 28	Rivetting China, etc. ... 16
Burnishing Brass ... 28	Hot-water Supply ... 28	Sanitary Plumbing ... 27
Carpet Yarn Printing ... 21	How to make a Woollen Mill	Scheele's Essays ... 9
Celluloid ... 31	Pay ... 21	Sealing Waxes ... 11
Ceramic Books ... 14, 15	India-rubber ... 13	Silk Dyeing ... 22
Charcoal ... 8	Industrial Alcohol ... 10	Silk Throwing ... 18
Chemical Essays ... 9	Inks ... 3, 11	Smoke Prevention ... 26
Chemistry of Pottery ... 16	Iron-corrosion ... 4	Soaps ... 7
Chemistry of Dye-stuffs ... 23	Iron, Science of ... 26	Spinning ... 21
Clay Analysis ... 16	Japanning ... 28	Staining Marble, and Bone ... 31
Coal-dust Firing ... 26	Lace-Making ... 20	Steam Drying ... 12
Colour Matching ... 22	Lacquering ... 28	Sugar Refining ... 32
Colliery Recovery Work ... 25	Lake Pigments ... 2	Steel Hardening ... 26
Colour-mixing for Dyers ... 22	Lead and its Compounds ... 11	Sweetmeats ... 30
Colour Theory ... 22	Leather Industry ... 13	Terra-cotta ... 15
Combining Machines ... 24	Leather-working Materials ... 14	Testing Paint Materials ... 4
Compounding Oils ... 6	Lithography ... 31	Testing Yarns ... 20
Condensing Apparatus ... 26	Lubricants ... 5, 6	Textile Fabrics ... 20
Cosmetics ... 8	Manures ... 10	Textile Materials ... 19, 20
Cotton Dyeing ... 23	Meat Preserving ... 30	Timber ... 29
Cotton Spinning ... 24	Mineral Pigments ... 3	Varnishes ... 5
Damask Weaving ... 20	Mine Ventilation ... 25	Vegetable Fats ... 7
Dampness in Buildings ... 30	Mine Haulage ... 25	Vegetable Preserving ... 30
Decorators' Books ... 28	Needlework ... 20	Waste Utilisation ... 10
Decorative Textiles ... 20	Oil and Colour Recipes ... 3	Water, Industrial Use ... 12
Dental Metallurgy ... 25	Oil Boiling ... 5	Waterproofing Fabrics ... 21
Dictionary of Paint Materials ... 2	Oil Merchants' Manual ... 7	Weaving Calculations ... 21
Drying Oils ... 5	Oils ... 5	White Lead and Zinc ... 4
Drying with Air ... 12	Ozone, Industrial Use of ... 12	Wood Waste Utilisation ... 29
Dyeing Marble ... 31	Paint Manufacture ... 2	Wood Dyeing ... 31
Dyeing Woollen Fabrics ... 23	Paint Materials ... 3	Wool Dyeing ... 22, 23
Dyers' Materials ... 22	Paint-material Testing ... 4	Writing Inks ... 11
Dye-stuffs ... 23	Paint Mixing ... 28	X-Ray Work ... 13
Electric Wiring ... 27	Paper-Mill Chemistry ... 17	Yarn Testing ... 20
Enamelling Metal ... 18	Paper-pulp Dyeing ... 17	Zinc White Paints ... 4

PUBLISHED BY

SCOTT, GREENWOOD & SON,
8 BROADWAY, LUDGATE HILL,
LONDON, E.C.

Telephone, Bank 5403.

Telegraphic Address, "Printeries, London".

Paints, Colours and Printing Inks.

THE CHEMISTRY OF PIGMENTS. By ERNEST J. PARRY, B.Sc. (Lond.), F.I.C., F.C.S., and J. H. COSTE, F.I.C., F.C.S. Demy 8vo. Five Illustrations. 285 pp. Price 10s. 6d. net. (Post free, 10s. 10d. home; 11s. 3d. abroad.)

Contents.

Introductory. Light—White Light—The Spectrum—The Invisible Spectrum—Normal Spectrum—Simple Nature of Pure Spectral Colour—The Recomposition of White Light—Primary and Complementary Colours—Coloured Bodies—Absorption Spectra—**The Application of Pigments.** Uses of Pigments: Artistic, Decorative, Protective—Methods of Application of Pigments: Pastels and Crayons, Water Colour, Tempera Painting, Fresco, Encaustic Painting, Oil-colour Painting, Ceramic Art, Enamel, Stained and Painted Glass, Mosaic—**Inorganic Pigments.** White Lead—Zinc White—Enamel White—Whitening—Red Lead—Litharge—Vermilion—Royal Scarlet—The Chromium Greens—Chromates of Lead, Zinc, Silver and Mercury—Brunswick Green—The Ochres—Indian Red—Venetian Red—Siennas and Umbers—Light Red—Cappagh Brown—Red Oxides—Mars Colours—Terre Verte—Prussian Brown—Cobalt Colours—Ceruleum—Smalt—Copper Pigments—Malachite—Bremen Green—Scheele's Green—Emerald Green—Verdigris—Brunswick Green—Non-arsenical Greens—Copper Blues—Ultramarine—Carbon Pigments—Ivory Black—Lamp Black—Bistre—Naples Yellow—Arsenic Sulphides: Orpiment, Realgar—Cadmium Yellow—Vandyck Brown—**Organic Pigments.** Prussian Blue—Natural Lakes—Cochineal—Carmine—Crimson—Lac Dye—Scarlet—Madder—Alizarin—Campeachy—Quercitron—Rhamnus—Brazil Wood—Alkanet—Santal Wood—Archil—Coal-tar Lakes—Red Lakes—Alizarin Compounds—Orange and Yellow Lakes—Green and Blue Lakes—Indigo—Dragon's Blood—Gamboe—Sepia—Indian Yellow, Puree—Bitumen, Asphaltum, Mummy—**Index.**

THE MANUFACTURE OF PAINT. A Practical Handbook for Paint Manufacturers, Merchants and Painters. By J. CRUICKSHANK SMITH, B.Sc. Demy 8vo. 200 pp. Sixty Illustrations and One Large Diagram. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

Preparation of Raw Material—Storing of Raw Material—Testing and Valuation of Raw Material—Paint Plant and Machinery—The Grinding of White Lead—Grinding of White Zinc—Grinding of other White Pigments—Grinding of Oxide Paints—Grinding of Staining Colours—Grinding of Black Paints—Grinding of Chemical Colours—Yellows—Grinding of Chemical Colours—Blues—Grinding Greens—Grinding Reds—Grinding Lakes—Grinding Colours in Water—Grinding Colours in Turpentine—The Uses of Paint—Testing and Matching Paints—Economic Considerations—**Index.**

DICTIONARY OF CHEMICALS AND RAW PRODUCTS USED IN THE MANUFACTURE OF PAINTS, COLOURS, VARNISHES AND ALLIED PREPARATIONS. By GEORGE H. HURST, F.C.S. Demy 8vo. 380 pp. Price 7s. 6d. net. (Post free, 8s. home; 8s. 6d. abroad.)

THE MANUFACTURE OF LAKE PIGMENTS FROM ARTIFICIAL COLOURS. By FRANCIS H. JENNISON, F.I.C., F.C.S. Sixteen Coloured Plates, showing Specimens of Eighty-nine Colours, specially prepared from the Recipes given in the Book. 136 pp. Demy 8vo. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

The Groups of the Artificial Colouring Matters—The Nature and Manipulation of Artificial Colours—Lake-forming Bodies for Acid Colours—Lake-forming Bodies' Basic Colours—Lake Bases—The Principles of Lake Formation—Red Lakes—Orange, Yellow, Green, Blue, Violet and Black Lakes—The Production of Insoluble Azo Colours in the Form of Pigments—The General Properties of Lakes Produced from Artificial Colours—Washing, Filtering and Finishing—Matching and Testing Lake Pigments—**Index**

PAINTS, COLOURS, ETC.—*continued.*

THE MANUFACTURE OF MINERAL AND LAKE PIGMENTS. Containing Directions for the Manufacture of all Artificial, Artists and Painters' Colours, Enamel, Soot and Metallic Pigments. A Text-book for Manufacturers, Merchants, Artists and Painters. By Dr. JOSEF BERSCH. Translated by A. C. WRIGHT, M.A. (Oxon.), B.Sc. (Lond.). Forty-three Illustrations. 476 pp., demy 8vo. Price 12s. 6d. net. (Post free, 13s. home; 13s. 6d. abroad.)

Contents.

Introduction—Physico-chemical Behaviour of Pigments—Raw Materials Employed in the Manufacture of Pigments—Assistant Materials—Metallic Compounds—The Manufacture of Mineral Pigments—The Manufacture of White Lead—Enamel White—Washing Apparatus—Zinc White—Yellow Mineral Pigments—Chrome Yellow—Lead Oxide Pigments—Other Yellow Pigments—Mosaic Gold—Red Mineral Pigments—The Manufacture of Vermilion—Antimony Vermilion—Ferric Oxide Pigments—Other Red Mineral Pigments—Purple of Cassius—Blue Mineral Pigments—Ultramarine—Manufacture of Ultramarine—Blue Copper Pigments—Blue Cobalt Pigments—Smalts—Green Mineral Pigments—Emerald Green—Verdigris—Chromium Oxide—Other Green Chromium Pigments—Green Cobalt Pigments—Green Manganese Pigments—Compounded Green Pigments—Violet Mineral Pigments—Brown Mineral Pigments—Brown Decomposition Products—Black Pigments—Manufacture of Soot Pigments—Manufacture of Lamp Black—The Manufacture of Soot Black without Chambers—Indian Ink—Enamel Colours—Metallic Pigments—Bronze Pigments—Vegetable Bronze Pigments.

PIGMENTS OF ORGANIC ORIGIN—Lakes—Yellow Lakes—Red Lakes—Manufacture of Carmine—The Colouring Matter of Lac—Safflower or Carthamine Red—Madder and its Colouring Matters—Madder Lakes—Manjit (Indian Madder)—Lichen Colouring Matters—Red Wood Lakes—The Colouring Matters of Sandal Wood and Other Dye Woods—Blue Lakes—Indigo Carmine—The Colouring Matter of Log Wood—Green Lakes—Brown Organic Pigments—Sap Colours—Water Colours—Crayons—Confectionery Colours—The Preparation of Pigments for Painting—The Examination of Pigments—Examination of Lakes—The Testing of Dye-Woods—The Design of a Colour Works—Commercial Names of Pigments—Appendix: Conversion of Metric to English Weights and Measures—Centigrade and Fahrenheit Thermometer Scales—Index.

RECIPES FOR THE COLOUR, PAINT, VARNISH, OIL, SOAP AND DRY-SALTERY TRADES. Compiled by AN ANALYTICAL CHEMIST. 350 pp. Demy 8vo. Price 7s. 6d. net. (Post free, 8s. home; 8s. 3d. abroad.)

Contents.

Pigments or Colours for Paints, Lithographic and Letterpress Printing Inks, etc.—Mixed Paints and Preparations for Paint-making, Painting, Lime-washing, Paperhanging, etc.—Varnishes for Coach-builders, Cabinetmakers, Wood-workers, Metal-workers, Photographers, etc.—Soaps for Toilet, Cleansing, Polishing, etc.—Perfumes—Lubricating Greases, Oils, etc.—Cements, Pastes, Glues and Other Adhesive Preparations—Writing, Marking, Endorsing and Other Inks—Sealing-wax and Office Requisites—Preparations for the Laundry, Kitchen, Stable and General Household Uses—Disinfectant Preparations—Miscellaneous Preparations—Index.

OIL COLOURS AND PRINTERS' INKS. By LOUIS EDGAR ANDÉS. Translated from the German. 215 pp. Crown 8vo. 56 Illustrations. Price 5s. net. (Post free, 5s. 4d. home; 5s. 6d. abroad.)

Contents.

Linseed Oil—Poppy Oil—Mechanical Purification of Linseed Oil—Chemical Purification of Linseed Oil—Bleaching Linseed Oil—Oxidizing Agents for Boiling Linseed Oil—Theory of Oil Boiling—Manufacture of Boiled Oil—Adulterations of Boiled Oil—Chinese Drying Oil and Other Specialities—Pigments for House and Artistic Painting and Inks—Pigment for Printers' Black Inks—Substitutes for Lampblack—Machinery for Colour Grinding and Rubbing—Machines for mixing Pigments with the Vehicle—Paint Mills—Manufacture of House Oil Paints—Ship Paints—Luminous Paint—Artists' Colours—Printers' Inks—VEHICLES—Printers' Inks—PIGMENTS and MANUFACTURE—Index.

(See also *Writing Inks*, p. 11.)

THREE HUNDRED SHADES AND HOW TO MIX THEM. For Architects, Decorators and Painters.

(See page 28.)

PAINTS, COLOURS, ETC.—*continued.*

CASEIN. By ROBERT SCHERER. Translated from the German by CHAS. SALTER. Demy 8vo. Illustrated. 160 pp. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

Casein: its Origin, Preparation and Properties. Various Methods of Preparing Casein. Composition and Properties of Casein. Casein Paints.—"Marble-Lime" Colour for Outside Work—Casein Enamel Paint—Casein Façade Paint—Cold-Water Paint in Powder Form—Kistory's Recipe for Casein Paint and Varnish—Pure Casein Paints for Walls, etc.—Casein Paints for Woodwork and Iron—Casein-Silicate Paints—Milk Paints—Casein-Silicate Paint Recipes—Trojel's Boiled Oil Substitute—Calsomine Wash—Quick-Drying Casein Paint—Boiled Oil Substitute—Ring's Cold-Water Paint—Formolactin—Waterproof Paint for Playing Cards—Casein Colour Lake—Casein-Cement Paint. **The Technics of Casein Painting. Casein Adhesives and Putties.**—Casein Glue in Plates or Flakes—Jeromin's Casein Adhesive—Hall's Casein Glue—Waterproof Glue—Liquid Casein Glue—Casein and Borax Glue—Solid Casein Adhesive—Casein Solution—Glue Powder—Casein Putties—Washable Cement for Deal Boards—Wenk's Casein Cement—Casein and Lime Cement—"Pitch Barm"—Casein Stopping—Casein Cement for Stone. **The Preparation of Plastic Masses from Casein.**—Imitation Ivory—Anti-Radiation and Anti-Corrosive Composition—Dickmann's Covering for Floors and Walls—Imitation Linoleum—Imitation Leather—Imitation Bone—Plastic Mass of Keratin and Casein—Insulating Mass—Plastic Casein Masses—Horny Casein Mass—Plastic Mass from Celluloid—Casein Cellulose Composition—Fireproof Cellulose Substitute—Nitrocellulose and Casein Composition—Franquet's Celluloid Substitute—Galalith. **Uses of Casein in the Textile Industry, for Finishing Colour Printing, etc.**—Caseogum—"Glutin"—Casein Dressing for Linen and Cotton Fabrics—Printing Colour with Metallic Lustre—Process for Softening, Sizing and Loading—Fixing Casein and Other Albuminoids on the Fibre—Fixing Insoluble Colouring Matters—Waterproofing and Softening Dressing—Casein for Mercerising Crêpe—Fixing Zinc White on Cotton with Formaldehyde—Casein-Magnesia—Casein Medium for Calico Printing—Loading Silk. **Casein Foodstuffs.**—Casein Food—Synthetic Milk—Milk Food—Emulsifiable Casein—Casein Phosphate for Baking—Making Bread, Low in Carbohydrates, from Flour and Curd—Preparing Soluble Casein Compounds with Citrates—Casein Food. **Sundry Applications of Casein.**

SIMPLE METHODS FOR TESTING PAINTERS' MATERIALS. By A. C. WRIGHT, M.A. (Oxon.), B.Sc. (Lond.). Crown 8vo. 160 pp. Price 5s. net. (Post free, 5s. 3d. home; 5s. 6d. abroad.)

IRON - CORROSION, ANTI - FOULING AND ANTI-CORROSIVE PAINTS. Translated from the German of LOUIS EDGAR ANDÉS. Sixty-two Illustrations. 275 pp. Demy 8vo. Price 10s. 6d. net. (Post free, 10s. 10d. home; 11s. 3d. abroad.)

Contents.

Iron-rust and its Formation—Protection from Rusting by Paint—Grounding the Iron with Linseed Oil, etc.—Testing Paints—Use of Tar for Painting on Iron—Anti-corrosive Paints—Linseed Varnish—Chinese Wood Oil—Lead Pigments—Iron Pigments—Artificial Iron Oxides—Carbon—Preparation of Anti-corrosive Paints—Results of Examination of Several Anti-corrosive Paints—Paints for Ship's Bottoms—Anti-fouling Compositions—Various Anti-corrosive and Ship's Paints—Official Standard Specifications for Ironwork Paints—Index.

THE TESTING AND VALUATION OF RAW MATERIALS USED IN PAINT AND COLOUR MANUFACTURE. By M. W. JONES, F.C.S. A Book for the Laboratories of Colour Works. 88 pp. Crown 8vo. Price 5s. net. (Post free, 5s. 3d. home and abroad.)

THE MANUFACTURE AND COMPARATIVE MERITS OF WHITE LEAD AND ZINC WHITE PAINTS. By G. PETIT, Civil Engineer, etc. Translated from the French. Crown 8vo. 100 pp. Price 4s. net. (Post free, 4s. 3d. home; 4s. 4d. abroad.)

Contents.

Chapters I., The Fundamental Principles of Painting in Oil. II., The Different Varieties of White Leads—The Dutch Process—Grinding White Lead in Oil. III., Other Processes of Manufacturing White Lead. IV., White Lead Substitutes—Sophistication of White Lead—Analysis of White Lead. V., White Lead Paints—Their Merits and Defects. VI., Toxicology of White Lead—Hygienic Measures in its Manufacture and Use. VII., Zinc White—Its Preparation. IX., Zinc White Paint and Zinc White Coatings—Their Merits and Defects.

STUDENTS' HANDBOOK OF PAINTS, COLOURS, OILS AND VARNISHES. By JOHN FURNELL. Crown 8vo. 12 Illustrations. 96 pp. Price 2s. 6d. net. (Post free, 2s. 9d. home and abroad.)

Varnishes and Drying Oils.

OIL CRUSHING, REFINING AND BOILING, THE MANUFACTURE OF LINOLEUM, PRINTING AND LITHOGRAPHIC INKS, AND INDIA-RUBBER SUBSTITUTES. By JOHN GEDDES MCINTOSH. Being Volume I. of the Second, greatly enlarged, English Edition, in three Volumes, of "The Manufacture of Varnishes and Kindred Industries," based on and including the work of Ach. Livache. Demy 8vo. 150 pp. 29 Illustrations. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

VARNISHES AND VARNISH MAKING MATERIALS. By J. G. MCINTOSH. Demy 8vo. 54 Illustrations. [*In the Press.*]

Contents.

Chapter I., Introduction. II., Amber and Amber Oil Varnishes. III., Copal, etc. IV., **Resins**—Assorting, Cleaning and Fusing. V., Asphaltum, Coal-Tar, Pitch, Rubber, etc. VI., Oil-Varnish Making—General Instructions. VII., Copal Oil Varnish. VIII., Rosin Oil Varnish—Brunswick Black—Super Black Japan. IX., Testing Varnish—Utilisation of Residues.

DRYING OILS, BOILED OIL AND SOLID AND LIQUID DRIERS. By L. E. ANDÉS. Expressly Written for this Series of Special Technical Books, and the Publishers hold the Copyright for English and Foreign Editions. Forty-two Illustrations. 342 pp. Demy 8vo. Price 12s. 6d. net. (Post free, 13s. home; 13s. 3d. abroad.)

Contents.

Properties of the Drying Oils; Cause of the Drying Property: Absorption of Oxygen; Behaviour towards Metallic Oxides, etc.—The Properties of and Methods for obtaining the Drying Oils—Production of the Drying Oils by Expression and Extraction; Refining and Bleaching; Oil Cakes and Meal; The Refining and Bleaching of the Drying Oils; The Bleaching of Linseed Oil—The Manufacture of Boiled Oil; The Preparation of Drying Oils for Use in the Grinding of Paints and Artists' Colours and in the Manufacture of Varnishes by Heating over a Fire or by Steam, by the Cold Process, by the Action of Air, and by Means of the Electric Current; The Driers used in Boiling Linseed Oil; The Manufacture of Boiled Oil and the Apparatus therefor; Livache's Process for Preparing a Good Drying Oil and its Practical Application—The Preparation of Varnishes for Letterpress, Lithographic and Copperplate Printing, for Oilcloth and Waterproof Fabrics: The Manufacture of Thickened Linseed Oil, Burnt Oil, Stand Oil by Fire Heat, Superheated Steam, and by a Current of Air—Behaviour of the Drying Oils and Boiled Oils towards Atmospheric Influences, Water, Acids and Alkalies—Boiled Oil Substitutes—The Manufacture of Solid and Liquid Driers from Linseed Oil and Rosin; Linolic Acid Compounds of the Driers—The Adulteration and Examination of the Drying Oils and Boiled Oil.

Oils, Fats, Greases, Petroleum.

LUBRICATING OILS, FATS AND GREASES: Their Origin, Preparation, Properties, Uses and Analyses. A Handbook for Oil Manufacturers, Refiners and Merchants, and the Oil and Fat Industry in General. By GEORGE H. HURST, F.C.S. Second Revised and Enlarged Edition. Sixty-five Illustrations. 317 pp. Demy 8vo. Price 10s. 6d. net. (Post free, 11s. home; 11s. 3d. abroad.)

Contents.

Introductory—Hydrocarbon Oils—Scotch Shale Oils—Petroleum—Vegetable and Animal Oils—Testing and Adulteration of Oils—Lubricating Greases—Lubrication—Appendices—Index.

TECHNOLOGY OF PETROLEUM: Oil Fields of the World—Their History, Geography and Geology—Annual Production and Development—Oil-well Drilling—Transport. By HENRY NEUBERGER and HENRY NOALHAT. Translated from the French by J. G. McINTOSH. 550 pp. 153 Illustrations. 26 Plates. Super Royal 8vo. Price 21s. net. (Post free, 21s. 9d. home; 23s. 6d. abroad.)

Contents.

Study of the Petroliferous Strata.
Excavations—Hand Excavation or Hand Digging of Oil Wells.
Methods of Boring.
Accidents—Boring Accidents—Methods of preventing them—Methods of remedying them—Explosives and the use of the "Torpedo" Levigation—Storing and Transport of Petroleum
General Advice—Prospecting, Management and carrying on of Petroleum Boring Operations.
General Data—Customary Formulæ—Memento. Practical Part. General Data bearing on Petroleum—Glossary of Technical Terms used in the Petroleum Industry—Copious Index.

THE PRACTICAL COMPOUNDING OF OILS, TALLOW AND GREASE FOR LUBRICATION, ETC.

By AN EXPERT OIL REFINER. Second Edition. 100 pp. Demy 8vo. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

Introductory Remarks on the General Nomenclature of Oils, Tallow and Greases suitable for Lubrication—**Hydrocarbon Oils**—Animal and Fish Oils—**Compound Oils**—Vegetable Oils—**Lamp Oils**—Engine Tallow, Solidified Oils and Petroleum Jelly—**Machinery Greases**: Loco and Anti-friction—Clarifying and Utilisation of Waste Fats, Oils, Tank Bottoms, Drainings of Barrels and Drums, Pickings Up, Dregs, etc.—The Fixing and Cleaning of Oil Tanks, etc.—Appendix and General Information.

ANIMAL FATS AND OILS: Their Practical Production

Purification and Uses for a great Variety of Purposes. Their Properties, Falsification and Examination. Translated from the German of LOUIS EDGAR ANDÉS. Sixty-two Illustrations. 240 pp. Second Edition, Revised and Enlarged. Demy 8vo. Price 10s. 6d. net. (Post free, 10s. 10d. home; 11s. 3d. abroad.)

Contents.

Introduction—Occurrence, Origin, Properties and Chemical Constitution of Animal Fats—Preparation of Animal Fats and Oils—**Machinery**—Tallow-melting Plant—Extraction Plant—**Presses**—Filtering Apparatus—**Butter**: Raw Material and Preparation, Properties, Adulterations, Beef Lard or Remelted Butter, Testing—**Candle-fish Oil**—Mutton-Tallow—**Hare Fat**—Goose Fat—**Neatsfoot Oil**—**Bone Fat**: Bone Boiling, Steaming Bones, Extraction, Refining—**Bone Oil**—Artificial Butter: Oleomargarine, Margarine Manufacture in France, Grasso's Process, "Kaiser's Butter," Jahr & Münzberg's Method, Filbert's Process, Winter's Method—**Human Fat**—**Horse Fat**—**Beef Marrow**—**Turtle Oil**—**Hog's Lard**: Raw Material—Preparation, Properties, Adulterations, Examination—**Lard Oil**—**Fish Oils**—**Liver Oils**—**Artificial Train Oil**—**Wool Fat**: Properties, Purified Wool Fat—**Spermaceti**: Examination of Fats and Oils in General.

THE MANUFACTURE OF LUBRICANTS, SHOE POLISHES AND LEATHER DRESSINGS.

By RICHARD BRUNNER. Translated from the Sixth German Edition by CHAS. SALTER. 10 Illustrations. Crown 8vo. 170 pp. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

The Manufacture of Lubricants and Greases—Properties of the Bodies used as Lubricants—**Raw Materials for Lubricants**—Solid Lubricants—Tallow Lubricants—Palm Oil Greases—**Lead Soap Lubricants**—**True Soap Greases**—Caoutchouc Lubricants—**Other Solid Lubricants**—**Liquid Lubricants**—Lubricating Oils in General—Refining Oils for Lubricating Purposes—**Cohesion Oils**—**Resin Oils**—Lubricants of Fat and Resin Oil—**Neatsfoot Oil**—**Bone Fat**—Lubricants for Special Purposes—**Mineral Lubricating Oils**—**Clockmakers'** and **Sewing Machine Oils**—The Application of Lubricants to Machinery—**Removing Thickened Grease and Oil**—**Cleaning Oil Rags and Cotton Waste**—The Use of Lubricants—**Shoe Polishes** and **Leather Softening Preparations**—The Manufacture of Shoe Polishes and Preparations for Varnishing and Softening Leather—The Preparation of **Bone Black**—**Blackening and Shoe Polishes**—**Leather Varnishes**—**Leather Softening Preparations**—The Manufacture of **Dégres**.

THE OIL MERCHANTS' MANUAL AND OIL TRADE READY RECKONER. Compiled by FRANK F. SHERRIFF. Second Edition Revised and Enlarged. Demy 8vo. 214 pp. 1904. With Two Sheets of Tables. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. 3d. abroad.)

Contents.

Trade Terms and Customs—Tables to Ascertain Value of Oil sold per cwt. or ton—Specific Gravity Tables—Percentage Tare Tables—Petroleum Tables—Paraffine and Benzoline Calculations—Customary Drafts—Tables for Calculating Allowance for Dirt, Water, etc.—Capacity of Circular Tanks Tables, etc., etc.

VEGETABLE FATS AND OILS: Their Practical Preparation, Purification and Employment for Various Purposes, their Properties, Adulteration and Examination. Translated from the German of LOUIS EDGAR ANDÉS. Ninety-four Illustrations. 340 pp. Second Edition. Demy 8vo. Price 10s. 6d. net. (Post free, 11s. home; 11s. 6d. abroad.)

Essential Oils and Perfumes.

THE CHEMISTRY OF ESSENTIAL OILS AND ARTIFICIAL PERFUMES. By ERNEST J. PARRY, B.Sc. (Lond.), F.I.C., F.C.S. 411 pp. 20 Illustrations. Demy 8vo. Price 12s. 6d. net. (Post free, 13s. home; 13s. 6d. abroad.)

Contents.

The General Properties of Essential Oils—Compounds occurring in Essential Oils—The Preparation of Essential Oils—The Analysis of Essential Oils—Systematic Study of the Essential Oils—Terpeneless Oils—The Chemistry of Artificial Perfumes—Appendix: Table of Constants—Index.

Soaps.

SOAPS. A Practical Manual of the Manufacture of Domestic, Toilet and other Soaps. By GEORGE H. HURST, F.C.S. 2nd edition. 390 pp. 66 Illustrations. Price 12s. 6d. net. (Post free, 13s. home; 13s. 6d. abroad.)

Contents.

Introductory—Soap-maker's Alkalies—Soap Fats and Oils—Perfumes—Water as a Soap Material—Soap Machinery—Technology of Soap-making—Glycerine in Soap Lyes—Laying out a Soap Factory—Soap Analysis—Appendices.

TEXTILE SOAPS AND OILS. Handbook on the Preparation, Properties and Analysis of the Soaps and Oils used in Textile Manufacturing, Dyeing and Printing. By GEORGE H. HURST, F.C.S. Crown 8vo. 195 pp. 1904. Price 5s. net. (Post free, 5s. 4d. home; 5s. 6d. abroad.)

SOAPS: THEIR MANUFACTURE AND ANALYSIS. By WM. H. SIMMONS, B.Sc. (Lond.), F.C.S. and H. A. APPLETON.

[In Preparation.]

Contents.

Chapters I. Introduction.—Definition and Nature of Soap—Its Action as a Detergent—Views of Berzelius, Persoz, Rotondi, Carpenter, and Hillyer. **II. Constitution of Fats and Oils and their Saponification.**—Researches of Chevreul and Liebig—Modern Theories of Hydrolysis—Saponification by (1) *Ferments*: Lipase, Steapsin, Emulsion, Castor Seed Ferment; (2) *Water*; (3) *Accelerators*: Hydrochloric Acid, Sulphuric Acid, Twitchell's Reagent; (4) *Bases* (a) Without Pressure, (b) With Pressure, Lime, Magnesia, Zinc Oxide. **III. Raw Materials Used in Soap-making.**—Tallow—Australian, North and South American (Beef and Mutton), Oleostearine, Home-melted or Town Tallow—Lard—Cocoanut Oil (Cochin, Ceylon, Coprah, Pressed)—Palm Kernöl Oil—Olive Oil—Olive Kernöl—Cottonseed Oil—Cottonseed Stearin—Arachis—Sesame—Linseed—Castor—Waste Fats (a) Bone Fat, (b) Kitchen Fat (Melted Stuff)—Fatty Acids—Stearines from Recovered Oils and Greases—Rosin—Shew Butter—Mowrah Oil—Vegetable Tallow—Various New Fats Offered—Alkali (Caustic and Carbonate Soda and Potash)—Silicate of Soda—Chloride of Soda—Water. **IV. Bleaching and Treatment of Oils Intended for Soap-making.**—Bleaching Crude Palm Oil—Washing Tallows—Refining Crude Cottonseed Oil—Mechanical Methods of Purification—Treatment with Ozone, Hydrogen Peroxide, Sodium Peroxide, etc. **V. Soap-making.**—Classification of Soaps—Direct Combination of Fatty Acids with Alkali—Cold Process Soaps—Saponification under Pressure—Soft Soap—Hydrated Marine Soap—Curd

Soap—Castile Soap—Milling Soap Base—Yellow Household Soaps—Mottled Soaps—Graining Out—Boiling on Strength—"Fitting"—Resting for Subsidence of Nigres, Lyes, etc.—Utilisation and Bleaching of Nigres. **VI. Household and "Boiled" Toilet Soaps.**—Cleansing—Crutching—Liquoring of Soaps—Neutralising, Colouring and Perfuming Unmilled Toilet Soaps—Medicating Disinfectant Soaps—Framing—Slabbing and Barring—Drying—Open and Close Piling—Stamping. **VII. Milled Toilet Soaps.**—Drying—Milling—Incorporation of Colour and Perfume—Compressing, Stamping—Wrapping and Packing—Transparent and Semi-transparent Soaps—Albume Soaps—Milk, Egg and Vegetable Albumen. **VIII. Essential Oils and Synthetic Perfumes.**—General Remarks—Anisi—Aspic—Bay—Bergamot—Bitter Almonds—Canada Snake Root—Cananga—Caraway—Cassia—Cedarwood—Cinnamon—Citronella—Clove—Eucalyptus—Fennel—Geranium—Gingergrass—Guaiac Wood—Lavender—Lemon—Lime—Linalol—Marjoram—Nexoli—Orange—Orris Concrete—Palmarosa—Patchouli—Perpermint—Peru Balsam—Petitgrain—Pimento—Rose—Rosemary—Sage—Sandalwood—Sassafras—Thyme Rouge—Verbena—Vetivert—Wintergreen—Ylang-ylang—Antipine—Conmarine—Heliotropin—Ionone—Mirbane—Musk—Niobi—Terebene—Terpineol—Vanilla. **IX. Medicated Soaps and Shaving Creams.**—Addition of Medicaments—Borax—Carbolic—Birch Tar—Ichthyöl—Lysol—Mercury Liniodide—Formalin—Thymol, etc. **X. Industrial Soaps.**—Textile Soaps—Miscellaneous Soaps—Marking Soaps. **XI. Recovery of Glycerine from Lyes.**—Treatment—Concentration—Purification and Distillation. **XII. Analysis of Soap and Other Products.**—Methods of Analysis—Comparative Valuation of Soaps—Typical Analysis. **XIII. Statistics of Soap Industry.**—Imports and Exports.

Cosmetical Preparations.

COSMETICS: MANUFACTURE, EMPLOYMENT AND TESTING OF ALL COSMETIC MATERIALS AND COSMETIC SPECIALITIES. Translated from the German of Dr. THEODOR KOLLER. Crown 8vo. 262 pp. Price 5s. net. (Post free, 5s. 4d. home; 5s. 6d. abroad.)

Contents.

Purposes and Uses of, and Ingredients used in the Preparation of Cosmetics—Preparation of Perfumes by Pressure, Distillation, Maceration, Absorption or Enfleurance, and Extraction Methods—Chemical and Animal Products used in the Preparation of Cosmetics—Oils and Fats used in the Preparation of Cosmetics—General Cosmetic Preparations—Mouth Washes and Tooth Pastes—Hair Dyes, Hair Restorers and Depilatories—Cosmetic Adjuncts and Specialities—Colouring Cosmetic Preparations—Antiseptic Washes and Soaps—Toilet and Hygienic Soaps—Secret Preparations for Skin, Complexion, Teeth, Mouth, etc.—Testing and Examining the Materials Employed in the Manufacture of Cosmetics—Index.

Glue, Bone Products and Manures.

GLUE AND GLUE TESTING. By SAMUEL RIDEAL, D.Sc. (Lond.), F.I.C. Fourteen Engravings. 144 pp. Demy 8vo. Price 10s. 6d. net. (Post free, 10s. 10d. home; 11s. abroad.)

Contents.

Constitution and Properties: Definitions and Sources, Gelatine, Chondrin and Allied Bodies, Physical and Chemical Properties, Classification, Grades and Commercial Varieties—**Raw Materials and Manufacture:** Glue Stock, Lining, Extraction, Washing and Clarifying, Filter Presses, Water Supply, Use of Alkalies, Action of Bacteria and of Antiseptics, Various Processes, Cleansing, Forming, Drying, Crushing, etc., Secondary Products—**Uses of Glue:** Selection and Preparation for Use, Carpentry, Veneering, Paper-Making, Book-binding, Printing Rollers, Hectographs, Match Manufacture, Sandpaper, etc., Substitutes for other Materials, Artificial Leather and Caoutchouc—**Gelatine:** General Characters, Liquid Gelatine, Photographic Uses, Size, Tanno-, Chrome and Formo-Gelatine, Artificial Silk, Cements, Pneumatic Tyres, Culinary, Meat Extracts, Isinglass, Medicinal and other Uses, Bacteriology—**Glue Testing:** Review of Processes, Chemical Examination, Adulteration, Physical Tests, Valuation of Raw Materials—**Commercial Aspects.**

BONE PRODUCTS AND MANURES: An Account of the most recent Improvements in the Manufacture of Fat, Glue, Animal Charcoal, Size, Gelatine and Manures. By THOMAS LAMBERT, Technical and Consulting Chemist. Illustrated by Twenty-one Plans and Diagrams. 162 pp. Demy 8vo. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

Chemical Composition of Bones—Arrangement of Factory—Properties of Glue—Glutin and Chondrin—Skin Glue—Liming of Skins—Washing—Boiling of Skins—Clarification of Glue Liquors—Glue-Boiling and Clarifying—House—Specification of a Glue—Size—Uses and Pre-

paration and Composition of Size—Concentrated Size—Properties of Gelatine—Preparation of Skin Gelatine—Drying—Bone Gelatine—Selecting Bones—Crushing—Dissolving—Bleaching—Boiling—Properties of Glutin and Chondrin—Testing of Glues and Gelatines—The Uses of Glue, Gelatine and Size in Various Trades—Soluble and Liquid Glues—Steam and Waterproof Glues—**Manures**—Importation of Food Stuffs—Soils—Germination—Plant Life—**Natural Manures**—Water and Nitrogen in Farmyard Manure—Full Analysis of Farmyard Manure—Action on Crops—Water-Closet System—Sewage Manure—Green Manures—**Artificial Manures**—**Mineral Manures**—Nitrogenous Matters—Shoddy—Hoofs and Horns—Leather Waste—Dried Meat—Dried Blood—Superphosphates—Composition—Manufacture—Common Raw Bones—Degreased Bones—Crude Fat—Refined Fat—Degelatinised Bones—Animal Charcoal—Bone Superphosphates—Guanos—Dried Animal Products—Potash Compounds—Sulphate of Ammonia—Extraction *in Vacuo*—French and British Gelatines compared—Index.

Chemicals, Waste Products and Agricultural Chemistry.

REISSUE OF CHEMICAL ESSAYS OF C. W. SCHEELÉ. First Published in English in 1786. Translated from the Academy of Sciences at Stockholm, with Additions. 300 pp. Demy 8vo. Price 5s. net. (Post free, 5s. 6d. home; 5s. 9d. abroad.)

Contents.

Memoir: C. W. Scheele and his work (written for this edition by J. G. McIntosh)—On Fluor Mineral and its Acid—On Fluor Mineral—Chemical Investigation of Fluor Acid, with a View to the Earth which it Yields, by Mr. Wiegler—Additional Information Concerning Fluor Minerals—On Manganese, Magnesium, or Magnesia Vitriolium—On Arsenic and its Acid—Remarks upon Salts of Benzoïn—On Silice, Clay and Alum—Analysis of the Calculus Vesical—Method of Preparing *Mercurius Dulcis Via Humida*—Cheaper and more Convenient Method of Preparing *Pulvis Algarothi*—Experiments upon *Molybdæna*—Experiments on Plumbago—Method of Preparing a New Green Colour—Of the Decomposition of Neutral Salts by Unslaked Lime and Iron—On the Quantity of Pure Air which is Daily Present in our Atmosphere—On Milk and its Acid—On the Acid of *Saccharum Lactis*—On the Constituent Parts of *Lapis Ponderosus* or Tungsten—Experiments and Observations on Ether—Index.

THE MANUFACTURE OF ALUM AND THE SULPHATES AND OTHER SALTS OF ALUMINA AND IRON. Their Uses and Applications as Mordants in Dyeing and Calico Printing, and their other Applications in the Arts, Manufactures, Sanitary Engineering, Agriculture and Horticulture. Translated from the French of **LUCIEN GESCHWIND**. 195 Illustrations. 400 pp. Royal 8vo. Price 12s. 6d. net. (Post free, 13s. home; 13s. 6d. abroad.)

Contents.

Theoretical Study of Aluminium, Iron, and Compounds of these Metals—Aluminium and its Compounds—Iron and Iron Compounds.

Manufacture of Aluminium Sulphates and Sulphates of Iron—Manufacture of Aluminium Sulphate and the Alums—Manufacture of Sulphates of Iron.

Uses of the Sulphates of Aluminium and Iron—Uses of Aluminium Sulphate and Alums—Application to Wool and Silk—Preparing and using Aluminium Acetates—Employment of Aluminium Sulphate in Carbonising Wool—The Manufacture of Lake Pigments—Manufacture of Prussian Blue—Hide and Leather Industry—Paper Making—Hardening Plaster—Lime Washes—Preparation of Non-inflammable Wood, etc.—Purification of Waste Waters—Uses and Applications of Ferrous Sulphate and Ferric Sulphates—Dyeing—Manufacture of Pigments—Writing Inks—Purification of Lighting Gas—Agriculture—Cotton Dyeing—Disinfectant—Purifying Waste Liquors—Manufacture of Nordhausen Sulphuric Acid—Fertilising.

Chemical Characteristics of Iron and Aluminium—Analysis of Various Aluminous or Ferruginous Products—Aluminium—Analysing Aluminium Products—Alunite—Alumina—Sodium Aluminate—Aluminium Sulphate—Iron—Analytical Characteristics of Iron Salts—Analysis of Pyritic Lignite—Ferrous and Ferric Sulphates—Rouil Mordant—Index.

AMMONIA AND ITS COMPOUNDS: Their Manufacture and Uses. By **CAMILLE VINCENT**, Professor at the Central School of Arts and Manufactures, Paris. Translated from the French by **M. J. SALTER**. Royal 8vo. 114 pp. Thirty-two Illustrations. Price 5s. net. (Post free, 5s. 4d. home; 5s. 6d. abroad.)

Contents.

General Considerations: Various Sources of Ammoniacal Products; Human Urine as a Source of Ammonia—Extraction of Ammoniacal Products from Sewage—Extraction of Ammonia from Gas Liquor—Manufacture of Ammoniacal Compounds from Bones, Nitrogenous Waste, Beetroot Wash and Peat—Manufacture of Caustic Ammonia, and Ammonium Chloride, Phosphate and Carbonate—Recovery of Ammonia from the Ammonia-Soda Mother Liquors—Index.

INDUSTRIAL ALCOHOL. A Practical Manual on the Production and Use of Alcohol for Industrial Purposes and for Use as a Heating Agent, as an Illuminant and as a Source of Motive Power. By J. G. M'INTOSH, Lecturer on Manufacture and Applications of Industrial Alcohol at The Polytechnic, Regent Street, London. Demy 8vo. 1907. 250 pp. With 75 Illustrations and 25 Tables. Price 7s. 6d. net. (Post free, 7s. 9d. home; 8s. abroad.)

Contents.

Alcohol and its Properties.—Ethylic Alcohol—Absolute Alcohol—Adulterations—Properties of Alcohol—Fractional Distillation—Destructive Distillation—Products of Combustion—Alcoholometry—Proof Spirit—Analysis of Alcohol—Table showing Correspondence between the Specific Gravity and Per Cents. of Alcohol over and under Proof—Other Alcohol Tables. **Continuous Aseptic and Antiseptic Fermentation and Sterilisation in Industrial Alcohol Manufacture.** The Manufacture of Industrial Alcohol from Beets.—Beet Slicing Machines—Extraction of Beet Juice by Maceration, by Diffusion—Fermentation in Beet Distilleries—Plans of Modern Beet Distillery. **The Manufacture of Industrial Alcohol from Grain.**—Plan of Modern Grain Distillery. **The Manufacture of Industrial Alcohol from Potatoes.** The Manufacture of Industrial Alcohol from Surplus Stocks of Wine, Spoilt Wine, Wine Marcs, and from Fruit in General. The Manufacture of Alcohol from the Sugar Cane and Sugar Cane Molasses—Plans. **Plant, etc., for the Distillation and Rectification of Industrial Alcohol.**—The Caffey and other "Patent" Stills—Intermittent versus Continuous Rectification—Continuous Distillation—Rectification of Spent Wash. **The Manufacture and Uses of Various Alcohol Derivatives,** Ether, Haloid Ethers, Compound Ethers, Chloroform—Methyl and Amyl Alcohols and their Ethereal Salts, Acetone—Barbet's Ether, Methyl Alcohol and Acetone Rectifying Stills. **The Uses of Alcohol in Manufactures, etc.**—List of Industries in which Alcohol is used, with Key to Function of Alcohol in each Industry. **The Uses of Alcohol for Lighting, Heating, and Motive Power.**

ANALYSIS OF RESINS AND BALSAMS. Translated from the German of Dr. KARL DIETERICH. Demy 8vo. 340 pp. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. 3d. abroad.)

MANUAL OF AGRICULTURAL CHEMISTRY. By HERBERT INGLE, F.I.C., Lecturer on Agricultural Chemistry, the Yorkshire College; Lecturer in the Victoria University. Second Edition. 388 pp. 11 Illustrations. Demy 8vo. Price 7s. 6d. net. (Post free, 8s. home; 8s. 6d. abroad.)

Contents.

Introduction—The Atmosphere—The Soil—The Reactions occurring in Soils—The Analysis of Soils—Manures, Natural—Manures (continued)—The Analysis of Manures—The Constituents of Plants—The Plant—Crops—The Animal—Foods and Feeding—Milk and Milk Products—The Analysis of Milk and Milk Products—Miscellaneous Products used in Agriculture—Appendix—Index.

THE UTILISATION OF WASTE PRODUCTS. A Treatise on the Rational Utilisation, Recovery and Treatment of Waste Products of all kinds. By Dr. THEODOR KOLLER. Translated from the Second Revised German Edition. Twenty-two Illustrations. Demy 8vo. 280 pp. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. 3d. abroad.)

Contents.

The Waste of Towns—**Ammonia and Sal-Ammoniac**—Rational Processes for Obtaining these Substances by Treating Residues and Waste—Residues in the Manufacture of Aniline Dyes—Amber Waste—Brewers' Waste—Blood and Slaughter-House Refuse—Manufactured Fuels—Waste Paper and Bookbinders' Waste—Iron Slags—Excrement—Colouring Matters from Waste—Dyers' Waste Waters—Fat from Waste—Fish Waste—Calamine Sludge—Tannery Waste—Gold and Silver Waste—India-rubber and Caoutchouc Waste—Residues in the Manufacture of Rosin Oil—Wood Waste—Horn Waste—Infusorial Earth—Iridium from Goldsmiths' Sweepings—Jute Waste—Cork Waste—Leather Waste—Glue Makers' Waste—Illuminating Gas from Waste and the By-Products of the Manufacture of Coal Gas—Meerschum—Molasses—Metal Waste—By-Products in the Manufacture of Mineral Waters—Fruit—The By-Products of Paper and Paper Pulp Works—By-Products in the Treatment of Coal Tar Oils—Fur Waste—The Waste Matter in the Manufacture of Parchment Paper—Mother of Pearl Waste—Petroleum Residues—Platinum Residues—Broken Porcelain. Earthenware and Glass—Salt Waste—Slate Waste—Sulphur—Burnt Pyrites—Silk Waste—Soap Makers' Waste—Alkali Waste and the Recovery of Soda—Waste Produced in Grinding Mirrors—Waste Products in the Manufacture of Starch—Stearic Acid—Vegetable Ivory Waste—Turf—Waste Waters of Cloth Factories—Wine Residues—Tinplate Waste—Wool Waste—Wool Sweat—The Waste Liquids from Sugar Works—Index.

Writing Inks and Sealing Waxes.

INK MANUFACTURE : Including Writing, Copying, Lithographic, Marking, Stamping, and Laundry Inks. By SIGMUND LEHNER. Three Illustrations. Crown 8vo. 162 pp. Translated from the German of the Fifth Edition. Price 5s. net. (Post free, 5s. 3d. home ; 5s. 6d. abroad.)

Contents.

Varieties of Ink—Writing Inks—Raw Materials of Tannin Inks—The Chemical Constitution of the Tannin Inks—Recipes for Tannin Inks—Logwood Tannin Inks—Ferric Inks—Alizarine Inks—Extract Inks—Logwood Inks—Copying Inks—Hektographs—Hektograph Inks—Safety Inks—Ink Extracts and Powders—Preserving Inks—Changes in Ink and the Restoration of Faded Writing—Coloured Inks—Red Inks—Blue Inks—Violet Inks—Yellow Inks—Green Inks—Metallic Inks—Indian Ink—Lithographic Inks and Pencils—Ink Pencils—Marking Inks—Ink Specialities—Sympathetic Inks—Stamping Inks—Laundry or Washing Blue—Index

SEALING-WAXES, WAFERS AND OTHER ADHESIVES FOR THE HOUSEHOLD, OFFICE, WORKSHOP AND FACTORY. By H. C. STANDAGE. Crown 8vo. 96 pp. Price 5s. net. (Post free, 5s. 3d. home ; 5s. 4d. abroad.)

Contents.

Materials Used for Making Sealing-Waxes—The Manufacture of Sealing-Waxes—Wafers—Notes on the Nature of the Materials Used in Making Adhesive Compounds—Cements for Use in the Household—Office Gums, Pastes and Mucilages—Adhesive Compounds for Factory and Workshop Use.

Lead Ores and Compounds.

LEAD AND ITS COMPOUNDS. By THOS. LAMBERT, Technical and Consulting Chemist. Demy 8vo. 226 pp. Forty Illustrations. Price 7s. 6d. net. (Post free, 7s. 10d. home ; 8s. 3d. abroad.)

Contents.

History—Ores of Lead—Geographical Distribution of the Lead Industry—Chemical and Physical Properties of Lead—Alloys of Lead—Compounds of Lead—Dressing of Lead Ores—Smelting of Lead Ores—Smelting in the Scotch or American Ore-hearth—Smelting in the Shaft or Blast Furnace—Condensation of Lead Fume—Desilverisation, or the Separation of Silver from Argentiferous Lead—Cupellation—The Manufacture of Lead Pipes and Sheets—Protoxide of Lead—Litharge and Massicot—Red Lead or Minium—Lead Poisoning—Lead Substitutes—Zinc and its Compounds—Pumice Stone—Drying Oils and Siccatives—Oil of Turpentine Resin—Classification of Mineral Pigments—Analysis of Raw and Finished Products—Tables—Index.

NOTES ON LEAD ORES : Their Distribution and Properties. By JAS. FAIRIE, F.G.S. Crown 8vo. 64 pages. Price 2s. 6d. net. (Post free, 2s. 9d. home ; 3s. abroad.)

(*White Lead and Zinc White Paints, see p. 4.*)

Industrial Hygiene.

THE RISKS AND DANGERS TO HEALTH OF VARIOUS OCCUPATIONS AND THEIR PREVENTION. By LEONARD A. PARRY, M.D., B.Sc. (Lond.). 196 pp. Demy 8vo. Price 7s. 6d. net. (Post free, 7s. 10d. home ; 8s. abroad.)

Contents.

Occupations which are Accompanied by the Generation and Scattering of Abnormal Quantities of Dust—Trades in which there is Danger of Metallic Poisoning—Certain Chemical Trades—Some Miscellaneous Occupations—Trades in which Various Poisonous Vapours are Inhaled—General Hygienic Considerations—Index.

Industrial Uses of Air, Steam and Water.

DRYING BY MEANS OF AIR AND STEAM. Explanations, Formulæ, and Tables for Use in Practice. Translated from the German of E. HAUSBRAND. Two folding Diagrams and Thirteen Tables. Crown 8vo. 72 pp. Price 5s. net. (Post free, 5s. 3d. home; 5s. 6d. abroad.)

Contents.

British and Metric Systems Compared—Centigrade and Fahr. Thermometers—Estimation of the Maximum Weight of Saturated Aqueous Vapour which can be contained in 1 kilo. of Air at Different Pressure and Temperatures—Calculation of the Necessary Weight and Volume of Air, and of the Least Expenditure of Heat, per Drying Apparatus with Heated Air, at the Atmospheric Pressure: *A*, With the Assumption that the Air is *Completely Saturated* with Vapour both before Entry and after Exit from the Apparatus—*B*, When the Atmospheric Air is *Completely Saturated before entry*, but at its *exit* is only $\frac{3}{4}$, $\frac{1}{2}$ or $\frac{1}{4}$ Saturated—*C*, When the Atmospheric Air is *not* Saturated with Moisture before Entering the Drying Apparatus—Drying Apparatus, in which, in the Drying Chamber, a Pressure is Artificially Created, Higher or Lower than that of the Atmosphere—Drying by Means of Superheated Steam, without Air—Heating Surface, Velocity of the Air Current, Dimensions of the Drying Room, Surface of the Drying Material, Losses of Heat—Index.

(See also "*Evaporating, Condensing and Cooling Apparatus*," p. 26.)

PURE AIR, OZONE AND WATER. A Practical Treatise of their Utilisation and Value in Oil, Grease, Soap, Paint, Glue and other Industries. By W. B. COWELL. Twelve Illustrations. Crown 8vo. 85 pp. Price 5s. net. (Post free, 5s. 3d. home; 5s. 6d. abroad.)

Contents.

Atmospheric Air; Lifting of Liquids; Suction Process; Preparing Blown Oils; Preparing Siccative Drying Oils—Compressed Air; Whitewash—Liquid Air; Retrocession—Purification of Water; Water Hardness—Fleshings and Bones—Ozonised Air in the Bleaching and Deodorising of Fats, Glues, etc.; Bleaching Textile Fibres—Appendix: Air and Gases; Pressure of Air at Various Temperatures; Fuel; Table of Combustibles; Saving of Fuel by Heating Feed Water; Table of Solubilities of Scale Making Minerals; British Thermal Units Tables; Volume of the Flow of Steam into the Atmosphere; Temperature of Steam—Index.

THE INDUSTRIAL USES OF WATER. COMPOSITION—EFFECTS—TROUBLES—REMEDIES—RESIDUARY WATERS—PURIFICATION—ANALYSIS.

By H. DE LA COUX. Royal 8vo. Translated from the French and Revised by ARTHUR MORRIS. 364 pp. 135 Illustrations. Price 10s. 6d. net. (Post free, 11s. home; 11s. 6d. abroad.)

Contents.

Chemical Action of Water in Nature and in Industrial Use—Composition of Waters—Solubility of Certain Salts in Water Considered from the Industrial Point of View—Effects on the Boiling of Water—Effects of Water in the Industries—Difficulties with Water—Feed Water for Boilers—Water in Dyeworks, Print Works, and Bleach Works—Water in the Textile Industries and in Conditioning—Water in Soap Works—Water in Laundries and Washhouses—Water in Tanning—Water in Preparing Tannin and Dyewood Extracts—Water in Papermaking—Water in Photography—Water in Sugar Refining—Water in Making Ices and Beverages—Water in Cider Making—Water in Brewing—Water in Distilling—Preliminary Treatment and Apparatus—Substances Used for Preliminary Chemical Purification—Commercial Specialties and their Employment—Precipitation of Matters in Suspension in Water—Apparatus for the Preliminary Chemical Purification of Water—Industrial Filters—Industrial Sterilisation of Water—Residuary Waters and their Purification—Soil Filtration—Purification by Chemical Processes—Analyses—Index.

(See Books on Smoke Prevention, Engineering and Metallurgy, p. 26, etc.)

X Rays.

PRACTICAL X RAY WORK. By FRANK T. ADDYMAN, B.Sc. (Lond.), F.I.C., Member of the Roentgen Society of London; Radiographer to St. George's Hospital; Demonstrator of Physics and Chemistry, and Teacher of Radiography in St. George's Hospital Medical School. Demy 8vo. Twelve Plates from Photographs of X Ray Work. Fifty-two Illustrations. 200 pp. Price 10s. 6d. net. (Post free, 10s. 10d. home; 11s. 3d. abroad.)

Contents.

Historical—Work leading up to the Discovery of the X Rays—The Discovery—**Apparatus and its Management**—Electrical Terms—Sources of Electricity—Induction Coils—Electrostatic Machines—Tubes—Air Pumps—Tube Holders and Stereoscopic Apparatus—Fluorescent Screens—**Practical X Ray Work**—Installations—Radioscopy—Radiography—X Rays in Dentistry—X Rays in Chemistry—X Rays in War—Index.

List of Plates.

Frontispiece—Congenital Dislocation of Hip-Joint.—I., Needle in Finger.—II., Needle in Foot.—III., Revolver Bullet in Calf and Leg.—IV., A Method of Localisation.—V., Stellate Fracture of Patella showing shadow of "Strapping"—VI., Sarcoma.—VII., Six-weeks-old Injury to Elbow showing new Growth of Bone.—VIII., Old Fracture of Tibia and Fibula badly set.—IX., Heart Shadow.—X., Fractured Femur showing Grain of Splint.—XI., Barrell's Method of Localisation.

India-Rubber and Gutta Percha.

INDIA-RUBBER AND GUTTA PERCHA. Translated from the French of T. SEELIGMANN, G. LAMY TORVILHON and H. FALCONNET by JOHN GEDDES McINTOSH. Royal 8vo.

[Out of print. Second Edition in preparation.]

Contents.

India-Rubber—Botanical Origin—Climatology—Soil—Rational Culture and Acclimation of the Different Species of India-Rubber Plants—Methods of Obtaining the Latex—Methods of Preparing Raw or Crude India-Rubber—Classification of the Commercial Species of Raw Rubber—Physical and Chemical Properties of the Latex and of India-Rubber—Mechanical Transformation of Natural Caoutchouc into Washed or Normal Caoutchouc (Purification) and Normal Rubber into Masticated Rubber—Softening, Cutting, Washing, Drying—Preliminary Observations—Vulcanisation of Normal Rubber—Chemical and Physical Properties of Vulcanised Rubber—General Considerations—Hardened Rubber or Ebonite—Considerations on Mineralisation and other Mixtures—Coloration and Dyeing—Analysis of Natural or Normal Rubber and Vulcanised Rubber—Rubber Substitutes—Imitation Rubber.

Gutta Percha—Botanical Origin—Climatology—Soil—Rational Culture—Methods of Collection—Classification of the Different Species of Commercial Gutta Percha—Physical and Chemical Properties—Mechanical Transformation—Methods of Analysing—Gutta Percha Substitutes—Index.

Leather Trades.

PRACTICAL TREATISE ON THE LEATHER INDUSTRY. By A. M. VILLON. Translated by FRANK T. ADDYMAN, B.Sc. (Lond.), F.I.C., F.C.S.; and Corrected by an Eminent Member of the Trade. 500 pp., royal 8vo. 123 Illustrations. Price 21s. net. (Post free, 21s. 6d. home; 22s. 6d. abroad.)

Contents.

Preface—Translator's Preface—List of Illustrations.

Part I., Materials used in Tanning—Skins: Skin and its Structure; Skins used in Tanning; Various Skins and their Uses—Tannin and Tanning Substances: Tannin; Barks (Oak); Barks other than Oak; Tanning Woods; Tannin-bearing Leaves; Excrecences; Tan-bearing Fruits; Tan-bearing Roots and Bulbs; Tanning Juices; Tanning Substances used in Various Countries; Tannin Extracts; Estimation of Tannin and Tannin Principles.

Part II., Tanning—The Installation of a Tannery: Tan Furnaces; Chimneys, Boilers, etc.; Steam Engines—Grinding and Trituration of Tanning Substances: Cutting up Bark; Grinding Bark; The Grinding of Tan Woods; Powdering Fruit, Galls and Grains; Notes on the Grinding of Bark—Manufacture of Sole Leather: Soaking; Sweating and Unhairing; Plumping and Colouring; Handling; Tanning; Tanning Elephants' Hides; Drying; Striking or Pinning—Manufacture of Dressing Leather: Soaking; Depilation; New Processes for the Depilation of Skins; Tanning; Cow Hides; Horse Hides; Goat Skins; Manufacture of Split Hides—On Various Methods of Tanning: Mechanical Methods; Physical Methods; Chemical Methods; Tanning with Extracts—Quantity and Quality; Quantity; Net Cost; Quality of Leather—Various Manipulations of Tanned Leather: Second Tanning; Grease Stains; Bleaching Leather; Waterproofing Leather; Weighting Tanned Leather; Preservation of Leather—Tanning Various Skins.

Part III., **Currying**—Waxed Calf: Preparation; Shaving; Stretching or Slicking; Oiling the Grain; Oiling the Flesh Side; Whitening and Graining; Waxing; Finishing; Dry Finishing; Finishing in Colour; Cost—White Calf: Finishing in White—Cow Hide for Upper Leathers: Black Cow Hide; White Cow Hide; Coloured Cow Hide—Smooth Cow Hide—Black Leather—Miscellaneous Hides: Horse; Goat; Waxed Goat Skin; Matt Goat Skin—Russia Leather: Russia Leather; Artificial Russia Leather.

Part IV., **Enamelled, Hungary and Chamoy Leather, Morocco, Parchment, Furs and Artificial Leather**—Enamelled Leather: Varnish Manufacture; Application of the Enamel; Enamelling in Colour—Hungary Leather: Preliminary; Wet Work or Preparation; Aluming; Dressing or Loft Work; Tallowing; Hungary Leather from Various Hides—Tawing: Preparatory Operations; Dressing; Dyeing Tawed Skins; Rugs—Chamoy Leather—Morocco: Preliminary Operations, Morocco Tanning; Mordants used in Morocco Manufacture; Natural Colours used in Morocco Dyeing; Artificial Colours; Different Methods of Dyeing; Dyeing with Natural Colours; Dyeing with Aniline Colours; Dyeing with Metallic Salts; Leather Printing; Finishing Morocco; Shagreen; Bronzed Leather—Gilding and Silvering; Gilding; Silvering; Nickel and Cobalt—Parchment—Furs and Furriery: Preliminary Remarks; Indigenous Furs; Foreign Furs from Hot Countries; Foreign Furs from Cold Countries; Furs from Birds' Skins; Preparation of Furs; Dressing; Colouring; Preparation of Birds' Skins; Preservation of Furs—Artificial Leather: Leather made from Scraps; Compressed Leather; American Cloth; Papier Mâché; Linoleum; Artificial Leather.

Part V., **Leather Testing and the Theory of Tanning**—Testing and Analysis of Leather: Physical Testing of Tanned Leather; Chemical Analysis—The Theory of Tanning and the other Operations of the Leather and Skin Industry: Theory of Soaking; Theory of Unhairing; Theory of Swelling; Theory of Handling; Theory of Tanning; Theory of the Action of Tannin on the Skin; Theory of Hungary Leather Making; Theory of Tawing; Theory of Chamoy Leather Making; Theory of Mineral Tanning.

Part VI., **Uses of Leather**—Machine Belts: Manufacture of Belting; Leather Chain Belts; Various Belts; Use of Belts—Boot and Shoe-making: Boots and Shoes; Laces—Saddlery: Composition of a Saddle; Construction of a Saddle—Harness: The Pack Saddle; Harness—Military Equipment—Glove Making—Carriage Building—Mechanical Uses.

Appendix, **The World's Commerce in Leather**—Europe; America; Asia; Africa: Australasia—Index.

THE LEATHER WORKER'S MANUAL. Being a Compendium of Practical Recipes and Working Formulæ for Curriers, Bootmakers, Leather Dressers, Blacking Manufacturers, Saddlers, Fancy Leather Workers. By H. C. STANDAGE. Demy 8vo. 165 pp. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

Blackings, Polishes, Glosses, Dressings, Renovators, etc., for Boot and Shoe Leather—Harness Blackings, Dressings, Greases, Compositions, Soaps, and Boot-top Powders and Liquids, etc., etc.—Leather Grinders' Sundries—Currier's Seasonings, Blacking Compounds, Dressings, Finishes, Glosses, etc.—Dyes and Stains for Leather—Miscellaneous Information—Chrome Tannage—Index.

Books on Pottery, Bricks, Tiles, Glass, etc.

THE MANUAL OF PRACTICAL POTTING. Compiled by Experts, and Edited by CHAS. F. BINNS. Third Edition, Revised and Enlarged. 200 pp. Demy 8vo. Price 17s. 6d. net. (Post free, 17s. 10d. home; 18s. 3d. abroad.)

Contents.

Introduction. The Rise and Progress of the Potter's Art—**Bodies.** China and Porcelain Bodies, Parian Bodies, Semi-porcelain and Vitreous Bodies, Mortar Bodies, Earthenwares Granite and C.C. Bodies, Miscellaneous Bodies, Sagger and Crucible Clays, Coloured Bodies, Jasper Bodies, Coloured Bodies for Mosaic Painting, Encaustic Tile Bodies, Body Stains, Coloured Dips—**Glazes.** China Glazes, Ironstone Glazes, Earthenware Glazes, Glazes without Lead, Miscellaneous Glazes, Coloured Glazes, Majolica Colours—**Gold and Gold Colours.** Gold, Purple of Cassius, Marone and Ruby, Enamel Coloured Bases, Enamel Colour Fluxes, Enamel Colours, Mixed Enamel Colours, Antique and Vellum Enamel Colours, Underglaze Colours, Underglaze Colour Fluxes, Mixed Underglaze Colours, Flow Powders, Oils and Varnishes—**Means and Methods.** Reclamation of Waste Gold, The Use of Cobalt, Notes on Enamel Colours, Liquid or Bright Gold—**Classification and Analysis.** Classification of Clay Ware, Lord Playfair's Analysis of Clays, The Markets of the World, Time and Scale of Firing, Weights of Potter's Material, Decorated Goods Count—Comparative Loss of Weight of Clays—Ground Felspar Calculations—The Conversion of Slop Body Recipes into Dry Weight—The Cost of Prepared Earthenware Clay—**Forms and Tables.** Articles of Apprenticeship, Manufacturer's Guide to Stocktaking, Table of Relative Values of Potter's Materials, Hourly Wages Table, Workman's Settling Table, Comparative Guide for Earthenware and China Manufacturers in the use of Slop Flint and Slop Stone, Foreign Terms applied to Earthenware and China Goods, Table for the Conversion of Metrical Weights and Measures on the Continent and South America—**Index.**

CERAMIC TECHNOLOGY: Being some Aspects of Technical Science as Applied to Pottery Manufacture. Edited by CHARLES F. BINNS. 100 pp. Demy 8vo. Price 12s. 6d. net. (Post free, 12s. 10d. home; 13s. abroad.)

Contents.

Preface—The Chemistry of Pottery—Analysis and Synthesis—Clays and their Components—The Biscuit Oven—Pyrometry—Glazes and their Composition—Colours and Colour-making—Index.

A TREATISE ON THE CERAMIC INDUSTRIES. A Complete Manual for Pottery, Tile and Brick Works. By EMILE BOURRY. Translated from the French by WILTON P. RIX, Examiner in Pottery and Porcelain to the City and Guilds of London Technical Institute, Pottery Instructor to the Hanley School Board. Royal 8vo. 760 pp. 323 Illustrations. Price 21s. net. (Post free, 22s. home; 24s. abroad.)

Contents.

Part I., General Pottery Methods. Definition and History. Definitions and Classification of Ceramic Products—Historic Summary of the Ceramic Art—Raw Materials of Bodies. Clays: Pure Clay and Natural Clays—Various Raw Materials: Analogous to Clay—Agglomerative and Agglutinative—Opening—Fusible—Refractory—Trials of Raw Materials—Plastic Bodies. Properties and Composition—Preparation of Raw Materials: Disaggregation—Purification—Preparation of Bodies: By Plastic Method—By Dry Method—By Liquid Method—Formation. Processes of Formation: Throwing—Expression—Moulding by Hand on the Jolley, by Compression, by Slip Casting—Slapping—Slipping—Drying. Drying of Bodies—Processes of Drying: By Evaporation—By Aeration—By Heating—By Ventilation—By Absorption—Glazes. Composition and Properties—Raw Materials—Manufacture and Application—Firing. Properties of the Bodies and Glazes during Firing—Description of the Kilns—Working of the Kilns—Decoration. Colouring Materials—Processes of Decoration.

Part II., Special Pottery Methods. Terra Cottas. Classification: Plain Ordinary, Hollow, Ornamental, Vitrified, and Light Bricks—Ordinary and Black Tiles—Paving Tiles—Pipes—Architectural Terra Cottas—Vases, Statues and Decorative Objects—Common Pottery—Pottery for Water and Filters—Tobacco Pipes—Lustre Ware—Properties and Tests for Terra Cottas—Fireclay Goods. Classification: Argillaceous, Aluminous, Carboniferous, Silicious and Basic Fireclay Goods—Fireclay Mortar (Pug)—Tests for Fireclay Goods—Faïences. Varnished Faïences—Enamelled Faïences—Silicious Faïences—Pipeclay Faïences—Pebble Work—Feldspathic Faïences—Composition, Processes of Manufacture and General Arrangements of Faïence Potteries—Stoneware. Stoneware Properly So-called: Paving Tiles—Pipes—Sanitary Ware—Stoneware for Food Purposes and Chemical Productions—Architectural Stoneware—Vases, Statues and other Decorative Objects—Fine Stoneware—Porcelain. Hard Porcelain for Table Ware and Decoration, for the Fire, for Electrical Conduits, for Mechanical Purposes; Architectural Porcelain, and Dull or Biscuit Porcelain—Soft Phosphated or English Porcelain—Soft Vitreous Porcelain, French and New Sévres—Argillaceous Soft or Seger's Porcelain—Dull Soft or Parian Porcelain—Dull Feldspathic Soft Porcelain—Index.

POTTERY DECORATING. A Description of all the Processes for Decorating Pottery and Porcelain. By R. HAINBACH. Translated from the German. Crown 8vo. 250 pp. Twenty-two Illustrations. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

Glazes and Engobes.—Glazes and Their Composition—Glaze Materials—The Preparation of Glazes—Coloured Glazes—Engobes and Glazes for same—Porcelain Glazes. **Ceramic Colours.**—Preparation of Pure Colours—Underglaze Colours—Applying the Colours on Earthenware—Glost Fire Colours—Muffle Colours—Decorating Porcelain with Metals—Decorating Porcelain by Electroplating—Lustre Decorating on Porcelain—Firing Muffle Colours—Imitation of Paintings on Porcelain—Index.

ARCHITECTURAL POTTERY. Bricks, Tiles, Pipes, Enamelled Terra-cottas, Ordinary and Incrusted Quarries, Stoneware Mosaics, Faïences and Architectural Stoneware. By LEON LEFÈVRE. Translated from the French by K. H. BIRD, M.A., and W. MOORE BINNS. With Five Plates. 950 Illustrations in the Text, and numerous estimates. 500 pp., royal 8vo. Price 15s. net. (Post free, 15s. 6d. home; 16s. 6d. abroad.)

Contents.

Part I. Plain Undecorated Pottery.—Clays, Bricks, Tiles, Pipes, Chimney Flues, Terra-cotta.

Part II. Made-up or Decorated Pottery.

THE ART OF RIVETING GLASS, CHINA AND EARTHENWARE. By J. HOWARTH. Second Edition. Paper Cover. Price 1s. net. (By post, home or abroad, 1s. 1d.)

NOTES ON POTTERY CLAYS. The Distribution, Properties, Uses and Analyses of Ball Clays, China Clays and China Stone. By JAS. FAIRIE, F.G.S. 132 pp. Crown 8vo. Price 3s. 6d. net. (Post free, 3s. 9d. home; 3s. 10d. abroad.)

A Reissue of

THE HISTORY OF THE STAFFORDSHIRE POTTERIES; AND THE RISE AND PROGRESS OF THE MANUFACTURE OF POTTERY AND PORCELAIN.

With References to Genuine Specimens, and Notices of Eminent Potters. By SIMEON SHAW. (Originally Published in 1829.) 265 pp. Demy 8vo. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. 3d. abroad.)

Contents.

Introductory Chapter showing the position of the Pottery Trade at the present time (1899)—**Preliminary Remarks**—**The Potteries**, comprising Tunstall, Brownhills, Greenfield and New Field, Golden Hill, Latebrook, Green Lane, Burslem, Longport and Dale Hall, Hot Lane and Cobridge, Hanley and Shelton, Etruria, Stoke, Penkhull, Fenton, Lane Delph, Foley, Lane End—**On the Origin of the Art**, and its Practice among the early Nations—**Manufacture of Pottery**, prior to 1700—**The Introduction of Red Porcelain** by Messrs. Elers, of Bradwell, 1690—**Progress of the Manufacture** from 1700 to Mr. Wedgwood's commencement in 1760—**Introduction of Fluid Glaze**—Extension of the Manufacture of Cream Colour—Mr. Wedgwood's Queen's Ware—Jasper, and Appointment of Potter to Her Majesty—Black Printing—**Introduction of Porcelain**. Mr. W. Littler's Porcelain—Mr. Cookworthy's Discovery of Kaolin and Petuntse, and Patent—Sold to Mr. Champion—re-sold to the New Hall Com.—Extension of Term—**Blue Printed Pottery**. Mr. Turner, Mr. Spode (1), Mr. Baddeley, Mr. Spode (2), Messrs. Turner, Mr. Wood, Mr. Wilson, Mr. Minton—Great Change in Patterns of Blue Printed—**Introduction of Lustre Pottery**. Improvements in Pottery and Porcelain subsequent to 1800.

A Reissue of

THE CHEMISTRY OF THE SEVERAL NATURAL AND ARTIFICIAL HETEROGENEOUS COMPOUNDS USED IN MANUFACTURING PORCELAIN, GLASS AND POTTERY. By SIMEON SHAW. (Originally published in 1837.) 750 pp. Royal 8vo. Price 14s. net. (Post free, 15s. home; 17s. abroad.)

Glassware, Glass Staining and Painting.

RECIPES FOR FLINT GLASS MAKING. By a British Glass Master and Mixer. Sixty Recipes. Being Leaves from the Mixing Book of several experts in the Flint Glass Trade, containing up-to-date recipes and valuable information as to Crystal, Demi-crystal and Coloured Glass in its many varieties. It contains the recipes for cheap metal suited to pressing, blowing, etc., as well as the most costly crystal and ruby. Second Edition. Crown 8vo. Price 10s. 6d. net. (Post free, 10s. 9d. home; 10s. 10d. abroad.)

Contents.

Ruby—Ruby from Copper—Flint for using with the Ruby for Coating—A German Metal—ornelian, or Alabaster—Sapphire Blue—Crysophis—Opal—Turquoise Blue—Gold Colour—Dark Green—Green (common)—Green for Malachite—Blue for Malachite—Black for Melachite—Black—Common Canary Batch—Canary—White Opaque Glass—Sealing-wax Red—Flint—Flint Glass (Crystal and Demi)—Achromatic Glass—Paste Glass—White Enamel—Firestone—Dead White (for moons)—White Agate—Canary—Canary Enamel—Index.

A TREATISE ON THE ART OF GLASS PAINTING.

Prefaced with a Review of Ancient Glass. By ERNEST R. SUFFLING. With One Coloured Plate and Thirty-seven Illustrations. Demy 8vo. 140 pp. Price 7s. 6d. net. (Post free, 7s. 10d. home ; 8s. abroad.)

Contents.

A Short History of Stained Glass—Designing Scale Drawings—Cartoons and the Cut Line—Various Kinds of Glass Cutting for Windows—The Colours and Brushes used in Glass Painting—Painting on Glass, Dispersed Patterns—Diapered Patterns—Aciding—Firing—Fret Lead Glazing—Index.

PAINTING ON GLASS AND PORCELAIN AND ENAMEL PAINTING.

A Complete Introduction to the Preparation of all the Colours and Fluxes used for Painting on Porcelain, Enamel, Faience and Stoneware, the Coloured Pastes and Coloured Glasses, together with a Minute Description of the Firing of Colours and Enamels. By FELIX HERMANN, Technical Chemist. With Eighteen Illustrations. 300 pp. Translated from the German second and enlarged Edition. Price 10s. 6d. net. (Post free, 10s. 10d. home ; 11s. abroad.)

Paper Making, Paper Dyeing, and Testing.

THE DYEING OF PAPER PULP. A Practical Treatise for the use of Papermakers, Paperstainers, Students and others. By JULIUS ERFURT, Manager of a Paper Mill. Translated into English and Edited with Additions by JULIUS HÜBNER, F.C.S., Lecturer on Papermaking at the Manchester Municipal Technical School. With Illustrations and **157 patterns of paper dyed in the pulp.** Royal 8vo, 180 pp. Price 15s. net. (Post free, 15s. 6d. home ; 16s. 6d. abroad.)

Contents.

Behaviour of the Paper Fibres during the Process of Dyeing, Theory of the Mordant—Colour Fixing Mediums (Mordants)—Influence of the Quality of the Water Used—Inorganic Colours—Organic Colours—Practical Application of the Coal Tar Colours according to their Properties and their Behaviour towards the Different Paper Fibres—Dyed Patterns on Various Pulp Mixtures—Dyeing to Shade—Index.

THE PAPER MILL CHEMIST. By HENRY P. STEVENS, M.A., Ph.D., F.I.C. Royal 12mo. 60 Illustrations. 300 pp. Price 7s. 6d. net. (Post free, 7s. 9d. home ; 7s. 10d. abroad.)

Contents.

Introduction.—Dealing with the Apparatus required in Chemical Work and General Chemical Manipulation, introducing the subject of Qualitative and Quantitative Analysis. **Fuels.**—Analysis of Coal, Coke and other Fuels—Sampling and Testing for Moisture, Ash, Calorific Value, etc.—Comparative Heating Value of different Fuels and Relative Efficiency. **Water.**—Analysis for Steam Raising and for Paper Making Purposes generally—Water Softening and Purification—A List of the more important Water Softening Plant, giving Power required, Weight, Space Occupied, Out-put and Approximate Cost. **Raw Materials and Detection of Adulterants.**—Analysis and Valuation of the more important Chemicals used in Paper Making, including Lime, Caustic Soda, Sodium Carbonate, Mineral Acids, Bleach Antichlor, Alum, Rosin and Rosin Size, Glue Gelatin and Casein, Starch, China Clay, Blanc Fixe, Satin White and other Loading Materials, Mineral Colours and Aniline Dyes. **Manufacturing Operations.**—Rags and the Chemical Control of Rag Boiling—Esparto Boiling—Wood Boiling—Testing Spent Liquors and Recovered Ash—Experimental Tests with Raw Fibrous Materials—Boiling in Autoclaves—Bleaching and making up Hand Sheets—Examination of Sulphite Liquors—Estimation of Moisture in Pulp and Half-stuff—Recommendations of the British Wood Pulp Association. **Finished Products.**—Paper Testing, including Physical, Chemical and Microscopical Tests, Area, Weight, Thickness, Apparent Specific Gravity, Bulk or Air Space. Determination of Machine Direction, Thickness, Strength, Stretch, Resistance to Crumpling and Friction, Transparency, Absorbency and other qualities of Blotting Papers—Determination of the Permeability of Filtering Papers—Detection and Estimation of Animal and Vegetable Size in Paper—Sizing Qualities of Paper—Fibrous Constituents—Microscopical Examination of Fibres—The Effect of Beating on Fibres—Staining Fibres—Mineral Matter—Ash—Qualitative and Quantitative Examination of Mineral Matter—Examination of Coated Papers and Colouring Matters in Paper.

CONTENTS OF "THE PAPER MILL CHEMIST"—*contd.*

Tables.—English and Metrical Weights and Measures with Equivalents—Conversion of Grams to Grains and *vice versa*—Equivalent Costs per lb., cwt., and ton—Decimal Equivalents of lbs., qrs., and cwt.s.—Thermometric and Barometric Scales—Atomic Weights and Molecular Weights—Factors for Calculating the Percentage of Substance Sought from the Weight of Substance Found—Table of Solubilities of Substances Treated of in Paper Making—Specific Gravity Tables of such substances as are used in Paper Making, including Sulphuric Acid, Hydrochloric Acid, Bleach, Milk of Lime, Caustic Soda, Carbonate of Soda, etc., giving Percentage Strength with Specific Gravity and Degrees Tw.—Hardness Table for Soap Tests—Dew Point—Wet and Dry Bulb Tables—Properties of Saturated Steam, giving Temperature, Pressure and Volume—List of Different Machines used in the Paper Making Industry, giving Size, Weight, Space Occupied, Power to Drive, Out-put and Approximate Cost—Calculation of Moisture in Pulp—Rag-Boiling Tables, giving Percentages of Lime, Soda and Time required—Loss in Weight in Rags and other Raw Materials during Boiling and Bleaching—Conditions of Buying and Selling as laid down by the Paper Makers' Association—Table of Names and Sizes of Papers—Table for ascertaining the Weight per Ream from the Weight per Sheet—Calculations of Areas and Volumes—Logarithms—Blank pages for Notes.

THE TREATMENT OF PAPER FOR SPECIAL PURPOSES. By L. E. ANDÉS. Translated from the German. Crown 8vo. 48 Illustrations. 250 pp. Price 6s. net. (Post free, 6s. 4d. home; 6s. 6d. abroad).

Contents.

I., **Parchment Paper, Vegetable Parchment.**—The Parchment Paper Machine—Opaque Supple Parchment Paper—Thick Parchment—Krugler's Parchment Paper and Parchment Slates—Double and Triple Osmotic Parchment—Utilising Waste Parchment Paper—Parchmented Linen and Cotton—Parchment Millboard—Imitation Horn and Ivory from Parchment Paper—Imitation Parchment Paper—Artificial Parchment—Testing the Sulphuric Acid. II., **Papers for Transfer Pictures.** III., **Papers for Preservative and Packing Purposes.**—Butter Paper—Wax Paper—Paraffin Paper—Wrapping Paper for Silverware—Waterproof Paper—Anticorrosive Paper. IV., **Grained Transfer Papers.** V., **Fireproof and Antifalsification Papers.** VI., **Paper Articles.**—Vulcanised Paper Maché—Paper Bottles—Plastic Articles of Paper—Waterproof Coverings for Walls and Ceilings—Paper Wheels, Roofing and Boats—Paper Barrels—Paper Boxes—Paper Horseshoes. VII., **Gummed Paper.** VIII., **Hectograph Papers.** IX., **Insecticide Papers.**—Fly Papers—Moth Papers. X., **Chalk and Leather Papers.**—Glacé Chalk Paper—Leather Paper—Imitation Leather. XI., **Luminous Papers—Blue-Print Papers—Blotting Papers.** XII., **Metal Papers—Medicated Papers.** XIII., **Marbled Papers.** XIV., **Tracing and Copying Papers—Iridescent or Mother of Pearl Papers.** XV., **Photographic Papers—Shellac Paper—Fumigating Papers—Test Papers.** XVI., **Papers for Cleaning and Polishing Purposes—Glass Paper—Pumic Paper—Emery Paper.** XVII., **Lithographic Transfer Papers.** XIX., **Sundry Special Papers—Satin Paper—Enamel Paper—Cork Paper—Split Paper—Electric Paper—Paper Matches—Magic Pictures—Laundry Blue Papers—Blue Paper for Bleachers.** XX., **Waterproof Papers—Washable Drawing Papers—Washable Card—Washable Coloured Paper—Waterproof Millboard—Sugar Paper.** XXI., **The Characteristics of Paper—Paper Testing.**

Enamelling on Metal.

ENAMELS AND ENAMELLING. For Enamel Makers, Workers in Gold and Silver, and Manufacturers of Objects of Art. By PAUL RANDAU. Translated from the German. With Sixteen Illustrations. Demy 8vo. 180 pp. Price 10s. 6d. net. (Post free, 10s. 10d. home; 11s. abroad.)

THE ART OF ENAMELLING ON METAL. By W. NORMAN BROWN. Twenty-eight Illustrations. Crown 8vo. 60 pp. Price 2s. 6d. net. (Post free, 2s. 9d. home and abroad.)

Silk Manufacture.

SILK THROWING AND WASTE SILK SPINNING. By HOLLINS RAYNER. Demy 8vo. 170 pp. 117 Illus. Price 5s. net. (Post free, 5s. 4d. home; 5s. 6d. abroad.)

Contents.

The Silkworm—Cocoon Reeling and Qualities of Silk—Silk Throwing—Silk Wastes—The Preparation of Silk Waste for Degumming—Silk Waste Degumming, Schapping and Discharging—The Opening and Dressing of Wastes—Silk Waste "Drawing" or "Preparing" Machinery—Long Spinning—Short Spinning—Spinning and Finishing Processes—Utilisation of Waste Products—Noil Spinning—Exhaust Noil Spinning.

Books on Textile and Dyeing Subjects.

THE CHEMICAL TECHNOLOGY OF TEXTILE FIBRES: Their Origin, Structure, Preparation, Washing, Bleaching, Dyeing, Printing and Dressing. By Dr. GEORG VON GEORGIEVICS. Translated from the German by CHARLES SALTER. 320 pp. Forty-seven Illustrations. Royal 8vo. Price 10s. 6d. net. (Post free, 11s. home; 11s. 3d. abroad.)

Contents.

The Textile Fibres—Washing, Bleaching, Carbonising—Mordants and Mordanting—Dyeing—Printing—Dressing and Finishing.

POWER-LOOM WEAVING AND YARN NUMBERING, According to Various Systems, with Conversion Tables. Translated from the German of ANTHON GRUNER. **With Twenty-six Diagrams in Colours.** 150 pp. Crown 8vo. Price 7s. 6d. net. (Post free, 7s. 9d. home; 8s. abroad.)

Contents.

Power-Loom Weaving in General. Various Systems of Looms—Mounting and Starting the Power-Loom. English Looms—Tappet or Treadle Looms—Dobbies—General Remarks on the Numbering, Reeling and Packing of Yarn—Appendix—Useful Hints. Calculating Warps—Weft Calculations—Calculations of Cost Price in Hanks.

TEXTILE RAW MATERIALS AND THEIR CONVERSION INTO YARNS. (The Study of the Raw Materials and the Technology of the Spinning Process.) By JULIUS ZIPSER. Translated from German by CHARLES SALTER. 302 Illustrations. 500 pp. Demy 8vo. Price 10s. 6d. net. (Post free, 11s. home; 11s. 6d. abroad.)

Contents.

PART I.—The Raw Materials Used in the Textile Industry.

MINERAL RAW MATERIALS. VEGETABLE RAW MATERIALS. ANIMAL RAW MATERIALS.

PART II.—The Technology of Spinning or the Conversion of Textile Raw Materials into Yarn.

SPINNING VEGETABLE RAW MATERIALS. Cotton Spinning—Installation of a Cotton Mill—Spinning Waste Cotton and Waste Cotton Yarns—Flax Spinning—Fine Spinning—Tow Spinning—Hemp Spinning—Spinning Hemp Tow String—Jute Spinning—Spinning Jute Line Yarn—Utilising Jute Waste.

PART III.—Spinning Animal Raw Materials.

Spinning Carded Woollen Yarn—Finishing Yarn—Worsted Spinning—Finishing Worsted Yarn—Artificial Wool or Shoddy Spinning—Shoddy and Mungo Manufacture—Spinning Shoddy and other Wool Substitutes—Spinning Waste Silk—Chappe Silk—Fine Spinning—Index.

GRAMMAR OF TEXTILE DESIGN. By H. NISBET, Weaving and Designing Master, Bolton Municipal Technical School. Demy 8vo. 280 pp. 490 Illustrations and Diagrams. Price 6s. net. (Post free, 6s. 4d. home; 6s. 6d. abroad.)

Contents.

Chapter I., INTRODUCTION.—General Principle of Fabric Structure and the use of Design Paper.

Chapter II., THE PLAIN WEAVE AND ITS MODIFICATIONS.—The Plain, Calico, or Tabby Weave.—Firmness of Texture—Variety of Texture—Variety of Form: Ribbed Fabrics—Corded Fabrics—Matt Weaves.

Chapter III., TWILL AND KINDRED WEAVES.—Classification of Twill Weaves.—1. Continuous Twills—(a) Warp-face Twills—(b) Weft-face Twills—(c) Warp and Weft-face Twills—The Angle of Twill—Influences affecting the Prominence of Twills and Kindred Weaves (a) Character of Weave, (b) Character of Yarn, (c) Number of Threads per Inch, (d) Direction of Twill in Relation to the Direction of Twist in Yarn.—2. Zigzag or Wavy Twills.—3. Rearranged Twills: Satin Weaves—Table of Intervals of Selection for the Construction of Satin Weaves—Corkscrew Twills—Rearrangement of Twill Weaves on Satin and other Bases.—4. Combined Twills.—5. Broken Twills.—6. Figured or Ornamented Twills.

Chapter IV., DIAMOND AND KINDRED WEAVES.—Diamond Weaves.—Honeycomb and Kindred Weaves—Brighton Weaves—Sponge Weaves—Huck-a-Back and Kindred Weaves—Greecian Weaves—Linear Zigzag Weaves.

Chapter V., BEDFORD CORDS.—Plain Calico-ribbed Bedford Cords—Plain Twill-ribbed Bedford Cords—Figured Bedford Cords—Tabulated Data of Particulars relating to the Manufacture of Seventeen Varieties of Bedford Cord Fabrics described in this Chapter.

[Continued on next page.]

CONTENTS OF "GRAMMAR OF TEXTILE DESIGN"— *continued.*

Chapter VI., **BACKED FABRICS.**—Weft-backed Fabrics—Warp-backed Fabrics—Reversible or Double-faced Fabrics.

Chapter VII., **FUSTIANS.**—Varieties of Fustians.—Imperials or Swansdowns—Cantoons or Diagonals—Moleskins—Beaverteens—Velveteens and Velveteen Cutting—Ribbed or Corded Velveteen—Figured Velveteen—**Corduroy**—Figured Corduroy—Corduroy Cutting Machines.

Chapter VIII., **TERRY PILE FABRICS.**—Methods of producing Terry Pile on Textile Fabrics—Terry-forming Devices—Varieties of Terry Fabrics—Action of the Reed in Relation to Shedding—Figured Terry Weaving—Practical Details of Terry Weaving.

Chapter IX., **GAUZE AND LENO FABRICS.**—Gauze, Net Leno, and Leno Brocade Varieties of Cross-Weaving.—Plain Gauze, and a Heald Gauze or Leno Harness—Net Leno Fabrics—Gauze and Net Leno Figuring by means of several Back Standard Healds to each Doup Heald—**Leno Specialities produced by a System of Crossing Warp Ends in front of the Reed**—A Device for the Production of Special Leno Effects—Full Cross Leno Fabrics—Relative Merits of a Top and a Bottom Doup Harness—Relative Merits of Different Types of Dobbies for Gauze and Leno Fabrics—Shaking Devices for Leno Weaving—Practical Details of Leno Weaving—**Tempered Steel-wire Doup Harnesses for Cross-weaving**—Mock or Imitation Leno Fabrics.

Chapter X., **TISSUE, LAPPET, AND SWIVEL FIGURING; ALSO ONDULÉ EFFECTS, AND LOOPED FABRICS.**—Tissue Figuring—Madras Muslin Curtains—**Lappet Figuring**—Spot Lappet Figuring—**Swivel Figuring**—Woven Ondulé Effects—Loom for Weaving Ondulé Effects—Weft Ondulé Effects—**Looped Fabrics.**—INDEX.

ART NEEDLEWORK AND DESIGN. POINT LACE. A

Manual of Applied Art for Secondary Schools and Continuation Classes.

By M. E. WILKINSON. Oblong quarto. With 22 Plates. Bound in Art Linen. Price 3s. 6d. net. (Post free, 3s. 10d. home; 4s. abroad.)

Contents.

Sampler of Lace Stitches—Directions for working Point Lace, tracing Patterns, etc.—List of Materials and Implements required for working. Plates I., Simple Lines, Straight and Slanting, and Designs formed from them. II., Patterns formed from Lines in previous Lesson. III., Patterns formed from Lines in previous Lesson. IV., Simple Curves, and Designs formed from them. V., Simple Leaf form, and Designs formed from it. VI., Elementary Geometrical forms, with Definitions. VII., Exercises on previous Lessons. VIII., Filling of a Square, Oblong and Circle with Lace Stitches. IX., Design for Tie End, based on simple Leaf form. X., Lace Butterflies (Freehand). XI., Twenty simple Designs evolved from Honiton Braid Leaf. XII., Design for Lace Handkerchief, based on previous Lesson. XIII., Design for Tea-cosy. XIV., Freehand Lace Collar. XV., Freehand Lace Cuff (to match). XVI., Application of Spray from Lesson XI. XVII., Adaptation of Curves within a Square, for Lace Cushion Centre. XVIII., Conventional Spray for corner of Tea-cloth. XIX., Geometrical form for Rosebowl D'Oyley, to be originally filled in. XX., Geometrical form for Flower-vase D'Oyley, to be originally filled in. Each Lesson contains Instructions for Working, and application of new Stitches from Sampler.

HOME LACE-MAKING. A Handbook for Teachers and

Pupils. By M. E. W. MILROY. Crown 8vo. 64 pp. With 3 Plates and 9 Diagrams. Price 1s. net. (Post free, 1s. 3d. home; 1s. 4d. abroad.)

THE CHEMISTRY OF HAT MANUFACTURING. Lec-

tures delivered before the Hat Manufacturers' Association. By WATSON SMITH, F.C.S., F.I.C. Revised and Edited by ALBERT SHONK. Crown 8vo. 132 pp. 16 Illustrations. Price 7s. 6d. net. (Post free, 7s. 9d. home; 7s. 10d. abroad.)

THE TECHNICAL TESTING OF YARNS AND TEXTILE FABRICS. With Reference to Official Specifica-

tions. Translated from the German of Dr. J. HERZFELD. Second Edition. Sixty-nine Illustrations. 200 pp. Demy 8vo. Price 10s. 6d. net. (Post free, 10s. 10d. home; 11s. abroad.)

DECORATIVE AND FANCY TEXTILE FABRICS.

By R. T. LORD. For Manufacturers and Designers of Carpets, Damask, Dress and all Textile Fabrics. 200 pp. Demy 8vo. 132 Designs and Illustrations. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

THEORY AND PRACTICE OF DAMASK WEAVING.

By H. KINZER and K. WALTER. Royal 8vo. Eighteen Folding Plates. Six Illustrations. Translated from the German. 110 pp. Price 8s. 6d. net. (Post free, 9s. home; 9s. 6d. abroad.)

TEXTILE BOOKS—*continued.***Contents.**

The Various Sorts of Damask Fabrics—Drill (Ticking, Handloom-made)—Whole Damask for Tablecloths—Damask with Ground- and Connecting-warp Threads—Furniture Damask—Lampas or Hangings—Church Damasks—**The Manufacture of Whole Damask**—Damask Arrangement with and without Cross-Shedding—The Altered Cone-arrangement—The Principle of the Corner Lifting Cord—The Roller Principle—The Combination of the Jacquard with the so-called Damask Machine—The Special Damask Machine—The Combination of Two Tyings.

FAULTS IN THE MANUFACTURE OF WOOLLEN GOODS AND THEIR PREVENTION. By NICOLAS

REISER. Translated from the Second German Edition. Crown 8vo. Sixty-three Illustrations. 170 pp. Price 5s. net. (Post free, 5s. 4d. home; 5s. 6d. abroad.)

Contents.

Improperly Chosen Raw Material or Improper Mixtures—Wrong Treatment of the Material in Washing, Carbonisation, Drying, Dyeing and Spinning—Improper Spacing of the Goods in the Loom—Wrong Placing of Colours—Wrong Weight or Width of the Goods—Breaking of Warp and Weft Threads—Presence of Doubles, Singles, Thick, Loose, and too Hard Twisted Threads as well as Tangles, Thick Knots and the Like—Errors in Cross-weaving—Inequalities, *i.e.*, Bands and Stripes—Dirty Borders—Defective Selvages—Holes and Buttons—Rubbled Places—Creases—Spots—Loose and Bad Colours—Badly Dyed Selvages—Hard Goods—Brittle Goods—Uneven Goods—Removal of Bands, Stripes, Creases and Spots.

SPINNING AND WEAVING CALCULATIONS, especially relating to Woollens. From the German of N. REISER. Thirty-four Illustrations. Tables. 160 pp. Demy 8vo. 1904. Price 10s. 6d. net. (Post free, 10s. 10d. home; 11s. abroad.)**Contents.**

Calculating the Raw Material—Proportion of Different Grades of Wool to Furnish a Mixture at a Given Price—Quantity to Produce a Given Length—Yarn Calculations—Yarn Number—Working Calculations—Calculating the Reed Count—Cost of Weaving, etc.

WATERPROOFING OF FABRICS. By Dr. S. MIERZINSKI.

Crown 8vo. 104 pp. 29 Illus. Price 5s. net. (Post free, 5s. 3d. home; 5s. 4d. abroad.)

Contents.

Introduction—Preliminary Treatment of the Fabric—Waterproofing with Acetate of Alumina—Impregnation of the Fabric—Drying—Waterproofing with Paraffin—Waterproofing with Ammonium Cuprate—Waterproofing with Metallic Oxides—Coloured Waterproof Fabrics—Waterproofing with Gelatine, Tannin, Caseinate of Lime and other Bodies—Manufacture of Tarpaulin—British Waterproofing Patents—Index.

HOW TO MAKE A WOOLLEN MILL PAY. By JOHN

MACKIE. Crown 8vo. 76 pp. Price 3s. 6d. net. (Post free, 3s. 9d. home; 3s. 10d. abroad.)

Contents.

Blends, Piles, or Mixtures of Clean Scoured Wools—Dyed Wool Book—The Order Book—Pattern Duplicate Books—Management and Oversight—Constant Inspection of Mill Departments—Importance of Delivering Goods to Time, Shade, Strength, etc.—Plums.

(For "Textile Soaps and Oils" see p. 7.)

Dyeing, Colour Printing, Matching and Dye-stuffs.**THE COLOUR PRINTING OF CARPET YARNS.** Manual

for Colour Chemists and Textile Printers. By DAVID PATERSON, F.C.S. Seventeen Illustrations. 136 pp. Demy 8vo. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

Structure and Constitution of Wool Fibre—Yarn Scouring—Scouring Materials—Water for Scouring—Bleaching Carpet Yarns—Colour Making for Yarn Printing—Colour Printing Pastes—Colour Recipes for Yarn Printing—Science of Colour Mixing—Matching of Colours—"Hank" Printing—Printing Tapestry Carpet Yarns—Yarn Printing—Steaming Printed Yarns—Washing of Steamed Yarns—Aniline Colours Suitable for Yarn Printing—Glossary of Dyes and Dye-wares used in Wool Yarn Printing—Appendix.

THE SCIENCE OF COLOUR MIXING. A Manual intended for the use of Dyers, Calico Printers and Colour Chemists. By DAVID PATERSON, F.C.S. Forty-one Illustrations, **Five Coloured Plates, and Four Plates showing Eleven Dyed Specimens of Fabrics.** 132 pp. Demy 8vo. Price 7s. 6d. net. (Post free, 7s. 10d. home ; 8s. abroad.)

Contents.

Colour a Sensation; Colours of Illuminated Bodies; Colours of Opaque and Transparent Bodies; Surface Colour—Analysis of Light; Spectrum; Homogeneous Colours; Ready Method of Obtaining a Spectrum—Examination of Solar Spectrum; The Spectroscope and Its Construction; Colourists' Use of the Spectroscope—Colour by Absorption; Solutions and Dyed Fabrics; Dichroic Coloured Fabrics in Gaslight—Colour Primaries of the Scientist *versus* the Dyer and Artist; Colour Mixing by Rotation and Lye Dyeing; Hue, Purity, Brightness; Tints; Shades, Scales, Tones, Sad and Sombre Colours—Colour Mixing; Pure and Impure Greens, Orange and Violets; Large Variety of Shades from few Colours; Consideration of the Practical Primaries: Red, Yellow and Blue—Secondary Colours; Nomenclature of Violet and Purple Group; Tints and Shades of Violet; Changes in Artificial Light—Tertiary Shades; Broken Hues; Absorption Spectra of Tertiary Shades—Appendix: Four Plates with Dyed Specimens Illustrating Text—Index.

DYERS' MATERIALS: An Introduction to the Examination, Evaluation and Application of the most important Substances used in Dyeing, Printing, Bleaching and Finishing. By PAUL HEERMAN, Ph.D. Translated from the German by A. C. WRIGHT, M.A. (Oxon.), B.Sc. (Lond.). Twenty-four Illustrations. Crown 8vo. 150 pp. Price 5s. net. (Post free, 5s. 4d. home ; 5s. 6d. abroad.)

COLOUR MATCHING ON TEXTILES. A Manual intended for the use of Students of Colour Chemistry, Dyeing and Textile Printing. By DAVID PATERSON, F.C.S. Coloured Frontispiece. Twenty-nine Illustrations and **Fourteen Specimens of Dyed Fabrics.** Demy 8vo. 132 pp. Price 7s. 6d. net. (Post free, 7s. 10d. home ; 8s. abroad.)

Contents.

Colour Vision and Structure of the Eye—Perception of Colour—Primary and Complementary Colour Sensations—Daylight for Colour Matching—Selection of a Good Pure Light—Diffused Daylight, Direct Sunlight, Blue Skylight, Variability of Daylight, etc., etc.—Matching of Hues—Purity and Luminosity of Colours—Matching Bright Hues—Aid of Tinted Films—Matching Difficulties Arising from Contrast—Examination of Colours by Reflected and Transmitted Lights—Effect of Lustre and Transparency of Fibres in Colour Matching—Matching of Colours on Velvet Pile—Optical Properties of Dye-stuffs, Dichroism, Fluorescence—Use of Tinted Mediums—Orange Film—Defects of the Eye—Yellowing of the Lens—Colour Blindness, etc.—Matching of Dyed Silk Trimmings and Linings and Bindings—Its Difficulties—Behaviour of Shades in Artificial Light—Colour Matching of Old Fabrics, etc.—Examination of Dyed Colours under the Artificial Lights—Electric Arc, Magnesium and Dufton, Gardner Lights, Welsbach, Acetylene, etc.—Testing Qualities of an Illuminant—Influence of the Absorption Spectrum in Changes of Hue under the Artificial Lights—Study of the Causes of Abnormal Modifications of Hue, etc.

COLOUR: A HANDBOOK OF THE THEORY OF COLOUR. By GEORGE H. HURST, F.C.S. **With Ten Coloured Plates** and Seventy-two Illustrations. 160 pp. Demy 8vo. Price 7s. 6d. net. (Post free, 7s. 10d. home ; 8s. abroad.)

Contents.

Colour and Its Production—Cause of Colour in Coloured Bodies—Colour Phenomena and Theories—The Physiology of Light—Contrast—Colour in Decoration and Design—Measurement of Colour.

Reissue of

THE ART OF DYEING WOOL, SILK AND COTTON.

Translated from the French of M. HELLOT, M. MACQUER and M. LE PILEUR D'APLIGNY. First Published in English in 1789. Six Plates. Demy 8vo. 446 pp. Price 5s. net. (Post free, 5s. 6d. home ; 6s. abroad.)

Contents.

Part I., The Art of Dyeing Wool and Woollen Cloth, Stuffs, Yarn, Worsted, etc. Part II., The Art of Dyeing Silk. Part III., The Art of Dyeing Cotton and Linen Thread, together with the Method of Stamping Silks, Cottons, etc.

THE CHEMISTRY OF DYE-STUFFS. By Dr. GEORG VON GEORGIEVICS. Translated from the Second German Edition. 412 pp. Demy 8vo. Price 10s. 6d. net. (Post free, 11s. home; 11s. 6d. abroad.)

Contents.

Introduction—Coal Tar—Intermediate Products in the Manufacture of Dye-stuffs—The Artificial Dye-stuffs (Coal-tar Dyes)—Nitroso Dye-stuffs—Nitro Dye-stuffs—Azo Dye-stuffs—Substantive Cotton Dye-stuffs—Azoxystilbene Dye-stuffs—Hydrazones—Ketoneimides—Triphenylmethane Dye-stuffs—Rosolic Acid Dye-stuffs—Xanthene Dye-stuffs—Xanthone Dye-stuffs—Flavones—Oxyketone Dye-stuffs—Quinoline and Acridine Dye-stuffs—Quinonimide or Diphenylamine Dye-stuffs—The Azine Group: Eurhodines, Safranines and Indulines—Eurhodines—Safranines—Quinoxalines—Indigo—Dye-stuffs of Unknown Constitution—Sulphur or Sulphine Dye-stuffs—Development of the Artificial Dye-stuff Industry—The Natural Dye-stuffs—Mineral Colours—Index.

THE DYEING OF COTTON FABRICS: A Practical Handbook for the Dyer and Student. By FRANKLIN BEECH, Practical Colourist and Chemist. 272 pp. Forty-four Illustrations of Bleaching and Dyeing Machinery. Demy 8vo. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

Structure and Chemistry of the Cotton Fibre—Scouring and Bleaching of Cotton—Dyeing Machinery and Dyeing Manipulations—Principles and Practice of Cotton Dyeing—Direct Dyeing; Direct Dyeing followed by Fixation with Metallic Salts; Direct Dyeing followed by Fixation with Developers; Direct Dyeing followed by Fixation with Couplers; Dyeing on Tannic Mordant; Dyeing on Metallic Mordant; Production of Colour Direct upon Cotton Fibres; Dyeing Cotton by Impregnation with Dye-stuff Solution—Dyeing Union (Mixed Cotton and Wool) Fabrics—Dyeing Half Silk (Cotton-Silk, Satin) Fabrics—Operations following Dyeing—Washing, Soaping, Drying—Testing of the Colour of Dyed Fabrics—Experimental Dyeing and Comparative Dye Testing—Index.

The book contains numerous recipes for the production on Cotton Fabrics of all kinds of a great range of colours.

THE DYEING OF WOOLLEN FABRICS. By FRANKLIN BEECH, Practical Colourist and Chemist. Thirty-three Illustrations. Demy 8vo. 228 pp. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

The Wool Fibre—Structure, Composition and Properties—Processes Preparatory to Dyeing—Scouring and Bleaching of Wool—Dyeing Machinery and Dyeing Manipulations—Loose Wool Dyeing, Yarn Dyeing and Piece Dyeing Machinery—The Principles and Practice of Wool Dyeing—Properties of Wool Dyeing—Methods of Wool Dyeing—Groups of Dyes—Dyeing with the Direct Dyes—Dyeing with Basic Dyes—Dyeing with Acid Dyes—Dyeing with Mordant Dyes—Level Dyeing—Blacks on Wool—Reds on Wool—Mordanting of Wool—Orange Shades on Wool—Yellow Shades on Wool—Green Shades on Wool—Blue Shades on Wool—Violet Shades on Wool—Brown Shades on Wool—Mode Colours on Wool—Dyeing Union (Mixed Cotton Wool) Fabrics—Dyeing of Gloria—Operations following Dyeing—Washing, Soaping, Drying—Experimental Dyeing and Comparative Dye Testing—Testing of the Colour of Dyed Fabrics—Index.

Bleaching and Washing.

A PRACTICAL TREATISE ON THE BLEACHING OF LINEN AND COTTON YARN AND FABRICS. By L. TAILFER, Chemical and Mechanical Engineer. Translated from the French by JOHN GEDDES McINTOSH. Demy 8vo. 303 pp. Twenty Illus. Price 12s. 6d. net. (Post free, 13s. home; 13s. 6d. abroad.)

Cotton Spinning and Combing.

COTTON SPINNING (First Year). By THOMAS THORNLEY, Spinning Master, Bolton Technical School. 160 pp. Eighty-four Illustrations. Crown 8vo. Second Impression. Price 3s. net. (Post free, 3s. 4d. home; 3s. 6d. abroad.)

Contents.

Syllabus and Examination Papers of the City and Guilds of London Institute—Cultivation, Classification, Ginning, Baling and Mixing of the Raw Cotton—Bale-Breakers, Mixing Lattices and Hopper Feeders—Opening and Scutching—Carding—Indexes.

COTTON SPINNING (Intermediate, or Second Year). By THOMAS THORNLEY. Second Impression. 180 pp. Seventy Illustrations. Crown 8vo. Price 5s. net. (Post free, 5s. 4d. home ; 5s. 6d. abroad.)

Contents.

Syllabuses and Examination Papers of the City and Guilds of London Institute—The Combing Process—The Drawing Frame—Bobbin and Fly Frames—Mule Spinning—Ring Spinning—General Indexes.

COTTON SPINNING (Honours, or Third Year). By THOMAS THORNLEY. 216 pp. Seventy-four Illustrations. Crown 8vo. Second Edition. Price 5s. net. (Post free, 5s. 4d. home ; 5s. 6d. abroad.)

Contents.

Syllabuses and Examination Papers of the City and Guilds of London Institute—Cotton—The Practical Manipulation of Cotton Spinning Machinery—Doubling and Winding—Reeling—Warping—Production and Costs—Main Driving—Arrangement of Machinery and Mill Planning—Waste and Waste Spinning—Indexes.

COTTON COMBING MACHINES. By THOS. THORNLEY, Spinning Master, Technical School, Bolton. Demy 8vo. 117 Illustrations. 300 pp. Price 7s. 6d. net. (Post free, 8s. home ; 8s. 6d. abroad.)

Contents.

The Sliver Lap Machine and the Ribbon Cap Machine—General Description of the Heilmann Comber—The Cam Shaft—On the Detaching and Attaching Mechanism of the Comber—Resetting of Combers—The Erection of a Heilmann Comber—Stop Motions: Various Calculations—Various Notes and Discussions—Cotton Combing Machines of Continental Make—Index.

Flax, Hemp and Jute Spinning.

MODERN FLAX, HEMP AND JUTE SPINNING AND TWISTING. A Practical Handbook for the use of Flax, Hemp and Jute Spinners, Thread, Twine and Rope Makers. By HERBERT R. CARTER, Mill Manager, Textile Expert and Engineer, Examiner in Flax Spinning to the City and Guilds of London Institute. Demy 8vo. 1907. With 92 Illustrations. 200 pp. Price 7s. 6d. net. (Post free, 7s. 9d. home ; 8s. abroad.)

Contents.

Raw Fibre.—Origin of Flax—Hemp and Jute Fibre—Description of the Plants—Mode of Cultivation—Suitable Climate and Soil—Sowing—Harvesting—Rippling Flax and Hemp—Water Retting—Dew Retting—Extraction of the Fibre—Marketing the Fibre—Bracquing—Flax, Hemp and Jute Marks—Comparative Prices—Ports of Export—Trade Centres—Fibre Selling Conditions—Duty on Fibre—Fibre Exports. **Hackling.**—Sorting and Storing the Raw Fibre—Softening Hemp and Jute—Jute Batching—Cutting—Piecing Out—Roughing—Hackling by Hand and Machine—Tippling—Sorting—Ventilation of Hackling Rooms. **Sliver Formation.**—Spreading Line—Heavy Spreading System—Good's Combined Hackle and Spreader—Jute Breaking and Carding—Flax and Hemp Tow Carding—Bell Calculation—Clock System—Theory of Spreading. **Line and Tow Preparing.**—Drawing and Doubling—Draft Calculation—Set Calculation—Tow Combing—Compound Systems—Automatic Stop Motions and Independent Heads—Details of Preparing Machinery—Ventilation—Humidification. **Gill Spinning.**—Gill Spinning for Shoe Threads, Rope Yarns, Binder and Trawl Twines—The Automatic Gill Spinner—Rope and Reaper Yarn Numbering. **The Flax, Hemp and Jute Roving Frame.**—Bobbin Winding—Differential Motion—Twist Calculation—Practical Changing—Rove Stock. **Dry and Half-Dry Spinning.**—Flyer and Ring Frames—Draft and Twist Calculation—Bobbin Dragging—Reaches—Set of Breast Beam and Tin-rod. **Wet Spinning** of Flax, Hemp and Tow—Hot and Cold Water Spinning—Improvements in the Water Trough—Turn off and Speed of Spindles—Reaches—Belting—Band Tying—Tape Driving—Oiling—Black Threads—Cuts per Spindle—Ventilation of the Wet Spinning Room. **Yarn Department.**—Reeling—Cop Winding—Cheese and Spool Winding—Balling Shoe Thread, Reaper Yarn, etc.—Yarn Drying and Conditioning—Yarn Bundling—Yarn Baling—Weight of Yarn—Yarn Tables—Duty on Yarn Imports. **Manufacture of Threads, Twines and Cords.**—Hank Winding—Wet and Dry Twisting—Cabling—Fancy Yarns—Twine Laying—Sizing and Polishing Threads and Twines—Softening Threads—Skeining Threads—Balling Twines—Leeson's Universal Winder—Randing Twines—Spooling Sewing Threads—Comparative Prices of Flax and Hemp Cords, Lines and Threads. **Rope Making.**—Construction of Hawfers and Cables—Stranding—Laying and Closing—Compound Rope Machines—Rules for Rope Makers—Weight of Ropes—Balling and Coiling Ropes. **Mechanical Department.**—Boilers, Engines and Turbines—Power Transmission by Belts and Ropes—Electric Light and Power Transmission—Fans—Oils and Oiling—Repairs—Plating. **Mill Construction.**—Flax, Hemp and Jute Spinning Mills and Ropeworks—Heating—Roofs—Chimneys, etc.

Collieries and Mines.

RECOVERY WORK AFTER PIT FIRES. By ROBERT LAMPRECHT, Mining Engineer and Manager. Translated from the German. Illustrated by Six large Plates, containing Seventy-six Illustrations. 175 pp., demy 8vo. Price 10s. 6d. net. (Post free, 10s. 10d. home; 11s. abroad.)

Contents.

Causes of Pit Fires—Preventive Regulations: (1) The Outbreak and Rapid Extension of a Shaft Fire can be most reliably prevented by Employing little or no Combustible Material in the Construction of the Shaft; (2) Precautions for Rapidly Localising an Outbreak of Fire in the Shaft; (3) Precautions to be Adopted in case those under 1 and 2 Fail or Prove Inefficient. Precautions against Spontaneous Ignition of Coal. Precautions for Preventing Explosions of Fire-damp and Coal Dust. Employment of Electricity in Mining, particularly in Fiery Pits. Experiments on the Ignition of Fire-damp Mixtures and Clouds of Coal Dust by Electricity—**Indications of an Existing or Incipient Fire—Appliances for Working in Irrespirable Gases:** Respiratory Apparatus; Apparatus with Air Supply Pipes; Reservoir Apparatus; Oxygen Apparatus—**Extinguishing Pit Fires:** (a) Chemical Means; (b) Extinction with Water. Dragging down the Burning Masses and Packing with Clay; (c) Insulating the Seat of the Fire by Dams. Dam Building. Analyses of Fire Gases. Isolating the Seat of a Fire with Dams; Working in Irrespirable Gases ("Gas-diving"); Air-Lock Work. Complete Isolation of the Pit. Flooding a Burning Section isolated by means of Dams. Wooden Dams; Masonry Dams. Examples of Cylindrical and Dome-shaped Dams. Dam Doors: Flooding the Whole Pit—**Rescue Stations:** (a) Stations above Ground; (b) Underground Rescue Stations—**Spontaneous Ignition of Coal in Bulk—Index.**

VENTILATION IN MINES. By ROBERT WABNER, Mining Engineer. Translated from the German. Royal 8vo. Thirty Plates and Twenty-two Illustrations. 240 pp. Price 10s. 6d. net. (Post free, 11s. home; 11s. 3d. abroad.)

Contents.

The Causes of the Contamination of Pit Air—The Means of Preventing the Dangers resulting from the Contamination of Pit Air—Calculating the Volume of Ventilating Current necessary to free Pit Air from Contamination—Determination of the Resistance Opposed to the Passage of Air through the Pit—Laws of Resistance and Formulae therefor—Fluctuations in the Temperament or Specific Resistance of a Pit—Means for Providing a Ventilating Current in the Pit—Mechanical Ventilation—Ventilators and Fans—Determining the Theoretical, Initial, and True (Effective) Depression of the Centrifugal Fan—New Types of Centrifugal Fan of Small Diameter and High Working Speed—Utilising the Ventilating Current to the utmost Advantage and distributing the same through the Workings—Artificially retarding the Ventilating Current—Ventilating Preliminary Workings—Blind Headings—Separate Ventilation—Supervision of Ventilation—INDEX.

HAULAGE AND WINDING APPLIANCES USED IN MINES. By CARL VOLK. Translated from the German. Royal 8vo. With Six Plates and 148 Illustrations. 150 pp. Price 8s. 6d. net. (Post free, 9s. home; 9s. 3d. abroad.)

Contents.

Haulage Appliances—Ropes—Haulage Tubs and Tracks—Cages and Winding Appliances—Winding Engines for Vertical Shafts—Winding without Ropes—Haulage in Levels and Inclines—The Working of Underground Engines—Machinery for Downhill Haulage.

Dental Metallurgy.

DENTAL METALLURGY: MANUAL FOR STUDENTS AND DENTISTS. By A. B. GRIFFITHS, Ph.D. Demy 8vo. Thirty-six Illustrations. 200 pp. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

Introduction—Physical Properties of the Metals—Action of Certain Agents on Metals—Alloys—Action of Oral Bacteria on Alloys—Theory and Varieties of Blowpipes—Fluxes—Furnaces and Appliances—Heat and Temperature—Gold—Mercury—Silver—Iron—Copper—Zinc—Magnesium—Cadmium—Tin—Lead—Aluminium—Antimony—Bismuth—Palladium—Platinum—Iridium—Nickel—Practical Work—Weights and Measures.

Engineering, Smoke Prevention and Metallurgy.

THE PREVENTION OF SMOKE. Combined with the Economical Combustion of Fuel. By W. C. POPPLEWELL, M.Sc., A.M.Inst., C.E., Consulting Engineer. Forty-six Illustrations. 190 pp. Demy 8vo. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. 3d. abroad.)

Contents.

Fuel and Combustion—Hand Firing in Boiler Furnaces—Stoking by Mechanical Means—Powdered Fuel—Gaseous Fuel—Efficiency and Smoke Tests of Boilers—Some Standard Smoke Trials—The Legal Aspect of the Smoke Question—The Best Means to be adopted for the Prevention of Smoke—Index.

GAS AND COAL DUST FIRING. A Critical Review of the Various Appliances Patented in Germany for this purpose since 1885. By ALBERT PÜTSCH. 130 pp. Demy 8vo. Translated from the German. With 103 Illustrations. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

Generators—Generators Employing Steam—Stirring and Feed Regulating Appliances—Direct Generators—Burners—Regenerators and Recuperators—Glass Smelting Furnaces—Metallurgical Furnaces—Pottery Furnace—Coal Dust Firing—Index.

THE HARDENING AND TEMPERING OF STEEL IN THEORY AND PRACTICE. By FRIDOLIN REISER. Translated from the German of the Third Edition. Crown 8vo. 120 pp. Price 5s. net. (Post free, 5s. 3d. home; 5s. 4d. abroad.)

Contents.

Steel—Chemical and Physical Properties of Steel, and their Casual Connection—Classification of Steel according to Use—Testing the Quality of Steel—Steel-Hardening—Investigation of the Causes of Failure in Hardening—Regeneration of Steel Spoilt in the Furnace—Welding Steel—Index.

SIDEROLGY: THE SCIENCE OF IRON (The Constitution of Iron Alloys and Slags). Translated from German of HANN S FREIHERR V. JÜPTNER. 350 pp. Demy 8vo. Eleven Plates and Ten Illustrations. Price 10s. 6d. net. (Post free, 11s. home; 11s. 6d. abroad.)

Contents.

The Theory of Solution.—Solutions—Molten Alloys—Varieties of Solutions—Osmotic Pressure—Relation between Osmotic Pressure and other Properties of Solutions—Osmotic Pressure and Molecular Weight of the Dissolved Substance—Solutions of Gases—Solid Solutions—Solubility—Diffusion—Electrical Conductivity—Constitution of Electrolytes and Metals—Thermal Expansion. **Micrography.**—Microstructure—The Micrographic Constituents of Iron—Relation between Micrographical Composition, Carbon-Content, and Thermal Treatment of Iron Alloys—The Microstructure of Slags. **Chemical Composition of the Alloys of Iron.**—Constituents of Iron Alloys—Carbon—Constituents of the Iron Alloys, Carbon—Opinions and Researches on Combined Carbon—Opinions and Researches on Combined Carbon—Applying the Curves of Solution deduced from the Curves of Recalescence to the Determination of the Chemical Composition of the Carbon present in Iron Alloys—The Constituents of Iron—Iron—The Constituents of Iron Alloys—Manganese—Remaining Constituents of Iron Alloys—A Silicon—Gases. **The Chemical Composition of Slag.**—Silicate Slags—Calculating the Composition of Silicate Slags—Phosphate Slags—Oxide Slags—Appendix—Index.

EVAPORATING, CONDENSING AND COOLING APPARATUS. Explanations, Formulæ and Tables for Use in Practice. By E. HAUSBRAND, Engineer. Translated by A. C. WRIGHT, M.A. (Oxon.), B.Sc. (Lond.). With Twenty-one Illustrations and Seventy-six Tables. 400 pp. Demy 8vo. Price 10s. 6d. net. (Post free, 11s. home; 11s. 6d. abroad.)

Contents.

R Coefficient of Transmission of Heat, k , and the Mean Temperature Difference, θ_m —Parallel and Opposite Currents—Apparatus for Heating with Direct Fire—The Injection of Saturated Steam—Superheated Steam—Evaporation by Means of Hot Liquids—The Transference of Heat in General, and Transference by means of Saturated Steam in Particular—The Transference of Heat from Saturated Steam in Pipes (Coils) and Double Bottoms—Evaporation in a Vacuum—The Multiple-effect Evaporator—Multiple-effect Evaporators

Contents of "Evaporating, Condensing and Cooling Apparatus".—*continued.*

from which Extra Steam is Taken—The Weight of Water which must be Evaporated from 100 Kilos. of Liquor in order its Original Percentage of Dry Materials from 1-25 per cent. up to 20-70 per cent.—The Relative Proportion of the Heating Surfaces in the Elements of the Multiple Evaporator and their Actual Dimensions—The Pressure Exerted by Currents of Steam and Gas upon Floating Drops of Water—The Motion of Floating Drops of Water upon which Press Currents of Steam—The Splashing of Evaporating Liquids—The Diameter of Pipes for Steam, Alcohol, Vapour and Air—The Diameter of Water Pipes—The Loss of Heat from Apparatus and Pipes to the Surrounding Air, and Means for Preventing the Loss—Condensers—Heating Liquids by Means of Steam—The Cooling of Liquids—The Volumes to be Exhausted from Condensers by the Air-pumps—A Few Remarks on Air-pumps and the Vacua they Produce—The Volumetric Efficiency of Air-pumps—The Volumes of Air which must be Exhausted from a Vessel in order to Reduce its Original Pressure to a Certain Lower Pressure—Index.

Sanitary Plumbing, Electric Wiring, Metal Work, etc.

EXTERNAL PLUMBING WORK. A Treatise on Lead Work for Roofs. By JOHN W. HART, R.P.C. 180 Illustrations. 272 pp. Demy 8vo. Second Edition Revised. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

HINTS TO PLUMBERS ON JOINT WIPING, PIPE BENDING AND LEAD BURNING. Third Edition, Revised and Corrected. By JOHN W. HART, R.P.C. 184 Illustrations. 313 pp. Demy 8vo. Price 7s. 6d. net. (Post free, 8s. home; 8s. 6d. abroad.)

Contents.

Pipe Bending—Pipe Bending (continued)—Pipe Bending (continued)—Square Pipe Bends—Half-circular Elbows—Curved Bends on Square Pipe—Bossed Bends—Curved Plinth Bends—Rain-water Shoes on Square Pipe—Curved and Angle Bends—Square Pipe Fixings—Joint-wiping—Substitutes for Wiped Joints—Preparing Wiped Joints—Joint Fixings—Plumbing Irons—Joint Fixings—Use of "Touch" in Soldering—Underhand Joints—Blown and Copper Bit Joints—Branch Joints—Branch Joints (continued)—Block Joints—Block Joints (continued)—Block Fixings—Astragal Joints—Pipe Fixings—Large Branch Joints—Large Underhand Joints—Solders—Autogenous Soldering or Lead Burning—Index.

SANITARY PLUMBING AND DRAINAGE. By JOHN W. HART. Demy 8vo. With 208 Illustrations. 250 pp. 1904. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

Sanitary Surveys—Drain Testing—Drain Testing with Smoke—Testing Drains with Water—Drain Plugs for Testing—Sanitary Defects—Closets—Baths and Lavatories—House Drains—Manholes—Iron Soil Pipes—Lead Soil Pipes—Ventilating Pipes—Water-closets—Flushing Cisterns—Baths—Bath Fittings—Lavatories—Lavatory Fittings—Sinks—Waste Pipes—Water Supply—Ball Valves—Town House Sanitary Arrangements—Drainage—Joining Pipes—Accessible Drains—Iron Drains—Iron Junctions—Index.

ELECTRIC WIRING AND FITTING FOR PLUMBERS AND GASFITTERS. By SYDNEY F. WALKER, R.N., M.I.E.E., M.I.Min.E., A.M.Inst.C.E., etc., etc. Crown 8vo. 150 pp. With Illustrations and Tables. Price 5s. net. (Post free, 5s. 3d. home; 5s. 6d. abroad.)

Contents.

Chapter I., **Electrical Terms Used.**—Pressure and Current—The Volt—Ampère—Electrical Resistance—Earth—Continuous and Alternating Currents—The Electric Circuit—Leakage—Heating of Conductors—Size and Forms of Conductors—The Kilowatt—Loss of Pressure—Arrangement of Conductors—Looping In—The Three Wire System—Switches—Fuses—Circuit—Breakers. II., **The Insulation of Wires, Their Protection, Fixing, etc.**—Conductors Insulated with Paper and Similar Materials—Sparking between Conductors—Dialite Insulation—Flexible Cords—Concentric Conductors—Twin Conductors—Three-Core Cables—Fireproof Insulation for Conductors—Jointing—T Joints—Covering T Joints in Vulcanized Rubber Cables. III., **Fixing the Wiring and Cables.**—Laying Out the Route—The Protection of the Wires and Cables—Wood Casing—Metallic Conduits—Non-Metallic Conductors—Fixing the Conduits and Running Wires in Them—Drawing Wires into Tubes—To Avoid Shock. IV., **Lamps.**—The Incandescent Lamp—Lamp Holders—Lamp Fittings—The Nernst Lamp. V., **Switches, Fuses, Distribution Boards, etc.**—The Electricity Meter—Prepayment Meters.

THE PRINCIPLES AND PRACTICE OF DIPPING, BURNISHING, LACQUERING AND BRONZING BRASS WARE. By W. NORMAN BROWN. 35 pp. Crown 8vo. Price 2s. net. (Post free, 2s. 3d. home and abroad.)

A HANDBOOK ON JAPANING AND ENAMELLING FOR CYCLES, BEDSTEADS, TINWARE, ETC. By WILLIAM NORMAN BROWN. 52 pp. and Illustrations. Crown 8vo. Price 2s. net. (Post free, 2s. 3d. home and abroad.)

THE PRINCIPLES OF HOT WATER SUPPLY. By JOHN W. HART, R.P.C. With 129 Illustrations. 177 pp., demy 8vo. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. abroad.)

Contents.

Water Circulation—The Tank System—Pipes and Joints—The Cylinder System—Boilers for the Cylinder System—The Cylinder System—The Combined Tank and Cylinder System—Combined Independent and Kitchen Boiler—Combined Cylinder and Tank System with Duplicate Boilers—Indirect Heating and Boiler Explosions—Pipe Boilers—Safety Valves—Safety Valves—The American System—Heating Water by Steam—Steam Kettles and Jets—Heating Power of Steam—Covering for Hot Water Pipes—Index.

House Decorating and Painting.

THREE HUNDRED SHADES AND HOW TO MIX THEM. For Architects, Painters and Decorators. By A. DESAINT, Artistic Interior Decorator of Paris. The book contains 100 folio Plates, measuring 12 in. by 7 in., each Plate containing specimens of three artistic shades. These shades are all numbered, and their composition and particulars for mixing are fully given at the beginning of the book. Each Plate is interleaved with grease-proof paper, and the volume is very artistically bound in art and linen with the Shield of the Painters' Guild impressed on the cover in gold and silver. Price 21s. net. (Post free, 21s. 6d. home; 22s. 6d. abroad.)

HOUSE DECORATING AND PAINTING. By W. NORMAN BROWN. Eighty-eight Illustrations. 150 pp. Crown 8vo. Price 3s. 6d. net. (Post free, 3s. 9d. home and abroad.)

A HISTORY OF DECORATIVE ART. By W. NORMAN BROWN. Thirty-nine Illustrations. 96 pp. Crown 8vo. Price 2s. 6d. net. (Post free, 2s. 9d. home and abroad.)

WORKSHOP WRINKLES for Decorators, Painters, Paper-hangers and Others. By W. N. BROWN. Crown 8vo. 128 pp. Second Edition. Price 2s. 6d. net. (Post free, 2s. 9d. home; 2s. 10d. abroad.)

Brewing and Botanical.

HOPS IN THEIR BOTANICAL, AGRICULTURAL AND TECHNICAL ASPECT, AND AS AN ARTICLE OF COMMERCE. By EMMANUEL GROSS, Professor at the Higher Agricultural College, Tetschen-Liebwerd. Translated from the German. Seventy-eight Illustrations. 340 pp. Demy 8vo. Price 12s. 6d. net. (Post free, 13s. home; 13s. 6d. abroad.)

Contents.

HISTORY OF THE HOP—THE HOP PLANT—Introductory—The Roots—The Stem—and Leaves—Inflorescence and Flower: Inflorescence and Flower of the Male Hop; Inflorescence and Flower of the Female Hop—The Fruit and its Glandular Structure: The

Fruit and Seed—Propagation and Selection of the Hop—Varieties of the Hop: (a) Red Hops; (b) Green Hops; (c) Pale Green Hops—Classification according to the Period of Ripening: Early August Hops; Medium Early Hops; Late Hops—Injuries to Growth—Leaves Turning Yellow, Summer or Sunbrand, Cones Dropping Off, Honey Dew, Damage from Wind, Hail and Rain; Vegetable Enemies of the Hop: Animal Enemies of the Hop—Beneficial Insects on Hops—**CULTIVATION**—The Requirements of the Hop in Respect of Climate, Soil and Situation: Climate; Soil; Situation—Selection of Variety and Cuttings—Planting a Hop Garden: Drainage; Preparing the Ground; Marking-out for Planting; Planting; Cultivation and Cropping of the Hop Garden in the First Year—Work to be Performed Annually in the Hop Garden: Working the Ground; Cutting: The Non-cutting System; The Proper Performance of the Operation of Cutting: Method of Cutting: Close Cutting, Ordinary Cutting, The Long Cut, The Topping Cut; Proper Season for Cutting: Autumn Cutting, Spring Cutting; Manuring; Training the Hop Plant: Poled Gardens, Frame Training; Principal Types of Frames; Pruning, Cropping, Topping, and Leaf Stripping the Hop Plant; Picking, Drying and Bagging—Principal and Subsidiary Utilisation of Hops and Hop Gardens—Life of a Hop Garden; Subsequent Cropping—Cost of Production, Yield and Selling Prices.

Preservation and Storage—Physical and Chemical Structure of the Hop Cone—Judging the Value of Hops.

Statistics of Production—The Hop Trade—Index.

Timber and Wood Waste.

TIMBER: A Comprehensive Study of Wood in all its Aspects (Commercial and Botanical), showing the Different Applications and Uses of Timber in Various Trades, etc. Translated from the French of PAUL CHARPENTIER. Royal 8vo. 437 pp. 178 Illustrations. Price 12s. 6d. net. (Post free, 13s. home; 14s. abroad.)

Contents.

Physical and Chemical Properties of Timber—Composition of the Vegetable Bodies—Chief Elements—M. Fremy's Researches—Elementary Organs of Plants and especially of Forests—Different Parts of Wood Anatomically and Chemically Considered—General Properties of Wood—**Description of the Different Kinds of Wood**—Principal Essences with Caducous Leaves—Coniferous Resinous Trees—**Division of the Useful Varieties of Timber in the Different Countries of the Globe**—European Timber—African Timber—Asiatic Timber—American Timber—Timber of Oceania—**Forests**—General Notes as to Forests; their Influence—Opinions as to Sylviculture—Improvement of Forests—Unwooding and Rewooding—Preservation of Forests—Exploitation of Forests—Damage caused to Forests—Different Alterations—**The Preservation of Timber**—Generalities—Causes and Progress of Deterioration—History of Different Proposed Processes—Dessication—Superficial Carbonisation of Timber—Processes by Immersion—Generalities as to Antiseptics Employed—Injection Processes in Closed Vessels—The Boucherie System, Based upon the Displacement of the Sap—Processes for Making Timber Uninflammable—**Applications of Timber**—Generalities—Working Timber—Paving—Timber for Mines—Railway Traverses—Accessory Products—Gums—Works of M. Fremy—Resins—Barks—Tan—Application of Cork—The Application of Wood to Art and Dyeing—Different Applications of Wood—Hard Wood—Distillation of Wood—Pyroligneous Acid—Oil of Wood—Distillation of Resins—Index.

THE UTILISATION OF WOOD WASTE. Translated from the German of ERNST HUBBARD. Crown 8vo. 192 pp. Fifty Illustrations. Price 5s. net. (Post free, 5s. 4d. home; 5s. 6d. abroad.)

Contents.

General Remarks on the Utilisation of Sawdust—Employment of Sawdust as Fuel, with and without Simultaneous Recovery of Charcoal and the Products of Distillation—Manufacture of Oxalic Acid from Sawdust—Process with Soda Lye; Thorn's Process; Bohlig's Process—Manufacture of Spirit (Ethyl Alcohol) from Wood Waste—Patent Dyes (Organic Sulphides, Sulphur Dyes, or Mercapto Dyes)—Artificial Wood and Plastic Compositions from Sawdust—Production of Artificial Wood Compositions for Moulded Decorations—Employment of Sawdust for Blasting Powders and Gunpowders—Employment of Sawdust for Briquettes—Employment of Sawdust in the Ceramic Industry and as an Addition to Mortar—Manufacture of Paper Pulp from Wood—Casks—Various Applications of Sawdust and Wood Refuse—Calcium Carbide—Manure—Wood Mosaic Plaques—Bottle Stoppers—Parquetry—Fire-lighters—Carborundum—The Production of Wood Wool—Bark—Index.

Building and Architecture.

THE PREVENTION OF DAMPNESS IN BUILDINGS;

with Remarks on the Causes, Nature and Effects of Saline, Efflorescences and Dry-rot, for Architects, Builders, Overseers, Plasterers, Painters and House Owners. By ADOLF WILHELM KEIM. Translated from the German of the second revised Edition by M. J. SALTER, F.I.C., F.C.S. Eight Coloured Plates and Thirteen Illustrations. Crown 8vo. 115 pp. Price 5s. net. (Post free, 5s. 3d. home; 5s. 4d. abroad.)

HANDBOOK OF TECHNICAL TERMS USED IN ARCHITECTURE AND BUILDING, AND THEIR ALLIED TRADES AND SUBJECTS.

By AUGUSTINE C. PASSMORE. Demy 8vo. 380 pp. Price 7s. 6d. net. (Post free, 8s. home; 8s. 6d. abroad.)

The Preserving of Foods and Sweetmeats.

THE MANUFACTURE OF PRESERVED FOODS AND SWEETMEATS.

By A. HAUSNER. With Twenty-eight Illustrations. Translated from the German of the third enlarged Edition. Crown 8vo. 225 pp. Price 7s. 6d. net. (Post free, 7s. 9d. home; 7s. 10d. abroad.)

Contents.

The Manufacture of Conserves—Introduction—The Causes of the Putrefaction of Food—The Chemical Composition of Foods—The Products of Decomposition—The Causes of Fermentation and Putrefaction—Preservative Bodies—The Various Methods of Preserving Food—The Preservation of Animal Food—Preserving Meat by Means of Ice—The Preservation of Meat by Charcoal—Preservation of Meat by Drying—The Preservation of Meat by the Exclusion of Air—The Appert Method—Preserving Flesh by Smoking—Quick Smoking—Preserving Meat with Salt—Quick Salting by Air Pressure—Quick Salting by Liquid Pressure—Gamble's Method of Preserving Meat—The Preservation of Eggs—Preservation of White and Yolk of Egg—Milk Preservation—Condensed Milk—The Preservation of Fat—Manufacture of Soup Tablets—Meat Biscuits—Extract of Beef—The Preservation of Vegetable Foods in General—Compressing Vegetables—Preservation of Vegetables by Appert's Method—The Preservation of Fruit—Preservation of Fruit by Storage—The Preservation of Fruit by Drying—Drying Fruit by Artificial Heat—Roasting Fruit—The Preservation of Fruit with Sugar—Boiled Preserved Fruit—The Preservation of Fruit in Spirit, Acetic Acid or Glycerine—Preservation of Fruit without Boiling—Jam Manufacture—The Manufacture of Fruit Jellies—The Making of Gelatine Jellies—The Manufacture of "Sulzen"—The Preservation of Fermented Beverages—**The Manufacture of Candies**—Introduction—The Manufacture of Candied Fruit—The Manufacture of Boiled Sugar and Caramel—The Candying of Fruit—Caramelised Fruit—The Manufacture of Sugar Sticks, or Barley Sugar—Bonbon Making—Fruit Drops—The Manufacture of Dragées—The Machinery and Appliances used in Candy Manufacture—Dyeing Candies and Bonbons—Essential Oils used in Candy Making—Fruit Essences—The Manufacture of Filled Bonbons, Liqueur Bonbons and Stamped Lozenges—Recipes for Jams and Jellies—Recipes for Bonbon Making—Dragées—Appendix—Index.

RECIPES FOR THE PRESERVING OF FRUIT, VEGETABLES AND MEAT.

By E. WAGNER. Translated from the German. Crown 8vo. 125 pp. With 14 Illustrations. Price 5s. net. (Post free, 5s. 3d. home; 5s. 4d. abroad.)

Contents.

Part I. Preserved Fruits.—Green Almonds—Gooseberries—Strawberries—Currants—Cherries—Black Nuts—White Nuts—Apricots—Greengages—Pears—Peaches—Plums—Figs—Melons—Apples—Chestnuts—Angelica—Pineapple. **Canned Fruit.**—Gooseberries—Cherries—Apricots—Plums—Rhubarb. **Glazed and Candied Fruits.**—Glazing Fruit—Candied Fruit—Blue Plums—Glazed Chestnuts—Glazed Pineapple Slices—Crystallised Strawberries, Marmalades, Jams and Fruit Juices.—Strawberry Marmalade—Cherry Marmalade—Jams—Fruit Jellies—Raspberry Juice—Cherry Juice—Lemon Syrup—Pineapple Juice. **Fruit Pulp for Ices.** **Citron Peel and Orange Peel.** **Part II. Preserved Vegetables.**—Asparagus—Peas—Beans—Carrots—Spinach—Artichokes—Tomatoes—Mixed Vegetables—Tinned Julienne—Celery—Mushrooms—Truffles—Pickled Gherkins—Gherkins in Mustard—Mixed Pickles. **Part III. Preserved Meats.**—Veal Cutlets—Fricondeau of Veal—Calves Head—Bouillon Meat—Ox Tongue—Beef à la Mode—Roast Hare—Roast Venison—Mutton and Cabbage—Savory Paste—Beef Paste—Foie Gras Paste.

Dyeing Fancy Goods.

THE ART OF DYEING AND STAINING MARBLE, ARTIFICIAL STONE, BONE, HORN, IVORY AND WOOD, AND OF IMITATING ALL SORTS OF WOOD. A Practical Handbook for the Use of Joiners, Turners, Manufacturers of Fancy Goods, Stick and Umbrella Makers, Comb Makers, etc. Translated from the German of D. H. SOXHLET, Technical Chemist. Crown 8vo. 168 pp. Price 5s. net. (Post free, 5s. 3d. home; 5s. 4d. abroad.)

Celluloid.

CELLULOID: Its Raw Material, Manufacture, Properties and Uses. A Handbook for Manufacturers of Celluloid and Celluloid Articles, and all Industries using Celluloid; also for Dentists and Teeth Specialists. By Dr. FR. BÖCKMANN, Technical Chemist. Translated from the Third Revised German Edition. Crown 8vo. 120 pp. With 49 Illustrations. Price 5s. net. (Post free, 5s. 3d. home; 5s. 4d. abroad.)

Contents.

Chapters I., **Raw Materials for the Manufacture of Celluloid:** Cellulose and Pyroxylin—Gun-cotton—Properties of Gun-cotton—Special Gun-cottons for Celluloid Manufacture—Nitrating Centrifugalizers—Collodion Wool—Methods of Preparing Collodion Wool—Camphor—Japanese (Formosa) Camphor, Ordinary Camphor—Borneo Camphor (Borneol), Sumatra Camphor, Camphol, Baros Camphor—Properties of Camphor—Artificial Camphor—Camphor Substitutes. II., **The Manufacture of Celluloid:** Manufacturing Camphor by the Aid of Heat and Pressure—Manufacture of Celluloid by Dissolving Gun-cotton in an Alcoholic Solution of Camphor—Preparing Celluloid by the Cold Process—Preparation with an Ethereal Solution of Camphor—Preparation with a Solution of Camphor and Wood Spirit. III., **The Employment of Pyroxylin for Artificial Silk:** Denitrating and Colouring Pyroxylin—Unflammable Celluloid—Celluloid and Cork Composition—Incombustible Celluloid Substitute—Xylonite or Fibrolithoid. IV., **Properties of Celluloid.** V., **Testing Celluloid.** VI., **Application and Treatment of Celluloid:** Caoutchouc Industry—Making Celluloid Ornaments—Working by the Cold Process—Working by the Warm Process—Celluloid Combs—Celluloid as a Basis for Artificial Teeth—Stained Celluloid Sheets as a Substitute for Glass—Celluloid Printing Blocks and Stamps—Collapsible Seamless Vessels of Celluloid—Making Celluloid Balls—Celluloid Posters—Pressing Hollow Celluloid Articles—Casting Celluloid Articles—Method for Producing Designs on Plates or Sheets of Celluloid, Xylonite, etc.—Imitation Tortoiseshell—Metallic Incrustations—Imitation Florentine Mosaic—Celluloid Collars and Cuffs—Phonograph Cylinder Composition—Making Umbrella and Stick Handles of Celluloid—Celluloid Dolls—Celluloid for Ships' Bottoms—Celluloid Pens—Colouring Finished Celluloid Articles—Printing on Celluloid—Employment of Celluloid (and Pyroxylin) in Lacquer Varnishes—Index.

Lithography, Printing and Engraving.

PRACTICAL LITHOGRAPHY. By ALFRED SEYMOUR. Demy 8vo. With Frontispiece and 33 Illus. 120 pp. Price 5s. net. (Post free, 5s. 4d. home; 5s. 6d. abroad.)

Contents.

Stones—Transfer Inks—Transfer Papers—Pressing Printing—Litho Press—Press Work—Machine Printing—Colour Printing—Substitutes for Lithographic Stones—Tin Plate Printing and Decoration—Photo-Lithography.

PRINTERS' AND STATIONERS' READY RECKONER AND COMPENDIUM. Compiled by VICTOR GRAHAM. Crown 8vo. 112 pp. 1904. Price 3s. 6d. net. (Post free, 3s. 9d. home; 3s. 10d. abroad.)

Contents.

Price of Paper per Sheet, Quire, Ream and Lb.—Cost of 100 to 1000 Sheets at various Sizes and Prices per Ream—Cost of Cards—Quantity Table—Sizes and Weights of Paper, Cards, etc.—Notes on Account Books—Discount Tables—Sizes of spaces—Leads to a lb.—Dictionary—Measure for Bookwork—Correcting Proofs, etc.

ENGRAVING FOR ILLUSTRATION. HISTORICAL AND PRACTICAL NOTES. By J. KIRKBRIDE. 72 pp. Two Plates and 6 Illustrations. Crown 8vo. Price 2s. 6d. net. (Post free, 2s. 9d. home; 2s. 10d. abroad.)

Bookbinding.

PRACTICAL BOOKBINDING. By PAUL ADAM. Translated from the German. Crown 8vo. 180 pp. 127 Illustrations. Price 5s. net. (Post free, 5s. 4d. home; 5s. 6d. abroad.)

Sugar Refining.

THE TECHNOLOGY OF SUGAR: Practical Treatise on the Modern Methods of Manufacture of Sugar from the Sugar Cane and Sugar Beet. By JOHN GEDDES McINTOSH. Second Revised and Enlarged Edition. Demy 8vo. Fully Illustrated. 436 pp. Seventy-six Tables. 1906. Price 10s. 6d. net. (Post free, 11s. home; 11s. 6d. abroad.)

Contents.

Chemistry of Sucrose, Lactose, Maltose, Glucose, Invert Sugar, etc.—Purchase and Analysis of Beets—Treatment of Beets—Diffusion—Filtration—Concentration—Evaporation—**Sugar Cane:** Cultivation—Milling—Diffusion—Sugar Refining—Analysis of Raw Sugars—Chemistry of Molasses, etc.

(See "*Evaporating, Condensing, etc., Apparatus*," p. 26.)

Bibliography.

CLASSIFIED GUIDE TO TECHNICAL AND COMMERCIAL BOOKS. Compiled by EDGAR GREENWOOD. Demy 8vo. 224 pp. 1904. Being a Subject-list of the Principal British and American Books in print; giving Title, Author, Size, Date, Publisher and Price. Price 7s. 6d. net. (Post free, 7s. 10d. home; 8s. 3d. abroad.)

THE TECHNICAL BOOKS in this Catalogue can be obtained through all Booksellers, or by post direct from the Publishers by remitting the amount given in brackets.

Full Particulars of Contents of any of the above books will be sent on application.

Books in the Press.—The Publishers will send Contents and prices of books in the press as soon as ready to any one sending their name and address.

Technical Books upon **all Subjects** can be obtained through SCOTT, GREENWOOD & SON, if requirements are fully stated.

SCOTT, GREENWOOD & SON,

Technical Book and Trade Journal Publishers,

8 BROADWAY, LUDGATE HILL,

LONDON, E.C.

Telegraphic Address, "Printeries, London".

Telephone, Bank 5403.

[October, 1907.]



GETTY CENTER LIBRARY



3 3125 00114 9240

